
**Analytical colorimetry —
Part 3:
Special indices**

*Analyse colorimétrique —
Partie 3: Indices spéciaux*

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[ISO 18314-3:2015](https://standards.iteh.ai/catalog/standards/sist/cedff93e-132c-4743-bd00-4b2dc5fd35bb/iso-18314-3-2015)

<https://standards.iteh.ai/catalog/standards/sist/cedff93e-132c-4743-bd00-4b2dc5fd35bb/iso-18314-3-2015>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18314-3:2015

<https://standards.iteh.ai/catalog/standards/sist/cedff93e-132c-4743-bd00-4b2dc5fd35bb/iso-18314-3-2015>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
1 Scope	1
2 Symbols and abbreviated terms	1
3 Whiteness index	2
3.1 CIE whiteness index	2
4 Yellowness index	2
5 Black values	2
5.1 Black value, M_Y	2
5.2 Colour depending black value, M_C	2
5.3 Absolute contribution of hue, dM	2
5.4 Relative black value, Myr	3
6 Grey values	3
6.1 Grey value, G_Y	3
6.2 Colour depending grey value, G_C	3
6.3 Absolute contribution of hue, dG	3
6.4 Relative grey value, Gyr	3
7 Flop-index	4
Annex A (informative) Considerations regarding black values	5
Bibliography	6

ITeH STANDARD PREVIEW
 (standards.iteh.ai)

ISO 18314-3:2015

<https://standards.iteh.ai/catalog/standards/sist/cedff93e-132c-4743-bd00-4b2dc5fd35bb/iso-18314-3-2015>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 256, *Pigments, dyestuffs and extenders*.

ISO 18314 consists of the following parts, under the general title *Analytical colorimetry*:

- *Part 1: Practical colour measurement*
- *Part 2: Saunderson correction, solutions of the Kubelka-Munk equation, tinting strength, hiding power*
- *Part 3: Special indices*

Analytical colorimetry —

Part 3: Special indices

1 Scope

This part of ISO 18314 specifies different methods of calculating special indices, which are generally used to describe lightness respectively jetness of samples including chroma or hue within one colour-coordinate.

This part of ISO 18314 is applicable to tristimulus values and chromaticity coordinates calculated using colour-matching functions of the CIE 1964 standard colourimetric system. It can be used for the specification of colour stimuli perceived as belonging to a reflecting or transmitting object, where a one-dimensional value is required.

2 Symbols and abbreviated terms

a, b	absolute parameters
FI	flop-index
G_C	colour depending grey value
G_Y	grey value
G_{yr}	relative grey value
$G_Y(GS)$	grey value of a virtual general standard
$G_Y(GS_f)$	fixed mean value (of 10 preparations) of the actual general standard
$G_Y(GS_v)$	grey value of the actual prepared general standard
$G_Y(\text{Sample})$	grey value of the sample
$L^*(\epsilon)$	CIE Lab-76 lightness value at the aspecular angle ϵ
M_C	colour depending black value
M_Y	black value
M_{yr}	relative black value
$M_Y(GS)$	black value of a defined virtual general standard
$M_Y(GS_f)$	fixed mean value (of 10 preparations) of the actual group standard
$M_Y(GS_v)$	black value of the actual prepared group standard
$M_Y(\text{Sample})$	black value of the sample
W_{CIE}	is the CIE whiteness index
X, Y, Z	tristimulus values of a test stimulus

- X_n, Y_n, Z_n tristimulus values of a specific white colour stimulus
- x, y chromaticity coordinates of a test stimulus
- x_n, y_n chromaticity coordinates of a specific white colour stimulus
- YI yellowness index

3 Whiteness index

3.1 CIE whiteness index

$$W_{CIE} = Y + 800 \cdot (x_n - x) + 1700 \cdot (y_n - y) \tag{1}$$

This formula is valid within the range of $40 < W_{CIE} < 5Y - 280$.

NOTE This formula follows CIE 15:2004 and ASTM E 313-10.

4 Yellowness index

$$YI = 100 \cdot \frac{a \cdot X - b \cdot Z}{Y} \tag{2}$$

The absolute parameters a and b depend on illuminant D65 and the standard observer 2° and 10°. See [Table 1](#).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Table 1 — Parameters a and b for standard observer 2° and 10°

Standard observer	a	b
2°	1,298 5	1,133 5
10°	1,301 3	1,149 8

NOTE This equation follows ASTM E 313-10 and DIN 6167.

5 Black values

5.1 Black value, M_Y

$$M_Y = 100 \cdot \log \frac{Y_n}{Y} \tag{3}$$

NOTE This equation follows DIN 55979.

5.2 Colour depending black value, M_C

$$M_C = 100 \cdot \left(\log \frac{X_n}{X} - \log \frac{Z_n}{Z} + \log \frac{Y_n}{Y} \right) \tag{4}$$

NOTE Black value, M_C , describes higher jetness if there is a blue shade and lower jetness if the shade is brown.

5.3 Absolute contribution of hue, dM

$$dM = M_C - M_Y \tag{5}$$

NOTE dM describes the amount of blue shade in case of positive values and the amount of brown shade in case of negative values.

5.4 Relative black value, M_{Yr}

$$M_{Yr}[\%] = \frac{M_Y(\text{Sample}) \cdot M_Y(\text{GS}_f)}{M_Y(\text{GS}) \cdot M_Y(\text{GS}_v)} \cdot 100\% \quad (6)$$

In case of carbon black pigments, a group standard can be defined as a general standard relating to the class of carbon black pigment. See [Table 2](#).

Table 2 — Virtual black values $M_Y(\text{GS})$ for group standards

Group standards (GS)	Virtual black value $M_Y(\text{GS})$
Gas black, powder, and beads	260
Oxidized gas black, powder, and beads	250
Furnace black, powder, and beads	255
Oxidized furnace black, powder, and beads	225
Lamp black, powder, and beads	205
Thermal black, powder, and beads	205
Acetylene black, powder, and beads	250

iTech STANDARD PREVIEW
(standards.iteh.ai)

6 Grey values

6.1 Grey value, G_Y

$$G_Y = 100 \cdot \log \frac{Y_n}{Y} \quad (7)$$

ISO 18314-3:2015
<https://standards.iteh.ai/catalog/standards/sist/cedff93e-132c-4743-bd00-4b2dc5fd35bb/iso-18314-3-2015>

6.2 Colour depending grey value, G_C

$$G_C = 100 \cdot \left(\log \frac{X_n}{X} - \log \frac{Z_n}{Z} + \log \frac{Y_n}{Y} \right) \quad (8)$$

6.3 Absolute contribution of hue, dG

$$dG = G_C - G_Y \quad (9)$$

NOTE dG describes the amount of blue shade in case of positive values and the amount of brown shade in case of negative values.

6.4 Relative grey value, G_{Yr}

$$G_{Yr}[\%] = \frac{G_Y(\text{Sample}) \cdot G_Y(\text{GS}_f)}{G_Y(\text{GS}) \cdot G_Y(\text{GS}_v)} \cdot 100\% \quad (10)$$

In case of carbon black pigments, a group standard can be defined as a general standard relating to the class of carbon black pigment. See [Table 3](#).

Table 3 — Virtual grey values G_Y (GS) for group standards

Group standards (GS)	Virtual grey value G_Y (GS)
Gas black, powder, and beads	95
Oxidized gas black, powder, and beads	99
Furnace black, powder, and beads	99
Oxidized furnace black, powder, and beads	85
Lamp black, powder, and beads	64
Thermal black, powder, and beads	50
Acetylene black, powder, and beads	85

7 Flop-index

The flop-index (FI) is a special measure to characterize the angular variation of lightness of almost neutral metallic colour shades. Its formal definition is

$$FI = 2,69 \frac{[L^*(\varepsilon_1) - L^*(\varepsilon_3)]^{1,11}}{[L^*(\varepsilon_2)]^{0,86}} \quad (11)$$

The parameters (exponents, pre-factor) have been chosen in a way so that for conventional metallic pigments the order of magnitude is $FI \approx 10$. $L^*(\varepsilon)$ denotes the CIE Lab-76 lightness value at the aspecular angle ε with $\varepsilon_1=15^\circ$, $\varepsilon_2=45^\circ$, $\varepsilon_3=110^\circ$.

NOTE This formula has been developed by D. H. Alman.^[1]

ISO 18314-3:2015

<https://standards.iteh.ai/catalog/standards/sist/cedff93e-132c-4743-bd00-4b2dc5fd35bb/iso-18314-3-2015>

Annex A (informative)

Considerations regarding black values

The impression of hue or colour intensity is a subjective sensory perception. Consequently, differentiation between jet-black paints is not totally without problems. A visual assessment is always significantly influenced by the ambient conditions and by the physical and mental state of the observer. For reliable determination, measurement equipment is required which provides reproducible results for the measurement range with minimum reflections.

Metrological assessment of the jetness is preferably performed using a spectral photometer with 45°/0° (or 0°/45°) geometry. Here the specimen is placed at an angle of 45° and generally subjected to circular illumination. The light reflected by the specimen is measured at an angle of 0°. The spectrophotometer might be selected in testing of calibration repeatability. The difference of standard value Y has to be lower than $\pm 0,003$ in the jetness area of $Y = 0,04$ until $Y = 0,05$.

The visual evaluation is influenced to a great extent by the ambient conditions and by the physical and mental state of the observer. It is consequently necessary to define and observe certain boundary conditions. As natural daylight is subject to continuous fluctuations, a standardised artificial light source has to be used that produces a light similar to that of daylight type D65 by filtering.

The observation angle has to correspond to the 45°/0° (or 0°/45°) geometry of the measuring instrument. As the light falls perpendicularly onto the paint coating, the observer views the specimen at an angle of 45°. The area around the specimens should be kept neutral. Reflections of other objects have to be avoided. Matt black specimen mountings and backgrounds and complete darkening of the examination room are of benefit for the evaluation of deep black specimens.