



Designation: D 5107 – 90 (Reapproved 1997)

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Practice for Preparatory Surface Cleaning of Architectural Sandstone¹

This standard is issued under the fixed designation D 5107; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers non-abrasive surface cleaning of architectural sandstone to remove grease, dirt, loose material, and surface deposits such as soot, fly ash, hydrocarbon residues, and algae and other biological growth in preparation for the application of water repellent coatings. Procedures include broom cleaning, vacuum cleaning, air blast cleaning, water cleaning (and detergent water cleaning), and chemical cleaning.

1.2 *Limitations*—This practice is intended to clean architectural sandstone without damaging it or altering the surface profile.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 4.

2. Referenced Documents

2.1 ASTM Standards:

- C 119 Terminology Relating to Dimension Stone²
- D 4262 Test Method for pH of Chemically Cleaned or Etched Concrete Surfaces³
- D 4263 Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method³
- D 4285 Test Method for Indicating Oil or Water in Compressed Air³

3. Significance and Use

3.1 Surface cleaning is necessary to prepare architectural sandstone surfaces for application of coatings intended for water repellent protection. Surface cleaning of the sandstone substrate helps to ensure proper adhesion of the coating.

3.2 Use of procedures described in this practice may not be adequate where protective systems will be used for continuous or intermittent immersion or mechanical loading.

¹ This practice is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.47 on Masonry Treatments.

Current edition approved Nov. 21, 1990. Published January 1991.

² *Annual Book of ASTM Standards*, Vol 04.07.

³ *Annual Book of ASTM Standards*, Vol 06.02.

4. Hazards

4.1 Moisture in the architectural sandstone may be detrimental to coating adhesion or (in some cases) cure. Moisture content shall be in compliance with coating manufacturer's recommendation. See also Test Method D 4263.

4.2 Localized staining (for example efflorescence and metallic staining) and previously applied coatings or preservative treatments not compatible with the treatment may require removal by other surface preparation methods.

4.3 Water cleaning, detergent water cleaning, and chemical cleaning should not be performed at temperatures below 40°F.

4.4 Many chemical cleaning products contain acids and should be handled according to manufacturers' recommendations. Use and disposal of materials should conform to established federal, state, local, and project requirements.

4.5 If pressure washing equipment is employed for water cleaning or for flushing the surface with detergent water cleaning or chemical cleaning, the minimum effective pressure should be used. Avoid excessive pressures that could damage the sandstone substrate.

5. Procedure

5.1 Air blast, water, scrubbing, sweeping, or vacuuming are acceptable cleaning methods. Chemical cleaning agents may be used to remove surface deposits such as soot, fly ash, and hydrocarbon residues not removed by any of the above methods. Chemical cleaning should be preceded and followed by a thorough fresh water rinse.

5.2 Existing conditions of the substrate will determine the selection of appropriate procedure(s). Prior to the initiation of cleaning, small test areas should be cleaned in inconspicuous areas by the selected procedure to determine effectiveness.

5.3 The six types of cleaning procedures are described below. One or more of the procedures may be required to remove contaminants from the sandstone surface:

5.3.1 *Broom Cleaning*—Removes most loosely adherent solid contaminants.

5.3.1.1 Working from top to bottom, sweep the surface with a clean industrial stiff-bristled broom or similar device. Remove sweepings from the immediate work area.

5.3.1.2 Clean broom-cleaned surfaces again using one or more of the surface preparation procedures specified in 5.3.2 through 5.3.6.