

SLOVENSKI STANDARD oSIST prEN 10217-7:2019

01-maj-2019

Varjene jeklene cevi za tlačne posode - Tehnični dobavni pogoji - 7. del: Cevi iz nerjavnega jekla

Welded steel tubes for pressure purposes - Technical delivery conditions - Part 7: Stainless steel tubes

Geschweißte Stahlrohre für Druckbeanspruchungen - Technische Lieferbedingungen -Teil 7: Rohre aus nichtrostenden Stählen ARD PREVIEW

Tubes soudés en acier pour service sous pression - Conditions techniques de livraison -Partie 7 : Tubes en aciers inoxydables T FprEN 10217-7:2020

https://standards.iteh.ai/catalog/standards/sist/fb6a6811-0072-48f3-94ea-

Ta slovenski standard je istoveten z: prEN 10217-7-2020

ICS:

23.020.32 Tlačne posode Pressure vessels

77.140.75 Jeklene cevi in cevni profili Steel pipes and tubes for

> specific use za posebne namene

oSIST prEN 10217-7:2019 en,fr,de oSIST prEN 10217-7:2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>kSIST FprEN 10217-7:2020</u> https://standards.iteh.ai/catalog/standards/sist/fb6a6811-0072-48f3-94ea-e1bf30799cfc/ksist-fpren-10217-7-2020

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM

DRAFT prEN 10217-7

February 2019

ICS 23.040.10; 77.140.75

Will supersede EN 10217-7:2014

English Version

Welded steel tubes for pressure purposes - Technical delivery conditions - Part 7: Stainless steel tubes

Tubes soudés en acier pour service sous pression -Conditions techniques de livraison - Partie 7 : Tubes en aciers inoxydables Geschweißte Stahlrohre für Druckbeanspruchungen -Technische Lieferbedingungen - Teil 7: Rohre aus nichtrostenden Stählen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 459/SC 10.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

e1bf30799cfc/ksist-fpren-10217-7-2020

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning: This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents		Page
Euroj	pean foreword	4
1	Scope	5
2	Normative references	5
3	Terms and definitions	7
4	Symbols	7
5	Classification and designation	7
5.1	Classification	
5.2	Designation	7
6	Information to be supplied by the purchaser	8
6.1	Mandatory information	8
6.2	Options	
6.3	Examples of an order	
6.3.1 6.3.2	Example 1Example 2	
	•	
7 7.1	Manufacturing process of S.T.A.N.D.A.R.D. P.R.F.V.L.F.V.	10
7.1 7.2	Steelmaking process	10
8 8.1	Requirements <u>KSIST FprEN 10217-7:2020</u> General <u>KSIST FprEN 10217-7:2020</u> Chemical composition <u>e1bi30799cic/ksist-ipren-10217-7-2020</u> Cast analysis <u>RSIST FprEN 10217-7-2020</u>	12
8.2	https://standards.iteh.ai/catalog/standards/sist/fb6a6811-0072-48f3-94ea-	13
8.2.1	Cast analysise1bi30799ctc/ksist-ipren-10217-7-2020	
8.2.2	Product analysis	13
8.3	Mechanical properties	
8.3.1	· · · · · · · · · · · · · · · · · · ·	
8.3.2 8.3.3	At elevated temperatureAt low temperature	
8.4	Corrosion resistance	
8.5	Appearance and internal soundness	
8.5.1	Appearance	23
8.5.2	Internal soundness	
8.6	Straightness	
8.7 8.8	Preparation of ends Dimensions, masses and tolerances	
8.8.1	Outside diameter and wall thickness	
8.8.2	Mass	
8.8.3	Lengths	25
8.8.4	Tolerances	25
9	Inspection	27
9.1	Type of inspection	27
9.2	Inspection documents	
9.2.1	Types of inspection documents	
9.2.2 9.3	Content of inspection documents Summary of inspection and verification testing	
<i>7</i> .3	Jummary of mopection and vermeation testing	20

10	Sampling	29
10.1	Test unit	29
10.2	Preparation of samples and test pieces	30
10.2.1	Selection and preparation of samples for product analysis	30
10.2.2	Location, orientation and preparation of samples and test pieces for mechanical	
	tests	30
11	Verification test methods	21
11.1	Chemical analysis	
11.2	Tensile test on the base material	
	At room temperature	
	At elevated temperature	
11.3	Transverse tensile test on the weld	
11.4	Technological tests	
11.4.1	General	
11.4.2	Flattening test	33
11.4.3	Ring tensile test	33
11.4.4	Drift expanding test	33
11.4.5	Ring expanding test	34
11.5	Weld bend test	34
11.6	Impact test	
11.7	Intergranular corrosion test	
11.8	Leak tightness test	35
11.8.1	Hydrostatic test of STANDARD PREVIEW	35
11.8.2	Eddy current test	35
11.9	Dimensional inspection standards.iteh.ai)	
	Visual examination	
	Non-destructive testingksist EprEN 10217-72020	
	Material identification: itch ai/catalog/standards/sist/fb6a6811-0072-48f3-94ca	
11.13	Retests, sorting and reprocessing ksist-fpren-10217-7-2020	37
12	Marking	37
12.1	Marking to be applied	37
12.2	Additional marking	38
13	Handling and packaging	38
Annex	A (informative) Technical changes from the previous edition	39
4.1	Introduction	
4.2	Technical changes	
	_	39
Annex	ZA (informative) Relationship between this European Standard and the Essential Requirements of Directive 2014/68/EU aimed to be covered	41
	- 15. 174 1. 174 1. 174 1. 174 1. 174 1. 174 1. 174 1. 174 1. 174 1. 174 1. 174 1. 174	T L

European foreword

This document (prEN 10217-7:2019) has been prepared by Technical Committee ECISS/TC 110 "Steel tubes and iron and steel fittings", the secretariat of which is held by UNI.

This document is currently submitted to the CEN Enquiry.

This document supersedes EN 10217-7:2014.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 2014/68/EU.

For relationship with EU Directive 2014/68/EU (formerly 97/23/EC), see informative Annex ZA, which is an integral part of this document.

This European Standard consists of the following parts, under the general title *Welded steel tubes for pressure purposes* — *Technical delivery conditions*:

- Part 1: Electric welded and submerged arc welded non-alloy steel tubes with specified room temperature properties
- Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties
- Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties
- Part 4: Electric welded non-alloy and alloy steel tubes with specified low temperature properties
- Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties
- Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties
- Part 7: Stainless steel tubes

Another European Standard series covering tubes for pressure purposes is:

EN 10216, Seamless steel tubes for pressure purposes.

1 Scope

This Part of EN 10217 specifies the technical delivery conditions in two test categories for welded tubes of circular cross-section made of austenitic and austenitic-ferritic stainless steel which are intended for pressure and corrosion resisting purposes at room temperature, at low temperatures or at elevated temperatures.

NOTE Once this document is published in the Official Journal of the European Union (OJEU) under Directive 2014/68/EU, pressure equipment directive, presumption of conformity to the Essential Safety Requirements (ESR) of Directive 2014/68/EU is limited to technical data of materials in this standard and does not presume adequacy of the material to a specific item of equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of this specific item of equipment to verify that the ESRs of the Pressure Equipment Directive are satisfied, needs to be done by the designer or manufacturer of the pressure equipment, taking also into account the subsequent manufacturing processes which may affect properties of the base materials.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020:2000, Definition and classification of grades of steel

EN 10021:2006, General technical delivery conditions for steel products

EN 10027-1, Designation systems for steels - Part 1: Steel names

EN 10027-2, Designation systems for steels — Part 2: Numerical system

EN 10028-7:2016, Flat products made of steels for pressure purposes — Part 7: Stainless steels

EN 10088-1, Stainless steels — Part 1: List of stainless steels

EN 10168:2004, Steel products — Inspection documents - List of information and description

EN 10204:2004, Metallic products — Types of inspection documents

EN 10266, Steel tubes, fittings and structural hollow sections — Symbols and definitions of terms for use in product standards

CEN/TR 10261, Iron and steel — European standards for the determination of chemical composition

EN ISO 148-1:2016, Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1:2016)

EN ISO 377:2017, Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377:2017)

EN ISO 1127, Stainless steel tubes — Dimensions, tolerances and conventional masses per unit length (ISO 1127)

EN ISO 2566-2, Steel — Conversion of elongation values — Part 2: Austenitic steels (ISO 2566-2)

EN ISO 3651-2:1998, Determination of resistance to intergranular corrosion of stainless steels — Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in media containing sulfuric acid (ISO 3651-2:1998)

EN ISO 4885, Ferrous materials — Heat treatments — Vocabulary (ISO 4885)

EN ISO 5173:2010, Destructive tests on welds in metallic materials — Bend tests (ISO 5173:2009)

EN ISO 6892-1:2016, Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)

EN ISO 6892-2:2018, Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature (ISO 6892-2:2018)

EN ISO 8492:2013, Metallic materials — Tube — Flattening test (ISO 8492:2013)

EN ISO 8493:2004, Metallic materials — Tube — Drift-expanding test (ISO 8493:1998)

EN ISO 8495:2013, Metallic materials — Tube — Ring-expanding test (ISO 8495:2013)

EN ISO 8496:2013, Metallic materials — Tube — Ring tensile test (ISO 8496:2013)

EN ISO 9712:2012, Non-destructive testing — Qualification and certification of NDT personnel (ISO 9712:2012) iTeh STANDARD PREVIEW

EN ISO 10893-1, Non-destructive testing of steel tubes—Part 1: Automated electromagnetic testing of seamless and welded (except submerged arc-welded) steel tubes for the verification of hydraulic leaktightness (ISO 10893-1) kSIST FprEN 10217-7:2020

https://standards.iteh.ai/catalog/standards/sist/fb6a6811-0072-48f3-94ea-EN ISO 10893-2, Non-destructive testing of steel tubes pren- Party 2: Automated eddy current testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of imperfections (ISO 10893-2)

EN ISO 10893-6, Non-destructive testing of steel tubes — Part 6: Radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-6)

EN ISO 10893-7, Non-destructive testing of steel tubes — Part 7: Digital radiographic testing of the weld seam of welded steel tubes for the detection of imperfections (ISO 10893-7)

EN ISO 10893-8, Non-destructive testing of steel tubes — Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8)

EN ISO 10893-9, Non-destructive testing of steel tubes — Part 9: Automated ultrasonic testing for the detection of laminar imperfections in strip/plate used for the manufacture of welded steel tubes (ISO 10893-9)

EN ISO 10893-10, Non-destructive testing of steel tubes — Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-10)

EN ISO 10893-11, Non-destructive testing of steel tubes — Part 11: Automated ultrasonic testing of the weld seam of welded steel tubes for the detection of longitudinal and/or transverse imperfections (ISO 10893-11)

EN ISO 14284:2002, Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284:1996)

ISO 11484:2009, Steel products — Employer's qualification system for non-destructive testing (NDT) personnel

ISO/TR 25901-3:2016, Welding and allied processes — Vocabulary — Part 3: Welding processes

3 Terms and definitions

For the purpose of this document, the terms and definitions given in EN 10020, EN 10021, EN ISO 4885 and EN 10266 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1

test category

classification that indicates the extent and level of inspection and testing

3.2

employer iTeh STANDARD PREVIEW

organization for which a person works on a regular basis (standards.iteh.ai)

Note 1 to entry: The employer may be either the tube manufacturer or supplier or a third party organization providing Non- Destructive Testing (NDT) services N 10217-7:2020

https://standards.iteh.ai/catalog/standards/sist/fb6a6811-0072-48f3-94ea-**Symbols** e1bf30799cfc/ksist-fbren-10217-7-2020

For the purpose of this document, the symbols given in EN 10266 and the following apply.

— TC test category.

NOTE See also Table 2 for symbols of the delivery condition.

5 Classification and designation

5.1 Classification

According to the classification system in EN 10020, the steel grades are classified as:

- austenitic steels (corrosion resisting);
- austenitic-ferritic steels.

5.2 Designation

For the tubes covered by this Part of EN 10217 the steel designation consists of:

the number of this Part of EN 10217 (EN 10217-7);

plus either:

— the steel name according to EN 10027-1;

or:

the steel number allocated according to EN 10027-2.

6 Information to be supplied by the purchaser

6.1 Mandatory information

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) the quantity (mass or total length or number);
- b) the term "tube";
- c) the dimensions (outside diameter D and wall thickness T) (see 8.8.1);
- d) the designation of the steel grade according to this Part of EN 10217 (see 5.2);
- e) the test category (see 9.3).

6.2 Options

A number of options are specified in this Part of EN 10217 and these are listed below. In the event that the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the tube shall be supplied in accordance with the basic specification (see 6.1).

- 1) Information about steelmaking process (see 7.1); (Standards.iteh.ai)
- 2) Tube manufacturing process and/or route (see 7.2.1);

kSIST FprEN 10217-7:2020

- 3) The inside weld is remelted (see Table 4) standards/sist/fb6a6811-0072-48f3-94ea-e1bf30799cfc/ksist-fpren-10217-7-2020
- 4) The inside weld is worked by rolling, remelting or grinding (see Table 1);
- 5) Delivery condition (see 7.2.3);
- 6) Product analysis (see 8.2.2);
- 7) Additional verifications of mechanical properties on samples that have undergone a different or additional heat treatment (see 8.3.1);
- 8) Verification of impact energy at room temperature (see 8.3.1);
- 9) Verification of proof strength $R_{\rm p0.2}$ or $R_{\rm p1.0}$ at elevated temperatures (see 8.3.2);
- 10) Verification of impact energy at low temperature (see 8.3.3);
- 11) Intergranular corrosion test (see 8.4);
- 12) Repair welding (see 8.5.1.5);
- 13) Selection of method for verification of leak-tightness test method (see 8.5.2.2);
- 14) Non-destructive testing of tube ends for detection of laminar imperfections (see 8.5.2.3);
- 15) Non-destructive testing of strip and plate edges for detection of laminar imperfections (see 8.5.2.3);

- 16) Special ends preparation (see 8.7);
- 17) Exact lengths (see 8.8.3);
- 18) Tolerance class D 4 for $D \le 168.3$ mm (see Table 10);
- 19) The type of inspection certificate 3.2 in place of the standard document (see 9.2.1);
- 20) Transverse tensile test on the weld (see 10.2.2.3);
- 21) Test pressure for hydrostatic leak-tightness test (see 11.8.1);
- 22) Wall thickness measurement away from the ends (see 11.9);
- 23) Selection of non-destructive testing method for the inspection of the weld seam (see Table 16);
- 24) Image quality class B of EN ISO 10893-6 for the radiographic inspection of the weld seam (see Table 16);
- 25) Additional marking (see 12.2);
- 26) Special protection (see Clause 13);
- 27) Image quality class B of ENISO 10893-7 for the digital radiographic testing of the weld (see Table 16);
- 28) Different values for the maximum height of the weld seam are to be agreed in the purchase order (see Table 11);

 kSIST FprEN 10217-7:2020

(standards.iteh.ai)

https://standards.iteh.ai/catalog/standards/sist/fb6a6811-0072-48f3-94ea-29) Height of the weld seam for tubes with route 012 057 062 and 07 (according to Table 1) and with thicknesses over 8 mm: maximum 4 mm (see Table 11).

6.3 Examples of an order

6.3.1 Example 1

2 000 m of welded tube W1 (see Table 2) with an outside diameter of 168,3 mm, a wall thickness of 4,5 mm, tolerance classes D 3 and T 3, in accordance with this Part of EN 10217, made of steel grade X2CrNi19-11, test category 1, with a 3.1 inspection certificate according to EN 10204:

EXAMPLE 2 000 m - Tube - 168,3 × 4,5 - EN 10217-7- X2CrNi19-11 - TC 1 - Option 5: W1

6.3.2 Example 2

300 m of cold finished welded tube WCA (see Table 2) with an outside diameter of 42,4 mm, a wall thickness of 2,6 mm, tolerance classes D 3 and T 3, in accordance with this Part of EN 10217, made of steel grade 1.4301, test category 2, with intergranular corrosion test (EN ISO 3651-2, method A), verification of proof strength at 300 °C, non-destructive testing of strip edges for detection of laminar imperfections, with a 3.2 inspection certificate according to EN 10204 issued by the manufacturer:

EXAMPLE 300 m - Tube - 42.4×2.6 - EN 10217-7 - 1.4301 - TC 2 - Option 5: WCA - Option 9: 300 °C - Option 11: A - Option 15 - Option 19: 3.2 (to be issued by the manufacturer)

7 Manufacturing process

7.1 Steelmaking process

The steelmaking process is at the discretion of the manufacturer, but see Option 1.

Option 1: The purchaser shall be informed about the steelmaking process used. The process shall be reported in the inspection document.

7.2 Tube manufacture and conditions

7.2.1 The tubes shall be manufactured from hot or cold rolled plate, sheet or strip in accordance with EN 10028-7. They shall be longitudinally welded by fusion across the abutting edges using either an arc welding or a laser welding or an electron beam welding process, or a combination thereof. The definitions of these respective fusion welding methods are given in ISO/TR 25901-3:2016, 4.2. Welding can be performed with or without the addition of filler metal in accordance with one of the routes as specified in Table 1.

Unless Option 2 is specified, the manufacturing process and/or route are at the discretion of the manufacturer.

Option 2: The tube manufacturing process and/or route is specified by the purchaser.

The finished tubes shall not include welds used for joining together lengths of the hot or cold rolled strip prior to forming.

Option 3: (see Table 1).

Option 4: (see Table 1).

(standards itch ai)

Option 4: (see Table 1). (standards.iteh.ai)

7.2.2 The production (welding) process shall be qualified and approved under the tube manufacture's own QA system. For tubes to be used in pressure equipment under categories II, III, or IV of Directive 2014/68/EU (formerly 97/23/EC), the relevant operating procedures and personnel at the manufacturing mill shall be approved by a Notified Body or a recognized third party organization as per Article 20 of directive 2014/68/EU.

Table 1 — Tube manufacturing process, route, starting material, forming operation and weld condition

1	2	3	4	5
Route	Manufacturing process ^a	Starting material	Forming operation	Weld condition ^b
01		Hot or cold rolled strip	Continuous forming from strip	As welded ^{c e}
02	Arc welding			Welded, outside ground ^c e or bead worked *
03				Welded, bead worked *
04	Laser welding	Hot or cold rolled strip	Continuous forming from strip	Welded, outside ground ^c or bead worked [*]

1	2	3	4	5
05	Arc welding	Hot or cold rolled plate or sheet	Single forming from plate or sheet	As welded ^{d e}
06	Laser welding and arc welding **	Hot or cold rolled plate or sheet	Single forming from plate or sheet	As welded ^{d e}
07	Electron beam welding and arc welding **	Hot or cold rolled plate or sheet	Single forming from plate or sheet	As welded ^{d e}

^{*} Bead worked = bead rolled or bead hammered.

kSIST FprEN 10217-7:2020

https://standards.iteh.ai/catalog/standards/sist/fb6a6811-0072-48f3-94ea-

7.2.3 The types of delivery condition of the tubes are shown in Table 2. Unless Option 5 is specified, the selection of type of delivery condition is at the discretion of the manufacturer.

Option 5: The type of delivery condition is specified by the purchaser.

Table 2 — Delivery conditions

Symbol	Type of delivery condition ^a	Surface condition	
W0 р	Welded from hot or cold rolled plate, sheet or strip 1D, 2D, 2E, 2B, 2R	As welded ^f	
W1 b	Welded from hot rolled plate, sheet or strip 1D, descaled and/or pickled ^e	Metallically clean	
W1A b	Welded from hot rolled plate, sheet or strip 1D, heat treated, descaled and/or pickled ^e		
W1R b	Welded from hot rolled plate, sheet or strip 1D, bright annealed	Metallically bright	
W2 b	Welded from cold rolled plate, sheet or strip 2D, 2E, 2B, 2R, descaled and/or pickled ^e	Metallically clean	

^{**} For these tubes, i.e. tubes welded from plate or sheet, the laser welding and the electron beam welding processes.

^a For these tubes, i.e. tubes welded from plate or sheet, the laser welding and the electron beam welding processes are normally used in combination with an arc welding process.

b The terms "as-welded", "welded, outside ground", "bead worked" and "cold working" apply to the condition of the tube before heat treatment if required in accordance with Table 2.

On request, the inside weld can be re-melted. *Option 3:* The inside weld is re-melted.

d On request, the inside weld can be worked by rolling, remelting or grinding. **Option 4:** The inside weld is worked by rolling, remelting or grinding.

Standards iteh.ai

The weld seam can be welded using one or more separate layers.