



Designation: E458 – 08

Standard Test Method for Heat of Ablation¹

This standard is issued under the fixed designation E458; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers determination of the heat of ablation of materials subjected to thermal environments requiring the use of ablation as an energy dissipation process. Three concepts of the parameter are described and defined: cold wall, effective, and thermochemical heat of ablation.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E285 Test Method for Oxyacetylene Ablation Testing of Thermal Insulation Materials

E422 Test Method for Measuring Heat Flux Using a Water-Cooled Calorimeter

E457 Test Method for Measuring Heat-Transfer Rate Using a Thermal Capacitance (Slug) Calorimeter

E459 Test Method for Measuring Heat Transfer Rate Using a Thin-Skin Calorimeter

E511 Test Method for Measuring Heat Flux Using a Copper-Constantan Circular Foil, Heat-Flux Transducer

E617 Specification for Laboratory Weights and Precision Mass Standards

3. Terminology

3.1 *Descriptions of Terms Specific to This Standard:*

3.1.1 *heat of ablation*—a parameter that indicates the ability of a material to provide heat protection when used as a sacrificial thermal protection device. The parameter is a func-

¹ This test method is under the jurisdiction of ASTM Committee E21 on Space Simulation and Applications of Space Technology and is the direct responsibility of Subcommittee E21.08 on Thermal Protection.

Current edition approved May 1, 2008. Published July 2008. Originally approved in 1972. Last previous edition approved in 2002 as E458–72(2002) DOI: 10.1520/E0458-08.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

tion of both the material and the environment to which it is subjected. In general, it is defined as the incident heat dissipated by the ablative material per unit of mass removed, or

$$Q^* = q/m \quad (1)$$

where:

Q^* = heat of ablation, kJ/kg,
 q = incident heat transfer rate, kW/m², and
 m = total mass transfer rate, kg/m²·s.

3.1.2 The heat of ablation may be represented in three different ways depending on the investigator's requirements:

3.1.3 *cold-wall heat of ablation*—The most commonly and easily determined value is the cold-wall heat of ablation, and is defined as the incident cold-wall heat dissipated per unit mass of material ablated, as follows:

$$Q^*_{cw} = q_{cw}/m \quad (2)$$

where:

Q^*_{cw} = cold-wall heat of ablation, kJ/kg,
 q_{cw} = heat transfer rate from the test environment to a cold wall, kW/m², and
 m = total mass transfer rate, kg/m²·s.

The temperature of the cold-wall reference for the cold-wall heat transfer rate is usually considered to be room temperature or close enough such that the hot-wall correction given in Eq 8 is less than 5 % of the cold-wall heat transfer rate.

3.1.4 *effective heat of ablation*—The effective heat of ablation is defined as the incident hot-wall heat dissipated per unit mass ablated, as follows:

$$Q^*_{eff} = q_{hw}/m \quad (3)$$

where:

Q^*_{eff} = effective heat of ablation, kJ/kg,
 q_{hw} = heat transfer rate from the test environment to a nonablating wall at the surface temperature of the material under test, kW/m², and
 m = total mass transfer rate, kg/m²·s.

3.1.5 *thermochemical heat of ablation*—The derivation of the *thermochemical heat of ablation* originated with the simplistic surface energy equation employed in the early 60s to describe the effects of surface ablation, that is:

$$q_{hw} - q_{rr} = q_{cond} + q_{abl} + q_{block} \quad (4)$$

where:

- q_{rr} = energy re-radiated from the heated surface, kW/m²,
 q_{cond} = net energy conducted into the solid during steady-state ablation = $mc_p(T_w - T_o)$, kW/m²,
 q_{abl} = energy absorbed by surface ablation which, in simple terms, can be represented by $m\Delta H_v$, kW/m²,
 q_{block} = energy dissipated (blockage) by transpiration of ablation products into the boundary layer, which, in simple terms, can be represented by $m\eta(h_r - h_w)$, kW/m²,
 T_w = absolute surface temperature of ablating material, K,
 c_p = specific heat at constant pressure of ablating material, kJ/kg·K,
 T_o = initial surface temperature of ablating material, K,
 ΔH_v = an effective heat of vaporization, kJ/kg,
 η = a transpiration coefficient,
 h_r = gas recovery enthalpy, kJ/kg, and
 h_w = the wall enthalpy, kJ/kg.

Using the definitions above, Eq 4 can be rewritten as:

$$q_{hw} - q_{rr} = mc_p(T_w - T_o) + m\Delta H_v + m\eta(h_r - h_w) \quad (5)$$

where it should be apparent that the definition of the *thermochemical heat of ablation* is obtained by dividing Eq 4 by m , where it is understood that m is a steady-state ablation rate. The result is:

$$Q_{tc}^* = (q_{hw} - q_{rr})/m = c_p(T_w - T_o) + \Delta H_v + \eta(h_r - h_w) \quad (6)$$

As seen from Eq 6, definition of the *thermochemical heat of ablation* requires an ability to measure the cold-wall heat flux, an ability to define the recovery enthalpy, an ability to measure the surface temperature, knowledge of the total hemispherical emittance (at the temperature and state of the ablating surface), and the ability to determine the steady-state mass loss rate. Assuming these parameters can be measured (or estimated), the right hand side of Eq 6 implies that the *thermochemical heat of ablation* is a linear function of the enthalpy difference across the boundary layer, that is, $(h_r - h_w)$. Consequently, a plot of Q_{tc}^* (determined from several tests at different conditions) versus $(h_r - h_w)$ should allow a linear fit of the data where the slope of the fit is interpreted as η , the transpiration coefficient, and the y-intercept is interpreted as $c_p\Delta T + \Delta H_v$. If the specific heat of the material is known, the curve fit allows the effective heat of vaporization to be empirically derived.

3.2 The three heat of ablation values described in 3.1.2 require two basic determinations: the heat transfer rate and the mass transfer rate. These two quantities then assume various forms depending on the particular heat of ablation value being determined.

4. Significance and Use

4.1 *General*—The heat of ablation provides a measure of the ability of a material to serve as a heat protection element in a severe thermal environment. The parameter is a function of both the material and the environment to which it is subjected. It is therefore required that laboratory measurements of heat of ablation simulate the service environment as closely as possible. Some of the parameters affecting the heat of ablation are

pressure, gas composition, heat transfer rate, mode of heat transfer, and gas enthalpy. As laboratory duplication of all parameters is usually difficult, the user of the data should consider the differences between the service and the test environments. Screening tests of various materials under simulated use conditions may be quite valuable even if all the service environmental parameters are not available. These tests are useful in material selection studies, materials development work, and many other areas.

4.2 *Steady-State Conditions*—The nature of the definition of heat of ablation requires steady-state conditions. Variances from steady-state may be required in certain circumstances; however, it must be realized that transient phenomena make the values obtained functions of the test duration and therefore make material comparisons difficult.

4.2.1 *Temperature Requirements*—In a steady-state condition, the temperature propagation into the material will move at the same velocity as the gas-ablation surface interface. A constant distance is maintained between the ablation surface and the isotherm representing the temperature front. Under steady-state ablation the mass loss and length change are linearly related.

$$mt = \rho_o\delta_L + (\rho_o - \rho_c)\delta_c \quad (7)$$

where:

- t = test time, s,
 ρ_o = virgin material density, kg/m³,
 δ_L = change in length or ablation depth, m,
 ρ_c = char density, kg/m³, and
 δ_c = char depth, m.

This relationship may be used to verify the existence of steady-state ablation in the tests of charring ablators.

4.2.2 *Exposure Time Requirements*—The exposure time required to achieve steady-state may be determined experimentally by the use of multiple models by plotting the total mass loss as a function of the exposure time. The point at which the curve departs significantly from linearity is the minimum exposure time required for steady-state ablation to be established. Cases exist, however, in the area of very high heating rates and high shear where this type of test for steady-state may not be possible.

5. Determination of Heat Transfer Rate

5.1 Cold-Wall Heat Transfer Rate:

5.1.1 Determine the cold-wall heat transfer rate to a specimen by using a calorimeter. These instruments are available commercially in several different types, some of which can be readily fabricated by the investigator. Selection of a specific type is based on the test configuration and the methods used, and should take into consideration such parameters as instrument response time, test duration, and heat transfer rate (1³).

5.1.1.1 The calorimeters discussed in 5.1.1 measure a “cold-wall” heat transfer rate because the calorimeter surface temperature is much less than the ablation temperature. The value thus obtained is used directly in computing the cold-wall heat of ablation.

³ The boldface numbers in parentheses refer to the references listed at the end of the standard.

5.1.2 Install the calorimeter in a calorimeter body that duplicates the test model in size and configuration. This is done in order to eliminate geometric parameters from the heat transfer rate measurement and to ensure that the quantity measured is representative of the heat transfer rate to the test model. If the particular test run does not allow an independent heat transfer rate measurement, as in some nozzle liner and pipe flow tests, mount the calorimeter as near as possible to the location of the mass-loss measurements. Take care to ensure that the nonablating calorimeter does not affect the flow over the area under test. In axisymmetric flow fields, measurements of mass loss and heat transfer rate in the same plane, yet diametrically opposed, should be valid.

5.2 Computation of Effective and Thermochemical Heats of Ablation:

5.2.1 In order to compute the effective and thermochemical heats of ablation, correct the cold-wall heat transfer rate for the effect of the temperature difference on the heat transfer. This correction factor is a function of the ratio of the enthalpy potentials across the boundary layer for the hot and cold wall as follows:

$$q_{hw}/q_{cw} = [(h_e - h_{hw})/(h_e - h_{cw})] \quad (8)$$

where:

h_e = gas recovery enthalpy at the boundary layer edge, kJ/kg,

h_{hw} = gas enthalpy at the surface temperature of the test model, kJ/kg, and

h_{cw} = gas enthalpy at a cold wall, kJ/kg.

5.2.2 This correction is based upon laminar flow in air and subject to the restrictions imposed in Ref (2). Additional corrections may be required regarding the effect of temperature on the transport properties of the test gas. The form and use of these corrections should be determined by the investigator for each individual situation.

5.3 Gas Enthalpy Determination:

5.3.1 The enthalpy at the boundary layer edge may be determined in several ways: energy balance, enthalpy probe, spectroscopy, etc. Details of the methods may be found elsewhere (3-6). Take care to evaluate the radial variation of enthalpy in the nozzle. Also, in low-density flows, consider the effect of nonequilibrium on the evaluation. Determination of the gas enthalpy at the ablator surface and the calorimeter surface requires pressure and surface temperature measurements. The hot-wall temperatures are generally measured by optical methods such as pyrometers, radiometers, etc. Other methods such as infrared spectrometers and monochromators have been used (7,8). Effects of the optical properties of the boundary layer of an ablating surface make accurate determinations of surface temperature difficult.

5.3.2 Determine the wall enthalpy from the assumed state of the gas flow (equilibrium, frozen, or nonequilibrium), if the pressure and the wall temperature are known. It is further assumed that the wall enthalpy is the enthalpy of the freestream gas, without ablation products, at the wall temperature. Make the wall static pressure measurements with an ordinary pitot arrangement designed for the flow regime of interest and by using the appropriate transducers.

5.4 Reradiation Correction:

5.4.1 Calculate the heat transfer rate due to reradiation from the surface of the ablating material from the following equation:

$$q_{rr} = \sigma \epsilon T_w^4 \quad (9)$$

where:

σ = Stefan-Boltzmann constant, and,

ϵ = thermal emittance of the ablating surface.

5.4.2 Eq 9 assumes radiation through a transparent medium to a blackbody at absolute zero. Consider the validity of this assumption for each case and if the optical properties of the boundary layer are known and are deemed significant, or the absolute zero blackbody sink assumption is violated, consider these effects in the use of Eq 9.

5.5 Mechanical Removal Correction:

5.5.1 Determine the heat transfer rate due to the mechanical removal of material from the ablating surface from the mass-loss rate due to mechanical processes and the enthalpy of the material removed as follows:

$$q_{mech} = m_{mech} h_m \quad (10)$$

5.5.2 Approximate the enthalpy of the material removed by the product of the specific heat of the mechanically removed material, and the surface temperature (9-13).

6. Determination of Mass Transfer Rate

6.1 The determination of the heat of ablation requires the measurement of the mass transfer rate of the material under test. This may be accomplished in several ways depending on the type of material under test. The heat of ablation value can be affected by the choice of method.

6.1.1 Ablation Depth Method:

6.1.1.1 The simplest method of measurement of mass-loss rate is the change in length or ablation depth. Make a pretest and post-test measurement of the length and calculate the mass-loss rate from the following relationship:

$$m = \rho_o (\delta_L/t) \quad (11)$$

6.1.1.2 Determine the change in length with the time of a model under test, by using motion picture techniques. Note that observation of the front surface alone does not, however, verify the existence of steady state ablation. Take care, however, to provide appropriate reference marks for measuring the length change from the film. Timing marks on the film are also required to accurately determine the time parameter. Avoid using framing speed as a reference, as it generally does not provide the required accuracy.

6.1.1.3 Use the length change measurement of mass-loss rate for non-charring ablators, subliming materials, or with charring ablators under steady state ablation conditions (see Section 4) and only with materials that do not swell or grow in length.

6.1.2 Direct Weighing Method:

6.1.2.1 A second method of determining mass transfer rate is by the use of a pretest and post-test mass measurement. This procedure yields the mass transfer rate directly. A disadvantage of this method is that the mass transfer rate obtained is