



Designation: D1474 – 98 (Reapproved2008)

Standard Test Methods for Indentation Hardness of Organic Coatings¹

This standard is issued under the fixed designation D1474; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 These test methods cover the determination of the indentation hardness of organic materials such as dried paint, varnish, and lacquer coatings, when applied to an acceptable plane rigid surface, for example, metal or glass.

1.2 Two methods are covered as follows:

Method A—Knoop Indentation Hardness	Sections 6-12
Method B—Pfund Indentation Hardness	13-19

1.3 Method A, which has the greater precision, provides hardness values in terms of Knoop Hardness Number (KHN). Method B provides hardness in terms of Pfund Hardness Number (PHN). Although the hardness value scales of these methods differ, the methods agree in the ranking of coating hardness.

1.4 Test Method A of these test methods is similar in content (but not technically equivalent) to ISO 6441-1 and ISO 6441-2.

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels

¹ These test methods are under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and are the direct responsibility of Subcommittee D01.23 on Physical Properties of Applied Paint Films.

Current edition approved July 1, 2008. Published July 2008. Originally approved in 1957. Last previous edition approved in 2002 as D1474 – 98 (2002). DOI: 10.1520/D1474-98R08.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers

D1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base (Withdrawn 2006)³

D1400 Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base (Withdrawn 2006)³

E384 Test Method for Knoop and Vickers Hardness of Materials

2.2 *Other Standards:*

ISO 6441-1 Hardness testing—Part 1: Determination of Knoop hardness by measurement of the indentation length using a microscope⁴

ISO 6441-2 Hardness testing—Part 2: Determination of Knoop hardness by measurement of the indentation depth⁴

3. Terminology

3.1 *Definitions:*

3.1.1 *indentation hardness, n*—the resistance to penetration by an indenter.

3.1.2 *Knoop indenter, n*—a pyramidal diamond of prescribed dimensions.

3.1.3 *Pfund indenter, n*—hemispherical quartz or sapphire indenter of prescribed dimensions.

3.1.4 *Knoop hardness number, KHN, n*—the indentation hardness determined with a Knoop indenter, and calculated as follows:

$$KHN = L/A_p = L/l^2 C_p \quad (1)$$

where:

L = load applied to the indenter, kg,

l = measured length of long diagonal of the indentation, mm,

C_p = indenter constant relating l^2 to A_p , and

A_p = projected area of indentation, mm².

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

*A Summary of Changes section appears at the end of this standard

3.1.5 *Pfund hardness number, PHN, n*—the indentation hardness determined with a Pfund indenter, and calculated as follows:

$$PHN = L/A = 4L/\pi d^2 = 1.27 (L/d^2) \quad (2)$$

where:

L = load/kg applied to the indenter, kg,
 A = area of projected indentation, mm², and
 d = diameter of projected indentation, mm.

4. Significance and Use

4.1 Indentation hardness measurements have proven to be useful in rating coatings on rigid substrates for their resistance to mechanical abuse, such as that produced by blows, gouging, and scratching. These measurements do not necessarily characterize the resistance to mechanical abuse of coatings that are required to remain intact when deformed.

5. Test Specimens

5.1 The substrate for the coating shall be an acceptable plane rigid surface such as glass or metal.

5.2 The coating thickness on any one panel shall be uniform within 0.1 mil (3 μm). Coatings to be compared shall be of equal thickness within 0.2 mil (5 μm). For maximum accuracy, the minimum permissible coating thickness shall be such that the depth of indentation does not exceed three fourths of the coating thickness, to minimize the effect of the substrate.

5.3 At least three replicate specimens shall be tested for each coating to be evaluated.

5.4 Coatings should be applied in accordance with Practices **D823** and their dry film thickness should be measured in accordance with Test Methods **D1005**, **D1186**, or **D1400**.

5.5 From precoated sheets cut at least three specimens. Use only plane (flat) sheets and round the edges slightly. The coating shall be free of oil and other foreign matter. Measure the film thickness as in **5.4**.

METHOD A—KNOOP INDENTATION HARDNESS

6. Summary of Method

6.1 This method consists of applying a load to the surface of a coating by means of a pyramidal shaped diamond having specified face angles, and converting the measurements of the resultant permanent impression to a hardness number.

7. Apparatus

7.1 *Hardness Tester*,⁵ consisting of a load applicator, a Knoop indenter, and a microscope fitted with a movable micrometer stage. The apparatus shall mechanically bring the indenter into contact with the test surface with negligible impact, apply the selected full load, maintain it for 18 ± 0.5 s, and withdraw the indenter.

⁵ A hardness tester meeting the apparatus requirements for this method is the Tukon Microhardness Tester, available from the Wilson Instruments, Inc., Division of Instron, 100 Royall St., Canton, MA 02021.

7.2 *Knoop Indenter*—The Knoop indenter is a pyramidal diamond with included longitudinal angles of 172° 30' and included transverse angle of 130° 0'.

NOTE 1—The ratio of the long to the short diagonal of the impression is approximately 7:1; the ratio of the long diagonal to the depth of penetration is approximately 30:1.

7.3 *Microscope*—The microscope shall have a filar micrometer eyepiece and sufficient objectives to permit the measurement of the length of impression to within ±1%. The specimen shall be firmly supported on a movable micrometer stage attached to the microscope.

8. Calibration

8.1 Adjust the illumination in the microscope to give maximum contrast when viewing an indentation.

8.2 By means of a calibrated scale, determine the factor for each microscope objective that converts the filar scale units of the eyepiece to millimetres.

8.3 With a 25-g load on the indenter, determine the KHN of a calibrated standard (Note 2) with an assigned value not greater than 50 KHN. If the obtained value is within ±5% of the assigned value, the instrument is considered to be in calibration.

NOTE 2—A suitable source of standard reference materials in this hardness range is available from the U.S. National Institute for Standards and Technology.⁶ By agreement of the parties concerned, a stable specimen (such as an aged coating or a baked enamel applied to a flat substrate) could be used to calibrate the participating hardness testers.

9. Procedure

9.1 Unless otherwise specified, make the hardness determinations at 73.5 ± 3.50°F (23 ± 2°C) and 50 ± 5% relative humidity after equilibrating the specimens under these conditions for at least 24 h.

9.2 Rigidly attach the specimen to the movable stage so that the surface to be measured is normal to the direction of indentation. Mount the panel so that it cannot move with respect to the stage in any direction during the test.

9.3 Use the microscope to select an area of the test specimen that is free of surface irregularities and imperfections. Place this area under the indenter by means of the movable micrometer stage.

NOTE 3—If good impressions cannot be obtained because of the roughness of the surface of the specimen, gently polish the surface with No. 400 carborundum and finish off with jewelers rouge before making the impression.

9.4 Present the apparatus to apply a load that permits the length of identification to read accurately but does not cause the depth of indentation to exceed three-quarters of the coating film thickness. Start the test cycle so that the indenter is mechanically brought into contact with the mounted specimen under a load of 25 g and full load is applied, maintained for 18 ± 0.5 s, and removed. For maximum accuracy, ensure that the indenter has not penetrated the coating to a depth beyond three

⁶ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.