

SLOVENSKI STANDARD SIST EN 62321-8:2017

01-september-2017

Določevanje posameznih substanc v elektrotehniških izdelkih - 8. del: Ftalati v polimerih s plinsko kromatografijo-masno spektrometrijo (GC-MS), plinsko kromatografijo-masno spektrometrijo z uporabo pirolize/toplotne desorpcije (Py/TD-GC-MS)

Determination of certain substances in electrotechnical products - Part 8: Phthalates in polymers by gas chromatography-mass spectrometry (GC-MS), gas chromatography-mass spectrometry using a pyrolyzer/thermal desorption accessory (Py/TD-GC-MS)

(standards.iteh.ai)

SIST EN 62321-8:2017 https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486-38404f9e055a/sist-en-62321-8-2017

Ta slovenski standard je istoveten z: EN 62321-8:2017

ICS:

29.020 Elektrotehnika na splošno Electrical engineering in

general

31.020 Elektronske komponente na Electronic components in

splošno general

71.040.50 Fizikalnokemijske analitske Physicochemical methods of

metode analysis

SIST EN 62321-8:2017 en

SIST EN 62321-8:2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62321-8:2017 https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486-38404f9e055a/sist-en-62321-8-2017 EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM EN 62321-8

June 2017

ICS 31.020; 71.040.50

English Version

Determination of certain substances in electrotechnical products - Part 8: Phthalates in polymers by gas chromatography-mass spectrometry (GC-MS), gas chromatography-mass spectrometry using a pyrolyzer/thermal desorption accessory (Py/TD-GC-MS) (IEC 62321-8:2017)

Détermination de certaines substances dans les produits électrotechniques - Partie 8: Analyse des phtalates dans les polymères par chromatographie en phase gazeuse-spectrométrie de masse (GC-MS), chromatographie en phase gazeuse-spectrométrie de masse par pyrolyse/thermodésorption (Py/TD-GC-MS)

(IEC 62321-8:2017)

Verfahren zur Bestimmung von bestimmten Substanzen in Produkten der Elektrotechnik - Teil 8: Phthalate in Polymeren mit Pyrolyse-Gaschromatographie-Massenspektrometrie (Py-GC-MS), Ionen-Anlagerungs-Massenspektrometrie (IAMS), Gaschromatographie-Massenspektrometrie (GC-MS) und Flüssigchromatographie-Massenspektrometrie (LC-MS)

iTeh STANDARD PREVIEW

This European Standard was approved by CENELEC on 2017-05-02. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such actional standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member. 3840419e055a/sist-en-62321-8-2017

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN 62321-8:2017

European foreword

The text of document 111/416/CDV, future edition 1 of IEC 62321-8, prepared by IEC/TC 111 "Environmental standardization for electrical and electronic products and systems" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 62321-8:2017.

The following dates are fixed:

•	latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement	(dop)	2018-02-02
•	latest date by which the national standards conflicting with the document have to be withdrawn	(dow)	2020-05-02

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

The text of the International Standard IEC 62321-8.2017 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

ISO 3696

ISO/IEC 17025

NOTE Harmonized as EN ISO 3696.

NOTE IST Harmonized as EN ISO/IEC 17025.

https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486IEC 62321-2:2013

NOTE Harmonized as EN 62321-2:2014.

IEC 62321-6:2015

NOTE Harmonized as EN62321-6:2016

EN 62321-8:2017

Annex ZA

(normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 When an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

PublicationYearTitleEN/HDYearIEC 62321-12013Determination of certain substances in electrotechnical products -- Part 1:EN 62321-12013Introduction and overview

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62321-8:2017 https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486-38404f9e055a/sist-en-62321-8-2017 SIST EN 62321-8:2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62321-8:2017 https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486-38404f9e055a/sist-en-62321-8-2017



IEC 62321-8

Edition 1.0 2017-03

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Determination of certain substances in electrotechnical products – Part 8: Phthalates in polymers by gas chromatography-mass spectrometry (GC-MS), gas chromatography-mass spectrometry using a pyrolyzer/thermal desorption accessory (Py/TD-GC-MS)₆₂₃₂₁₋₈₂₀₁₇

https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486-

Détermination de certaines substances dans les produits électrotechniques – Partie 8: Analyse des phtalates dans les polymères par chromatographie en phase gazeuse-spectrométrie de masse (GC-MS), chromatographie en phase gazeuse-spectrométrie de masse par pyrolyse/thermodésorption (Py/TD-GC-MS)

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION ELECTROTECHNIQUE INTERNATIONALE

ICS 31.020; 71.040.50 ISBN 978-2-8322-4144-8

Warning! Make sure that you obtained this publication from an authorized distributor. Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

F	DREWO	RD	6
IN	TRODU	CTION	8
1	Scop	e	9
2	Norm	native references	9
3	Term	s, definitions and abbreviated terms	10
	3.1	Terms and definitions	
	3.2	Abbreviated terms	
4	Princ	iple	11
5	Reag	ents and materials	11
	5.1	GC-MS method	
	5.2	Py/TD-GC-MS method	
6	Appa	ratus	
	6.1	GC-MS method	12
	6.2	Py/TD-GC-MS method	
7	Samp	Dling	14
	7.1	General	14
	7.2	GC-MS method al. CTLA. N.D. D.	14
	7.3	Py/TD-GC-MS method	14
8	Proce	edure (standards.iteh.ai)	14
	8.1	General instructions for the analysis	14
	8.1.1	Overview <u>SIST EN 62321-8:2017</u>	14
	8.1.2	3X4D4tyeD559/gigt_en_67371_X_7DD7	14
	8.1.3	Py/TD-GC-MS method	14
	8.2	Sample preparation	
	8.2.1	GC-MS method	15
	8.2.2	7 .	
	8.3	Instrumental parameters	
	8.3.1	GC-MS method	
	8.3.2	7 .	
	8.4	Calibrants	
	8.5	Calibration	
	8.5.1	GC-MS method	
9	8.5.2	,	
Э		Jation of phthalate concentration	
	9.1	GC-MS method	
10	9.2 Dragi	Py/TD-GC-MS methodsion	
10			
	10.1 10.1.	GC-MS method	
	10.1.	, 3	
		Py/TD-GC-MS method	
	10.2	•	
	10.2.		
11		ity assurance and control	
	11.1	General	
			· · · · · · · · · · · · · · · · · · ·

11.2	GC-MS method	21
11.2	.1 Performance	27
11.2	.2 Limit of detection (LOD) or method detection limit (MDL) and limit of quantification (LOQ)	28
11.3	Py/TD-GC-MS method	29
11.3	.1 Sensitivity	29
11.3	.2 Blank test	29
11.3	.3 Limit of detection (LOD) or method detection limit (MDL) and limit of quantification (LOQ)	29
12 Test	report	30
Annex A mass spe	(informative) Determination of phthalates in polymers by ion attachment ectrometry (IAMS)	31
A.1	Principle	31
A.2	Reagents and materials	
A.3	Apparatus	31
A.4	Sampling	
A.5	Procedure	32
A.5.1	1 General instructions for the analysis	32
A.5.2	Sample preparation	32
A.5.3	3 Instrumental parameters	33
A.5.4	Calibration	34
A.5.5	J Calibration	
A.6	Calculation of phthalates concentration.iteh.ai	
A.7	Quality assurance and control	
A.7.1	1 General <u>SIST EN 62321-82017</u>	35
A.7.2	Sensitivityandards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486- 38404f9e055a/sist-en-62321-8-2017 Recovery	35
A.7.3	Recovery	35
A.7.4		36
A.7.5	Limit of detection (LOD) or method detection limit (MDL) and limit of quantification (LOQ)	37
A.8	Test report	37
	(informative) Determination of phthalates in polymers by liquid graphy-mass spectrometry(LC-MS)	38
B.1	Principle	38
B.2	Reagents and materials	38
B.3	Apparatus	38
B.4	Sampling	39
B.5	Procedure	39
B.5.1	1 General instructions for the analysis	39
B.5.2	Sample preparation	39
B.5.3	•	
B.5.4		
B.5.5		
B.6	Calculation of phthalates concentration	
B.7	Quality assurance and control	
B.7.1		
B.7.2		44
B.7.3	quantification (LOQ)	
B.8	Test report	45

Annex C (informative) Examples of chromatograms at suggested conditions	46
C.1 GC-MS method	46
C.2 Py/TD-GC-MS method	47
C.3 LC-MS method	47
C.4 IAMS method	_
Annex D (informative) Verification of the EGA thermal desorption zone	51
Annex E (informative) Example of IAMS and Py/TD-GC-MS instruments	52
Annex F (informative) Example of false positive detection of phthalates	54
Annex G (informative) Examples of sample preparation for quantitative analysis of phthalates by GC-MS	55
G.1 General	55
G.2 Soxhlet extraction of phthalates using proper organic solvents	55
Annex H (informative) Extraction of phthalates by dissolution in THF using sonication and precipitation of polymer matrix	58
Annex I (informative) Commercially available reference materials considered suitable for GC-MS and Py/TD-GC-MS	60
I.1 GC-MS	60
I.2 Py/TD-GC-MS	60
Annex J (informative) Commercially available capillary columns considered suitable for GC-MS and Py-GC-MS	62
Annex K (informative) Labware cleaning procedure for phthalate testing	63
K.1 With the use of a furnace (non-volumetric glassware only)	63
K.2 Without the use of a furnace (glassware and plastic-ware)	63
K.3 Estimation of cleanness of the inner areas of volumetric glassware	
Annex L (informative) Results of international internation	65
Annex M (informative) Sample analysis sequence	70
M.1 GC-MS	70
Annex N (informative) Flow chart	71
Bibliography	72
Figure C.1 – Total ion current chromatogram of each phthalate (10 μg/ml, 1 μl, splitless)	46
Figure C.2 – Extracted ion chromatogram of DINP (10 μ g/ml, 1 μ l, splitless)	46
Figure C.3 – Extracted ion chromatogram of DIDP (10 μg/ml, 1 μl, splitless)	47
Figure C.4 – Total ion current chromatogram of 100 μg/ml of phthalate mixture by Py/TD-GC-MS	47
Figure C.5 – Total ion current chromatogram of 5 μg/ml of phthalate mixture by LC-MS	48
Figure C.6 – Mass spectrum of each phthalate by IAMS	
Figure C.7 – Total ion current chromatogram of each absolute amount (0,08 μg) of phthalate mixture by IAMS	
Figure C.8 – Total ion current chromatogram of approximately 0,3 mg of PVC which contains 300 mg/kg of each phthalate mixture by IAMS (Absolute amount: 0,09 μ g)	50
Figure D.1 – Example of EGA thermogram of a PVC sample containing phthalates	51
Figure E.1 – Example of IAMS instrument	52
Figure E.2 – Example of Py/TD-GC-MS instrument	
Figure F.1 – Typical laboratory wares made of plastic materials that may cause	
phthalate contamination	54

Figure F.2 – Example of a chromatogram of a blank solvent (THF) in a plastic bottle showing DEHP contamination.	54
Figure G.1 – Recovery ratios of Di-(2-ethylhexyl) phthalate using Soxhlet extraction with different organic solvents	57
Figure G.2 – Comparison of recovery ratios of phthalates using different extracting conditions	57
Figure I.1 – Sample preparation of reference materials	61
Figure N.1 – Flow chart for screening step and quantitative step	71
Table 1 – Measurement condition of GC-MS	17
Table 2 – Reference masses for the quantification of each phthalate	17
Table 3 – Measurement condition of Py/TD-GC-MS	18
Table 4 – Calibration standard solution of phthalates	19
Table 5 – IIS5 Threshold judgement	23
Table 6 – IIS5 Repeatability and reproducibility	24
Table 7 – IIS5 screening and threshold judgement	25
Table 8 – IIS5 Repeatability and reproducibility	26
Table A.1 – Measurement condition of IAMS	34
Table A.2 – Certified value of constituent phthalates in KRISS CRM 113-03-006	36
Table B.1 – Measurement condition of LC-MS	42
Table B.2 – Standard stock solution concentrations iteh.ai)	43
Table G.1 – Recovery ratios of phthalates according to different Soxhlet extraction times (extracting solvent: n-hexane) <u>SISTEN 62321-8:2017</u>	56
Table H.1 – Comparison of the efficiency of the sample preparation method of dissolution in THF using sonication and precipitation of polymeric matrix with that of Soxhlet extraction for soluble sample.	58
Table H.2 – Comparison of the efficiency of the sample preparation method of dissolution in THF using sonication and precipitation of polymeric matrix with that of Soxhlet extraction for insoluble samples	59
Table I.1 – Example list of commercially available reference solutions considered suitable for GC-MS	60
Table I.2 – Example list of commercially available reference materials considered suitable for Py/TD-GC-MS	61
Table J.1 – Example list of commercially available capillary columns considered suitable for GC-MS and Py-GC-MS analysis	62
Table L.1 – Statistical data for Py/TD-GC-MS	65
Table L.2 – Statistical data for GC-MS	67
Table L.3 – Statistical data for IAMS	68
Table L.4 – Statistical Data For LC-MS	69
Table M.1 – Sample analysis sequence for GC-MS analysis	70
Table M.2 – Sample analysis sequence for Py/TD-GC-MS analysis	70

INTERNATIONAL ELECTROTECHNICAL COMMISSION

DETERMINATION OF CERTAIN SUBSTANCES IN ELECTROTECHNICAL PRODUCTS –

Part 8: Phthalates in polymers by gas chromatography-mass spectrometry (GC-MS), gas chromatography-mass spectrometry using a pyrolyzer/thermal desorption accessory (Py/TD-GC-MS)

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.

 SIST EN 62321-8:2017
- 4) In order to promote international uniformity lecunational committees undertake to apply IEC Publications transparently to the maximum extent possible in their mational and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62321-8 has been prepared by IEC technical committee 111: Environmental standardization for electrical and electronic products and systems.

The text of this International Standard is based on the following documents:

CDV	Report on voting
111/416/CDV	111/430/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

IEC 62321-8:2017 © IEC 2017

-7-

A list of all parts in the IEC 62321 series, published under the general title: *Determination of certain substances in electrotechnical products*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- · replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 62321-8:2017</u> https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486-38404f9e055a/sist-en-62321-8-2017

IEC 62321-8:2017 © IEC 2017

INTRODUCTION

The widespread use of electrotechnical products has drawn increased attention to their impact on the environment. In many countries all over the world this has resulted in the adaptation of regulations affecting wastes, substances and energy use of electrotechnical products.

The use of certain substances (e.g. lead (Pb), cadmium (Cd), polybrominated diphenyl ethers (PBDEs) and specific phthalates) in electrotechnical products is a source of concern in current and proposed regional legislation.

The purpose of the IEC 62321 series is therefore to provide test methods that will allow the electrotechnical industry to determine the levels of certain substances of concern in electrotechnical products on a consistent global basis.

This first edition of IEC 62321-8 introduces a new part in the IEC 62321 series.

WARNING – Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 62321-8:2017</u> https://standards.iteh.ai/catalog/standards/sist/be4d156e-dae2-4c0f-a486-38404f9e055a/sist-en-62321-8-2017

- 8 -

-9-

DETERMINATION OF CERTAIN SUBSTANCES IN ELECTROTECHNICAL PRODUCTS –

Part 8: Phthalates in polymers by gas chromatography-mass spectrometry (GC-MS), gas chromatography-mass spectrometry using a pyrolyzer/thermal desorption accessory (Py/TD-GC-MS)

1 Scope

This part of IEC 62321 specifies two normative and two informative techniques for the determination of di-isobutyl phthalate (DIBP), di-n-butyl phthalate (DBP), benzylbutyl phthalate (BBP), di-(2-ethylhexyl) phthalate (DEHP), di-n-octyl phthalate (DNOP), di-isononyl phthalate (DINP) and di-iso-decyl phthalate (DIDP) in polymers of electrotechnical products.

Gas chromatography-mass spectrometry (GC-MS) and gas chromatography-mass spectrometry (Py/TD-GC-MS) techniques are described in the normative part of this document.

The GC-MS method is considered the referee technique for the quantitative determination of DIBP, DBP, BBP, DEHP, DNOP, DINP and DIDP in the range of 50 mg/kg to 2 000 mg/kg.

The GC-MS coupled with a pyrolyzer/thermal desorption (TD) accessory is suitable for screening and semi-quantitative analysis of DIBP, DBP, BBP, DEHP, DNOP, DINP, and DIDP in polymers that are used as parts of the electrotechnical products in the range of 100 mg/kg to 2 000 mg/kg.

SISTEN 62321-8:2017

The IAMS technique is suitable for screening and semi-quantitative analysis of DIBP, DBP, BBP, DEHP, DNOP, DINP, and DIDP. Determination of DBP and DIBP, DEHP and DNOP by IAMS has not been established due to peak and mass spectral resolution limitations.

The LC-MS technique is limited to the determination of of BBP, DEHP, DNOP, DINP, and DIDP. Determination of DBP and DIBP by LC-MS has not been established due to peak and mass spectral resolution limitations.

A flow chart depicting how the normative Py/TD-GC-MS and GC-MS methods and informative methods using ion attachment mass spectrometry (IAMS) coupled with direct injection probe (DIP) and liquid chromatography-mass spectrometry (LC-MS) can be used are provided in annexes of this document.

These four test methods have been evaluated by the test of PE (polyethylene) and PVC (polyvinyl chloride) materials containing individual phthalates between ~450 mg/kg to 30 000 mg/kg as depicted in the normative and informative parts of this document. The use of the four methods described in this document for other polymer types, phthalate compounds or concentration ranges other than those specified above has not been specifically evaluated.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62321-1:2013, Determination of certain substances in electrotechnical products – Part 1: Introduction and overview