



Designation: D451 – 91 (Reapproved2008)

Standard Test Method for Sieve Analysis of Granular Mineral Surfacing For Asphalt Roofing Products¹

This standard is issued under the fixed designation D451; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the particle size distribution of granular mineral surfacing material such as crushed slate, stone, coated granules, and so forth, used on the weather surface of prepared asphalt roofing and shingles.

1.2 The values stated in SI units are to be regarded as standard. The values given in parentheses are mathematical conversions to inch-pound units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

3. Summary of Test Method

3.1 A weighed sample of granular mineral surfacing material is separated through a series of sieves of progressively smaller openings for the determination of particle size distribution.

4. Significance and Use

4.1 This test method is used to determine the grading of materials used as granular mineral surfacing. The results are used to determine compliance of the particle size distribution with applicable specification requirements.

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.02 on Steep Roofing Products and Assemblies.

Current edition approved July 1, 2008. Published July 2008. Originally approved in 1973. Last previous edition approved in 2002 as D451 – 91 (2002). DOI: 10.1520/D0451-91R08.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Apparatus

5.1 *Sieves*—A set of the sieves listed in **Table 1**, conforming to Specification **E11**. For routine testing, the group of sieves actually used shall include only those appropriate for the granular material being graded. Coarser or finer sieves, on which less than 0.05 mass % of the specimen would be found after sieving, need not be included in the group.

5.2 *Sieve Shaker*— A mechanically operated sieve shaker that produces a uniform rotary motion and tapping action with 140 to 160 taps per minute. The sieve shaker shall be fitted with a hard maple plug to receive the impact of the tapping device. The entire apparatus shall be rigidly mounted by bolting to a solid foundation, preferably concrete.

5.3 *Sample Splitter*— A riffle sampler with 9.5 or 12.7-mm ($\frac{3}{8}$ or $\frac{1}{2}$ -in) divisions, for reducing the sample to the specimen required for sieve analysis.

5.4 *Balance*—A laboratory balance sensitive to 0.1 g.

6. Sampling

6.1 Each shipment of mineral granules of a single type shall be considered a unit for sampling. If a shipment contains more than one type of granule, the entire quantity of each type in the vehicle shall be considered a unit for sampling.

6.2 Take the sample of mineral granules shipped in bulk from the chute or conveyor while the vehicle is being loaded or unloaded. The ideal place is just where the material drops from the chute or belt. Collect equal portions from the full width and thickness of the stream at regular intervals with such frequency that a minimum of five samples will be taken and the total mass of the sample will not be less than 7.3 kg (16 lb). Do not allow the sampling receptacle to overflow under any circumstances. Overflow would tend to reject a higher proportion of the large particles than the small ones, and a representative sample would not be obtained. The sample should not include the initial material discharge from the chute or conveyor.

6.3 Take the sample from a shipment of mineral granules shipped in bags, selected at random and equal in number to the cube root of the total number of bags in the vehicle. Collect equal portions of 800 to 900 g from each of the bags taken for sampling and combine.