
**Mechanical vibration and shock —
Characterization of the dynamic
mechanical properties of visco-elastic
materials —**

Part 6:

Time-temperature superposition

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Vibrations et chocs mécaniques — Caractérisation des propriétés
mécaniques dynamiques des matériaux visco-élastiques —*

Partie 6: Superposition du temps et de la température

<https://standards.iteh.ai/catalog/standards/sist/38585781-6eee-49f-a9a6-e20c2d6ea1d4/iso-18437-6-2017>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18437-6:2017

<https://standards.iteh.ai/catalog/standards/sist/38585781-6eee-49f-a9a6-e20c2d6ea1d4/iso-18437-6-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Prediction of complete range of visco-elastic properties and description of data	3
4.1 Time-temperature superposition (TTS) principle.....	3
4.2 Data acquisition.....	3
4.2.1 New data.....	3
4.2.2 Existing data.....	4
4.2.3 Data scatter and determination of thermorheological simplicity.....	4
4.3 Shifting.....	5
4.3.1 Vertical shifting.....	5
4.3.2 Horizontal shifting.....	5
4.3.3 Dynamic visco-elastic functions master curves.....	6
5 Verification	6
6 Main sources of uncertainty	6
6.1 General.....	6
6.2 Narrow width of overlapping between the segments (isotherms).....	6
6.3 Presence of big experimental error (more than 10 %) in the segments.....	7
6.4 Low density of experimental datum points in the segment.....	7
6.5 Inappropriately arranged input data — presence of “end effects” in the segments.....	7
6.6 Selection of reference temperature.....	7
7 Results and processing	7
7.1 Data presentation.....	7
7.2 Test report.....	8
Annex A (informative) Closed form shifting (CFS) methodology	9
Annex B (informative) Example of storage modulus master curve construction	13
Annex C (informative) Computer-interpretable listings	23
Bibliography	24

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 108, *Mechanical vibration, shock and condition monitoring*.
ISO 18437-6:2017

<https://standards.iteh.ai/catalog/standards/sist/38585781-6eee-49f-a9a6-70b21f4b160e/iso-18437-6-2017>

A list of all parts in the ISO 18437 series can be found on the ISO website.

Introduction

Visco-elastic materials are used extensively to reduce vibration amplitudes in structural systems through dissipation of energy (damping) or isolation of components and in acoustical applications that require a modification of the reflection, transmission or absorption of energy. The design, modelling and characterization of such systems often require specific dynamic mechanical properties in order to function in an optimum manner. For most visco-elastic materials, these properties depend on frequency, temperature and amplitude of applied excitation. The aim of this document is to provide details on the best way of data acquisition for subsequent processing and to provide a standard method for analysis using the time-temperature superposition principle. This document applies to the linear behaviour observed at small strain (stress) amplitudes and to thermorheologically simple materials.

This document presents a method for checking the validity of a thermorheological simplicity of a material and for identifying and eliminating questionable data. It provides minimal criteria for data acquisition to be applied in mathematical methodologies, which allow multiple data sets of dynamic visco-elastic properties measured at different temperatures to be cast into a single master curve according to the time-temperature superposition (TTS) principle. When sufficient data are obtained or available, a standard method, which uses a closed form shifting algorithm^{[16][17]}, is defined.

TTS is the most widely-used method for accelerated prediction of long-term visco-elastic behaviour of materials^[13]. In the frequency domain, TTS can be used for predicting the behaviour of materials at frequencies that are experimentally not assessable.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 18437-6:2017](https://standards.iteh.ai/catalog/standards/sist/38585781-6eee-49f-a9a6-e20c2d6ea1d4/iso-18437-6-2017)

<https://standards.iteh.ai/catalog/standards/sist/38585781-6eee-49f-a9a6-e20c2d6ea1d4/iso-18437-6-2017>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18437-6:2017

<https://standards.iteh.ai/catalog/standards/sist/38585781-6eee-49f-a9a6-e20c2d6ea1d4/iso-18437-6-2017>

Mechanical vibration and shock — Characterization of the dynamic mechanical properties of visco-elastic materials —

Part 6: Time-temperature superposition

1 Scope

This document specifies a standard method for the acquisition and analysis of data obtained using the test methods found in ISO 18437-1 to ISO 18437-5, ISO 6721-4 to ISO 6721-7 and ISO 6721-12.

It is applicable to visco-elastic materials that are thermorheologically simple and that have been tested at equilibrium state for every temperature.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 18437-1, *Mechanical vibration and shock — Characterization of the dynamic mechanical properties of visco-elastic materials — Part 1: Principles and guidelines*

<https://standards.iteh.ai/catalog/standards/sist/38585781-6eee-49f-a9a6-e20c2d6ea1d4/iso-18437-6-2017>

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18437-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

dynamic visco-elastic function

fundamental visco-elastic property, i.e. storage moduli and loss moduli, measured in tension, shear and compression and loss factor as functions of frequency and temperature

3.2

storage modulus

M'

real part of the complex modulus

Note 1 to entry: It is a measure of the energy stored and regained during a loading cycle.

Note 2 to entry: Storage moduli in tension, shear and compression are denoted as E' , G' and K' , respectively.

Note 3 to entry: It is expressed in pascals (Pa).

[SOURCE: ISO 472:2013, 2.998, modified — Notes to entry have been added.]

**3.3
loss modulus**

M''
imaginary part of the complex modulus

Note 1 to entry: It is a measure of the energy lost (dissipated) during a loading cycle.

Note 2 to entry: Loss moduli in tension, shear and compression are denoted as E'' , G'' and K'' , respectively.

Note 3 to entry: It is expressed in pascals (Pa).

[SOURCE: ISO 472:2013, 2.559, modified — Notes to entry have been added.]

**3.4
loss factor**

$\tan \delta$
ratio of the *loss modulus* (3.3) to the *storage modulus* (3.2) measured in tension, shear, compression or longitudinal compression

Note 1 to entry: It is given by the quotient $\tan \delta = M''/M'$.

[SOURCE: ISO 472:2013, 2.557, modified — the definition has been revised.]

**3.5
time-temperature superposition
TTS**

principle by which, for visco-elastic materials, time and temperature are equivalent to the extent that data at one temperature can be superimposed upon data taken at different temperature merely by shifting the data curves along the logarithmic time axis

Note 1 to entry: In case of dynamic measurements, the term “frequency-temperature superposition” would be more accurate, but is less commonly used. The term “method of reduced variables” is also used to refer to this principle.

[SOURCE: ISO 18437-2:2005, 3.3, modified — “frequency axis” has been replaced by “logarithmic time axis” and Note 1 to entry has been added.]

**3.6
thermorheologically simple material**

material for which *time-temperature superposition* (3.5) is applicable

Note 1 to entry: A material which fails to superimpose, due to multiple transitions or crystallinity is, for example, thermorheologically complex.

Note 2 to entry: In thermorheologically complex systems, all relaxation times at a certain temperature may not be simply related to the relaxation times at a different temperature by a constant ratio. Thus, a multiphase system is thermorheologically complex if the individual *shift factors* (3.7) depend on time as well as temperature.

**3.7
shift factor**

$\lg a_T$
measure of the amount of shift along the logarithmic (base 10) axis of frequency for one set of constant-temperature data to superimpose upon another set of data

Note 1 to entry: The expression “shift factor” commonly refers to horizontal shift factor.

[SOURCE: ISO 18437-2:2005, 3.4, modified — Note 1 to entry has been added.]

3.8 vertical shift factor

$\lg b_T$

measure of the amount of shift along the logarithmic (base 10) axis of modulus to account the effect of a change from reference temperature to the temperature of interest

3.9 master curve

curve constructed by *time-temperature superposition* (3.5), which is identical to the behaviour of material that would be found (measured) at broad frequency range at the reference temperature if the experiment can be performed

4 Prediction of complete range of visco-elastic properties and description of data

4.1 Time-temperature superposition (TTS) principle

TTS is the most widely-used method for the accelerated prediction of complete visco-elastic behaviour of materials[13]. TTS is applied as follows: a series of dynamic mechanical experiments is carried out at different constant temperatures over a given short frame of frequencies, commonly called the experimental window. Thus, a set of isothermal segments of dynamic visco-elastic function is obtained. The isotherms are first shifted vertically, to account for temperature and density change and then horizontally along the logarithmic frequency scale towards a reference segment measured at reference temperature, T_R . The curve constructed by TTS is called a master curve. TTS asserts that the resulting master curve is identical to the behaviour of a material if it was measured with a broad frequency range at the reference temperature. The result of applying TTS to isotherms measured within experimentally reasonable frequency frames is a measure of material behaviour over a broad frequency range.

NOTE 1 Loss factor, as the ratio between loss and storage data, does not require vertical shifting[17].

There are several criteria for the applicability of TTS[13].

- a) The shapes of the isotherms at different temperatures shall match over a substantial range of frequencies.
- b) The same values of shift factor, a_T , shall superimpose all dynamic visco-elastic functions.
- c) The temperature dependence of a_T shall be a smooth function of temperature with no gross fluctuations or irregularities.

NOTE 2 The temperature dependence of the shift function, a_T , is commonly modelled with time-temperature superposition models, such as Arrhenius[14] or Williams-Landel-Ferry (WLF)[13] relationships. More information on the WLF model is given in ISO 18437-4 and ISO 4664-1.

4.2 Data acquisition

4.2.1 New data

The acquisition of new data shall be sufficiently detailed with enough temperatures and frequencies so as to provide sufficient overlap of the frequency data points when shifted from one temperature to another. An example of good quality data are dynamic mechanical analyser (DMA) data taken every 5 °C using frequencies of: 0,1; 0,2; 0,3; 0,5; 1; 2; 3; 5; 10; 20; and 30 Hz and/or the dynamic data which has one decade of overlapping between neighbouring isotherms along the logarithmic frequency axis.

Theoretically, TTS is not limited to any frequency range of experimental window. However, the frequency range shall be selected in line with other existing standards and capabilities of a measuring instrument.

The temperature range shall be defined according to capabilities of an experimental setup, taking into account that the maximum temperature shall be limited to the temperature at which the sample still sustains its geometry, i.e. does not change geometry due to its own weight.

4.2.2 Existing data

If the existing data meet the criteria in 4.2.1, then they may be processed in the same way as new data. If the data are isochronal or do not have sufficient overlapping, then the corresponding experiments shall be carried out in accordance with the requirements given in this document.

If this is not possible, then an alternative method that is not part of this document can suffice^[15] but shall not be construed to be part of this document.


4.2.3 Data scatter and determination of thermorheological simplicity

If the material is thermorheologically simple, a_T is a smooth function of temperature with no gross fluctuations or irregularities and there is only one transition in the complete spectrum of frequencies and temperatures, then a plot of the loss factor versus storage modulus (called a wicket plot) will be a simple smooth curve, usually of an inverted “U” shape^[15].

NOTE If there is more than one temperature transition in a polymer but all have the same shift function, a_T , then all the temperature and frequency data will still reduce to a single wicket plot curve but that curve will not be a simple single inverted “U”.

The wicket plot shall be used as a quantitative indication of the scatter of experimental data. The width of the band of data, as well as the departure of individual points from the centre of the band, is indicative of scatter. Individual points that are sufficiently displaced from the smooth wicket plot band shall be removed or the data shall be repeated to determine its validity. Nothing is revealed about the accuracy of the temperature and frequency data or about any systematic error.

[Figure 1](#) is an example of a wicket plot. <https://www.iso.org/standards/catalog/standards/sist/38585781-6eee-49f-a9a6-e20c2d6ea1d4/iso-18437-6-2017>



Key

X lg Young's modulus, in Pa

Y loss factor

Figure 1 — Example of a Wicket plot of computer-generated data for a high loss material with a maximum 10 % error in modulus and maximum 10 % error in loss factor

4.3 Shifting

4.3.1 Vertical shifting

Storage and loss data shall be firstly adjusted vertically and then shifted horizontally.

Frequently for solid visco-elastic materials the vertical shifting is small and may be ignored when forming master curves by TTS[14]. However, for some visco-elastic materials and/or certain testing conditions, e.g. broad temperature range, the vertical adjustment of dynamic visco-elastic functions can be significant. The lack of implementation of vertical shifting can lead to substantial errors in the prediction of properties over a wide frequency range. Therefore, vertical shifting shall proceed any horizontal shifting.

4.3.2 Horizontal shifting

The closed form shifting (CFS) algorithm[16][17] for calculation of horizontal shift factors shall be used whenever sufficient data are available to use this method. The method is based on the assumption that

two neighbouring segments can be superimposed when the overlapping area between them is equal to zero.

The details of the method are beyond the scope of this document but are presented in [Annex A](#) and [Annex B](#).

This methodology shall be used when implementing this document. As an example, a Microsoft® Excel¹⁾ macro with CFS methodology is included in [Annex C](#).

4.3.3 Dynamic visco-elastic functions master curves

Criterion b) of the applicability of TTS (see [4.1](#)) implies that the horizontal shift factors shall be defined from one function only. Since the storage modulus is usually measured more accurately and has less scatter than the loss modulus or loss factor, it shall be chosen for TTS. Horizontal shift factors determined from [4.3.2](#) shall be applied for shifting of other dynamic visco-elastic functions such as loss modulus and loss factor (see ISO 18437-2 and ISO 18437-3). It shall be taken into account that loss modulus, in the same way as storage modulus, requires vertical shifting.

A master curve of the storage modulus based on data measured at different temperatures is obtained by plotting $b_T M'$ versus $a_T \omega$ using base 10 logarithmic scale for both axes.

NOTE When the storage modulus is essentially flat, the loss modulus or loss factor can provide more accurate shifting. Corresponding formulae are available in Reference [\[17\]](#) but are not part of this document.

5 Verification

iTeh STANDARD PREVIEW

A check of the data consistency shall be done by plotting loss factor versus the logarithmic magnitude of the storage modulus without regard to temperature or frequency to verify that it is a single smooth band of data. For more details, see [4.3](#), ISO 18437-4 and ISO 10112.

The segments of dynamic visco-elastic functions to be shifted shall fulfil the TTS criteria in [4.1](#). If for any reason the criteria are violated, the TTS in its simple form as described in [4.1](#) shall be rejected; no master curve shall be drawn without subjecting the data to a more complicated analysis^[13].

6 Main sources of uncertainty

6.1 General

Uncertainties of the shifting procedure (not the experimental technique) mostly follow from the anomalies in measured segments due to the weaknesses of the experiment itself, such as the improper sample preparation or sample treatment, bad clamping of the sample, improper implementation of the experiment or improper pre-processing of the data.

The main sources of uncertainties are described in [6.2](#) to [6.6](#).

6.2 Narrow width of overlapping between the segments (isotherms)

When the experiment yields segments with narrow overlapping, the shifting may result in the master curve and/or shift factors with a low precision. In this case, it is recommended to reestablish the experimental procedure that will yield segments with satisfactory overlapping (see [4.2.1](#)).

1) Excel is the trademark of a product supplied by Microsoft®. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.