
**Welding and allied processes — Types
of joint preparation —**

Part 1:

**Manual metal arc welding, gas-
shielded metal arc welding, gas
welding, TIG welding and beam
welding of steels**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Soudage et techniques connexes — Types de préparation de joints —

*Partie 1: Soudage manuel à l'arc avec électrode enrobée, soudage à
l'arc avec électrode fusible sous protection gazeuse, soudage aux gaz,
soudage TIG et soudage par faisceau des aciers*



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9692-1:2013

<https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de9e8/iso-9692-1-2013>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Materials	1
4 Welding processes	1
5 Finish	2
6 Type of joint preparation	2
Bibliography	14

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9692-1:2013](https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de9e8/iso-9692-1-2013)

<https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de9e8/iso-9692-1-2013>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. www.iso.org/directives

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. www.iso.org/patents

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*, Subcommittee SC 7, *Representation and terms*.

This second edition of ISO 9692-1 ~~is cancelled and replaced by ISO 9692-1:2013, which has been technically revised.~~ www.iso.org/iso/9692-1-2013

ISO 9692 consists of the following parts, under the general title *Welding and allied processes — Types of joint preparation*:

- *Part 1: Manual metal arc welding, gas-shielded metal arc welding, gas welding, TIG welding, and beam welding of steels*
- *Part 2: Submerged arc welding of steels*
- *Part 3: Metal inert gas welding and tungsten inert gas welding of aluminium and its alloys*
- *Part 4: Clad steels*

Introduction

This part of ISO 9692 defines the parameters characterizing the joint preparation and the collection of frequently recurring values and shapes.

The specifications given in this part of ISO 9692 have been compiled on the basis of experience and contain dimensions for types of joint preparation that are generally found to lead to suitable welding conditions. However, the extended field of application makes it necessary to give a range of dimensions. The dimension ranges specified represent design limits and are not tolerances for manufacturing purposes. Manufacturing limits depend, for instance, on welding process, parent metal, welding position, and quality level. Because of the common character of this part of ISO 9692, the examples given cannot be regarded as the only solution for the selection of a joint type.

Specific fields of application and manufacturing requirements (e.g. pipeline construction) may be covered by selected ranges specified in other standards adapted from this basic part of ISO 9692.

Requests for official interpretations of any aspect of this part of ISO 9692 should be directed to the Secretariat of ISO/TC 44/SC 7 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9692-1:2013](https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de9e8/iso-9692-1-2013)

<https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de9e8/iso-9692-1-2013>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9692-1:2013

<https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de9e8/iso-9692-1-2013>

Welding and allied processes — Types of joint preparation —

Part 1:

Manual metal arc welding, gas-shielded metal arc welding, gas welding, TIG welding and beam welding of steels

1 Scope

This part of ISO 9692 specifies types of joint preparation for manual metal arc welding, gas-shielded metal arc welding, gas welding, TIG welding, and beam welding of steel (see [Clauses 3](#) and [4](#)).

It applies to joint preparation for full penetration butt welds and for fillet welds. For partial penetration butt welds, types of joint preparation and dimensions differing from those specified in this part of ISO 9692 may be stipulated.

The root gaps referred to in this part of ISO 9692 are those gaps presented after tack welding, if used.

Consideration is given to altering the joint preparation details (where appropriate) to facilitate temporary backing, "one-sided welding," etc.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6947, *Welding and allied processes — Welding positions*

3 Materials

Joint preparations recommended in this part of ISO 9692 are suitable for all kinds of steel.

4 Welding processes

Joint preparations recommended in this part of ISO 9692 are suitable for welding carried out in accordance with the following processes as specified in [Tables 1](#) to [4](#) (combinations of different processes are possible):

- a) (3) gas welding; oxyfuel gas welding;
- b) (111) manual metal arc welding (metal arc welding with covered electrode); shielded metal arc welding;
- c) (13) gas-shielded metal arc welding; gas metal arc welding includes:
 - (131) MIG welding with solid wire electrode; gas metal arc welding using inert gas and solid wire electrode;
 - (132) MIG welding with flux cored electrode; flux cored arc welding;
 - (133) MIG welding with metal cored electrode; gas metal arc welding using inert gas and metal cored wire;

- (135) MAG welding with solid wire electrode; gas metal arc welding using active gas and solid wire electrode;
 - (136) MAG welding with flux cored electrode; gas metal arc welding using active gas and flux cored electrode;
 - (138) MAG welding with metal cored electrode; gas metal arc welding using active gas and metal cored electrode;
- d) (141) TIG welding with solid filler material (wire/rod); gas tungsten arc welding using inert gas and solid filler material (wire/rod);
- e) (5) beam welding:
- (51) electron beam welding;
 - (512) electron beam welding in atmosphere;
 - (52) laser welding; laser beam welding.

NOTE The numbers in parentheses refer to the reference number of the welding process specified in ISO 4063.^[2]

5 Finish

The longitudinal edges of the root face should be de-burred and may be chamfered (up to 2 mm).

iTeh STANDARD PREVIEW

6 Type of joint preparation (standards.iteh.ai)

The recommended types of joint preparation and dimensions are specified in [Tables 1 to 4](#).

[ISO 9692-1:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de9e8/iso-9692-1-2013>

Table 1 — Joint preparations for butt welds, welded from one side

Ref. No.	Material thickness t mm	Type of preparation	Symbol (in accordance with ISO 2553(1))	Cross-section	Dimensions			Recommended welding process (reference No. in accordance with ISO 4063(2))	Weld illustration	Remarks
					Angle ^a α, β	Gap ^b b mm	Thickness of root face c mm			
1.1	≤ 2	Raised edges			—	—	—	3 111 141 512		Usually without filler metal
1.2.1	≤ 4	Square preparation			—	—	3 111 141		—	
1.2.2	$3 < t \leq 8$						13 141c			
	≤ 15						52		Where applicable with backing strip	
1.2.3	≤ 100	Square preparation with backing			—	—	51		—	
1.2.4		Square preparation with centering lip			—	—				
1.3	$3 < t \leq 10$ $8 < t \leq 12$	Single-V preparation			≤ 4	≤ 2	3 111 13 141		Where applicable with backing strip	
							52d			

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 9692-1:2013
<https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961f63de5e9/iso-9692-1-2013>

Table 1 (continued)

Ref. No.	Material thickness t mm	Type of preparation	Symbol (in accordance with ISO 2553(1))	Cross-section	Dimensions				Recommended welding process (reference No. in accordance with ISO 4063(2))	Weld illustration	Remarks
					Angle ^a α, β	Gap ^b b mm	Thickness of root face c mm	Depth of preparation h mm			
1.4	>16	Steep-flanked single-V preparation			$5^\circ \leq \beta \leq 20^\circ$	$5 \leq b \leq 15$	—	—	111 13		With backing strip
1.5	$5 \leq t \leq 40$	Single-V preparation with broad root face			$\alpha \approx 60^\circ$	$1 \leq b \leq 4$	$2 \leq c \leq 4$	—	111 13 141		—
1.6	>12	Single-U preparation with V root			$60^\circ \leq \alpha \leq 90^\circ$ $8^\circ \leq \beta \leq 15^\circ$	$1 \leq b \leq 3$	—	~4	111 13 141		$6 \leq R \leq 9$
1.7	>12	Single-V preparation with V root			$60^\circ \leq \alpha \leq 90^\circ$ $10^\circ \leq \beta \leq 15^\circ$	$2 \leq b \leq 4$	≤ 2	—	111 13 141		—

ISO 9692-1:2013
<https://standards.iteh.ai/catalog/standards/sist/c022fda0-641d-4c3a-8295-8961663de9e8/iso-9692-1-2013>

Table 1 (continued)

Ref. No.	Material thickness t mm	Type of preparation	Symbol (in accordance with ISO 2553(1))	Cross-section	Dimensions				Recommended welding process (reference No. in accordance with ISO 4063(2))	Weld illustration	Remarks
					Angle ^a α, β	Gap ^b b mm	Thickness of root face c mm	Depth of preparation h mm			
1.8	>12	Single-U preparation			$8^\circ \leq \beta \leq 12^\circ$	≤ 4	≤ 3	—		—	
1.9.1	$3 < t \leq 10$	Single-bevel preparation			$35^\circ \leq \beta \leq 60^\circ$	$2 \leq b \leq 4$	$1 \leq c \leq 2$	—		—	
1.9.2					$35^\circ \leq \beta \leq 60^\circ$	$2 \leq b \leq 4$	$1 \leq c \leq 2$	—		—	
1.10	>16	Steep-flanked single-bevel preparation			$15^\circ \leq \beta \leq 60^\circ$	$6 \leq b \leq 12$	—	111 13 141		With backing strip	