



Designation: C1381/C1381M – 97(Reapproved 2008)^{ε1}

Standard Specification for Molded Glass Fiber Reinforced Gypsum Parts¹

This standard is issued under the fixed designation C1381/C1381M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—The units statement in subsection 1.2 was corrected and the standard was changed to a dual designation editorially in July 2008.

1. Scope

1.1 This specification covers molded glass fiber reinforced gypsum (GRG) parts, which are nonload-bearing, thin-shell, ornamental shapes for architectural embellishment of interior building construction.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 The information presented refers to the molded surface of the part.

1.4 The text of this standard references footnotes, which provide explanatory material. These footnotes shall not be considered as requirements of the standard.

2. Referenced Documents

- 2.1 *ASTM Standards*:²
- C11 Terminology Relating to Gypsum and Related Building Materials and Systems
 - C1355/C1355M Specification for Glass Fiber Reinforced Gypsum Composites

3. Terminology

3.1 *Definitions*—Definitions of terms shall be in accordance with Terminology C11.

3.2 *Definitions of Terms Specific to This Standard*:

¹ This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.01 on Specifications and Test Methods for Gypsum Products.

Current edition approved May 1, 2008. Published July 2008. Originally approved in 1998. Last previous edition approved in 2002 as C1381 – 97(2002)^{ε1}. DOI: 10.1520/C1381_C1381M-97R08E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.1 *control thickness, n*—the thickness of the GRG part where abutting other GRG parts, other products or at fastening points.

3.2.2 *embedments, n*—materials encapsulated into the part for the purpose of suspension, attachment, and stiffening.

3.2.3 *finish surface, n*—a surface against a mold.

3.2.4 *GRG part, n*—an individual molded component used as architectural embellishment.

3.2.5 *GRG product, n*—combination of GRG parts used as architectural embellishment.

3.2.6 *mock-up, n*—a presentation assembly of GRG parts defined by the purchase agreement.

3.2.7 *part thickness, n*—thickness of a part at any measurement point.

4. Materials and Manufacture

4.1 *Materials*—GRG parts shall be produced using the same materials used to make the composites in conformance with Specification C1355/C1355M.

4.2 *Manufacture*:

4.2.1 *GRG parts* shall be manufactured from the mixed slurry of alpha gypsum cement, potable water and additives, when used, and not less than 5 % by weight glass fiber reinforcement using either the hand lay-up or the spray-up process in a mold.

4.2.2 *GRG parts* shall be produced according to approved shop drawings.

4.2.3 Shop drawings shall specify part dimensions, quantities, recommended attachment points and methods, reinforcements, embedments, and tolerance.

5. Mechanical Properties

5.1 *GRG parts* shall be made from materials to make composites having properties in accordance with Specification C1355/C1355M.

6. Dimensions and Tolerances of GRG Parts

6.1 *Part Thickness*—The thickness of the GRG part shall be not less than $\frac{3}{16}$ in. [5 mm].