



# SLOVENSKI STANDARD

## oSIST prEN ISO 3452-1:2020

01-februar-2020

---

**Neporušitvene preiskave - Pregled s penetranti - 1. del: Splošna načela (ISO/DIS 3452-1:2019)**

Non-destructive testing - Penetrant testing - Part 1: General principles (ISO/DIS 3452-1:2019)

Zerstörungsfreie Prüfung - Eindringprüfung - Teil 1: Allgemeine Grundlagen (ISO/DIS 3452-1:2019)

Essais non destructifs - Examen par ressuage - Partie 1: Principes généraux (ISO/DIS 3452-1:2019)

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f126f518f468/osist-pr-en-iso-3452-1-2020>

**Ta slovenski standard je istoveten z: prEN ISO 3452-1**

---

**ICS:**

19.100      Neporušitveno preskušanje      Non-destructive testing

**oSIST prEN ISO 3452-1:2020**

**en,fr,de**

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

[oSIST prEN ISO 3452-1:2020](https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020>

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 3452-1

ISO/TC 135/SC 2

Secretariat: **SABS**Voting begins on:  
**2019-12-06**Voting terminates on:  
**2020-02-28**

---

## Non-destructive testing — Penetrant testing —

### Part 1: General principles

*Essais non destructifs — Examen par ressuage —**Partie 1: Principes généraux*

ICS: 19.100

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3452-1:2020](https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020)<https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

## ISO/CEN PARALLEL PROCESSING



Reference number  
ISO/DIS 3452-1:2019(E)

© ISO 2019

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3452-1:2020](https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Safety precautions</b>	<b>2</b>
<b>5 General principles</b>	<b>2</b>
5.1 Personnel	2
5.2 Description of the method	2
5.3 Process sequence	2
5.4 Equipment	3
5.5 Effectiveness	3
<b>6 Products, sensitivity and designation</b>	<b>3</b>
6.1 Product family	3
6.2 Testing products	3
6.3 Sensitivity	3
6.4 Designation	4
<b>7 Compatibility</b>	<b>4</b>
7.1 General	4
7.2 Compatibility of penetrant testing products	4
7.3 Compatibility of penetrant testing products and the material to be tested	4
<b>8 Test procedure</b>	<b>5</b>
8.1 Written test procedure	5
8.2 Precleaning	5
8.2.1 General	5
8.2.2 Mechanical precleaning	5
8.2.3 Chemical precleaning	5
8.2.4 Drying	5
8.3 Temperature	5
8.4 Application of penetrant	6
8.4.1 Methods of application	6
8.4.2 Penetration time	6
8.5 Excess penetrant removal	6
8.5.1 General	6
8.5.2 Water	6
8.5.3 Solvents	6
8.5.4 Emulsifier	6
8.5.5 Water and solvent	7
8.5.6 Excess penetrant removal check	7
8.5.7 Drying after excess penetrant removal	7
8.6 Developing	7
8.6.1 General	7
8.6.2 Dry developer	8
8.6.3 Water suspendable developer	8
8.6.4 Solvent based developer	8
8.6.5 Water soluble developer	8
8.6.6 Water or solvent based for special application (e.g. peelable developer)	8
8.6.7 No developer	8
8.7 Inspection	9
8.7.1 General	9
8.7.2 Viewing conditions	9
8.7.3 Wipe-off technique	9
8.7.4 Recording	9

**ISO/DIS 3452-1:2019(E)**

8.8	Postcleaning and corrosion protection.....	10
8.8.1	Postcleaning.....	10
8.8.2	Corrosion protection.....	10
8.9	Retesting.....	10
<b>9</b>	<b>Test report.....</b>	<b>10</b>
<b>Annex A</b> (normative)	<b>Main stages of penetrant examination.....</b>	<b>12</b>
<b>Annex B</b> (normative)	<b>Process and control tests.....</b>	<b>13</b>
<b>Annex C</b> (informative)	<b>Example test report.....</b>	<b>20</b>
<b>Bibliography</b> .....		<b>21</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 3452-1:2020](https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020)  
<https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 138, *Non-destructive testing*, in collaboration with ISO Technical Committee ISO/TC 135, *Non-destructive testing*, Subcommittee SC 2, *Surface methods*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 3452-1:2013) which has been technically revised. Changes from the first edition include a table referring to the testing products.

The main changes compared to the previous edition are as follows:

- clarification of understanding of product family
- new procedure “no developer” added
- technically revised according to the state of the art.

A list of all parts in the ISO 3452 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## **iTeh STANDARD PREVIEW** **(standards.iteh.ai)**

[oSIST prEN ISO 3452-1:2020](https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020)

<https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12fd518f468/osist-pren-iso-3452-1-2020>



# Non-destructive testing — Penetrant testing —

## Part 1: General principles

### 1 Scope

This part of ISO 3452 specifies a method of penetrant testing used to detect discontinuities, e.g. cracks, laps, folds, porosity and lack of fusion, which are open to the surface of the material to be tested using white light or UV-A (365 nm) radiation. It is mainly applied to metallic materials, but can also be performed on other materials, provided that they are inert to the test media and not excessively porous (castings, forgings, welds, ceramics, etc.)

It also includes requirements for process and control testing, but is not intended to be used for acceptance criteria and gives neither information relating to the suitability of individual test systems for specific applications nor requirements for test equipment.

NOTE 1 Methods for determining and monitoring the essential properties of penetrant testing products to be used are specified in ISO 3452-2 and ISO 3452-3.

NOTE 2 The term *discontinuity* is used in this part of ISO 3452 in the sense that no evaluation concerning acceptability or non-acceptability is included.

NOTE 3 CEN/TR 16338 addresses penetrant testing using actinic blue light.

### 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3059, *Non-destructive testing — Penetrant testing and magnetic particle testing — Viewing conditions*

ISO 3452-2, *Non-destructive testing — Penetrant testing — Part 2: Testing of penetrant materials*

ISO 3452-3, *Non-destructive testing — Penetrant testing — Part 3: Reference test blocks*

ISO 3452-4, *Non-destructive testing — Penetrant testing — Part 4: Equipment*

ISO 3452-5, *Non-destructive testing — Penetrant testing — Part 5: Penetrant testing at temperatures higher than 50 degrees C*

ISO 3452-6, *Non-destructive testing — Penetrant testing — Part 6: Penetrant testing at temperatures lower than 10 degrees C*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 12706, *Non-destructive testing — Penetrant testing — Vocabulary*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 12706 apply.

## ISO/DIS 3452-1:2019(E)

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 4 Safety precautions

As penetrant inspection techniques often require the use of harmful, flammable and/or volatile materials, safety regulations shall be taken into account.

Prolonged or repeated contact of these materials with the skin or any mucous membrane should be avoided. Working areas shall be adequately ventilated and sited away from sources of heat, sparks or naked flames in accordance with all applicable safety regulations.

The penetrant testing products and equipment shall be used with care and always in compliance with the instructions supplied by the manufacturer.

UV-A sources shall always be maintained in a good condition.

In addition to the need to follow legislation (e.g. optical radiation legislation), care shall be taken to ensure the safe implementation of the method.

### 5 General principles

#### 5.1 Personnel

Testing shall be carried out by proficient, suitably trained and qualified personnel and, where applicable, shall be supervised by competent personnel nominated by the employer or, by delegation of the employer, the inspection company in charge of testing. To demonstrate appropriate qualification it is recommended that personnel be certified according to ISO 9712 or an equivalent formalized system. Penetrant testing operations, unless otherwise agreed, shall be authorized by a competent supervisory individual (Level 3 or equivalent) approved by the employer.

#### 5.2 Description of the method

Prior to penetrant testing the surface to be inspected shall be clean and dry. Suitable penetrants are then applied to the test area and enter into discontinuities open to the surface. After the appropriate penetration time has elapsed the excess penetrant is removed from the surface and the developer applied. The developer absorbs the penetrant that has entered and remains in the discontinuities and may give a clearly visible enhanced indication of the discontinuity.

Should complementary NDT be required, it is preferable that the penetrant inspection is performed first, so as not to introduce contaminants into open discontinuities. If penetrant inspection is used following another NDT technique or method, the surface shall be cleaned carefully to remove contaminants before application.

#### 5.3 Process sequence

The penetrant process shall be continuous with no undue delays between the stages. If process parameters are not met, surfaces shall be cleaned and reprocessed.

Testing generally proceeds through the following stages:

- a) preparation and precleaning (see 8.2);
- b) application of penetrant (see 8.4);
- c) excess penetrant removal (see 8.5);

- d) application of developer (see 8.6);
- e) inspection (see 8.7);
- f) postcleaning and protection (see 8.8).

See [Annex A](#).

## 5.4 Equipment

The equipment used for carrying out penetrant testing depends on the number, size, weight and shape of the parts to be tested. The equipment shall be as specified in ISO 3452-4.

## 5.5 Effectiveness

The effectiveness of the penetrant testing depends upon many factors, including

- a) types of penetrant materials and testing equipment,
- b) surface preparation and condition;
- c) material under examination and expected discontinuities,
- d) temperature of the test surface,
- e) penetration and development time, and
- f) viewing conditions.

Control checks shall be carried out to demonstrate that the correct testing parameters are used. See [Annex B](#).

oSIST prEN ISO 3452-1:2020

<https://standards.iteh.ai/catalog/standards/sist/70c2fe2c-375d-459e-95e8-f12f1518f468/osist-pr-en-iso-3452-1-2020>

## 6 Products, sensitivity and designation

### 6.1 Product family

Various test systems exist in penetrant testing. The penetrant testing system and the product family shall be selected according to the application. Various factors have an impact on the effectiveness and sensitivity of the process, e.g. the surface roughness and condition, size and shape of the parts to be tested and the sensitivity level of the product family. For example using a high sensitivity penetrant on a rough surface may result in a less sensitive test than using a lower sensitive penetrant.

A product family is understood as a combination of the following penetrant testing materials: penetrant, excess penetrant remover (except method A) and developer. A product family may be defined by the manufacturer, user or inspection authority and does not necessarily have to be from the same manufacturer.

### 6.2 Testing products

The products used for testing are given in [Table 1](#).

### 6.3 Sensitivity

Sensitivity levels shall be determined according to ISO 3452-2. By using specific product families different sensitivity levels may be achieved. Therefore ISO 3452-2 describes penetrant baseline sensitivity and product family sensitivity.