



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 3452-2:2020**

**01-februar-2020**

---

**Neporušitvene preiskave - Pregled s penetranti - 2. del: Preiskava penetrantskih snovi (ISO/DIS 3452-2:2019)**

Non-destructive testing - Penetrant testing - Part 2: Testing of penetrant materials (ISO/DIS 3452-2:2019)

Zerstörungsfreie Prüfung - Eindringprüfung - Teil 2: Prüfung von Eindringmitteln (ISO/DIS 3452-2:2019)

Essais non destructifs - Examen par ressuage - Partie 2: Essai des produits de ressuage (ISO/DIS 3452-2:2019)

**ITeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[kSIST FprEN ISO 3452-2:2021](https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-pr-en-iso-3452-2-2020)

[https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-](https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-pr-en-iso-3452-2-2020)

**Ta slovenski standard je istoveten z: prEN ISO 3452-2**

---

**ICS:**

19.100      Neporušitveno preskušanje      Non-destructive testing

**oSIST prEN ISO 3452-2:2020**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[kSIST FprEN ISO 3452-2:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-fpren-iso-3452-2-2021>

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 3452-2

ISO/TC 135/SC 2

Secretariat: **SABS**Voting begins on:  
**2019-12-06**Voting terminates on:  
**2020-02-28**

---

---

## Non-destructive testing — Penetrant testing —

### Part 2: Testing of penetrant materials

*Essais non destructifs — Examen par ressuage —**Partie 2: Essai des produits de ressuage*

ICS: 19.100

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 3452-2:2021](https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-fpren-iso-3452-2-2021)<https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-fpren-iso-3452-2-2021>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 3452-2:2019(E)

© ISO 2019

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[kSIST FprEN ISO 3452-2:2021](https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-fpren-iso-3452-2-2021)

<https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-fpren-iso-3452-2-2021>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Classification</b> .....	<b>2</b>
4.1 Testing products.....	2
4.2 Sensitivity levels.....	2
4.2.1 General.....	2
4.2.2 Penetrant baseline sensitivity.....	2
4.2.3 Product family sensitivity.....	2
4.2.4 Fluorescent systems.....	2
4.2.5 Colour contrast systems.....	2
4.2.6 Dual-purpose product family.....	2
<b>5 Testing of penetrant materials</b> .....	<b>3</b>
5.1 Personnel.....	3
5.2 Testing facilities.....	3
5.2.1 Type testing.....	3
5.2.2 Batch testing.....	3
5.2.3 Process and control testing.....	3
5.3 Reporting.....	3
5.3.1 Type testing.....	3
5.3.2 Batch testing.....	3
5.4 Tests.....	3
5.4.1 Sensitivity test.....	3
5.4.2 Penetrants.....	4
5.4.3 Excess penetrant removers (excluding method A).....	4
5.4.4 Developers.....	4
5.4.5 Batch tests for spray cans.....	5
<b>6 Test methods and requirements</b> .....	<b>5</b>
6.1 Appearance.....	5
6.2 Penetrant system sensitivity.....	5
6.2.1 Fluorescent penetrants (Type I).....	5
6.2.2 Colour contrast penetrants (Type II).....	8
6.3 Density.....	10
6.3.1 Test method.....	10
6.3.2 Requirements.....	10
6.4 Viscosity.....	10
6.4.1 Test method.....	10
6.4.2 Requirements.....	10
6.5 Flashpoint.....	10
6.5.1 Test method.....	10
6.5.2 Requirements.....	10
6.6 Washability (Method A penetrants).....	10
6.7 Fluorescent brightness.....	11
6.7.1 Test method.....	11
6.7.2 Requirements.....	11
6.8 UV stability.....	11
6.8.1 Test method.....	11
6.8.2 Requirements.....	11
6.9 Thermal stability of fluorescent brightness.....	11
6.9.1 Test method.....	11
6.9.2 Requirements.....	12

## ISO/DIS 3452-2:2019(E)

6.10	Water tolerance .....	12
6.10.1	Test method .....	12
6.10.2	Requirements .....	12
6.11	Corrosive properties .....	12
6.11.1	General .....	12
6.11.2	Type testing .....	12
6.11.3	Batch testing .....	16
6.12	Content of sulfur and halogens (for products designated low in sulfur and halogens) .....	16
6.12.1	Test method .....	16
6.12.2	Requirements .....	16
6.13	Residue on evaporation/solid content .....	17
6.13.1	Solvent removers .....	17
6.13.2	Form d and e developers .....	17
6.14	Penetrant tolerance .....	17
6.14.1	Lipophilic emulsifier (Method B) .....	17
6.14.2	Hydrophilic emulsifier (Method D) .....	17
6.15	Developer performance .....	17
6.16	Re-dispersability .....	17
6.16.1	Water-suspendable developers .....	17
6.16.2	Solvent based developers (non-aqueous) .....	17
6.17	Density of carrier liquid .....	18
6.17.1	Test method .....	18
6.17.2	Requirements .....	18
6.18	Product performance (pressurized containers) .....	18
6.19	Particle size distribution .....	18
6.20	Water content .....	18
6.20.1	Test method .....	18
6.20.2	Requirements .....	18
<b>7</b>	<b>Packaging and labelling</b> .....	<b>18</b>
	<a href="https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59055ab/ksist-pr-en-iso-3452-2-2021">https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59055ab/ksist-pr-en-iso-3452-2-2021</a>	
	<b>Annex A (normative) Comparison of fluorescent brightness</b> .....	<b>19</b>
	<b>Annex B (normative) Equipment for determination of the visibility of fluorescent indications</b> .....	<b>21</b>
	<b>Annex C (informative) List of reference materials</b> .....	<b>22</b>
	<b>Bibliography</b> .....	<b>24</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 138, *Non-destructive testing*, in collaboration with ISO Technical Committee ISO/TC 135, *Non-destructive testing*, Subcommittee SC 2, *Surface methods*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 3452-2:2006), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the normative references were updated;
- [tables 1, 4, 8, 9](#) were corrected;
- a new [Clause 5.1](#) was inserted;
- [clause 6.6](#) was revised;
- the former [Annex B](#) was deleted;
- editorial changes were made.

A list of all parts in the ISO 3452 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[kSIST FprEN ISO 3452-2:2021](#)

<https://standards.iteh.ai/catalog/standards/sist/1d101992-83ab-47c7-876b-5555c59633ab/ksist-fpren-iso-3452-2-2021>



# Non-destructive testing — Penetrant testing —

## Part 2: Testing of penetrant materials

**SAFETY PRECAUTIONS** — The materials required by this part of ISO 3452 include chemicals which may be harmful, flammable and/or volatile. All necessary precautions shall be observed. All relevant International, national and local regulations pertaining to health and safety, environmental requirements, etc. shall be observed.

### 1 Scope

This part of ISO 3452 specifies the technical requirements and test procedures for penetrant materials for their type testing and batch testing. This part of ISO 3452 covers the temperature range 10 °C to 50 °C. Additional tests in part 5 or part 6 of ISO 3452 may be required outside this range.

On-site control tests and methods are detailed in ISO 3452-1.

### 2 Normative references

The following referenced documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3059, *Non-destructive testing — Penetrant testing and magnetic particle testing — Viewing conditions*

ISO 3452-1:2013, *Non-destructive testing — Penetrant testing — Part 1: General principles*

ISO 3452-3, *Non-destructive testing — Penetrant testing — Part 3: Reference test blocks*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 12706, *Non-destructive testing — Penetrant testing — Vocabulary*

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 12706 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **batch**

quantity of material manufactured in one production having uniform properties throughout and with a unique identifying number or mark

## ISO/DIS 3452-2:2019(E)

### 3.2 candidate

sample of the testing product submitted for evaluation in accordance with this part of ISO 3452

## 4 Classification

### 4.1 Testing products

Penetrant testing products shall be classified by type, method and form in accordance with ISO/DIS 3452-1:2019 Table 1.

### 4.2 Sensitivity levels

#### 4.2.1 General

Penetrant baseline sensitivity and product family sensitivity are determined independently and one or both of them shall be carried out.

#### 4.2.2 Penetrant baseline sensitivity

For penetrant baseline sensitivity the penetrant is submitted with its designated remover and is tested using a standard reference developer. The allocated penetrant sensitivity level is only valid when the penetrant is used with the designated remover.

#### 4.2.3 Product family sensitivity (standards.iteh.ai)

The product family sensitivity is determined by submitting a complete set of products for assessment. The allocated product family sensitivity level is only valid when this complete set of products is used.

#### 4.2.4 Fluorescent systems

Sensitivity levels shall be defined by reference products:

- sensitivity level 1/2 (very low);
- sensitivity level 1 (low);
- sensitivity level 2 (medium);
- sensitivity level 3 (high);
- sensitivity level 4 (ultra-high).

Sensitivity level 1/2 applies to Type I method A only.

#### 4.2.5 Colour contrast systems

Sensitivity levels shall be defined using the type 1 reference block in accordance with ISO 3452-3:

- sensitivity level 1 (normal);
- sensitivity level 2 (high).

#### 4.2.6 Dual-purpose product family

There are no sensitivity levels for dual-purpose penetrants when used as a fluorescent system. However these products may be classified as colour contrast products (see [4.2.3](#)).

## 5 Testing of penetrant materials

### 5.1 Personnel

Testing shall be carried out by proficient, suitably trained and qualified personnel. For non-destructive Testing (NDT) operations (e.g. sensitivity and washability), unless otherwise agreed to demonstrate appropriate proficiency it is recommended that personnel be trained according to ISO 9712 or an equivalent formalized system. Operating authorization for personnel shall be issued by the employer in accordance with a written procedure.

### 5.2 Testing facilities

#### 5.2.1 Type testing

Type testing shall be carried out on penetrant materials according to ISO 3452-1 with exceptions as defined in ISO 3452-2 to ensure their conformance to the requirements.

Type testing shall be carried out by an independent laboratory having a formalised quality system and the relevant technical competencies. ISO/IEC 17025 accreditation for the testing of penetrant materials would satisfy this requirement.

#### 5.2.2 Batch testing

Batch testing to the requirements of ISO 3452-2 shall be carried out on each production batch according to ISO 3452-1 to ensure the batch has the same properties as the corresponding type approval sample. In the case of penetrant material packed in spray cans, the content of sulfur and halogens shall be additionally determined according to [6.12](#).

Batch testing shall be carried out under a defined and maintained quality system. A system meeting the requirements of ISO 9001 is considered suitable.

#### 5.2.3 Process and control testing

Process and control tests to monitor the implementation of the method are described in ISO 3452-1.

### 5.3 Reporting

#### 5.3.1 Type testing

The testing laboratory (see [5.2.1](#)) shall provide a certificate of compliance with this part of ISO 3452 and a report that details the results obtained.

If any changes are made to the penetrant material composition, then a new type test and product identity shall be required.

#### 5.3.2 Batch testing

Manufacturers of penetrant materials shall provide certificates of compliance with this part of ISO 3452 (for example, see EN 10204 or ISO 10474).

### 5.4 Tests

#### 5.4.1 Sensitivity test

A sensitivity test shall be carried out for each individual penetrant material and/or product family.

Type testing shall be carried out according to [6.2](#).

## ISO/DIS 3452-2:2019(E)

For batch testing the test shall be carried out by comparison with the previously approved retain sample. In addition for each penetrant material the following test are required.

### 5.4.2 Penetrants

Type and batch testing of penetrant properties shall be carried out in accordance with [Table 2](#).

**Table 2 — Properties of penetrants and required tests**

Property	Test type	Reference
Appearance	Type and Batch	<a href="#">6.1</a>
Density	Type and batch	<a href="#">6.3</a>
Viscosity	Type and batch	<a href="#">6.4</a>
Flashpoint	Type and batch	<a href="#">6.5</a>
Washability (Method A penetrants only)	Batch	<a href="#">6.6</a>
Fluorescent brightness (Type I penetrants)	Type and batch	<a href="#">6.7</a>
UV stability (Type I penetrants)	Type	<a href="#">6.8</a>
Thermal stability (Type I penetrants)	Type	<a href="#">6.9</a>
Water tolerance (Method A penetrants only)	Type	<a href="#">6.10</a>
Corrosive properties	Type and batch	<a href="#">6.11</a>
Content of sulfur and halogens <sup>a</sup>	Type and batch	<a href="#">6.12</a>
Water content (Methods A and E)	Batch	<a href="#">6.20</a>

<sup>a</sup> Only required for products designated "low in sulfur and halogens".

### 5.4.3 Excess penetrant removers (excluding method A)

Type and batch testing of penetrant remover properties shall be carried out in accordance with [Table 3](#).

**Table 3 — Properties of excess penetrant removers and required tests**

Property	Test type	Reference
Appearance	Batch	<a href="#">6.1</a>
Density	Type and batch	<a href="#">6.3</a>
Viscosity (for Methods B and D only)	Type and batch	<a href="#">6.4</a>
Flashpoint	Type and batch	<a href="#">6.5</a>
Water tolerance (Method B only)	Type and batch	<a href="#">6.10</a>
Corrosive properties	Type and batch	<a href="#">6.11</a>
Content of sulfur and halogens <sup>a</sup>	Type and batch	<a href="#">6.12</a>
Residue on evaporation/solid content (Method C only)	Type and batch	<a href="#">6.13</a>
Penetrant tolerance (Methods B and D only)	Type	<a href="#">6.14</a>
Water content (Method B only)	Batch	<a href="#">6.20</a>
Other contaminants on request (as required)	Batch	

<sup>a</sup> Only required for products designated "low in sulfur and halogens".

### 5.4.4 Developers

Type and batch testing of developer properties shall be carried out in accordance with [Table 4](#).