

---

---

**Fine ceramics (advanced ceramics,  
advanced technical ceramics) —  
Testing method for macro-  
heterogeneity in microstructure**

*Céramiques techniques — Méthode d'essai relative aux macro-  
hétérogénéités dans la microstructure*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 18550:2016](https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-ef3303b35347/iso-18550-2016)

[https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-  
ef3303b35347/iso-18550-2016](https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-ef3303b35347/iso-18550-2016)



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 18550:2016

<https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-ef3303b35347/iso-18550-2016>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Apparatus</b> .....	<b>1</b>
<b>6 Test specimen</b> .....	<b>2</b>
<b>7 Procedure</b> .....	<b>2</b>
7.1 Measurement of specimen thickness .....	2
7.2 Observation .....	2
7.3 Magnification .....	2
<b>8 Measurement of macro-heterogeneities</b> .....	<b>3</b>
8.1 Determination of specimen volume under examination .....	3
8.2 Measurement of the size of macro-heterogeneities .....	3
<b>9 Analysis</b> .....	<b>3</b>
9.1 Maximum and minimum size .....	3
9.2 Size interval .....	3
9.3 Size and population of defect .....	3
9.4 Graph .....	4
<b>10 Test report</b> .....	<b>4</b>
<b>Annex A (informative) Refractive indices of solid and liquids</b> .....	<b>5</b>
<b>Annex B (informative) Examples of macro-heterogeneities observed in transmission mode</b> .....	<b>6</b>
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 206, *Fine ceramics*.

ISO 18550:2016

<https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-ef3303b35347/iso-18550-2016>

# Fine ceramics (advanced ceramics, advanced technical ceramics) — Testing method for macro-heterogeneity in microstructure

## 1 Scope

This International Standard specifies a test method for determining macro-heterogeneities within the microstructure of fine ceramics that are above a certain size within the volume of the material and affect materials mechanical strength properties. This method is limited to fine ceramics with a porosity of less than 10 vol% and that are transparent for visible light in the form of a thin specimen.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

**iTeh STANDARD PREVIEW**

## 3 Terms and definitions (standards.iteh.ai)

For the purposes of this document, the following terms and definitions apply.

### 3.1

#### **coarse macro-heterogeneity**

macro-heterogeneity, e.g. agglomerates, pores, inclusion, grains, with a size above 10 µm significantly affecting the mechanical strength

### 3.2

#### **coarse macro-heterogeneity distribution**

size distribution of coarse macro-heterogeneities

### 3.3

#### **equivalent circle diameter**

diameter of a circle having the same area as the coarse macro-heterogeneity

## 4 Principle

A variety of ceramics are composed of transparent materials and their macro-heterogeneity is observed in the transmission mode on a thin specimen.

## 5 Apparatus

**5.1 Microscope**, enabling the observation in the transmission mode. The microscope shall have a maximum magnification of the objective lens of ×10 and an illumination system with an adjustable aperture. A certified graticule shall be used for the calibration of the magnification.

**5.2 Cutting machine**, suitable machine capable of cutting the ceramics.

**5.3 Grinding machine**, suitable machine capable of grinding the ceramics.

**5.4 Polishing machine**, suitable machine capable of polishing the ceramics.

**5.5 Micrometer**, capable of measuring the thickness of the polished ceramic section with an accuracy of 2  $\mu\text{m}$ .

**5.6 Microscope slide**, suitable transparent microscope slide for mounting the test-piece in the microscope.

**5.7 Transparent film with circles of various diameter**, to determine the equivalent circle diameter of defects.

## 6 Test specimen

The specimen shall be thin enough for observation in the transmission mode of the microscope. The typical thickness depends on the material and its porosity, and is between 30  $\mu\text{m}$  and 200  $\mu\text{m}$ .

The specimen shall be prepared as follows.

- a) Cut a thin slab from the ceramic using a cutting machine. A thickness of the slab of more than 1 mm plus the final thickness is recommended. For a ceramic with thickness of less than 2 mm, this process can be omitted.
- b) One face of the slab shall be ground using a grinding machine and polished with a polishing machine by using polishing grains of a sequence of decreasing sizes with the finishing grit size of less than 1  $\mu\text{m}$ .
- c) The other face of the slab shall be ground to adjust the thickness of the slab appropriately. Finally, the ground face shall be polished with the polishing machine by using polishing grains of a sequence of decreasing sizes as mentioned above to prepare a thin specimen for observation.
- d) Finally, mount the thin specimen on the microscope slide for observation. Transparent thermoplastic resin is recommended for mounting.
- e) The thickness of the specimen must be adjusted for adequate transparency before examination. With a specimen of adequate transparency, defects located at any depth in the specimen can be well focused. Scratches on both front and back surfaces are conveniently used to examine the applicability of this International Standard. If they are clearly seen from the opposite side, this International Standard can be applied.

## 7 Procedure

### 7.1 Measurement of specimen thickness

The thickness of the specimen shall be measured at the centre of the specimen with a micrometer to the nearest 0,002 mm.

### 7.2 Observation

Adjust the microscope as follows; set the numerical aperture of the condenser lens in the illumination system 0,1 or less. The objective lens used for observation should have the magnification under  $\times 10$ .

### 7.3 Magnification

The minimum sizes of defects subjected for examination is 10  $\mu\text{m}$  equivalent circle diameter. With the numerical aperture of the lens of 0,1, the maximum thicknesses of specimens which can be examined in one micrograph will be 48  $\mu\text{m}$  and 28  $\mu\text{m}$  multiplied by the refractive index of the specimen, for the objective lenses of magnifications  $\times 4$  and  $\times 10$ , respectively.

The position of focus should be at half of the specimen thickness from the top surface. The refractive index of major phase shall be used for a specimen with multiple phases.

If the specimen is highly transparent, a thicker specimen can be used. A series of micrographs shall be taken by changing the position of focus through the depth direction of specimen. The interval in the position of focus shall be less than  $48 \mu\text{m}$  and  $28 \mu\text{m}$  multiplied by the refractive index of the specimen, for the objective lenses of magnifications  $\times 4$  and  $\times 10$ , respectively.

The photographed areas shall not overlap and micrographs should cover at least 100 macro-heterogeneities which shall be analysed.

## 8 Measurement of macro-heterogeneities

### 8.1 Determination of specimen volume under examination

The volume,  $V$ , under examination is given by the image area,  $A_i$ , the thickness,  $t$ , of the slab, and the number,  $n_L$ , of locations under examination.

$$V = A_i \times t \times n_L \quad (1)$$

### 8.2 Measurement of the size of macro-heterogeneities

The net magnification shall be adjusted to make the defect of the minimum size appear to be over 5 mm equivalent circle diameter on the micrograph. A transparent film with circles of various diameters shall be used to determine the equivalent circle diameter. Determine the size for at least 100 macro-heterogeneities.

## 9 Analysis

ISO 18550:2016  
<https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-ef3303b35347/iso-18550-2016>

### 9.1 Maximum and minimum size

Determine the largest and smallest macro-heterogeneity.

### 9.2 Size interval

At least five size intervals shall be taken between the size of the largest and smallest defects in the analysis. The intervals may not be equal, but at least five macro-heterogeneities should be present in each interval, except in the interval containing the largest macro-heterogeneity.

### 9.3 Size and population of defect

The size and the population of macro-heterogeneities for each size interval are given by Formulae (2) and (3).

$$d_{i,m} = (d_{i,l} + d_{i,u})/2 \quad (2)$$

where

$d_{i,m}$  is the mean size of interval  $i$ ;

$d_{i,l}$  is the lower limit of the interval  $i$ ;

$d_{i,u}$  is the upper limit of the interval  $i$ .

$$p_i = n_i / (d_{i,u} - d_{i,l}) V \quad (3)$$

where

$p_i$  is the population on interval  $i$ ;

$n_i$  is the number of defects belonging to interval  $i$ .

The unit to express population is the number of macro-heterogeneities/mm<sup>3</sup>/μm.

## 9.4 Graph

Plot the logarithm of the population as a function of the size of macro-heterogeneities.

## 10 Test report

The test report shall be in accordance with the provisions of ISO/IEC 17025 and shall include at least the following information:

- a) a reference to this International Standard, i.e. ISO 18550;
- b) the name of the specimen;
- c) the preparation method of specimen:
  - 1) machining method;
  - 2) thickness of specimen;
- d) the observation method:

[ISO 18550:2016](https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-ef3303b35347/iso-18550-2016)  
<https://standards.iteh.ai/catalog/standards/sist/fc12e775-c438-4924-a9bf-ef3303b35347/iso-18550-2016>

  - 1) name of microscope;
  - 2) objective lens (type, magnification, optical system);
  - 3) numerical aperture in observation;
- e) the micrographs [micrographs of specimen and microscale taken at the magnification of observation and the results (e), if required];
- f) the measured results for size distribution of coarse non-uniform structure:
  - 1) size distribution of non-uniform structure (equivalent circle diameter);
  - 2) volume for observation.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**



## Annex A (informative)

### Refractive indices of solid and liquids

Refractive index (R.I.) varies with the wave length. It decreases with increasing wave length. Materials of crystallographically cubic symmetry have a single value at each wave length. Those of non-cubic crystal structures have multiple values. Average values are given for them in [Table A.1](#). Values at the wave length of 632,8 nm are listed in [Table A.1](#).

**Table A.1 — Refractive indices (R.I.) of various materials at the wave length 632,8 nm**

Materials	R.I.
Al <sub>2</sub> O <sub>3</sub>	1,770
AlN	2,165
MgO	1,735
SiC	2,635
SiO <sub>2</sub>	1,457
Si <sub>3</sub> N <sub>4</sub>	2,023
BaTiO <sub>3</sub>	2,411
TiO <sub>2</sub>	2,874
ZrO <sub>2</sub>	2,208

Source: <http://www.filmetrics.com/refractive-index-database>