
**Timber structures — Cross laminated
timber —**

**Part 1:
Component performance, production
requirements and certification scheme**

iTeh STANDARD PREVIEW
*Structures en bois — Plaques reconstituées à base de lamelles
croisées —*
(standards.iteh.ai)

*Partie 1: Performances des composants et exigences de production et
système de certification*

ISO 16696-1:2019

<https://standards.iteh.ai/catalog/standards/sist/e6ba409b-15a6-4b21-96c3-4cb5b4195e1f/iso-16696-1-2019>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16696-1:2019

<https://standards.iteh.ai/catalog/standards/sist/e6ba409b-15a6-4b21-96c3-4cb5b4195e1f/iso-16696-1-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols and subscripts	6
4.1 Symbols.....	6
4.2 Subscripts.....	6
5 CLT panel dimensional tolerances	7
5.1 Dimensional tolerances at time of manufacture.....	7
5.1.1 General.....	7
5.1.2 Panel thickness.....	7
5.1.3 Layer thickness.....	7
5.1.4 Panel width.....	7
5.1.5 Panel length.....	7
5.1.6 Grooves and edge bonds.....	7
5.2 Squareness.....	7
5.3 Straightness.....	8
6 Component requirements	8
6.1 Solid sawn timber.....	8
6.1.1 Solid sawn timber species.....	8
6.1.2 Solid sawn timber sizes.....	8
6.1.3 Moisture content.....	8
6.1.4 Solid sawn timber face-bonding surface.....	8
6.1.5 Face-bonding dimensional tolerances.....	9
6.2 Wood based panels.....	9
6.2.1 General.....	9
6.2.2 Moisture content.....	9
6.2.3 Wood based panels face-bonding surface.....	9
6.2.4 Face-bonding dimensional tolerances.....	9
6.3 Adhesive requirements.....	9
6.3.1 General.....	9
6.3.2 Testing for minor changes of adhesive systems.....	9
6.3.3 Finger joints in laminations when used.....	9
6.3.4 Edge joints in laminations when used.....	10
6.3.5 Glue line integrity for glue lines between layers (face joints).....	10
6.3.6 Shear strength of edge bonds in solid sawn timber layers.....	10
6.4 Large finger joints of panels.....	10
6.4.1 General.....	10
6.4.2 Bending strength.....	10
7 Cross laminated timber performance criteria	10
7.1 Layup requirements.....	10
7.2 Mechanical resistance of cross laminated timber products.....	11
7.3 Durability against biological attack.....	11
7.3.1 General.....	11
7.3.2 Solid sawn timber layers without preservative treatment.....	11
7.3.3 Solid sawn timber layers with preservative treatment.....	11
7.3.4 CLT treated with preservative treatment.....	11
7.4 Formaldehyde emission.....	12
7.5 Dimensional stability.....	12
7.5.1 General.....	12
7.5.2 Maximum deviations.....	12

7.5.3	Corrected sizes and moisture deformation factor	12
7.6	Appearance classification.....	12
8	Production, testing, and trade marking.....	13
Annex A (normative)	Panel layup (construction).....	16
Annex B (normative)	Examples of CLT appearance classification.....	17
Annex C (normative)	Ply grading.....	18
Annex D (normative)	Production assessment, trade marking and factory production control.....	19
Annex E (informative)	Supplementary properties.....	24
Bibliography		25

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 16696-1:2019](https://standards.iteh.ai/catalog/standards/sist/e6ba409b-15a6-4b21-96c3-4cb5b4195e1f/iso-16696-1-2019)

<https://standards.iteh.ai/catalog/standards/sist/e6ba409b-15a6-4b21-96c3-4cb5b4195e1f/iso-16696-1-2019>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 165, *Timber structures*.

A list of all parts in the ISO 16696 series can be found on the ISO website: <http://www.iso.org/iso/16696-1-2019>

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The general principle of this document is that a certain level of performance and production techniques are required in the production of cross laminated timber (CLT) to be acceptable for structural application of the product. This document specifies the minimum requirements for CLT production and performance assessment.

This document was based heavily on the draft European Standard EN 16351 prepared by Technical Committee CEN/TC 124 and the North American Standard ANSI/APA PRG 320. The technical contents from these standards were merged and modified to bring it into conformance with ISO procedures and requirements. The ISO 16696 series consists of two parts: this document (Part 1) gives performance and production requirements for CLT, which also includes conformance requirements, as provided in [Annex D](#); ISO 16696-2 provides guidance on how CLT is to be installed and used.

The bibliography lists standards referenced during the development of this document.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 16696-1:2019

<https://standards.iteh.ai/catalog/standards/sist/e6ba409b-15a6-4b21-96c3-4cb5b4195e1f/iso-16696-1-2019>

Timber structures — Cross laminated timber —

Part 1:

Component performance, production requirements and certification scheme

1 Scope

This document establishes the basic principles for component performance and minimum production requirements for cross laminated timber (CLT). This document also contains scheme requirements for conformance, as provided in [Annex D](#).

The document is applicable to CLT products which are manufactured from solid-sawn timber or wood based panels built up of at least three layers in which the grain of adjoining layers are at right angles to each other.

This document provides CLT dimension tolerances; component requirements; performance criteria; production, testing and trade marking guidance; and minimum requirements for factory production control. This document is based on known species, species combination and/or wood based panel structural performance and bondability.

CLT qualified in accordance with the provisions of this document are intended to resist the effects of moisture on structural performance as can occur due to construction delays or other conditions of similar severity.

NOTE This document does not include how CLT is to be used and installed, as it will be detailed in ISO 16696-2.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 16351, *Timber structures — Cross laminated timber — Requirements*

ISO/IEC 3130, *Wood — Determination of moisture content for physical and mechanical tests*

ISO 10983, *Timber — Finger joints — Minimum production requirements and testing methods*

ISO/IEC 12460 (all parts), *Wood-based panels — Determination of formaldehyde release*

ISO/IEC 13910, *Structural timber — Sampling, full-size testing, and evaluation of the characteristic values of strength graded timber*

ISO/IEC 16979, *Wood based panels — Determination of moisture content*

ISO 20152-1, *Timber structures — Bond performance of adhesives — Part 1: Basic requirements*

ISO 20152-2:2011, *Timber structures — Bond performance of adhesives — Part 2: Additional requirements*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO 16696-1:2019(E)

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

actual size

measured size of a CLT product at a related moisture content

3.2

adhesive

substance capable of bonding materials together

3.3

adherend

material held to another material by an adhesive

3.4

bond

attachment at an interface between adhesive and adherends or the act of attaching adherends together by adhesive

3.5

bondline

layer of adhesive which attaches two adherends

3.6

characteristic value

structural property estimate, typically a population mean for stiffness properties or a tolerance limit (5th percentile with 75 % confidence) for strength properties

Note 1 to entry: As estimated from the test data that is representative of the population being sampled as determined in accordance with ISO 12122-1.

3.7

corrected size

actual size of a CLT product corrected by calculation to the reference moisture content

3.8

corrective action

action to eliminate the cause of nonconformities

3.9

cross laminated timber

CLT

a prefabricated engineered wood product made of at least three orthogonal layers of graded sawn lumber or wood based panels that are laminated by gluing with structural adhesives

3.10

CLT thickness

dimension of the CLT panel measured perpendicular to the plane of the panel

3.11

delamination

separation of layers in a laminate due to failure of the adhesive either in the adhesive itself or at the interface between the adhesive and the adherend

3.12

edge

panel edge

narrow face of a panel that exposes the ends or narrow faces of the laminations

3.13**edge gluing
edge joints**

gluing the edges of adjacent lamination within a CLT layer

3.14**end joint**

joint made by gluing of the finger joints of the same laminations within a CLT layer prior to laminating adjacent layers

3.15**face**

one of the four longitudinal surfaces of a piece or panel

3.16**face bondline**

bondline joining the wide faces of the laminations in adjacent layers

3.17**factory production control****FPC**

procedures, regular inspections and tests which ensure that products placed on the market conform to the performance requirements stated by the manufacturer

3.18**finger angle**

α

inclination of the fingers of a finger joint

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Note 1 to entry: see [Figure 1](#).

[ISO 16696-1:2019](#)

3.19**finger joint**

self-locating end joint formed by machining a number of similar, tapered, symmetrical fingers in the ends of solid sawn timber components, which are formed by a finger joint cutter and then bonded together

<https://standards.iteh.ai/catalog/standards/sist/e6ba409b-15a6-4b21-96c3-4cb5b4195e1f/iso-16696-1-2019>

Note 1 to entry: see [Figure 1](#).

3.20**finger length**

l_j

distance between the finger base and the tip of the finger, measured along the centre line of the finger

Note 1 to entry: see [Figure 1](#).

3.21**finished thickness and width**

thickness and width after planing

3.22**lamination**

solid sawn timber or wood based panels, including stress rated boards and manufactured timber which has been prepared to be a layer

3.23**large finger joint**

finger joint through the full cross sectional area at the end of plane cross laminated components solely made of solid sawn timber layer, having identical cross sectional layups and bonded together

Note 1 to entry: see [Figure 2](#).

3.24

layer

all laminations on one side of a face bondline and consist of one solid sawn timber grade or one grade of wood based panel

3.25

layup

cross-sectional arrangement of layers of solid sawn timber or wood based panels, which may have different species, strength classes, strength profiles, thicknesses or technical classes (3.41), into a CLT product

3.26

manufacturing standard

procedures established by manufacturer to produce and maintain a product with the stated performance requirements

3.27

major strength direction

general direction of the grain of the outermost layers of the CLT panel

3.28

maximum delamination length

largest delamination length in any single glue line measured around the circumference of the test piece

3.29

minor strength direction

direction perpendicular to the major strength direction of the CLT panel

3.30

moisture content

u

amount of water present in solid sawn timber or wood based panels, expresses as percentage of oven dry mass

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 16696-1:2019

<https://standards.iteh.ai/catalog/standards/sist/c6ba409b-15a6-4b21-96c3-4cb5b4195e1f/iso-16696-1-2019>

Note 1 to entry: Determined in accordance with ISO 3130 or ISO 16979.

3.31

panel

single CLT billet formed by bonding lamination with a structural adhesive

3.32

pitch

distance between fingers, measured from centre to centre

Note 1 to entry: see [Figure 1](#).

3.33

ply

all laminations between two adjacent bondline and consist of one solid sawn timber grade or one grade of wood-based panel

3.34

service class 1

service class characterized by a moisture content in the materials corresponding to a temperature of 20 °C and a relative humidity of the surrounding air exceeding 65 % for a few weeks per year

Note 1 to entry: In Service Class 1, the average equilibrium moisture content of most softwoods does not exceed 12 %.

[SOURCE: ISO 20152-1:2010, 3.1]

3.35**service class 2**

service class characterized by a moisture content in the materials corresponding to a temperature of 20 °C and a relative humidity of the surrounding air exceeding 85 % for a few weeks per year

Note 1 to entry: In Service Class 2, the average equilibrium moisture content of most softwoods does not exceed 20 %. Such conditions include resistance to the effects of moisture on structural performance due to construction delays or other conditions of similar severity.

[SOURCE: ISO 20152-1:2010, 3.2]

3.36**service class 3**

service class characterized by climatic conditions leading to higher moisture content than Service Class 2 such as occurs when a member is fully exposed to the weather

[SOURCE: ISO 20152-1:2010, 3.3]

3.37**solid sawn timber grade**

a solid sawn wood product population produced with standardized rules that maintain well-defined limits on strength-controlling characteristics or properties

3.38**specific gravity**

ratio of the oven-dry mass of a specimen to the mass of a volume of water equal to the volume of the specimen at the specified moisture content

3.39**surveillance of FPC**

continual monitoring of the factory production control test plan(s) and production processes

3.40**target size**

size specified (at the reference moisture content) to which deviations are related

3.41**technical class**

class of product performance included in a standard for the purpose of relating product performance to its intended use

3.42**tip gap**

l_t

distance between fingertip and slot base in a bonded finger joint

Note 1 to entry: see [Figure 1](#).

3.43**tip width**

b_t

distance between finger faces, measured at the tip of the finger

Note 1 to entry: see [Figure 1](#).

3.44**total delamination length**

sum of delamination lengths of all glue lines around the circumference of a test piece

3.45

wood based panel

engineered wood product that is intended for structural use and bonded with adhesives, such as oriented strand board (OSB), plywood, laminated veneer lumber (LVL), and plywood and single-layered solid wood panels

3.46

wood failure

rupture in or between wood fibres

3.47

wood failure percentage

area of wood fibre remaining at the bondline following the rupture of wood fibres from the specified shear test, expressed as a percentage of total area involved in such failure

4 Symbols and subscripts

4.1 Symbols

b_{cut} tip width of the cutter, in mm

b_l finished lamination width, in mm

E modulus of elasticity in bending, in MPa

f_b characteristic bending strength of CLT, in MPa

h depth of cross section, in mm

h_a actual depth, in mm

h_{cor} corrected depth, in mm

k moisture deformation factor perpendicular to the grain for a change in moisture content of 1 % for moisture contents between 6 % and 25 %

l length, in mm

n number

p pitch, in mm

S section modulus, in mm³, of the composite CLT section for calculating the moment capacity of CLT

t thickness, in mm

t_l finished lamination thickness, in mm

u_a actual moisture content, in %

4.2 Subscripts

a actual

cor corrected

ref referenced