

## SLOVENSKI STANDARD SIST ISO 3601-5:2016

01-maj-2016

Nadomešča:

SIST ISO 3601-5:2003

Fluidni sistemi - Tesnilke O - 5. del: Specifikacija elastomernih materialov, primernih za industrijsko uporabo

Fluid power systems - O-rings - Part 5: Specification of elastomeric materials for industrial applications

## iTeh STANDARD PREVIEW

(standards.iteh.ai)

Transmissions hydrauliques et pneumatiques - Joints toriques - Partie 5: Matériaux élastomères convenant pour applications industrielles

https://standards.iteh.ai/catalog/standards/sist/727b6f49-cd8f-4c62-83ef-2940e645de50/sist-iso-3601-5-2016

Ta slovenski standard je istoveten z: ISO 3601-5:2015

ICS:

23.100.60 Filtri, tesnila in Filters, seals and

onesnaževanje tekočin contamination of fluids

SIST ISO 3601-5:2016 en

SIST ISO 3601-5:2016

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 3601-5:2016

# INTERNATIONAL STANDARD

ISO 3601-5

Second edition 2015-04-01

## Fluid power systems — 0-rings —

Part 5:

## **Specification of elastomeric materials for industrial applications**

Transmissions hydrauliques et pneumatiques — Joints toriques —

iTeh STPartie 5: Matériaux élastomères convenant pour applications industrielles (standards.iteh.ai)



## iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 3601-5:2016</u> https://standards.iteh.ai/catalog/standards/sist/727b6f49-cd8f-4c62-83ef-2940e645de50/sist-iso-3601-5-2016



### COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Cor	itent	ts	Page
Fore	word		iv
Intro	ductio	on	v
1	Scop	oe	1
2	Nori	1	
3	<b>Tern</b> 3.1 3.2	ns, definitions, and symbols  Terms and definitions  Symbols	
4	Mate	erials	2
	4.1 4.2 4.3 4.4	Commonly used elastomeric materials Curing systems O-ring requirements. Detailed requirements of O-ring materials	2 2 3
5	Desi	12	
6	Iden	itification statement	12
Anne	ex A (in	nformative) <b>0-ring stress/strain and compression set testing</b>	13

## iTeh STANDARD PREVIEW (standards.iteh.ai)

### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: Foreword — Supplementary information.

The committee responsible for this document is ISO/TC 131, *Fluid power systems*, Subcommittee SC 7, *Sealing devices*.

SIST ISO 3601-5:2016

This second edition cancels and replaces the first redition 7 (480-3604-5:2002), which has been technically revised. 2940e645de50/sist-iso-3601-5-2016

ISO 3601 consists of the following parts, under the general title *Fluid power systems — O-rings*:

- Part 1: Inside diameters, cross-sections, tolerances and designation codes
- Part 2: Housing dimensions for general applications
- Part 3: Quality acceptance criteria
- Part 4: Anti-extrusion rings (back-up rings)
- Part 5: Suitability of elastomeric materials for industrial applications

## Introduction

In fluid power systems, power is transmitted and controlled through a fluid (liquid or gas) under pressure within an enclosed circuit. One component of such a system can be a toroidal sealing, an O-ring. This part of ISO 3601 evaluates the suitability of a number of elastomeric materials (rubber) which can be used for O-rings in industrial applications.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 3601-5:2016

# iTeh STANDARD PREVIEW (standards.iteh.ai)

## Fluid power systems — 0-rings —

## Part 5:

## Specification of elastomeric materials for industrial applications

## 1 Scope

This part of ISO 3601 contains the material specification of a selection of standard elastomeric materials (rubber) for 0-rings used in general industrial applications. It also indicates the ability of the materials to satisfy many of the requirements associated with fluid power components.

Only materials which are in universal usage are specified; other compounds are available and can be used.

The required physical properties and test methods (including test specimen) should be agreed upon between equipment manufacturer/user and O-ring manufacturer/supplier.

## 2 Normative references TANDARD PREVIEW

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties

ISO 48, Rubber, vulcanized or thermoplastic Determination of hardness (hardness between 10 IRHD and 100 IRHD)

ISO 188, Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests

ISO~815:1, Rubber, vulcanized~or~thermoplastic -- Determination~of~compression~set -- Part~1:~At~ambient~or~elevated~temperatures

ISO 1382, Rubber — Vocabulary

ISO 1629, Rubber and latices — Nomenclature

ISO 1817, Rubber, vulcanized — Determination of the effect of liquids

ISO 2921, Rubber, vulcanized — Determination of low-temperature retraction (TR test)

ISO 3601-1, Fluid power systems — 0-rings — Part 1: Inside diameters, cross-sections, tolerances and designation codes

ISO 5598, Fluid power systems and components — Vocabulary

ASTM D1414, Standard Test Methods for Rubber O-Rings

## 3 Terms, definitions, and symbols

#### 3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 3601-1, ISO 1382, and ISO 5598 apply.

### 3.2 Symbols

- $d_1$  inside diameter of 0-ring
- *d*<sup>2</sup> cross section diameter of 0-ring

#### 4 Materials

### 4.1 Commonly used elastomeric materials

Table 1 gives a selection of elastomeric materials commonly used for 0-rings in general industrial applications.

Table 1 — Commonly used elastomeric materials for O-rings

Basic elastomer	Codea	Curing system	<b>Nominal hardness (IRHD)</b> b °, CM						
Acrylonitrile-butadiene	NBR	S	70, 90						
Acrylonitrile-butadiene	NBR	Р	75, 90						
Hydrogenated NBR	HNBR		75, 90						
Fluorocarbon	FKM		70, 75, 80, 90						
Silicone	CTVMQID	RD PRI	70						
Ethylene-propylene-diene	EPDM	S	70, 80						
Ethylene-propylene-diene	(SEPOMCIAT	ds.iţeh.a	70,80						
Polyacrylate	ACM	2601 5 2016	70						
NOTE Other hardness and materials are possible depending on the application of 49-cd8f-4c62-83ef-									
a Codes in accordance with ISO 1629. 2940e645de50/sist-iso-3601-5-2016									
b See ISO 48									

#### 4.2 Curing systems

An important process in moulding operations to make O-rings is vulcanization. Vulcanization is a chemical process for converting rubber or related polymers into more durable and, in case of elastomers, more elastic materials through the addition of sulfur or other equivalent "curatives." These additives modify the polymer by forming crosslinks between individual polymer chains.

The curing system used depends on the polymer type and the desired properties. Two of the most widely and often used systems are sulfur (S) and peroxide (P) curing systems.

NOTE Not all curing systems are suitable for all elastomers.

## 4.3 O-ring requirements

The O-ring requirements of the basic elastomers according to <u>Table 1</u> are specified in <u>Table 2</u>. This table can be used for the inspection of production parts, incoming goods, or in case of complaints.

			BR S	NBR P		HNBR		FKM		VMQ		<b>EPDM</b> S		EPDM P		ACM		Test method	
Hardness (IRHD)	°, CM°	70	90	75	90	75	90	70	75	80	90	70	70	80	70	80	70		
Tolerance in hardness for	_		<del>-</del>												100 40 CM				
<i>d</i> <sub>2</sub> ≥ 1,60 mm	°, CM°		+5/-5											ISO 48 CM					
d <sub>2</sub> < 1,60 mm	°, CMc		+5/-8																
Compression set, max.a	%	35	35	30	30	40	50	25	25	25	30	35	30	35	30	30	40	ISO 815-1, Method A	
24 (+0/-2) h <sup>b</sup> at temperature	°C	100	100	100	100	150	150	200	200	200	200	175	100	100	150	150	150		
Compression set, max.	%	50	50	40	40	45	50	30	30	30	30	40	40	40	35	35	50	ISO 815-1, Method A	
for $d_2 \ge 2,62 \text{ mm}$ 72 (+0/-2) hb at temperature	°C	100	100	100	100	125	125	175	175	175	175	175	100	100	125	125	150		
Compression set, max.a	%	50	50	45	50	45	50	30	30	30	30	50	45	45	35	35	50	100 015 1	
for $d_2 < 2,62 \text{ mm}$ 72 (+0/-2) h <sup>b</sup> at temperature	°C	100	100	100	100	125	125	175	175	175	175	175	100 [7	100	125	125	150	ISO 815-1, Method A	

NOTE 1 The frequency of the lot testing should be agreed between the supplier and purchaser at the time of order.

NOTE 2 For all values  $d_2 < 1$  mm, no reliable measurement procedures have been developed.

- <sup>a</sup> For values  $d_2 < 2$  mm, the limits can be increased by +5 %.
- b Purchaser and supplier should agree upon the duration of the compression set test.
- For indication of the hardness, see ISO 486.45 do 50/gist inc. 2601.5.2016

## 4.4 Detailed requirements of 0-ring materials

Operating conditions shall be taken into consideration when O-ring materials are selected.

Therefore users should determine the compatibility of the O-ring material with the operational parameters (e.g. fluid, temperature, pressure, etc.) of the application.

The detailed requirements of 0-ring materials according to <u>Table 1</u> are specified in <u>Tables 3</u> to <u>10</u>. These tables should be used to qualify standard 0-ring materials.