



**SLOVENSKI STANDARD**  
**SIST EN 13163:2013+A2:2017**  
**01-januar-2017**

**Nadomešča:**  
**SIST EN 13163:2013+A1:2015**

---

**Toplotnoizolacijski proizvodi za stavbe - Proizvodi iz ekspaniranega polistirena (EPS) - Specifikacija**

Thermal insulation products for buildings - Factory made expanded polystyrene (EPS) products - Specification

Wärmedämmstoffe für Gebäude - Werkmäßig hergestellte Produkte aus expandiertem Polystyrol (EPS) - Spezifikation  
**(standards.iteh.ai)**

Produits isolants thermiques pour le bâtiment - Produits manufacturés en polystyrène expansé (EPS) - Specification  
[standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017](https://standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017)

**Ta slovenski standard je istoveten z: EN 13163:2012+A2:2016**

---

**ICS:**

91.100.60	Materiali za toplotno in zvočno izolacijo	Thermal and sound insulating materials
-----------	---	--

<b>SIST EN 13163:2013+A2:2017</b>	<b>en,fr,de</b>
-----------------------------------	-----------------

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 13163:2013+A2:2017](https://standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017)

<https://standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017>

EUROPEAN STANDARD

EN 13163:2012+A2

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2016

ICS 91.100.60

Supersedes EN 13163:2012+A1:2015

English Version

## Thermal insulation products for buildings - Factory made expanded polystyrene (EPS) products - Specification

Produits isolants thermiques pour le bâtiment -  
Produits manufacturés en polystyrène expansé (EPS) -  
Spécification

Wärmedämmstoffe für Gebäude - Werkmäßig  
hergestellte Produkte aus expandiertem Polystyrol  
(EPS) - Spezifikation

This European Standard was approved by CEN on 6 October 2012 and includes Amendment 1 approved by CEN on 15 December 2014 and Amendment 2 approved by CEN on 11 July 2016.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**



<b>Contents</b>	<b>Page</b>
European foreword.....	6
<b>1 Scope</b> .....	<b>9</b>
<b>2 Normative references</b> .....	<b>9</b>
<b>3 Terms, definitions, symbols, units and abbreviated terms</b> .....	<b>11</b>
3.1 Terms and definitions.....	11
3.2 Symbols, units and abbreviated terms.....	12
<b>4 Requirements</b> .....	<b>15</b>
4.1 General.....	15
4.2 For all applications.....	16
4.2.1 Thermal resistance and thermal conductivity.....	16
4.2.2 Length and width.....	16
4.2.3 Thickness.....	16
4.2.4 Squareness.....	16
4.2.5 Flatness.....	17
4.2.6 Reaction to fire of the product as placed on the market.....	17
4.2.7 Durability characteristics.....	17
4.3 For specific applications.....	18
4.3.1 General.....	18
4.3.2 Dimensional stability.....	18
4.3.3 Squareness.....	19
4.3.4 Compressive stress at 10 % deformation.....	19
4.3.5 Bending strength.....	19
4.3.6 Tensile strength perpendicular to faces.....	20
4.3.7 Deformation under specified compressive load and temperature conditions.....	20
4.3.8 Compressive creep.....	21
4.3.9 Shear behaviour.....	21
4.3.10 Cyclic loading behaviour.....	22
4.3.11 Water absorption.....	22
4.3.12 Freeze-thaw resistance.....	22
4.3.13 Water vapour transmission.....	23
4.3.14 Dynamic stiffness.....	23
4.3.15 Compressibility (only applicable on EPS T products).....	23
4.3.16 Apparent density.....	25
4.3.17 Reaction to fire of the product in standardised assemblies simulating end-use applications.....	25
4.3.18 Continuous glowing combustion.....	25
4.3.19 Release of dangerous substances.....	25
<b>5 Test methods</b> .....	<b>25</b>
5.1 Sampling.....	25
5.2 Conditioning.....	25
5.3 Testing.....	26
5.3.1 General.....	26
5.3.2 Thermal resistance and thermal conductivity.....	26
<b>6 Designation code</b> .....	<b>28</b>

<b>7</b>	<b>Assessment and Verification of the Constancy of Performance (AVCP)</b> .....	<b>30</b>
7.1	General .....	30
7.2	Product Type Determination (PTD) .....	30
7.3	Factory Production Control (FPC) .....	30
<b>8</b>	<b>Marking and labelling</b> .....	<b>30</b>
<b>Annex A (normative) Determination of the declared values of thermal resistance and thermal conductivity</b> .....		
		<b>32</b>
A.1	General .....	32
A.2	Input data .....	32
A.3	Declared values .....	32
A.3.1	General .....	32
A.3.2	Case where thermal resistance and thermal conductivity are declared .....	32
A.3.3	Case where thermal resistance is declared .....	33
<b>Annex B (normative) <math>\square_{A1}</math> Product type determination <math>\square_{A1}</math> (<math>\square_{A1}</math> PTD <math>\square_{A1}</math>) and factory production control (FPC)</b> .....		
		<b>34</b>
B.1	$\square_{A1}$ Product type determination $\square_{A1}$ and factory production control .....	34
B.2	Indirect testing for factory production control .....	39
B.2.1	General .....	39
B.2.2	Compressive stress at 10 % deformation .....	39
B.2.3	Thermal conductivity .....	40
B.2.4	Thickness effect .....	41
B.2.5	Dynamic stiffness .....	41
<b>Annex C (normative) Product classification</b> .....		
		<b>42</b>
<b>Annex D (normative) Multi layered EPS products</b> .....		
		<b>44</b>
D.1	General .....	44
D.2	Requirements .....	44
D.2.1	For all applications .....	44
D.2.2	For specific applications .....	45
D.3	Test methods .....	45
D.4	Evaluation of conformity .....	45
<b>Annex E (informative) Verification of the reaction to fire classification of raw materials</b> .....		
		<b>46</b>
E.1	General .....	46
E.2	Material covered by this annex .....	46
E.3	Preparation of samples .....	46
E.4	$\square_{A1}$ Product type determination $\square_{A1}$ for EPS raw material .....	46
E.5	Factory Production Control for EPS raw material .....	47
E.5.1	General .....	47
E.5.2	Testing frequency .....	47
E.6	Certification of conformity for EPS raw material .....	47
E.6.1	Bodies involved in the evaluation of conformity procedure .....	47
E.6.2	Test specimens .....	47
E.6.3	$\square_{A1}$ Product type determination $\square_{A1}$ .....	47
E.7	Continuous surveillance of EPS raw material .....	48
E.7.1	Production .....	48
E.7.2	Factory production control .....	48
E.8	Material certificate for EPS raw material .....	48
E.9	Requirement for raw material supply .....	49
E.9.1	Declaration for the raw material supply .....	49
E.9.2	Labelling .....	49
<b>Annex F (informative) Additional properties</b> .....		
		<b>50</b>

## EN 13163:2012+A2:2016 (E)

F.1	General.....	50
F.2	Long-term compressive behaviour.....	50
F.3	Shear behaviour.....	50
F.4	Water vapour diffusion resistance factor .....	51
F.5	Examples of determination of thermal conductivity .....	52
F.6	Additional information .....	53
Annex ZA (informative) $\square_{A1}$ Clauses of this European Standard addressing the provisions of the EU Construction Products Regulation $\square_{A1}$ .....		54
Bibliography.....		65
Tables		
Table 1 — Classes of dimensional tolerances .....		17
Table 2 — Dimensional stability under specified temperature or specified temperature and humidity conditions.....		18
Table 3 — Levels for compressive stress at 10 % deformation.....		19
Table 4 — Levels for bending strength.....		20
Table 5 — Levels of deformation under specified compressive load and temperature conditions .....		21
Table 6 — Levels for dynamic stiffness.....		23
Table 7 — Classes for thickness tolerances.....		24
Table 8 — Levels for compressibility.....		24
Table 9 — Test methods, test specimens and conditions.....		27
Table A.1 — Values for $k$ for one sided 90 % tolerance interval with a confidence level of 90 % .....		33
Table B.1 — Number of tests for $\square_{A1}$ PTD $\square_{A1}$ and minimum product testing frequencies .....		34
Table B.2 — Minimum product testing frequencies for the reaction to fire characteristics .....		37
Table C.1 — Classification of EPS products .....		42
Table C.2 — Classification EPS products with acoustical properties.....		43
Table E.1 — Testing frequency of raw material.....		48
Table F.1 — Correlation between bending strength and shear strength.....		51
Table F.2 — Tabulated values of water vapour diffusion resistance index and water vapour permeability.....		52
Table ZA.1 — Relevant clauses for factory made expanded polystyrene and intended use.....		55
Table ZA.2 — Systems of AVCP .....		56
Table ZA.3.1 — Assignment of AVCP tasks for factory made expanded polystyrene products under system 1 for reaction to fire and system 3 (see Table ZA.2) .....		57
Table ZA.3.2 — Assignment of AVCP tasks for factory made expanded polystyrene products under system 3 (see Table ZA.2) .....		58
Table ZA.3.3 — Assignment of AVCP tasks for factory made expanded polystyrene products under combined system 4 for reaction to fire and system 3 (see Table ZA.2).....		59

**Figures**

<b>Figure B.1 — Relationship between compressive stress at 10 % deformation and apparent density for indirect testing.....</b>	<b>40</b>
<b>Figure F.1 — Example of a relationship between thermal conductivity (at 50 mm reference thickness and 10 °C mean temperature) apparent density for indirect testing of non infrared absorbing EPS.....</b>	<b>53</b>
<b>Figure ZA.1 —  Example CE marking information .....</b>	<b>64</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 13163:2013+A2:2017](https://standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017)

<https://standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017>

## EN 13163:2012+A2:2016 (E)

## European foreword

This document (EN 13163:2012+A2:2016) has been prepared by Technical Committee CEN/TC 88 “Thermal insulating materials and products”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2017, and conflicting national standards shall be withdrawn at the latest by August 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of <sup>A2</sup> the EU Construction Products Regulation (CPR) <sup>A2</sup>.

<sup>A1</sup> For relationship with EU Construction Products Regulation (CPR), see informative Annex ZA, which is an integral part of this standard. <sup>A1</sup>

This document includes Amendment 1, approved by CEN on 2014-12-15 and Amendment 2, approved by CEN on 2016-07-11.

iTeh STANDARD PREVIEW

This document supersedes <sup>A2</sup> EN 13163:2012+A1:2015 <sup>A2</sup> (standard.iTeh.ai)

The start and finish of text introduced or altered by amendment is indicated in the text by tags <sup>A1</sup> <sup>A1</sup> and <sup>A2</sup> <sup>A2</sup>.

<https://standards.iTeh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017>

The main changes <sup>A2</sup> brought by EN 13163:2012 to the 2008 edition were <sup>A2</sup>:

- a) better harmonisation between the individual standards of the package (EN 13162 to EN 13171) on definitions, requirements, classes and levels;
- b) new annex on multi-layered products;
- c) new annex on voluntary verification of the reaction to fire classification of raw materials;
- d) changes on some editorial and technical content and addition of information on some specific items such as for EPS dimensional stability, compressibility;
- e) addition of links to EN 15715, *Thermal insulation products — Instructions for mounting and fixing for reaction to fire testing — Factory made products*;
- f) changes to the Annex ZA.

<sup>A1</sup> Amendment 1 modifies EN 13163:2012 identifying those clauses of the standard which are needed for the compliance of the European Standard with the Construction Products Regulation (CPR).

This amendment introduces

- g) an addition to the foreword;



- h) an addition in 3.2;
- i) a new subclause 4.3.19;
- j) modification of Clause 7;
- k) modification of Clause 8;
- l) modification of Annex B;
- m) modification of Annex E;
- n) a new Annex ZA.  $\square_{A1}$

$\square_{A2}$  The main changes brought by the 2<sup>nd</sup> amendment to EN 13163:2012+A1:2015 are:

- p) the adjustment of dimensions;
- q) the modification of several clauses;
- r) the addition of a symbol.  $\square_{A2}$

This standard is one of a series of standards for thermal insulation products used in buildings, but this standard may be used in other areas where appropriate.

In pursuance of Resolution BT 20/1993 revised, CEN/TC 88 have proposed defining the standards listed below as a European package of standards.

The package of standards comprises the following group of interrelated standards for the specifications of factory made thermal insulation products, all of which come within the scope of CEN/TC 88:

EN 13162, *Thermal insulation products for buildings — Factory made mineral wool (MW) products — Specification*

EN 13163, *Thermal insulation products for buildings — Factory made expanded polystyrene (EPS) products — Specification*

EN 13164, *Thermal insulation products for buildings — Factory made extruded polystyrene foam (XPS) products — Specification*

EN 13165, *Thermal insulation products for buildings — Factory made rigid polyurethane foam (PU) products — Specification*

EN 13166, *Thermal insulation products for buildings — Factory made phenolic foam (PF) products — Specification*

EN 13167, *Thermal insulation products for buildings — Factory made cellular glass (CG) products — Specification*

EN 13168, *Thermal insulation products for buildings — Factory made wood wool (WW) products — Specification*

EN 13169, *Thermal insulation products for buildings — Factory made expanded perlite board (EPB) products — Specification*

**EN 13163:2012+A2:2016 (E)**

EN 13170, *Thermal insulation products for buildings — Factory made products of expanded cork (ICB) — Specification*

EN 13171, *Thermal insulation products for buildings — Factory made wood fibre (WF) products — Specification*

The reduction in energy used and emissions produced during the installed life of insulation products exceeds by far the energy used and emissions made during the production and disposal processes.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

[SIST EN 13163:2013+A2:2017](https://standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017)

<https://standards.iteh.ai/catalog/standards/sist/e9044683-8a9f-4987-b87a-060f037c6a62/sist-en-13163-2013a2-2017>

## 1 Scope

This European Standard specifies the requirements for factory made expanded polystyrene products, with or without rigid or flexible facings or coatings, which are used for the thermal insulation of buildings. The products are manufactured in the form of boards or rolls or other preformed ware (flat, tapered, tongue and grooves, shiplap, profiled etc.).

Products covered by this standard are also used for sound insulation and in prefabricated thermal insulation systems and composite panels; the performance of systems incorporating these products is not covered.

This standard describes product characteristics and includes procedures for testing, evaluation of conformity, marking and labelling.

This standard does not specify the required class or level of a given property to be achieved by a product to demonstrate fitness for purpose in a particular application. The classes and levels required for a given application are to be found in regulations or non-conflicting standards.

Products with a declared thermal resistance lower than  $0,25 \text{ m}^2\cdot\text{K}/\text{W}$  or a declared thermal conductivity at  $10 \text{ }^\circ\text{C}$  greater than  $0,060 \text{ W}/(\text{m}\cdot\text{K})$  are not covered by this standard.

This standard does not cover in-situ insulation products (covered by  $\text{A}_2$  EN 16025-1 and -2  $\text{A}_2$ ), products intended to be used for the insulation of building equipment and industrial installations (covered by EN 14309), products intended to be used in civil engineering applications (covered by EN 14933) and products intended to be used in beam and block systems in floors (covered by EN 15037-4).

iTeh STANDARD PREVIEW

## 2 Normative references (standards.iteh.ai)

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 822, *Thermal insulating products for building applications — Determination of length and width*

EN 823, *Thermal insulating products for building applications — Determination of thickness*

EN 824, *Thermal insulating products for building applications — Determination of squareness*

EN 825, *Thermal insulating products for building applications — Determination of flatness*

EN 826, *Thermal insulating products for building applications — Determination of compression behaviour*

EN 1602, *Thermal insulating products for building applications — Determination of the apparent density*

EN 1603, *Thermal insulating products for building applications — Determination of dimensional stability under constant normal laboratory conditions (23 °C/ 50 % relative humidity)*

EN 1604, *Thermal insulating products for building applications — Determination of dimensional stability under specified temperature and humidity conditions*

EN 1605, *Thermal insulating products for building applications — Determination of deformation under specified compressive load and temperature conditions*

EN 1606, *Thermal insulating products for building applications — Determination of compressive creep*

**EN 13163:2012+A2:2016 (E)**

EN 1607, *Thermal insulating products for building applications — Determination of tensile strength perpendicular to faces*

EN 12085, *Thermal insulating products for building applications — Determination of linear dimensions of test specimens*

EN 12086:1997, *Thermal insulating products for building applications — Determination of water vapour transmission properties*

EN 12087, *Thermal insulating products for building applications — Determination of long term water absorption by immersion*

EN 12088, *Thermal insulating products for building applications — Determination of long term water absorption by diffusion*

EN 12089, *Thermal insulating products for building applications — Determination of bending behaviour*

EN 12090, *Thermal insulating products for building applications — Determination of shear behaviour*

EN 12091, *Thermal insulating products for building applications — Determination of freeze-thaw resistance*

EN 12429, *Thermal insulating products for building applications — Conditioning to moisture equilibrium under specified temperature and humidity conditions*

EN 12431, *Thermal insulating products for building applications — Determination of thickness for floating floor insulation products*

EN 12667, *Thermal performance of building material and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Products of high and medium thermal resistance*

EN 12939, *Thermal performance of building materials and products — Determination of thermal resistance by means of guarded hot plate and heat flow meter methods — Thick products of high and medium thermal resistance*

EN 13172:2012, *Thermal insulation products — Evaluation of conformity*

EN 13501-1, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13793, *Thermal insulating products for building applications — Determination of behaviour under cyclic loading*

EN 13820, *Thermal insulating materials for building applications — Determination of organic content*

EN 13823, *Reaction to fire tests for building products — Building products excluding floorings exposed to the thermal attack by a single burning item*

EN 15715:2009, *Thermal insulation products — Instructions for mounting and fixing for reaction to fire testing - Factory made products*

EN 29052-1, *Acoustics — Determination of dynamic stiffness — Part 1: Materials used under floating floors in dwellings (ISO 9052-1)*

EN ISO 1182, *Reaction to fire tests for building products — Non-combustibility test (ISO 1182)*

EN ISO 1716, *Reaction to fire tests for products — Determination of the gross heat of combustion (calorific value) (ISO 1716)*

EN ISO 9229:2007, *Thermal insulation — Vocabulary (ISO 9229:2007)*

EN ISO 11925-2, *Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test (ISO 11925-2)*

ISO 16269-6:2005, *Statistical interpretation of data — Part 6: Determination of statistical tolerance intervals*

### 3 Terms, definitions, symbols, units and abbreviated terms

#### 3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 9229:2007 apply with exception or in addition of the following:

##### 3.1.1

##### **expanded polystyrene (EPS)**

rigid cellular plastic material, manufactured by moulding beads or granules of expandable polystyrene or one of its copolymers, with an air filled closed cellular structure, which is divided into four types related to the intended use:

- EPS<sub>i</sub>: for load bearing applications, where *i* stands for the declared value (expressed in compressive stress at 10 % deformation)
- EPS S: for non load bearing applications
- EPS SD: for non load bearing applications with acoustic properties
- EPS T: for floating floor applications

##### 3.1.2

##### **expanded polystyrene block**

rigid insulation product or material generally of rectangular cross section and with a thickness not significantly smaller than the width, supplied trimmed or untrimmed

##### 3.1.3

##### **expanded polystyrene board**

rigid insulation product (cut, moulded, or continuously foamed) of rectangular shape and cross section in which the thickness is significantly smaller than the other dimensions; it may be of uniform thickness or tapered and the edges may be of various sorts (e.g. square, half lapped, tongue and groove)

##### 3.1.4

##### **expanded polystyrene roll**

boards or strips bonded to a flexible facing, supplied in a wound or folded form, which form a continuous insulation layer when unrolled

##### 3.1.5

##### **preformed ware**

insulation shapes formed by cutting or routing from blocks or boards or by shape moulding

## EN 13163:2012+A2:2016 (E)

## 3.1.6

**level**

value, which is the upper or lower limit of a requirement, and given by the declared value of the characteristic concerned

## 3.1.7

**class**

combination of two levels of the same property between which the performance shall fall

## 3.1.8

**multi-layered insulation product**

product which can be faced or coated made from two or more layers of a thermal insulation material from the same European Standard, which are bonded together either horizontally by chemical or physical adhesion

## 3.1.9

**composite insulation product**

product which can be faced or coated, made from two or more layers bonded together by chemical or physical adhesion consisting of at least one factory made thermal insulation material layer

## 3.1.10

**facing**

functional or decorative surface layer with a thickness of less than 3 mm, e.g. paper, plastic film, fabric or metal foil, which is not considered as separate thermal insulation layer to be added to the thermal resistance of the product

## 3.1.11

**coating**

functional or decorative surface layer with a thickness of less than 3 mm usually applied by painting, spraying, pouring or trowelling, which is not considered as separate thermal insulation layer to be added to the thermal resistance of the product

## 3.2 Symbols, units and abbreviated terms

Symbols and units used in this standard:

$1 - \alpha$	is the prediction interval	1
$b$	is the width	mm
$b_0$	is a regression coefficient	kPa
$b_1$	is a regression coefficient	kPa·m <sup>3</sup> /kg
$c$	is the compressibility	mm
$d$	is the thickness	mm
$\delta$	is the water vapour permeability	mg/(Pa·h·m)
$d_B$	is the thickness under a load of 2 kPa after removal of an additional load of 48 kPa	mm
$d_L$	is the thickness under a load of 250 Pa	mm
$d_N$	is the nominal thickness of the product	mm
$d_s$	is the thickness of the test specimen	mm

$\Delta\varepsilon_b$	is the relative change in width	%
$\Delta\varepsilon_d$	is the relative change in thickness	%
$\Delta\varepsilon_l$	is the relative change in length	%
$\varepsilon_1$	is the deformation after step A in accordance with EN 1605	%
$\varepsilon_2$	is the deformation after step B in accordance with EN 1605	%
$\varepsilon_{ct}$	is the compressive creep	%
$\varepsilon_{l,max}$	is the maximum relative deformation in accordance with EN 13793	%
$\varepsilon_t$	is the total relative thickness reduction	%
$E_{dyn}$	is the dynamic elasticity modulus	MN/m <sup>2</sup>
$G$	is the shear modulus	kPa
$i$	is a counter	1
$k$	is a factor related to the number of test results available	1
$l$	is the length	mm
$\lambda_{90,90}$	is the 90 % fractile with a confidence level of 90 % for the thermal conductivity	W/(m·K)
$\lambda_D$	is the declared of thermal conductivity	W/(m·K)
$\lambda_i$	is one test result of thermal conductivity	W/(m·K)
$\lambda_{mean}$	is the mean thermal conductivity	W/(m·K)
$\lambda_{pred}$	is the predicted thermal conductivity with a prediction interval of 90 %	W/(m·K)
$\lambda_U$	is the design value of thermal conductivity	W/(m·K)
$\mu$	is the water vapour diffusion resistance factor	1
$n$	is the number of test results	1
$\rho_a$	is the apparent density	kg/m <sup>3</sup>
$\rho_{mean}$	is the mean density	kg/m <sup>3</sup>
$R_{90/90}$	is the 90 % fractile with a confidence level of 90 % for the thermal resistance	m <sup>2</sup> ·K/W
$R_D$	is the declared thermal resistance	m <sup>2</sup> ·K/W
$R_i$	is one test result of thermal resistance	m <sup>2</sup> ·K/W
$R_{mean}$	is the mean thermal resistance	m <sup>2</sup> ·K/W
$R_U$	is the design value of thermal resistance	m <sup>2</sup> ·K/W
$s'$	is the dynamic stiffness	MN/m <sup>3</sup>
$\sigma_{10}$	is the compressive stress at 10 % deformation	kPa
$\sigma_{10,mean}$	is the mean compressive stress at 10 % deformation	kPa
$\sigma_{10,pred}$	is the predicted compressive stress at 10 % deformation with a prediction interval of 90 %	kPa
$\sigma_b$	is the bending strength	kPa