



Designation: ~~D737-96~~ Designation: **D 737 – 04 (Reapproved 2008)^{ε1}**

Standard Test Method for Air Permeability of Textile Fabrics¹

This standard is issued under the fixed designation D 737; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

^{ε1} NOTE—Editorial changes were made in August 2008.

1. Scope

1.1 This test method covers the measurement of the air permeability of textile fabrics.

1.2 This test method applies to most fabrics including woven fabrics, nonwoven fabrics, air bag fabrics, blankets, napped fabrics, knitted fabrics, layered fabrics, and pile fabrics. The fabrics may be untreated, heavily sized, coated, resin-treated, or otherwise treated.

1.3 The values stated in SI units are to be regarded as the standard. The values stated in inch-pound units may be approximate.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 123 Terminology Relating to Textiles

D 1776 Practice for Conditioning Textiles for Testing² Practice for Conditioning and Testing Textiles

D 2904 Practice for Interlaboratory Testing of a Textile Test Method That Produces Normally Distributed Data

D 2906 Practice for Statements on Precision and Bias for Textiles² Practice for Statements on Precision and Bias for Textiles

D 4850 Terminology Relating to Fabric

F 778 Methods for Gas Flow Resistance Testing of Filtration Media

2.2 *ASTM Adjuncts:*

TEX-PAC

NOTE 1—TEX-PAC is a group of programs on floppy disks available through ASTM Headquarters, 100 Barr Harbor Drive, West Conshohocken, PA 19428. Methods for Gas Flow Resistance Testing of Filtration Media

3. Terminology

3.1 *Definitions*—For definitions of other textile terms used in this test method refer to Terminology D 123

3.1 For definition of textile terms used in this test method: air permeability, and fabric, refer to Terminology D 4850.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *air permeability, n*—the rate of air flow passing perpendicularly through a known area under a prescribed air pressure differential between the two surfaces of a material.

3.2.1.1 *Discussion*—Air permeability of fabric at a stated pressure differential between two surfaces of the fabric is generally expressed in SI units as $\text{cm}^3/\text{s}/\text{cm}^2$ and in inch-pound units as $\text{ft}^3/\text{min}/\text{ft}^2$ calculated at operating conditions.

3.2.2 *cross-machine direction, CD, n*—the direction in the plane of the fabric perpendicular to the direction of manufacture.

3.2.2.1 *Discussion*—This term is used to refer to the direction analogous to coursewise or filling direction in knitted or woven fabrics, respectively.

3.2.3 *fabric, in textiles, n*—a planar structure consisting of yarns or fibers.

3.2.4 *machine direction, MD, n*—the direction in the plane of the fabric parallel to the direction of manufacture.

¹ This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.59 on Fabric Test Methods, General. Current edition approved Feb. 10, 1996. Published April 1996. Originally published as D737-43T. Discontinued November 1995 and reinstated as D737-96. Current edition approved July 1, 2008. Published August 2008. Originally approved in 1943. Last previous edition approved in 2004 as D 737 – 04.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

~~3.2.4.1 Discussion—This term is used to refer to the direction analogous to warpwise or warp direction in knitted or woven fabrics, respectively.~~

3.2 For definitions of cross-machine direction; machine direction and other textile terms used in this test method, refer to Terminology D 123.

4. Summary of Test Method

4.1 The rate of air flow passing perpendicularly through a known area of fabric is adjusted to obtain a prescribed air pressure differential between the two fabric surfaces. From this rate of air flow, the air permeability of the fabric is determined.

5. Significance and Use

5.1 This test method is considered satisfactory for acceptance testing of commercial shipments since current estimates of between-laboratory precision are acceptable, and this test method is used extensively in the trade for acceptance testing.

~~5.1. In case of a dispute arising from differences in reported test results when using this test method for acceptance testing of commercial shipments, the purchaser and the supplier should conduct comparative tests to determine if there is a statistical bias between their laboratories. Competent statistical assistance is recommended for the investigation of bias. As a minimum, the two parties should take a group of test specimens that are as homogeneous as possible and that are from a lot of material of the type in question. Test specimens then should be randomly assigned in equal numbers to each laboratory for testing. The average results from the two laboratories should be compared using the appropriate statistical analysis and an acceptable probability level chosen by the two parties before testing is begun. If a bias is found, either its cause must be found and corrected, or the purchaser and the supplier must agree to interpret future test results with consideration of the known bias.~~

5.1.1 If there are differences of practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is a statistical bias between them, using competent statistical assistance. As a minimum, ensure the test samples to be used are as homogeneous as possible, are drawn from the material from which the disparate test results were obtained, and are randomly assigned in equal number to each laboratory for testing. The test results from the two laboratories should be compared using a statistical test for unpaired data, at a probability level chosen prior to the testing series. If bias is found, either its cause must be found and corrected, or future test results for that material must be adjusted in consideration of the known bias.

5.2 Air permeability is an important factor in the performance of such textile materials as gas filters, fabrics for air bags, clothing, mosquito netting, parachutes, sails, tentage, and vacuum cleaners. In filtration, for example, efficiency is directly related to air permeability. Air permeability also can be used to provide an indication of the breathability of weather-resistant and rainproof fabrics, or of coated fabrics in general, and to detect changes during the manufacturing process.

5.3 Performance specifications, both industrial and military, have been prepared on the basis of air permeability and are used in the purchase of fabrics where permeability is of interest.

5.4 Construction factors and finishing techniques can have an appreciable effect upon air permeability by causing a change in the length of airflow paths through a fabric. Hot calendaring can be used to flatten fabric components, thus reducing air permeability. Fabrics with different surface textures on either side can have a different air permeability depending upon the direction of air flow.

5.4.1 For woven fabric, yarn twist also is important. As twist increases, the circularity and density of the yarn increases, thus reducing the yarn diameter and the cover factor and increasing the air permeability. Yarn crimp and weave influence the shape and area of the interstices between yarns and may permit yarns to extend easily. Such yarn extension would open up the fabric, increase the free area, and increase the air permeability.

5.4.2 Increasing yarn twist also may allow the more circular, high-density yarns to be packed closely together in a tightly woven structure with reduced air permeability. For example, a worsted gabardine fabric may have lower air permeability than a woolen hosiery fabric.

6. Apparatus

6.1 *Air Permeability Testing Apparatus*³ consisting of the following:

6.1.1 *Test Head* that provides a circular test area of 38.3 cm² (5.93 in.²) ± 0.3 %.

NOTE 2₁—Alternate test areas may be used, such as 5 cm² (0.75 in.²), 6.45 cm² (1.0 in.²), and 100 cm² (15.5 in.²).

6.1.2 *Clamping System to Secure Test Specimens*, of different thicknesses under a force of at least 50 ± 5 N (11 ± 1 lbf) to the test head without distortion and minimal edge leakage underneath the test specimen.

6.1.2.1 A suitable means to minimize edge leakage is to use a 55 Type A durometer hardness polychloroprene (neoprene) clamping ring 20 mm (0.75 in.) wide and 3 mm (0.125 in.) thick around the test area above and underneath the test specimen.

² Annual Book of ASTM Standards, Vol 14.02.

³ : For additional information on obtaining apparatus, equipment, or supplies that may be suitable for use in this standard, please visit the ASTM Manufacturers' Equipment Directory at www.astm.org.

NOTE 3—Since 2—Since air leakage may affect test results, precautions must be taken, especially with very heavy or lofty fabrics, to prevent leakage. The use of a weighted ring and rubber gaskets on the clamp surfaces has been found to be helpful. ~~Test Method~~ **Methods F 778** describes a series of usable clamping adaptations to eliminate edge leakage. Gaskets should be used with caution because in some cases, and with repeated-use gaskets may deform resulting in a small change in test area. A weighted ring can be used with fabrics, such as knits or those that readily conform to the test head. The weighted ring is not recommended for lofty or stiff fabric.

6.1.3 Means for drawing a steady flow of air perpendicularly through the test area and for adjusting the airflow rate that preferably provides pressure differentials of between 100 and 2500 Pa (10 and 250 mm or 0.4 and 10 in. of water) between the two surfaces of the fabric being tested. At a minimum, the test apparatus must provide a pressure drop of 125 Pa (12.7 mm or 0.5 in. of water) across the specimen.

6.1.4 *Pressure Gage or Manometer*, connected to the test head underneath the test specimen to measure the pressure drop across the test specimen in pascals (millimetres or inches) of water with an accuracy of $\pm 2\%$.

6.1.5 *Flowmeter*, volumetric counter or measuring aperture to measure air velocity through the test area in $\text{cm}^3/\text{s}/\text{cm}^2$ ($\text{ft}^3/\text{min}/\text{ft}^2$) with an accuracy of $\pm 2\%$.

6.1.6 *Calibration Plate*, or other means, with a known air permeability at the prescribed test pressure differential to verify the apparatus.

6.1.7 Means of calculating and displaying the required results, such as scales, digital display, and computer-driven systems.

6.2 *Cutting Dies or Templates*, to cut specimens having dimensions at least equal to the area of the clamping surfaces of the test apparatus (optional).

7. Sampling and Test Specimens

7.1 *Lot Sample*—As a lot sample for acceptance testing, randomly select the number of rolls or pieces of fabric directed in an applicable material specification or other agreement between the purchaser and the supplier. Consider the rolls or pieces of fabric to be the primary sampling units. In the absence of such an agreement, take the number of fabric rolls or pieces specified in Table 1.

NOTE 4—An 3—An adequate specification or other agreement between the purchaser and the supplier requires taking into account the variability between rolls or pieces of fabric and between specimens from a swatch from a roll or piece of fabric to provide a sampling plan with a meaningful producer's risk, consumer's risk, acceptable quality level, and limiting quality level.

7.2 *Laboratory Sample*—For acceptance testing, take a swatch extending the width of the fabric and approximately 1 m (1 yd) along the lengthwise direction from each roll or piece in the lot sample. For rolls of fabric, take a sample that will exclude fabric from the outer wrap of the roll or the inner wrap around the core of the roll of fabric.

7.3 *Test Specimens*—From each laboratory sampling unit, take ten specimens unless otherwise agreed upon between purchaser and supplier. Use the cutting die or template described in 6.2, or if practical, make air permeability tests of a textile fabric without cutting.

7.3.1 *Cutting Test Specimens*—When cutting specimens, cut having dimensions at least equal to the area of the clamping mechanism. Label to maintain specimen identity.

7.3.1.1 Take specimens or position test areas representing a broad distribution across the length and width, preferably along the diagonal of the laboratory sample, and no nearer the edge than one tenth its width unless otherwise agreed upon between the purchaser and supplier. Ensure specimens are free of folds, creases, or wrinkles. Avoid getting oil, water, grease, and so forth, on the specimens when handling.

8. Preparation of Test Apparatus and Calibration

8.1 Set-up procedures for machines from different manufacturers may vary. Prepare and verify calibration of the air permeability tester as directed in the manufacturer's instructions.

8.2 When using microprocessor automatic data gathering systems, set the appropriate parameters as specified in the manufacturer's instructions.

8.3 For best results, level the test instrument.

8.4 Verify calibration for the range and required water pressure differential that is expected for the material to be tested.

9. Conditioning

9.1 Precondition the specimens by bringing them to approximate moisture equilibrium in the standard atmosphere for preconditioning textiles as specified in Practice D 1776.

TABLE 1 Number of Rolls or Pieces of Fabric in the Lot Sample

Number of Rolls or Pieces in Lot, Inclusive	Number of Rolls or Pieces in Lot Sample
1 to 3	all
4 to 24	4
25 to 50	5
over 50	10 % to a maximum of 10 rolls or pieces