

SLOVENSKI STANDARD oSIST prEN ISO 8044:2019

01-april-2019

Korozija kovin in zlitin - Osnovni pojmi in definicije (ISO/DIS 8044:2019)

Corrosion of metals and alloys - Basic terms and definitions (ISO/DIS 8044:2019)

Korrosion von Metallen und Legierungen - Grundbegriffe (ISO/DIS 8044:2019)

Corrosion des métaux et alliages - Termes principaux et définitions (ISO/DIS 8044:2019)

Ta slovenski standard je istoveten z: prEN ISO 8044

https://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sist-

en-iso-8044-2020

<u>ICS:</u>

01.040.77 Metalurgija (Slovarji) 77.060 Korozija kovin

Metallurgy (Vocabularies) Corrosion of metals

oSIST prEN ISO 8044:2019

en,fr,de

oSIST prEN ISO 8044:2019

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 8044:2020

https://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sisten-iso-8044-2020

DRAFT INTERNATIONAL STANDARD ISO/DIS 8044

ISO/TC 156

Voting begins on: **2019-01-30**

Secretariat: SAC

Voting terminates on: 2019-04-24

Corrosion of metals and alloys — Basic terms and definitions

Corrosion des métaux et alliages — Termes principaux et définitions

ICS: 77.060; 01.040.77

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 8044:2020

https://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sisten-iso-8044-2020

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION. This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number ISO/DIS 8044:2019(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 8044:2020

https://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sisten-iso-8044-2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: <u>Foreword - Supplementary information</u>

The committee responsible for this document is ISO/TC 156, *Corrosion of metals and alloys*.

This fourth edition cancels and replaces the third edition (ISO 8044:1999), which has been revised to include additional terms and definitions.

ISO/DIS 8044:2019(E) ISO/DIS 8044

Contents			
Fo	Foreword		
Int	Introduction		
1	Sc	cope	4
2 Gen		eneral terms	4
3 Types of corrosion		ypes of corrosion	7
4 (prrosion protection	14
5 Corrosion testing		prrosion testing	16
6 Electrochemical terms		ectrochemical terms	17
(5.1	The electrochemical cell	17
(5.2	Reaction rates	22
(5.3	Passivation	24
(5.4	Electrochemical protection DARD PREVIEW	26
(6.5	Electrochemical corrosion tests and s.iteh.ai	27
Fig	Figure 1 — Current/Potential curves for a corroding electrode		
Fig	Figure 2 — Anodic current density/potential curve showing active, passive and transpassive states		
Bił	Bibliography		

ISO/DIS 8044

Introduction

The definitions in this International Standard have been drawn up with the objective of achieving a proper balance between precision and simplicity. The main objective of this International Standard is to provide definitions that can be understood to have the same meaning by all concerned. Some corrosion terms in present use have developed through common usage and are not always logical. It has not, therefore, been possible to define certain terms in the form they are used in some countries. Because of the occasional conflicts between tradition and logic some definitions inevitably represent a compromise.

An example of this kind of conflict is the term "corrosion". This has been used to mean the process, results of the process and damage caused by the process. In this International Standard corrosion is understood to mean the process. Any detectable result of corrosion in any part of a corrosion system is termed "corrosion effect". The term "corrosion damage" covers any impairment of the function of the technical system of which the metal and the environment form a part. Consequently the term "corrosion protection" implies that the important thing is to avoid corrosion damage rather than to prevent corrosion, which in many cases is impossible and sometimes not necessary.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN ISO 8044:2020</u>

https://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sisten-iso-8044-2020 ISO/DIS 8044:2019(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 8044:2020

https://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sisten-iso-8044-2020

Corrosion of metals and alloys — Basic terms and definitions

1 Scope

This International Standard defines terms relating to corrosion that are widely used in modern science and technology. In addition, some definitions are supplemented with short explanations.

NOTE 1 Throughout the document IUPAC rules for electrode potential signs are applied. The term "metal" is also used to include alloys and other metallic materials.

NOTE 2 Terms and definitions related to inorganic surface treatment of metals are given in ISO 2080.

NOTE 3 See also the ISO online browsing platform (OBP): www.iso.org/obp/ui/

2 General terms

2.1

corrosion

physicochemical interaction between a metalic material and its environment that results in changes in the properties of the metal, and which may lead to significant impairment of the function of the metal, the environment, or the technical system, of which these form a part

Note 1 to entry: This interaction is often of an electrochemical nature.

2¹/₂tps://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sist-

corrosive agent

en-iso-8044-2020

substance which will initiate or promote corrosion when in contact with a given metal"

2.3

corrosive environment

environment that contains one or more *corrosive agents* (2.2)

2.4

corrosion system

system consisting of one or more metals and those parts of the environment that influence *corrosion* (2.1)

Note 1 to entry: Parts of the environment may be, for example, coatings, surface layers or additional *electrodes* (6.1.2).

2.5

corrosion effect

change in any part of the *corrosion system* (2.4) caused by *corrosion* (2.1)

2.6

corrosion damage

iv

ISO/DIS 8044:2019(E) ISO/DIS 8044

corrosion effect (2.5) that causes impairment of the function of the metal, the environment or the technical system, of which these form a part

2.7

corrosion failure

corrosion damage (2.6) characterized by the total loss of function of the technical system

2.8

corrosion product

substance formed as a result of *corrosion* (2.1)

2.9

scale

solid layer of corrosion products (2.8) formed on a metal at high temperature

Note 1 to entry: The term "scale" is also used in some countries for deposits from supersaturated water.

2.10

rust

visible *corrosion products* (2.8) consisting mainly of hydrated iron oxides

2.11

corrosion depth

distance between a point on the surface of a metal affected by *corrosion* (2.1) and the original surface of the metal

<u>IST EN ISO 8044:2020</u>

2:12 s://standards.iteh.ai/catalog/standards/sist/e6e3aa4f-1a96-435a-892e-f6c6122ac59c/sist-

corrosion rate

corrosion effect (2.5) on a metal per time

Note 1 to entry: The unit used to express the corrosion rate depends on the technical system and on the type of corrosion effect. Thus corrosion rate may be expressed as an increase in *corrosion depth* (2.11) per time, or the mass of metal turned into *corrosion products* (2.8) per area of surface and per time, etc. The corrosion effect may vary with time and may not be the same at all points of the corroding surface. Therefore, reports of corrosion rates should be accompanied by information on the type, time dependency and location of the corrosion effect.

2.13

corrosion resistance

ability of a metal to maintain *serviceability* (2.16) in a given *corrosion system* (2.4)

2.14

corrosivity

ability of an environment to cause *corrosion* (2.1) of a metal in a given *corrosion system* (2.4)

2.15

corrosion likelihood

qualitative and/or quantitative expression of the expected *corrosion effects* (2.5) in a defined *corrosion system* (2.4)

2015© – All rights reserved

ISO/DIS 8044

2.16

serviceability (with respect to corrosion)

ability of a *corrosion system* (2.4) to perform its specified functions without impairment due to *corrosion* (2.1)

2.17

durability (with respect to corrosion)

ability of a *corrosion system* (2.4) to maintain *serviceability* (2.16) over a specified time when the specified requirements for use and maintenance have been fulfilled

2.18

service life (with respect to corrosion) time during which a *corrosion system* (2.4) meets the requirements for *serviceability* (2.16)

2.19

critical humidity

value of the relative humidity of an atmosphere above which there is a sharp increase in the *corrosion rate* (2.12) of a given metal

2.20

corrosion attack Teh STANDARD PREVIEW

corrosion effect (2.5) that is detrimental but has not progressed to the point of impairment of the function of the metal, the environment, or the technical system of which they form a part

2.21

pickling

removal of oxides or other compounds from a metal surface by chemical or electrochemical action

2.22

pitting resistance equivalent number

PREN

indication of the resistance of stainless steels and nickel-based alloys to pitting in the presence of chloride-containing water

Note 1 to entry: An example formula for PREN is given by

PREN = % Cr + 3,3 [(% Mo) + 0,5 (% W)] + 16 (% N).

Note 2 to entry: The higher the PREN, the higher is the resistance to pitting corrosion.

2.23

trap

micro structural site at which the residence time for a hydrogen atom is long compared to the residence time in an interstitial lattice site

2.24 time of wetness

vi

ISO/DIS 8044:2019(E) ISO/DIS 8044

period when a metallic surface is covered by adsorptive and/or liquid films of electrolyte to be capable of causing atmospheric corrosion

2.25

threshold stress (for stress corrosion cracking)

tensile stress above which stress corrosion cracks initiate and grow, for the specified test conditions

2.26

threshold stress intensity factor for stress corrosion cracking

Kiscc

stress intensity factor above which stress corrosion crack propagation is sustained

Note 1 to entry: The threshold stress intensity factor is a concept of linear elastic fracture mechanics (LEFM) and is applicable when the plastic zone size is large compared with the microstructure, the crack is sufficiently long, and a high constraint to plastic deformation prevails, i.e. under plane strain predominant conditions. For growing stress corrosion cracks, LEFM is not necessarily applicable in all detail but is adopted as a pragmatic tool that is commonly used.

Note 2 to entry: Stress corrosion cracks may initiate at a surface or a surface defect and grow in the "short crack" regime at stress intensity factor levels below the apparent threshold stress intensity factor. Therefore, LEFM is not applicable in the "short crack" regime.

³ Types of corrosion (standards.iteh.ai)

3.1

electrochemical corrosion

corrosion (2.1) involving at least one anodic reaction (6.1.9) and one cathodic reaction (6.1.6)

3.2

en-iso-8044-2020

chemical corrosion

corrosion (2.1) not involving electrochemical reaction

3.3

gaseous corrosion

corrosion (2.1) with dry gas as the only *corrosive environment* (2.3) and without any liquid phase on the surface of the metal

3.4

atmospheric corrosion

corrosion (2.1) with the earth's atmosphere at ambient temperature as the *corrosive environment* (2.3)

3.5

marine corrosion

corrosion (2.1) with sea water as the main agent of the *corrosive environment* (2.3)

Note 1 to entry: This definition includes both immersed and splash zone conditions.

3.6