



Designation: ~~B348-08~~ Designation: **B 348 – 08a**

## Standard Specification for Titanium and Titanium Alloy Bars and Billets<sup>1</sup>

This standard is issued under the fixed designation B 348; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification<sup>2</sup> covers annealed titanium and titanium alloy bars and billets as follows:

- 1.1.1 *Grade 1*—Unalloyed titanium,
- 1.1.2 *Grade 2*—Unalloyed titanium,
  - 1.1.2.1 *Grade 2H*—Unalloyed titanium (Grade 2 with 58 ksi minimum UTS),
- 1.1.3 *Grade 3*—Unalloyed titanium,
- 1.1.4 *Grade 4*—Unalloyed titanium,
- 1.1.5 *Grade 5*—Titanium alloy (6 % aluminum, 4 % vanadium),
- 1.1.6 *Grade 6*—Titanium alloy (5 % aluminum, 2.5 % tin),
- 1.1.7 *Grade 7*—Unalloyed titanium plus 0.12 to 0.25 % palladium,
  - 1.1.7.1 *Grade 7H*—Unalloyed titanium plus 0.12 to 0.25 % palladium (Grade 7 with 58 ksi minimum UTS),
- 1.1.8 *Grade 9*—Titanium alloy (3 % aluminum, 2.5 % vanadium),
- 1.1.9 *Grade 11*—Unalloyed titanium plus 0.12 to 0.25 % palladium,
- 1.1.10 *Grade 12*—Titanium alloy (0.3 % molybdenum, 0.8 % nickel),
- 1.1.11 *Grade 13*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.12 *Grade 14*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.13 *Grade 15*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),
- 1.1.14 *Grade 16*—Unalloyed titanium plus 0.04 to 0.08 % palladium,
  - 1.1.14.1 *Grade 16H*—Unalloyed titanium plus 0.04 to 0.08 % palladium (Grade 16 with 58 ksi minimum UTS),
- 1.1.15 *Grade 17*—Unalloyed titanium plus 0.04 to 0.08 % palladium,
- 1.1.16 *Grade 18*—Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.04 to 0.08 % palladium,
- 1.1.17 *Grade 19*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum),
- 1.1.18 *Grade 20*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum) plus 0.04 %–0.08 % palladium,
- 1.1.19 *Grade 21*—Titanium alloy (15 % molybdenum, 3 % aluminum, 2.7 % niobium, 0.25 % silicon),
- 1.1.20 *Grade 23*—Titanium alloy (6 % aluminum, 4 % vanadium with extra low interstitial elements, ELI),
- 1.1.21 *Grade 24*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.04 % to 0.08 % palladium,
- 1.1.22 *Grade 25*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.3 % to 0.8 % nickel and 0.04 % to 0.08 % palladium,
- 1.1.23 *Grade 26*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,
  - 1.1.23.1 *Grade 26H*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium (Grade 26 with 58 ksi minimum UTS),
- 1.1.24 *Grade 27*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,
- 1.1.25 *Grade 28*—Titanium alloy (3 % aluminum, 2.5 % vanadium plus 0.08–0.14 % ruthenium),
- 1.1.26 *Grade 29*—Titanium alloy (6 % aluminum, 4 % vanadium, extra low interstitial, ELI plus 0.08 to 0.14 % ruthenium),
- 1.1.27 *Grade 30*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),
- 1.1.28 *Grade 31*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),
- 1.1.29 *Grade 32*—Titanium alloy (5 % aluminum, 1 % tin, 1 % zirconium, 1 % vanadium, 0.8 % molybdenum),
- 1.1.30 *Grade 33*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),
- 1.1.31 *Grade 34*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),
- 1.1.32 *Grade 35*—Titanium alloy (4.5 % aluminum, 2 % molybdenum, 1.6 % vanadium, 0.5 % iron, 0.3 % silicon),

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.01 on Titanium.

Current edition approved ~~May 15~~ Aug. 1, 2008. Published ~~June~~ August 2008. Originally approved in 1959. Last previous edition approved in ~~2006~~ 2008 as ~~B348-06a~~ B 348 – 08.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SB-348 in Section II of that Code.

- 1.1.33 *Grade 36*—Titanium alloy (45 % niobium),  
 1.1.34 *Grade 37*—Titanium alloy (1.5 % aluminum), and  
 1.1.35 *Grade 38*—Titanium alloy (4 % aluminum, 2.5 % vanadium, 1.5 % iron).

NOTE 1—H grade material is identical to the corresponding numeric grade (that is, Grade 2H = Grade 2) except for the higher guaranteed minimum UTS, and may always be certified as meeting the requirements of its corresponding numeric grade. Grades 2H, 7H, 16H, and 26H are intended primarily for pressure vessel use.

The H grades were added in response to a user association request based on its study of over 5200 commercial Grade 2, 7, 16, and 26 test reports, where over 99 % met the 58 ksi minimum UTS.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

## 2. Referenced Documents

### 2.1 *ASTM Standards*:<sup>3</sup>

- E 8 Test Methods for Tension Testing of Metallic Materials  
 E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications  
 E 539 Test Method for X-Ray Fluorescence Spectrometric Analysis of 6Al-4V Titanium Alloy  
 E 1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique  
 E 1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method  
 E 1941 Test Method for Determination of Carbon in Refractory and Reactive Metals and Their Alloys  
 E 2371 Test Method for Analysis of Titanium and Titanium Alloys by Atomic Emission Plasma Spectrometry  
 E120 Test Methods for Chemical Analysis of Titanium and Titanium Alloys  
 E1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique  
 E1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method  
 2626 Guide for Spectrometric Analysis of Reactive and Refractory Metals

## 3. Terminology

### 3.1 *Definitions of Terms Specific to This Standard*:

3.1.1 *bar, n*—a hot rolled, forged, or cold worked semifinished solid section product whose cross sectional area is equal to or less than 16 in.<sup>2</sup> (10 323 mm<sup>2</sup>); rectangular bar must be less than or equal to 10 in. (254 mm) in width and greater than 0.1875 in. (4.8 mm) in thickness.

3.1.2 *billet, n*—a solid semifinished section hot rolled or forged from an ingot, with a cross sectional area greater than 16 in.<sup>2</sup> (10 323 mm<sup>2</sup>) whose width is less than five times its thickness.

## 4. Ordering Information

4.1 Orders for material under this specification shall include the following information as applicable:

- 4.1.1 Grade number (Section 1),  
 4.1.2 Product classification (Section 3),  
 4.1.3 Chemistry (Table 1),  
 4.1.4 Mechanical properties (Table 2),  
 4.1.5 Marking (Section 16),  
 4.1.6 Finish (Section 8),  
 4.1.7 Packaging (Section 16),  
 4.1.8 Required reports (Section 15), and  
 4.1.9 Disposition of rejected material (Section 14).

## 5. Chemical Composition

5.1 The grades of titanium and titanium alloy metal covered by this specification shall conform to the requirements as to chemical composition prescribed in Table 1.

5.1.1 The elements listed in Table 1 are intentional alloy additions or elements which are inherent to the manufacture of titanium sponge, ingot or mill product.

5.1.1.1 Elements other than those listed in Table 1 are deemed to be capable of occurring in the grades listed in Table 1 by and only by way of unregulated or unanalyzed scrap additions to the ingot melt. Therefore, product analysis for elements not listed in Table 1 shall not be required unless specified and shall be considered to be in excess of the intent of this specification.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Chemical Requirements<sup>A</sup>**

Element	Composition, %											
	Grade 1	Grade 2	Grade 2H	Grade 3	Grade 4	Grade 5	Grade 6	Grade 7	Grade 7H	Grade 9	Grade 11	Grade 12
Nitrogen, max	0.03	0.03	0.03	0.05	0.05	0.05	0.03	0.03	0.03	0.03	0.03	0.03
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08
Hydrogen, <sup>B,C</sup> max	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015
Iron, max	0.20	0.30	0.30	0.30	0.50	0.40	0.50	0.30	0.30	0.25	0.20	0.30
Oxygen, max	0.18	0.25	0.25	0.35	0.40	0.20	0.20	0.25	0.25	0.15	0.18	0.25
Aluminum	...	...	...	...	...	5.5–6.75	4.0–6.0	...	...	2.5–3.5	...	...
Vanadium	...	...	...	...	...	3.5–4.5	...	...	...	2.0–3.0	...	...
Tin	...	...	...	...	...	...	2.0–3.0	...	...	...	...	...
Ruthenium	...	...	...	...	...	...	...	...	...	...	...	...
Palladium	...	...	...	...	...	...	...	0.12–0.25	0.12–0.25	...	0.12–0.25	...
Cobalt	...	...	...	...	...	...	...	...	...	...	...	...
Molybdenum	...	...	...	...	...	...	...	...	...	...	...	0.2–0.4
Chromium	...	...	...	...	...	...	...	...	...	...	...	...
Nickel	...	...	...	...	...	...	...	...	...	...	...	0.6–0.9
Niobium	...	...	...	...	...	...	...	...	...	...	...	...
Zirconium	...	...	...	...	...	...	...	...	...	...	...	...
Silicon	...	...	...	...	...	...	...	...	...	...	...	...
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Titanium <sup>G</sup>	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance

  

Element	Composition, %										
	Grade 13	Grade 14	Grade 15	Grade 16	Grade 16H	Grade 17	Grade 18	Grade 19	Grade 20	Grade 21	
Nitrogen, max	0.03	0.03	0.05	0.03	0.03	0.03	0.03	0.03	0.03	0.03	
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.05	0.05	0.05	
Hydrogen, <sup>B,C</sup> max	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.02	0.02	0.015	
Iron, max	0.20	0.30	0.30	0.30	0.30	0.20	0.25	0.30	0.30	0.40	
Oxygen, max	0.10	0.15	0.25	0.25	0.25	0.18	0.15	0.12	0.12	0.17	
Aluminum	...	...	...	...	...	...	2.5–3.5	3.0–4.0	3.0–4.0	2.5–3.5	
Vanadium	...	...	...	...	...	...	2.0–3.0	7.5–8.5	7.5–8.5	...	
Tin	...	...	...	...	...	...	...	...	...	...	
Ruthenium	0.04–0.06	0.04–0.06	0.04–0.06	...	...	...	...	...	...	...	
Palladium	...	...	...	0.04–0.08	0.04–0.08	0.04–0.08	0.04–0.08	...	0.04–0.08	...	
Cobalt	...	...	...	...	...	...	...	...	...	...	
Molybdenum	...	...	...	...	...	...	...	3.5–4.5	3.5–4.5	14.0–16.0	
Chromium	...	...	...	...	...	...	...	5.5–6.5	5.5–6.5	...	
Nickel	0.4–0.6	0.4–0.6	0.4–0.6	...	...	...	...	...	...	...	
Niobium	...	...	...	...	...	...	...	...	...	2.2–3.2	
Zirconium	...	...	...	...	...	...	...	3.5–4.5	3.5–4.5	...	
Silicon	...	...	...	...	...	...	...	...	...	0.15–0.25	
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.15	0.15	0.1	
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	
Titanium <sup>G</sup>	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance	

  

Element	Composition, %									
	Grade 23	Grade 24	Grade 25	Grade 26	Grade 26H	Grade 27	Grade 28	Grade 29	Grade 30	
Nitrogen, max	0.03	0.05	0.05	0.03	0.03	0.03	0.03	0.03	0.03	
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	
Hydrogen, <sup>B,C</sup> max	0.0125	0.015	0.0125	0.015	0.015	0.015	0.015	0.015	0.015	
Iron, max	0.25	0.40	0.40	0.30	0.30	0.20	0.25	0.25	0.30	
Oxygen, max	0.13	0.20	0.20	0.25	0.25	0.18	0.15	0.13	0.25	
Aluminum	5.5–6.5	5.5–6.75	5.5–6.75	...	...	...	2.5–3.5	5.5–6.5	...	
Vanadium	3.5–4.5	3.5–4.5	3.5–4.5	...	...	...	2.0–3.0	3.5–4.5	...	
Tin	...	...	...	...	...	...	...	...	...	
Ruthenium	...	...	...	0.08–0.14	0.08–0.14	0.08–0.14	0.08–0.14	0.08–0.14	0.08–0.14	
Palladium	...	0.04–0.08	0.04–0.08	...	...	...	...	...	...	0.04–0.08
Cobalt	...	...	...	...	...	...	...	...	...	0.20–0.80
Molybdenum	...	...	...	...	...	...	...	...	...	
Chromium	...	...	...	...	...	...	...	...	...	
Nickel	...	...	0.3–0.8	...	...	...	...	...	...	
Niobium	...	...	...	...	...	...	...	...	...	
Zirconium	...	...	...	...	...	...	...	...	...	
Silicon	...	...	...	...	...	...	...	...	...	
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	

**TABLE 1** *Continued*

Element	Composition, %								
	Grade 23	Grade 24	Grade 25	Grade 26	Grade 26H	Grade 27	Grade 28	Grade 29	Grade 30
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Titanium <sup>G</sup>	balance	balance	balance	balance	balance	balance	balance	balance	balance

  

Element	Composition, %								
	Grade 31	Grade 32	Grade 33	Grade 34	Grade 35	Grade 36	Grade 37	Grade 38	
Nitrogen, max	0.05	0.03	0.03	0.05	0.05	0.03	0.03	0.03	
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.04	0.08	0.08	
Hydrogen, <sup>B,C</sup> max	0.015	0.015	0.015	0.015	0.015	0.0035	0.015	0.015	
Iron, max or range	0.30	0.25	0.30	0.30	0.20–0.80	0.03	0.30	1.2–1.8	
Oxygen, max or range	0.35	0.11	0.25	0.35	0.25	0.16	0.25	0.20–0.30	
Aluminum	...	4.5–5.5	...	...	4.0–5.0	...	1.0–2.0	3.5–4.5	
Vanadium	...	0.6–1.4	...	...	1.1–2.1	...	...	2.0–3.0	
Tin	...	0.6–1.4	...	...	...	...	...	...	
Ruthenium	...	...	0.02–0.04	0.02–0.04	...	...	...	...	
Palladium	0.04–0.08	...	0.01–0.02	0.01–0.02	...	...	...	...	
Cobalt	0.20–0.80	...	...	...	...	...	...	...	
Molybdenum	...	0.6–1.2	...	...	1.5–2.5	...	...	...	
Chromium	...	...	0.1–0.2	0.1–0.2	...	...	...	...	
Nickel	...	...	0.35–0.55	0.35–0.55	...	...	...	...	
Niobium	...	...	...	...	...	42.0–47.0	...	...	
Zirconium	...	0.6–1.4	...	...	...	...	...	...	
Silicon	...	0.06–0.14	...	...	0.20–0.40	...	...	...	
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	
Titanium <sup>G</sup>	balance	balance	Remainder	Remainder	Remainder	Remainder	Remainder	balance	

<sup>A</sup> Analysis shall be completed for all elements listed in this table for each grade. The analysis results for the elements not quantified in the table need not be reported unless the concentration level is greater than 0.1 % each or 0.4 % total.

<sup>B</sup> Lower hydrogen may be obtained by negotiation with the manufacturer.

<sup>C</sup> Final product analysis.

<sup>D</sup> Need not be reported.

<sup>E</sup> A residual is an element present in a metal or an alloy in small quantities and is inherent to the manufacturing process but not added intentionally. In titanium these elements include aluminum, vanadium, tin, chromium, molybdenum, niobium, zirconium, hafnium, bismuth, ruthenium, palladium, yttrium, copper, silicon, cobalt, tantalum, nickel, boron, manganese, and tungsten.

<sup>F</sup> The purchaser may, in his written purchase order, request analysis for specific residual elements not listed in this specification.

<sup>G</sup> The percentage of titanium is determined by difference.

5.1.2 Elements intentionally added to the melt must be identified, analyzed and reported in the chemical analysis.

5.2 When agreed upon by the producer and purchaser and requested by the purchaser in his written purchase order, chemical analysis shall be completed for specific residual elements not listed in this specification.

5.3 *Product Analysis*—Product analysis tolerances do not broaden the specified heat analysis requirements, but cover variations between laboratories in the measurement of chemical content. The manufacturer shall not ship material which is outside the limits specified in Table 1 for the applicable grade. Product analysis limits shall be as specified in Table 3.

## 6. Mechanical Properties

6.1 Material supplied under this specification shall conform to the mechanical property requirements given in Table 2, as applicable.

6.2 Tension testing specimens are to be machined and tested in accordance with Test Methods E 8. Tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in./min through the specified yield strength, and then increasing the rate so as to produce failure in approximately one additional minute.

## 7. Dimensions, Weight, and Permissible Variations

7.1 *Size*—Tolerances on titanium and titanium alloy material covered by this specification shall be as specified in Tables 4–11, as applicable.

7.2 *Weight*—Quantity extras are applicable to individual items of a grade, thickness, width, and length ordered at one time for shipment at one time to one destination. Different lengths of the same size and grade may be combined for quantity extra. The shipping weight of any item of an ordered size in any finish may exceed the theoretical weight by as much as 10 %.

## 8. Workmanship, Finish, and Appearance

8.1 Titanium and titanium alloy bar and billet shall be free of injurious external and internal imperfections of a nature that will interfere with the purpose for which it is intended. Annealed material may be furnished as descaled, sandblasted, ground, or rough turned. The manufacturer shall be permitted to remove minor surface imperfections by spot grinding if such grinding does not reduce the thickness of the material below the minimum permitted by the tolerance for the thickness ordered.