
Kovinski profili - Definicije, zahteve in preskusne metode - 1. del: Notranji omet

Metal lath and beads - Definitions, requirements and test methods - Part 1: Internal plastering

Putzträger und Putzprofile aus Metall - Begriffe, Anforderungen und Prüfverfahren - Teil 1: Innenputze

Lattis et cornières métalliques - Définitions, exigences et méthodes d'essai - Partie 1 : Enduits intérieurs

iTeh STANDARD PREVIEW

(standards.itteh.ai)

<https://standards.itteh.ai/catalog/standards/sist/a5e570e2-ec06-432e-b98d-c06c5c36da40/osist-pr-en-13658-1-2017>

Ta slovenski standard je istoveten z:

prEN 13658-1

ICS:

77.140.65	Jeklene žice, jeklene vrvi in verige	Steel wire, wire ropes and link chains
91.100.10	Cement. Mavec. Apno. Malta	Cement. Gypsum. Lime. Mortar

oSIST prEN 13658-1:2017

en,fr,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 13658-1:2017](https://standards.iteh.ai/catalog/standards/sist/a5e570e2-ec06-432e-b98d-c08c3c56da40/osist-pren-13658-1-2017)

<https://standards.iteh.ai/catalog/standards/sist/a5e570e2-ec06-432e-b98d-c08c3c56da40/osist-pren-13658-1-2017>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 13658-1

August 2017

ICS 77.140.65; 91.100.10

Will supersede EN 13658-1:2005

English Version

Metal lath and beads - Definitions, requirements and test methods - Part 1: Internal plastering

Lattis et cornières métalliques - Définitions, exigences et méthodes d'essai - Partie 1 : Enduits intérieurs

Putzträger und Putzprofile aus Metall - Begriffe, Anforderungen und Prüfverfahren - Teil 1: Innenputze

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 241.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

European foreword.....	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Requirements	8
4.1 Fire behaviour	8
4.1.1 Reaction to fire	8
4.1.2 Fire resistance	9
4.2 Requirements for lath	9
4.2.1 Material	9
4.2.2 Description	9
4.2.3 Dimensions	9
4.3 Requirements for beads	10
4.3.1 Material	10
4.3.2 Description	10
4.3.3 Dimensions	11
4.4 Dangerous substances	12
5 Testing and sampling	12
5.1 Dimensional measurements of lath	12
5.1.1 General	12
5.1.2 Thickness or diameter	12
5.1.3 Length and width	12
5.1.4 Coating thickness of lath and beads	13
5.2 Dimensional measurements of beads	14
5.2.1 General	14
5.2.2 Thickness or diameter	14
5.2.3 Length	14
5.2.4 Straightness	14
5.2.5 Profile dimensions	14
5.2.6 Coating thickness	15
6 Assessment and verification of constancy of performance — AVCP	15
6.1 General	15
6.2 Type testing	15
6.2.1 General	15
6.2.2 Test samples, testing and compliance criteria	16
6.2.3 Test reports	16
6.2.4 Shared other party results	16
6.2.5 Cascading determination of the product type results	17
6.3 Factory production control (FPC)	18
6.3.1 General	18
6.3.2 Requirements	19
6.3.3 Product specific requirements	21
6.3.4 Initial inspection of factory and of FPC	21
6.3.5 Continuous surveillance of FPC (only for products covered by AVCP system 1+, 1 and 2+)	22

6.3.6	Procedure for modifications.....	22
6.3.7	One-off products, pre-production products (e.g. prototypes) and products produced in very low quantity	22
7	Designation	23
7.1	Lath	23
7.2	Beads	24
8	Marking, labelling and packaging.....	24
Annex ZA	(informative) Relationship of this European Standard with Regulation (EU) No. 305/2011	37
ZA.1	Scope and relevant characteristics	37
ZA.2	System of Assessment and Verification of Constancy of Performance (AVCP)	37
ZA.3	Assignment of AVCP tasks	37
Bibliography	40

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN 13658-1:2017](https://standards.iteh.ai/catalog/standards/sist/a5e570e2-ec06-432e-b98d-c08c3c56da40/osist-pren-13658-1-2017)

<https://standards.iteh.ai/catalog/standards/sist/a5e570e2-ec06-432e-b98d-c08c3c56da40/osist-pren-13658-1-2017>

European foreword

This document (prEN 13658-1:2017) has been prepared by Technical Committee CEN/TC 241 “Gypsum and gypsum based products”, the secretariat of which is held by AFNOR.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 13658-1:2005.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of Regulation (EU) No. 305/2011.

For relationship with Regulation (EU) No. 305/2011, see informative Annex ZA, which is an integral part of this document.

The main technical changes that have been made in this new edition of EN 13658-1 are the following:

a) Normative references updated;

b) Terms and definitions updated;

c) Tables 1 and 2 updated;

d) Figures updated;

e) Clause 6 and Annex ZA updated in line with the CPR.

<https://standards.iteh.ai/catalog/standards/sist/a5e570e2-ec06-432e-b98d-c08e3c56da40/osist-pr-en-13658-1-2017>

This European Standard on *Metal lath and beads — Definitions, requirements and test methods* consists of two parts:

- *Part 1: Internal plastering;*
- *Part 2: External rendering.*

1 Scope

This European Standard specifies the requirements and test methods of metal lath and beads for internal plastering.

This European Standard covers metal lath intended to be used for fixing to structures or solid backgrounds to provide a key to hold the plaster in position. Metal lath is used vertically to support linings for walls, partitions and columns and horizontally to support linings for ceilings and beams. Used in this way it enables fire protecting plastering systems to be provided.

This European Standard covers metal beads intended to be used to improve the protection of corners and also provide features to the internal finish of the construction as well as metal beads intended to be used as depth gauge beads and movement or expansion beads. They also contribute to fire protection.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 485-2:2016, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 2: Mechanical properties*

EN 485-4:1993, *Aluminium and aluminium alloys — Sheet, strip and plate — Part 4: Tolerances on shape and dimensions for cold-rolled products*

EN 573-3:2013, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 3: Chemical composition and form of products*

EN 988:1996, *Zinc and zinc alloys — Specifications for rolled flat products for building*

EN 1364-1:2015, *Fire resistance tests for non-loadbearing elements — Part 1: Walls*

EN 1364-2:1999, *Fire resistance tests for non-loadbearing elements — Part 2: Ceilings*

EN 1365-1:2012, *Fire resistance tests for loadbearing elements — Part 1: Walls*

EN 1365-3:1999, *Fire resistance tests for loadbearing elements — Part 3: Beams*

EN 1365-4:1999, *Fire resistance tests for loadbearing elements — Part 4: Columns*

EN 10088 (all parts), *Stainless steels*

EN 10143:2006, *Continuously hot-dip coated steel sheet and strip — Tolerances on dimensions and shape*

EN 10169-1:2003, *Continuously organic coated (coil coated) steel flat products — Part 1: General information (definitions, materials, tolerances, test methods)*

EN 10218-2:2012, *Steel wire and wire products — General — Part 2: Wire dimensions and tolerances*

EN 10244-1:2009, *Steel wire and wire products — Non-ferrous metallic coatings on steel wire — Part 1: General principles*

EN 10258:1997, *Cold-rolled stainless steel and narrow strip and cut lengths — Tolerances on dimensions and shape*

prEN 13658-1:2017 (E)

EN 10264-4:2012, *Steel wire and wire products — Steel wire for ropes — Part 4: Stainless steel wire*

EN 10346:2015, *Continuously hot-dip coated steel flat products for cold forming — Technical delivery conditions*

EN 13501-1:2007+A1:2009, *Fire classification of construction products and building elements — Part 1: Classification using data from reaction to fire tests*

EN 13501-2:2016, *Fire classification of construction products and building elements — Part 2: Classification using data from fire resistance tests, excluding ventilation services*

EN 13914-2:2016, *Design, preparation and application of external rendering and internal plastering — Part 2: Internal plastering*

EN ISO 1460:1994, *Metallic coatings — Hot dip galvanized coatings on ferrous materials — Gravimetric determination of the mass per unit area (ISO 1460:1992)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 Metal lath:**3.1.1****expanded flat metal lath**

corrosion resistant diamond shaped mesh to provide a key for plastering

Note 1 to entry: See Figure 3 a).

3.1.2**expanded corrugated metal lath**

corrosion resistant diamond mesh to provide extra stiffness

Note 1 to entry: See Figure 3 b).

3.1.3**expanded ribbed lath**

corrosion resistant mesh formed by expanding with integral solid ribs of at least 7 mm height to provide extra stiffness

Note 1 to entry: See Figure 4.

3.1.4**expanded mini ribbed lath**

corrosion resistant mesh formed by expanding with integral solid ribs between 4 mm and 7 mm height

Note 1 to entry: See Figure 4.

3.1.5**stainless steel ribbed lath**

stainless steel mesh with integral solid ribs of at least 7 mm height

3.1.6**paperbacked ribbed lath**

corrosion protected paperbacked mesh with integral ribs of at least 7 mm height

3.1.7**standard paperbacked wire lath**

corrosion resistant wire spot welded mesh to form a square mesh to provide a key for plastering with a sheet of cardboard positioned between the horizontal and the vertical wires or between the mesh and the reinforcing wires

Note 1 to entry: See Figures 5 a), 5 b) and 6.

3.1.8**reinforced paperbacked wire lath**

same as 3.1.7, but the reinforcing wires are thicker in order to increase stiffness

3.1.9**high ribbed paperbacked wire lath**

same as 3.1.8, but with thicker wires to provide still greater stiffness

3.1.10**damp proof regular paperbacked wire lath**

same as 3.1.8, but with a bituminous paper bonded to the back of the cardboard sheet to provide extra damp control

3.1.11**standard wire mesh**

corrosion resistant spot welded wire mesh, flat or profiled, to form a square mesh to provide a key for plastering

Note 1 to entry: See Figure 7.

3.1.12**normal claylath**

woven mesh of steel wire with clay pressed on the intersection of the wire and then fired

Note 1 to entry: See Figure 8.

3.1.13**stainless steel claylath**

woven mesh of stainless steel wire with clay pressed on the intersection of the wire and then fired

Note 1 to entry: See Figure 8.

3.2 Metal beads and their uses:**3.2.1****angle bead**

corrosion resistant profiled section used to protect the plastered external angles

Note 1 to entry: This section can also be fabricated from wire.

3.2.2**stop bead**

corrosion resistant profiled section used to provide a straight and protected edge to receive the internal plaster

Note 1 to entry: This section can also be fabricated from wire.

prEN 13658-1:2017 (E)**3.2.3****featured bead**

corrosion resistant profiled section used to enhance the internal plaster finish at the edge

Note 1 to entry: This section can also be fabricated from wire.

3.2.4**movement bead**

corrosion resistant profiled section connected with a flexible plastic extrusion capable of a movement within the range of $\pm 1,5$ mm of the internal plaster surface

Note 1 to entry: This section can also be fabricated from wire.

3.2.5**depth gauge bead**

profiled section which can be set on plane surfaces to control the depth of plaster applied

Note 1 to entry: See Table 2.

3.3 Metal beads, functional features:**3.3.1****profiled face/edge**

surface or edge of bead used to provide the feature or function

3.3.2**wing**

area of metal strip joining the bead face or edge, usually expanded or perforated or welded wire used for fixing and also key for plaster

3.3.3**open area**

percentage of wing area perforated or expanded or percentage of opening between welded wires

Note 1 to entry: See Table 2 for the geometry of some profiles.

4 Requirements**4.1 Fire behaviour****4.1.1 Reaction to fire**

When the intended use of metal lath and beads is for situations in building construction works where there is a risk of exposure to fire, metal lath and beads shall be classified A1 without the need of testing^{0F1)} unless they have organic coatings or flexible middle parts.

Metal lath and beads for internal plastering having an exposed surface containing organic material may be classified E without the need of testing²⁾.

1) According to Commission Decision 96/603/EC as amended.

2) According to Commission Delegated Regulation (EU) No 1293/2014.

For the purpose of classification in classes other than classes E and F, they shall be tested and classified in accordance with EN 13501-1.

4.1.2 Fire resistance

Metal lath and beads can be used in walls, partitions and ceilings and encasement systems providing fire ratings.

When required, the fire rating of the system shall be tested to EN 1364-1, EN 1364-2, EN 1365-1, EN 1365-3 and EN 1365-4 as appropriate and classified to EN 13501-2.

4.2 Requirements for lath

4.2.1 Material

Lath shall be manufactured from the materials and finishes shown in Table 3. The corrosion resistant selected material and finish shall provide a satisfactory level of protection against corrosion under conditions of intended use, i.e. regional requirements.

4.2.2 Description

- a) Expanded lath, ribbed lath and wire lath or mesh shall be formed to provide the functional requirements of stiffness to span between supports or fixings and have aperture sizes to provide an efficient keying matrix for the plaster. Typical products meeting these requirements are given in Tables 3 and 4 and in Figures 3, 4, 5 and 6;
- b) normal and stainless steel clay lath are produced in open, half open and closed versions (see Figure 8). At least 60 % of the surface area shall be covered with clay.

4.2.3 Dimensions

4.2.3.1 Nominal thickness and diameter

- a) For expanded lath, ribbed lath and wire lath, the thickness/diameter shall be as given in Tables 3 and 4. The tolerances shall be those specified in EN 10143, EN 10218-2 and EN 10264-4;
- b) for normal and stainless steel clay lath, the nominal sizes of the wire for production (before firing) shall be 0,7 mm and 0,9 mm. Tolerances shall be those specified in EN 10258 for stainless steel wire.

4.2.3.2 Length and width

- a) For expanded lath, ribbed lath and wire lath, the nominal length and width of lath shall be declared by the manufacturer. Tolerances shall be $\pm 1\%$ for length and ± 15 mm for width;
- b) for normal and stainless steel clay lath, the nominal length and width of lath shall be declared by the manufacturer (see Figure 8); tolerance shall be $\pm 2\%$.

4.2.3.3 Mesh type and size dimensions

- a) For expanded flat lath, when measured as illustrated in Figure 3, the aperture shall be at least 13 mm in the LWM (long way mesh) direction and at least 5 mm in the SWM (short way mesh) direction;

NOTE The dimensions are for "clear aperture" not centre to centre of strands.

prEN 13658-1:2017 (E)

- b) expanded corrugated lath is produced from flat lath. The minimum height of the corrugated ribs shall be 5 mm;
- c) expanded ribbed and expanded mini ribbed lath are formed with a rib on each longitudinal edge and with ribs spaced at maximum intervals of 110 mm. For expanded ribbed lath, the minimum height of the ribs shall be 7 mm and for expanded mini ribbed lath between 4 mm and 7 mm. The aperture sizes in the LWM and the SWM directions as specified by the manufacturer shall correspond to Figure 4.

4.2.3.4 Standard paperbacked wire lath

The wires shall have a minimum nominal equivalent diameter of 1,4 mm (see Figure 5 and Table 5).

4.2.3.5 Reinforced paperbacked wire lath

Same as 4.2.3.4, but the reinforcing wires shall have a minimum nominal equivalent wire diameter of 2,8 mm spaced at distances not greater than 150 mm. The moment of inertia in the direction where increased stiffness is required shall be at least 10 mm⁴.

4.2.3.6 High ribbed paperbacked wire lath

Same as 4.2.3.4 but the reinforcing wires shall have a minimum nominal equivalent wire diameter of 3,9 mm spaced at distances not greater than 150 mm. The moment of inertia in the direction where increased stiffness is required shall be at least 30 mm⁴.

4.2.3.7 Normal and stainless steel claylath

For requirements, see Table 6 and Figure 8. The figure shows the open type. In half open and closed claylath the apertures between the crosses may be closed with fired clay requirements for beads.

4.2.3.8 Welded wire mesh

For requirements see Figure 7.

4.3 Requirements for beads**4.3.1 Material**

Beads shall be manufactured from hot-dip coated steel sheet or strip conforming to EN 10346, austenitic stainless steel sheet or strip to EN 10088-1 and EN 10088-2, aluminium sheet or strip to EN 573-3, organic coated galvanized steel sheet or strip to EN 10169-1 or subsequently organic coated, galvanized steel sheet or strip to EN 10346. Alternatively, beads can be manufactured from galvanized wire to EN 10244-1 and EN 10244-2 (class A), austenitic stainless wire to EN 10088-1, EN 10088-3 and EN 10088-5 or zinc alloys to EN 988.

The material or coatings shall be that defined in this standard (see Table 3) or to an equivalent level to prevent corrosion at normal conditions of use (i.e. regional requirements, marine environment, reaction between gypsum and some stainless steels).

4.3.2 Description

Beads shall be formed to provide functional or featured profiles. They shall be free from kinks or deformations which would detract from their function. The beads may incorporate a various profiles with one or more wings depending upon their function. The wings shall be expanded or perforated or welded wire to facilitate fixing using mechanical or plaster fixing methods.

4.3.3 Dimensions

4.3.3.1 Thickness or diameter

- a) Metal strip: Beads formed from metal strip shall have a minimum thickness of 0,4 mm for hot-dip coated steel, or subsequently organic coated, hot-dip coated steel (sheet thickness to be measured before coating). The minimum thickness for aluminium strip shall be 0,4 mm and for stainless steel strip 0,3 mm.
- b) Fabricated wire beads: Beads fabricated from galvanized or stainless steel wire shall have a minimum nominal equivalent diameter of 1,4 mm.
- c) Precoated hot-dip coated steel strip, organic coated: the thickness of the coating shall be specified by the manufacturer.
- d) Subsequently organic coated, galvanized steel strip: the thickness of the additional organic coating shall not be less than 20 µm and shall be specified by the manufacturer.

4.3.3.2 Length

The nominal length of the bead shall be declared by the manufacturer. The tolerances shall be for:

- perforated or expanded metal strip: ± 10 mm;
- galvanized or stainless steel wire: ± 20 mm.

4.3.3.3 Straightness

The beads shall be straight to an accuracy which allows for the following maximum deviations from the flat surface when measured as described in 5.2.4 and shown in Figure 1:

$$\text{— for angle beads} \quad \frac{L}{400} \quad (1)$$

$$\text{— for stop and featured beads} \quad \frac{L}{600} \quad (2)$$

where

L is the length.

4.3.3.4 Profile dimensions

The profile dimensions and angles shall be as shown in Table 2 and measured as described in 5.2.5.

4.3.3.5 Wing width

The minimum width of wings is given in Table 2.

4.3.3.6 Wing open area

The open area of each wing shall be > 10 % for depth gauge beads, > 20 % for perforated strip, > 40 % for expanded strip, > 80 % for welded mesh.

4.3.3.7 Movement bead

The manufacturer shall declare that the bead provides movement of ± 1,5 mm without damage.