



Designation: ~~F619-02~~ Designation: **F 619 – 03 (Reapproved 2008)**

Standard Practice for Extraction of Medical Plastics¹

This standard is issued under the fixed designation F 619; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers methods of extraction of medical plastics and may be applicable to other materials. This practice identifies a method for obtaining “extract liquid” for use in determining the biological response in preclinical testing. Further testing of the “extract liquid” is specified in other ASTM standards. The extract may undergo chemical analysis as part of the preclinical evaluation of the biological response, and the material after extraction may also be examined.

1.2 This practice may be used for, but is not limited to the following areas: partial evaluation of raw materials, auditing materials within the manufacturing process, and testing final products. This practice may also be used as a referee method for the measurement of extractables in plastics used in medical devices.

~~1.3 The values stated in SI units are to be regarded as the standard.~~

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D 543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents

D 570 Test Method for Water Absorption of Plastics

D 1193 Specification for Reagent Water

D 1239 Test Method for Resistance of Plastic Films to Extraction by Chemicals

~~D 1898 Practice for Sampling of Plastics²~~ Practice for Sampling of Plastics³

F 748 Practice for Selecting Generic Biological Test Methods for Materials and Devices

2.2 *Other Documents:*

USP NF 24 or current edition⁴

3. Terminology Definitions

3.1 *extraction vehicle*—a liquid specified for use in testing the plastic. Specific extraction vehicles are to be designated by the ASTM standard that references this practice (see Section 7 for a list of standard extraction vehicles).

3.2 *extract liquid*— that liquid which, after extraction of the specimen, is used in tests.

3.3 *specimen portion*— the unit or units of plastic placed into the extraction vehicle.

3.4 *blank*—the extraction vehicle not containing the specimen under test which is used for comparison with the extract liquid.

4. Summary of Practice

4.1 Standard-size specimens of the plastic, which may closely simulate the intended device depending upon the use, are immersed in defined volumes of selected liquids (extraction vehicles) for the time and temperature specified.

¹ This practice is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.16 on Biocompatibility Test Methods.

Current edition approved Apr. 10, 2002; Aug. 1, 2008. Published June 2002; August 2008. Originally published as F619-79; approved in 1979. Last previous edition F619-79 (1997)^{ε1} approved in 2003 as F 619 – 03.

² Annual Book of ASTM Standards, Vol 08.01.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Withdrawn.

⁵ Annual Book of ASTM Standards, Vol 13.01.

⁶ Available from U.S. Pharmacopeia (USP), 12601 Twinbrook Pkwy., Rockville, MD 20852-1790, <http://www.usp.org>.

4.2 A choice is made, based on the end use, of the extraction vehicles (see Section 7) and one of the combinations of time and temperature for the test (see Section 12).

4.3 The resultant test liquids (extract liquids) are kept in glass containers until used for testing. The test liquids shall be stored tightly stoppered at normal room temperature. Test liquids for biological testing are kept in sterile glass containers. Consideration should be given as to whether the extraction should be done under aseptic conditions. The test liquids for biological testing should be used within 24 h.

5. Significance and Use

5.1 These extraction procedures are the initial part of several test procedures used in the biocompatibility screening of plastics used in medical devices.

5.2 The limitations of the results obtained from this practice should be recognized. The choice of extraction vehicle, duration of immersion, and temperature of the test is necessarily arbitrary. The specification of these conditions provides a basis for standardization and serves as a guide to investigators wishing to compare the relative resistance of various plastics to extraction vehicles.

5.3 Correlation of test results with the actual performance or serviceability of materials is necessarily dependent upon the similarity between the testing and end-use conditions (see 12.1.2 and Note 4).

5.4 Caution should be exercised in the understanding and intent of this practice as follows:

5.4.1 No allowance or distinction is made for variables such as end-use application and duration of use. Decisions on selection of tests to be done should be made based on Practice F 748.

~~5.4.2 No allowance is made to distinguish between nonporous or porous materials or~~ 5.4.2 This practice was originally designed for use with nonporous, solid materials. Its application for other materials, such as those that are ~~absorptive~~ porous, or ~~resorbable~~ absorptive, or resorptive, should be considered with caution. Consideration should be given to altering the specified material to liquid ratio to allow additional liquid to fully hydrate the material and additional liquid or other methods to fully submerge the test article. Additional procedures that fully remove the extract liquid from the test article, such as pressure or physically squeezing the material, should also be considered as appropriate. Although no definitions are given in this practice for the following terms, such items as extraction vehicle surface tension at the specified extraction condition and plastic specimen physical structure should be taken into account.

5.5 Test Methods D 543, D 570, and D 1239 may be useful in providing supplemental information.

6. Apparatus

6.1 *Autoclave*, capable of maintaining a temperature of $121 \pm 2.0^\circ\text{C}$ ($249.8 \pm 3.8^\circ\text{F}$) for at least 1 h and equipped with a display of temperature and pressure. A slow exhaust cycle is necessary. A rack to hold the extraction containers above the water level is also necessary. Loss of fluid volume should be recorded.

6.1.1 Sealed, unvented extraction vessels should not be removed until internal temperature and pressure have reached ambient conditions and the door can be opened. It is recommended that the extraction vessels be left undisturbed until any risk of boil over has passed. When the extraction vessels are cool to the touch, the lids should be sealed.

6.2 *Heating Equipment*:

6.2.1 Ovens or incubators that will maintain temperatures of 37, 50, $70 \pm 2^\circ\text{C}$ (98, 122, $158 \pm 3^\circ\text{F}$).

6.2.2 Water baths capable of maintaining temperatures described in 6.2.1. Those with the ability to agitate the extraction vessels are preferred.

6.3 *Extraction Containers*—Suitable containers that protect the extract liquid from the biological and chemical contamination. They should allow expansion of the liquid, but then be sealed to prevent evaporation. One suggested container is the screw-cap culture test tube of borosilicate glass, unless a larger container is required for the size and shape of the material to be extracted. Screw caps, if used, shall have polytetrafluoroethylene liners.

6.4 *Balance*, accurate to ± 0.1 mg.

6.4.1 Caution should be exercised when performing weighings in glassware. Depending upon the required accuracy, the relative humidity should be the same for weighings at different times.

6.5 *Micrometers*, capable of measuring dimensions of test specimens to 0.025 mm (0.001 in.).

7. Reagents and Materials

7.1 *Purity of Reagents*—Reagent grade, or better, chemicals shall be used in all tests.⁵ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Extraction Vehicles*—The following list of standard extraction vehicles is intended to simulate the main constituents of human body fluids. The extraction vehicles shall be:

⁴ Available from U.S. Pharmacopeia (USP), 12601 Twinbrook Pkwy., Rockville, MD 20852.

⁵ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For Suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.