



SLOVENSKI STANDARD
SIST ISO 10258:2016

01-maj-2016

Nadomešča:
SIST ISO 10258:1998

Bakrovi sulfidni koncentracije - Določevanje bakra - Titrimetrijska metoda

Copper sulfide concentrates - Determination of copper content - Titrimetric methods

iTeh STANDARD PREVIEW
Concentrés de sulfure de cuivre - Dosage du cuivre - Méthodes titrimétriques
(standards.iteh.ai)

Ta slovenski standard je istoveten z: ISO 10258:2015

<https://standards.iteh.ai/catalog/standards/sist/008558a3-b272-46ec-8ae8-8b89b29766/sist-iso-10258-2016>

ICS:

73.060.99 Druge rude Other metalliferous minerals

SIST ISO 10258:2016 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 10258:2016

<https://standards.iteh.ai/catalog/standards/sist/008558a3-b272-46ec-8ae8-ffb89b29766/sist-iso-10258-2016>

INTERNATIONAL
STANDARD

ISO
10258

Second edition
2015-07-01

**Copper sulfide concentrates —
Determination of copper content —
Titrimetric methods**

*Concentrés de sulfure de cuivre — Dosage du cuivre — Méthodes
titrimétriques*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 10258:2016](https://standards.iteh.ai/catalog/standards/sist/008558a3-b272-46ec-8ae8-ffb89b29766/sist-iso-10258-2016)

[https://standards.iteh.ai/catalog/standards/sist/008558a3-b272-46ec-8ae8-
ffb89b29766/sist-iso-10258-2016](https://standards.iteh.ai/catalog/standards/sist/008558a3-b272-46ec-8ae8-ffb89b29766/sist-iso-10258-2016)



Reference number
ISO 10258:2015(E)

© ISO 2015

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 10258:2016

<https://standards.iteh.ai/catalog/standards/sist/008558a3-b272-46ec-8ae8-ffb89b29766/sist-iso-10258-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
3.1 Method 1 (Long iodide method).....	1
3.2 Method 2 (Short iodide method).....	1
4 Reagents	1
5 Apparatus	3
6 Sample	4
6.1 Test sample.....	4
6.2 Test portion.....	4
7 Procedure	4
7.1 Number of determinations.....	4
7.2 Blank test.....	4
7.3 Determination — method 1: Long iodide method.....	5
7.3.1 Decomposition of test portion.....	5
7.3.2 Separation of copper.....	5
7.3.3 Dissolution of copper precipitate.....	5
7.3.4 Titration.....	6
7.3.5 FAAS determination of copper in the insoluble residue, filtrate, and filter paper.....	6
7.4 Determination — method 2: Short iodide method.....	7
7.4.1 Decomposition of the test portion.....	7
7.4.2 Titration.....	7
8 Expression of results	8
9 Precision	8
9.1 Expression of precision.....	8
9.2 Method for obtaining the final result (see Annex B).....	9
9.3 Precision between laboratories.....	9
9.4 Check of trueness.....	10
10 Test report	11
Annex A (normative) Procedure for the preparation and determination of the mass of a predried test portion	12
Annex B (informative) Flowsheet of the procedure for the acceptance of analytical values for test samples	14
Annex C (informative) Derivation of precision formulae	15
Bibliography	20

ISO 10258:2015(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information \(standards.iteh.ai\)](http://Foreword - Supplementary information (standards.iteh.ai))

The committee responsible for this document is ISO/TC 183, *Copper, lead, zinc and nickel ores and concentrates*.

This second edition cancels and replaces the first edition (ISO 10258:1994), of which the warning in [A.3.1](#) in [Annex A](#) has been revised.

Copper sulfide concentrates — Determination of copper content — Titrimetric methods

1 Scope

This International Standard specifies two titrimetric methods for the determination of the copper content of copper sulfide concentrates in the range 15 % (m/m) to 50 % (m/m), using sodium thiosulfate after separation (method 1) or without separation (method 2) of copper from interfering elements.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 385, *Laboratory glassware — Burettes*

ISO 648, *Laboratory glassware — Single-volume pipettes*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 4787, *Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use*

ISO 9599, *Copper, lead, zinc and nickel sulfide concentrates — Determination of hygroscopic moisture content of the analysis sample — Gravimetric method*

<https://standards.iteh.ai/catalog/standards/sist/008558a3-b272-46ec-8ae8-ffb89b29766/sist-iso-10258-2016>

3 Principle

3.1 Method 1 (Long iodide method)

A test portion is decomposed in nitric and sulfuric acids, and arsenic, antimony, and tin are removed by treatment with hydrobromic acid. Copper is separated from interfering elements by precipitation of copper sulfide with sodium thiosulfate. The precipitate is dissolved in nitric and sulfuric acids, ammonium hydrogen difluoride is added to eliminate interference of residual iron, and excess potassium iodide is also added. Free iodine isolated by reaction between iodide ions and copper(II) ions is titrated with sodium thiosulfate using soluble starch as the indicator.

3.2 Method 2 (Short iodide method)

A test portion is decomposed in nitric and sulfuric acids, and arsenic, antimony, and tin are removed by treatment with hydrobromic acid. Ammonium hydrogen difluoride is added to eliminate interference of iron, and excess potassium iodide is also added. Free iodine isolated by reaction between iodide ions and copper(II) ions is titrated with sodium thiosulfate using soluble starch as the indicator.

4 Reagents

During the analysis, use only reagents of recognized analytical grade and distilled water or water of equivalent purity.

4.1 Copper metal, minimum purity 99,99 %.

4.2 Potassium iodide.

ISO 10258:2015(E)

4.3 Ammonium hydrogen difluoride.**4.4 Sulfuric acid**, diluted 1 + 1.

Slowly add 500 ml of concentrated sulfuric acid (ρ_{20} 1,84 g/ml) to 500 ml of water, while stirring and cooling.

4.5 Sulfuric acid, diluted 1 + 999.

Add 1 ml of dilute sulfuric acid (4.4) to 500 ml of water.

4.6 Nitric acid, concentrated (ρ_{20} 1,42 g/ml).**4.7 Nitric acid**, diluted 1 + 1.

Slowly add 500 ml of concentrated nitric acid (4.6) to 500 ml of water.

4.8 Hydrofluoric acid (ρ_{20} 1,14 g/ml).**4.9 Bromine.****4.10 Bromine water**, saturated.**4.11 Hydrobromic acid** (ρ_{20} 1,50 g/ml).**4.12 Acetic acid**, diluted 1 + 3.

Slowly add 25 ml of glacial acetic (ρ_{20} 1,05 g/ml) to 75 ml of water.

4.13 Nitration mixture.

Slowly add 250 ml of concentrated sulfuric acid (ρ_{20} 1,84 g/ml) to 250 ml of concentrated nitric acid (4.6).

4.14 Ammonium hydrogen difluoride, 250 g/l solution.**4.15 Sodium carbonate**, 20 g/l solution.**4.16 Sodium thiosulfate pentahydrate**, 200 g/l solution.**4.17 Potassium thiocyanate**, 100 g/l solution.**4.18 Starch**, 2 g/l solution.

Moisten 1 g of soluble starch with cold water, slowly pour into 500 ml of hot water while stirring, and boil for about 1 min.

4.19 Ethanol.**4.20 Standard solutions.**

Standard solutions should be prepared at the same ambient temperature as that at which the determinations will be conducted.

4.20.1 Sodium thiosulfate, standard volumetric solution (20 g/l).

4.20.1.1 Preparation

Dissolve 20 g of sodium thiosulfate (pentahydrate) in 1 l of freshly boiled and cooled water. Add 0,2 g of sodium carbonate, stir to dissolve and allow to stand for at least one day. Standardize this solution as specified in [4.20.1.2](#).

4.20.1.2 Standardization

Clean a piece of copper metal ([4.1](#)) by immersing it in warm dilute acetic acid ([4.12](#)). Wash the copper thoroughly with water followed by ethanol ([4.19](#)) and allow to dry in air. Weigh into three separate 400 ml conical beakers to the nearest 0,1 mg, a mass of clean copper metal which approximates the copper content in the test portion. Record these masses as m_1 , m_2 , and m_3 .

Dissolve the copper using 10 ml of dilute nitric acid ([4.7](#)) followed by 5 ml of dilute sulfuric acid ([4.4](#)). Heat to evaporate to dryness. Add 40 ml of water, heat to dissolve the soluble salts, and cool. Continue the standardization as specified in [7.3.4](#) for method 1 and in [7.4.2](#) for method 2. Record the volumes of sodium thiosulfate solution used in the titration as V_1 , V_2 , and V_3 .

The standardization factor of the standard volumetric solution varies with the volume of sample solution, mass of potassium iodide, mass of copper, and temperature of solution. The same volume of solution and mass of potassium iodide as those used for the standardization should be used for the analysis of the test portion. The temperatures of standardization and determination should be essentially the same.

Calculate the standardization factors f_1 , f_2 , and f_3 using the following formulae:

$$f_1 = \frac{m_1}{V_1} \quad (1)$$

$$f_2 = \frac{m_2}{V_2} \quad (2)$$

$$f_3 = \frac{m_3}{V_3} \quad (3)$$

Calculate, to four significant figures, the mean standardization factor f for the sodium thiosulfate standard volumetric solution, provided that the range of the values of f_1 , f_2 , and f_3 does not exceed 10^{-5} g Cu/ml. If this range is exceeded, repeat the standardization.

4.20.2 Copper, standard solution (0,1 mg/ml).

Weigh, to the nearest 0,1 mg, 0,1 g of copper metal ([4.1](#)) into a 200 ml beaker, decompose with 10 ml of dilute nitric acid ([4.7](#)). Heat to remove nitrogen oxides, cool, and add about 50 ml of water. Transfer to a 1 000 ml volumetric flask, fill up nearly to the mark with water, mix and cool to room temperature; then fill up exactly to the mark and mix again.

5 Apparatus

Ordinary laboratory equipment and the following.

5.1 Volumetric glassware, of class A complying with ISO 385, ISO 648, and ISO 1042, and used in accordance with ISO 4787.

5.2 Analytical balance, sensitive to 0,1 mg.

5.3 Platinum crucibles.

ISO 10258:2015(E)**5.4 Atomic absorption spectrometer (AAS)**, with a copper hollow cathode lamp.

Instrumental conditions:

- Flame: air/acetylene;
- Wavelength: 324,7 nm.

5.5 Inductively coupled plasma (ICP) atomic emission spectrometer (optional).**6 Sample****6.1 Test sample**

Prepare an air-equilibrated test sample in accordance with ISO 9599.

NOTE A test sample is not required if predried test portions are to be used (see [Annex A](#)).

6.2 Test portion

Taking multiple increments, extract a test portion from the test sample as specified in [Table 1](#) and weigh to the nearest 0,1 mg. At the same time as test portions are being weighed for analysis, weigh test portions for the determination of hygroscopic moisture in accordance with ISO 9599.

Alternatively, the method specified in [Annex A](#) can be used to prepare predried test portions directly from the laboratory sample.

Table 1 — Recommended test Portion masses

Copper content (presumed) % (m/m)		Mass of test portion g
≥	<	
15	25	0,8
25	50	0,4

7 Procedure**7.1 Number of determinations**

Carry out the determinations at least in duplicate, as far as possible under repeatability conditions, on each test sample.

NOTE Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material in the same laboratory by the same operator using the same equipment, within short intervals of time.

7.2 Blank test

Carry out a blank test in parallel with the analysis using the same quantities of all reagents but omitting the test portion. The purpose of the blank test in this method is to check the quality of reagents. If a significant blank titration value is obtained as a result of the blank test, check all reagents and rectify the problem.

7.3 Determination — method 1: Long iodide method

7.3.1 Decomposition of test portion

Transfer the test portion to a 400 ml conical beaker and moisten with 10 ml of water. Add 20 ml of dilute nitric acid (4.7), cover with a watch glass and heat for about 10 min at 60 °C to 70 °C. Add 10 ml of dilute sulfuric acid (4.4) and heat gradually to decompose the test portion.

After the completion of the initial reaction, rinse the underside of the watch glass with a minimum volume of water, collecting the washings in the conical beaker. Continue heating until strong white fumes are evolved, then cool.

If the residue appears dark (presence of carbon), slowly add a small amount of the nitration mixture (4.13) to the hot solution until the solution becomes colourless or bluish and heat until strong white fumes are evolved.

If decomposition of the deposited sulfur is insufficient, add 5 ml of nitric acid (4.6) and 1 ml of bromine (4.9), and heat until strong white fumes are evolved.

Carefully add 5 ml of water and 10 ml of hydrobromic acid (4.11) and heat until strong white fumes are evolved. Remove from the source of heat and cool. After addition of 5 ml of dilute sulfuric acid (4.4) and 10 ml of hydrobromic acid (4.11), heat until strong white fumes are evolved. Remove from the source of heat and cool.

Add 80 ml of water, warm to dissolve soluble salts, and heat until boiling. Filter through a medium porosity filter paper, wash well with hot water, and collect the filtrate in a 400 ml conical beaker. Reserve the filter paper and residue for the determination of copper by flame atomic absorption spectrometry (FAAS) (as described in 7.3.5) unless it has been proven, through previous testing, that the copper in the sample is completely soluble using the initial dissolution.

SIST ISO 10258:2016

7.3.2 Separation of copper

Dilute the filtrate to 200 ml and heat to 70 °C to 90 °C, slowly add 40 ml of sodium thiosulfate solution (4.16) while stirring, to produce a yellow or yellowish brown emulsion. Heat gradually and continue boiling gently until the precipitate coagulates. Filter the solution through a medium porosity filter paper and wash the filter paper and precipitate with hot water. Retain the filtrate for FAAS measurements of copper (as described in 7.3.5).

Using water, rinse away the copper sulfide precipitate into the original conical beaker and decompose the remaining precipitate on the filter paper using drop by drop addition of bromine water (4.10) followed by nitric acid (4.6). Repeat this treatment as required, then wash well with hot water, collecting this solution in the beaker containing the main precipitate. Retain the filter paper for FAAS measurements of copper (as described in 7.3.5).

NOTE Instead of using the above step, the following method can be used: Transfer the precipitate and filter paper into the original beaker, cover with a watch glass, and add 30 ml of nitration mixture (4.13). Heat slowly to decompose the precipitate and the filter paper, and evaporate to dryness. Use more nitration mixture if the residue appears dark. Continue heating strongly to destroy any elemental sulfur. After adding 10 ml of nitric acid (4.6) around the top of the beaker to rinse away the residual sulfur, add 2 ml of dilute sulfuric acid (4.4) and heat until strong white fumes are evolved. Remove from the heat source and cool. Add 40 ml of water, warm to dissolve the soluble salts, and cool. Proceed to 7.3.4.

7.3.3 Dissolution of copper precipitate

Add 2 ml of dilute sulfuric acid (4.4) and 10 ml of nitric acid (4.6), heat slowly to decompose the precipitate, and then evaporate to dryness. Continue heating strongly to destroy any elemental sulfur. After adding 10 ml of nitric acid (4.6) around the top of the beaker to rinse away the residual sulfur, add 2 ml of dilute sulfuric acid (4.4), and heat until strong white fumes are evolved. Remove from the source of heat and cool.