

# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 13543

ISO/TC 183

Secretariat: SA

Voting begins on:  
2015-05-08

Voting terminates on:  
2015-08-08

---

---

### Copper, lead and zinc sulfide concentrates — Determination of mass of contained metal in a lot

*Concentrés sulfurés de cuivre, de plomb et de zinc — Détermination de la masse de métal contenu dans un lot*

ICS: 73.060.99

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/76420a7d-f750-4e53-8ee5-13199059dbc9/iso-13543-2016>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



---

---

Reference number  
ISO/DIS 13543:2015(E)

© ISO 2015

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
Full standard:  
<https://standards.iteh.ai/catalog/standards/sist/76420a7d-f750-4e53-8ee5-13199059dbc9/iso-13543-2016>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions .....</b>	<b>1</b>
<b>4 Determination of mass of contained metal .....</b>	<b>2</b>
4.1 General .....	2
4.2 Wet mass of the lot .....	2
4.3 Metal content of the lot .....	2
4.4 Dry mass of the lot .....	2
4.5 Mass of contained metal .....	2
4.5.1 Major elements .....	2
4.5.2 Precious metals .....	3
<b>5 Determination of variance of mass of contained metal .....</b>	<b>3</b>
<b>6 Examples of calculation of contained metal and its variance .....</b>	<b>4</b>
6.1 Static scale .....	4
6.1.1 General .....	4
6.1.2 Mass of contained copper .....	4
6.1.3 Mass of contained gold .....	5
6.2 Draft survey .....	6
<b>Bibliography .....</b>	<b>8</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2. [www.iso.org/directives](http://www.iso.org/directives)

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received. [www.iso.org/patents](http://www.iso.org/patents)

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 183, *Copper, lead, zinc and nickel ores and concentrates*.

This second edition cancels and replaces the first edition (ISO 13543:1996), which has been technically revised.

# Copper, lead and zinc sulfide concentrates — Determination of mass of contained metal in a lot

**WARNING** — This International Standard may involve hazardous materials, operations and equipment. It is responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

## 1 Scope

This International Standard specifies the method for determining the mass of contained metal in a lot, based on the wet mass, moisture content and dry basis metal content of the lot. The procedure for estimating the variance and confidence intervals for the mass of contained metal is also specified.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 10251, *Copper, lead, zinc and nickel concentrates — Determination of mass loss of bulk material on drying*

ISO 12743, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

ISO 12744, *Copper, lead, zinc and nickel concentrates — Experimental methods for checking the precision of sampling*

ISO 12745, *Copper, lead and zinc ores and concentrates — Precision and bias of mass measurement techniques*

## 3 Terms and definitions

For the purposes of this document, the following definitions apply.

### 3.1

#### **lot**

Quantity of concentrate to be sampled

### 3.2

#### **wet mass of the lot**

Combined mass of concentrate and moisture of the lot at the time of weighing and sampling

### 3.3

#### **moisture determination**

Quantitative measurement of the mass loss of the moisture test portion under the conditions of drying specified in ISO 10251

### 3.4

#### **chemical analysis**

Quantitative determination of the required chemical constituents of the analysis test portion

### 3.5

#### **precision**

Measure of the random variations within a set of measurements

### 3.6

#### **dry mass of the lot**

Mass of concentrate in the lot after correcting for the mass of moisture in the lot

## **4 Determination of mass of contained metal**

### **4.1 General**

The mass of contained metal in a lot is determined from measurements of the wet mass, moisture content and dry basis metal content.

### **4.2 Wet mass of the lot**

The wet mass of the lot shall be determined using static scales, belt scales or draft surveys. However, due to their superior precision, static scales are recommended.

### **4.3 Metal content of the lot**

Samples for chemical analysis shall be collected in accordance with ISO 12743 and analysed in accordance with the relevant ISO chemical analysis Standards.

### **4.4 Dry mass of the lot**

Calculate the dry mass of the lot using the following equation:

$$m_D = m_w \left( 1 - \frac{M}{100} \right) \quad (1)$$

where

$m_D$  is the dry mass of the lot, in tonnes

$m_w$  is the wet mass of the lot, in tonnes

$M$  is the moisture content of the lot, in percent of the wet mass (m/m)

### **4.5 Mass of contained metal**

#### **4.5.1 Major elements**

For the major elements copper, lead, zinc, and nickel, the mass of contained metal in the lot is given by the following equation:

$$m_M = \frac{m_D a_L}{100} \quad (2)$$

where

$m_M$  is mass of contained metal in the lot, in tonnes

$m_D$  is the dry mass of the lot, in tonnes

$a_L$  is the metal content of the lot on a dry basis, in percent (m/m)

Alternatively, Formula (2) may be rewritten as follows:

$$m_M = \frac{m_D F a_L}{100} \quad (3)$$

where  $F$  is the moisture factor given by:

$$F = 1 - \frac{M}{100} \quad (4)$$

#### 4.5.2 Precious metals

For the precious metals silver and gold, the mass of contained metal in the lot is given by the following equation:

$$m_M = \frac{m_W F a_L}{100} \quad (5)$$

where

$m_M$  is the mass of contained metal in the lot, in kilograms

$m_W$  is the wet mass of lot, in tonnes

$F$  is the moisture factor

$a_L$  is the precious metal content of the lot on a dry basis, in grams per tonne (m/m)

### 5 Determination of variance of mass of contained metal

The variance of the mass of contained metal in the lot may be determined from Formula (3) by taking the partial derivatives with respect to the wet mass, the moisture factor and the metal content of the lot as follows:

$$s_M^2 = \left( \frac{\partial m_M}{\partial m_W} \right)^2 s_W^2 + \left( \frac{\partial m_M}{\partial F} \right)^2 s_F^2 + \left( \frac{\partial m_M}{\partial a_L} \right)^2 s_T^2 \quad (6)$$

where

$s_M^2$  is the estimated variance of the mass of contained metal in the lot

$s_W^2$  is the estimated variance of the mass of contained metal in the lot

$s_F^2$  is the estimated total variance of the moisture factor =  $(s_H/100)^2$  with  $s_H$  being the total precision (one standard deviation) of moisture determination

$s_T^2$  is the estimated total variance of the moisture factor =  $(s_H/100)^2$  with  $s_H$  being the total precision (one standard deviation) of moisture determination

NOTE The estimated total variances of the moisture factor and the metal content include the contributions from primary sampling, sample processing and analysis.

Determining the partial derivatives and substituting them into Formula (6) gives:

$$s_M^2 = \left( \frac{F a_L}{100} \right)^2 s_W^2 + \left( \frac{m_W a_L}{100} \right)^2 s_F^2 + \left( \frac{m_W F}{100} \right)^2 s_T^2 \quad (7)$$

Formula (7) may be simplified as follows:

$$s_M^2 = m_M^2 \left[ \frac{s_M^2}{m_W^2} + \frac{s_F^2}{F^2} + \frac{s_T^2}{a_L^2} \right] \quad (8)$$

Formula (8) is applicable to both the major elements and the precious metals.

The variance of the wet mass of the lot shall be determined in accordance with the procedures specified in ISO 12745 for estimating the precision of mass measurement techniques. The variances of the moisture factor and the metal content of the lot shall be determined according to the procedures specified in ISO 12744. The analyses shall be carried out according to the methods prescribed in relevant International Standards.

## 6 Examples of calculation of contained metal and its variance

### 6.1 Static scale

#### 6.1.1 General

Assume a 500 t lot containing 30 % copper (m/m), 10 g of gold/t (m/m) and 8 % moisture (m/m) is weighed using a static hopper scale with a capacity of 25 t, i.e. 20 hopper loads. The precision (one standard deviation) of the hopper scale is 0,2 % relative. The lot is divided into 10 sub-lots, and a single moisture determination is carried out on each subsample. A single lot sample is constituted for chemical analysis. The total precisions of the copper, gold and moisture determinations (one standard deviation) are 0,05 % copper, 0,5 g of gold/t and 0,1 % moisture absolute (m/m) respectively.

#### 6.1.2 Mass of contained copper

$$m_W = 500 \text{ t}$$

$$s_W^2 = \left( \frac{25 \times 0,2}{100} \right)^2 \times 20 = 0,05$$

$$F = 1 - \frac{8}{100} = 0,92$$

$$s_F^2 = \frac{(0,1/100)^2}{10} = 0,000\,000\,1$$

$$a_L = 30\% \text{ copper}$$

$$s_T^2 = (0,05)^2 = 0,0025$$

Formulae (3) and (8) give:

$$m_M = \left( \frac{500 \times 0,92 \times 30}{100} \right) = 138 \text{ t copper}$$



$$\begin{aligned}
 s_W^2 &= 138^2 \times \left( \frac{0,05}{500^2} + \frac{0,000\,000\,1}{0,92^2} + \frac{0,0025}{30^2} \right) \\
 &= 138^2 \times (0,000\,000\,2 + 0,000\,000\,12 + 0,000\,00278) \\
 &= 0,003\,8 + 0,002\,3 + 0,0529 \\
 &= 0,059
 \end{aligned}$$

Calculation of the standard deviation  $s_M$  gives:

$$s_M = 0,24 \text{ t copper}$$

Hence, at the 95 % confidence level (i.e. two standard deviations), the mass of contained copper metal is:

$$m_M = 138 \pm 0,5 \text{ t copper (i.e. } \pm 0,4\% \text{ relative)}$$

The 95 % confidence range is 137,5 t of copper to 138,5 t of copper.

The precision of the measured copper content of the lot is the major contributor to the uncertainty in the mass of contained metal. This may be reduced by carrying out additional analyses on the lot sample, or, in future, by analysing each sub-lot separately.

### 6.1.3 Mass of contained gold

$$\begin{aligned}
 m_W &= 500 \text{ t} \\
 s_W^2 &= \left( \frac{25 \times 0,2}{100} \right)^2 \times 20 = 0,05 \\
 F &= 1 - \frac{8}{100} = 0,92 \\
 s_F^2 &= \frac{(0,1/100)^2}{10} = 0,000\,0001 \\
 a_L &= 10 \text{ g of gold/t} \\
 s_T^2 &= (0,5)^2 = 0,25
 \end{aligned}$$

Formulae (5) and (8) give:

$$\begin{aligned}
 m_M &= \left( \frac{500 \times 0,92 \times 10}{10^3} \right) = 4,6 \text{ kg gold} \\
 s_W^2 &= 4,6^2 \times \left( \frac{0,05}{500^2} + \frac{0,000\,000\,1}{0,92^2} + \frac{0,25}{10^2} \right) \\
 &= 4,6^2 \times (0,000\,000\,2 + 0,000\,000\,12 + 0,0025) \\
 &= 0,000\,004\,2 + 0,000\,002\,5 + 0,0529
 \end{aligned}$$