



## Standard Test Method for Detection of Copper Corrosion from Lubricating Grease<sup>1</sup>

This standard is issued under the fixed designation D 4048; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

- 1.1 This test method covers the detection of the corrosiveness to copper of lubricating grease.
- 1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.
- 1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard/warning statements, see Sections ~~Note 17~~, 8, and 10.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

D 97 Test Method for Pour Point of Petroleum Oils-Products

~~D 130 Test Method for Detection of Copper Corrosion from Petroleum Products by the Copper Strip Tarnish Test<sup>2</sup>~~ Test Method for Corrosiveness to Copper from Petroleum Products by Copper Strip Test

D 2500 Test Method for Cloud Point of Petroleum Oils<sup>2</sup>Products

#### 2.2 ~~ASTM Adjuncts:~~ ASTM Adjuncts:

Copper Strip Corrosion Standard<sup>3</sup>

### 3. Terminology

- 3.1 There are no terms in this test method that require new or other than dictionary definitions.

### 4. Summary of Test Method

4.1 A prepared copper strip is totally immersed in a sample of grease and heated in an oven or liquid bath at a specified temperature for a definite period of time. Commonly used conditions are  $100 \pm 1^\circ\text{C}$  ( $212 \pm 2^\circ\text{F}$ ) for  $24 \text{ h} \pm 5 \text{ min}$ . At the end of this heating period, the strip is removed, washed, and compared with the ASTM-Copper Strip Corrosion Standards.

### 5. Significance and Use

5.1 This test method measures the tendency of lubricating grease to corrode copper under specific static conditions. It may be of some value in predicting possible chemical attack on lubricated parts, such as bearings that contain copper or copper alloys. Such corrosion, for example, can cause premature bearing failures. However, no correlations with actual field service, most of which are under dynamic conditions, have been established. It does not measure either the ability of the lubricant to inhibit copper corrosion caused by factors other than the lubricant itself nor does it measure the stability of the grease in the presence of copper.

### 6. Apparatus

6.1 *Test Jars*—Cloud and pour jars, cylindrical jars of clear glass with flat bottoms, 30 mm to 33.5-mm ( $1\frac{3}{16}$  in. to  $1\frac{5}{16}$  in.) inside diameter, and 115 mm to 125 mm ( $4\frac{1}{2}$  in. to 5 in.) in height as described in Test Methods D 97 and D 2500.

6.2 *Test Jar Covers—Beakers*, 50-mL; borosilicate glass, approximately 40 mm (1.6 in.) by 50 mm (2.0 in.) suitable for covering individual test jars. Small porcelain or glazed silica crucibles or crucible covers or watch glasses or vented corks that

<sup>1</sup>This test method is under the jurisdiction of ASTM Committee D-2 on Petroleum products and lubricants and is the direct responsibility of Subcommittee D02.G on Lubricating Grease.

Current edition approved June 10, 1997. Published October 1997. Originally published as D4048-81. Last previous edition D4048-91.

<sup>2</sup>This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.G0.01 on Chemical and General Laboratory Tests.

Current edition approved May 1, 2008. Published September 2008. Originally published in 1981. Last previous edition approved in 2002 as D 4048-02.

<sup>3</sup>For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards*, Vol 05.01, volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup>Available from ASTM Headquarters for a nominal charge. Request Adjunct PCN 12-401300-00.

<sup>5</sup>Available from ASTM International Headquarters. Order Adjunct No. ADJD0130. Originally produced in 1973.

lightly cover the test jars, allowing pressure equalization between the inside and outside of the jars, yet minimizing exposure of the inside of the jars to foreign vapors present in the oven will also be satisfactory.

6.3 *Oven*—A circulating air oven or liquid bath capable of maintaining a temperature of  $100 \pm 1^\circ\text{C}$  ( $212 \pm 2^\circ\text{F}$ ) or other desired temperatures with the same precision.

6.4 *Polishing Vise*—For holding the copper strip firmly without marring the edges while polishing. Any convenient type of holder (see the Appendix X1 on Optional Useful Equipment in Test Method D 130) may be used, provided that the strip is held tightly and that the surface of the strip being polished is supported above the surface of the holder.

6.5 *Viewing Test Tubes*—Flat glass test tubes may be used to protect corroded strips for close inspection or storage. (See the Appendix X1 on Optional Useful Equipment in Test Method D 130.)

6.6 *ASTM Copper Strip Corrosion Standards Standard*, consist—consists of reproductions in color of typical strips representing degrees of tarnish and corrosion, the reproductions being encased in plastic in the form of a plaque.

6.6.1 Keep the plastic-encased printed ASTM Copper Strip Corrosion Standards Standard protected from light to avoid the possibility of fading. Inspect for fading by comparing two different plaques, one of which has been carefully protected from light (new). Observe both sets in diffused daylight (or equivalent), first from a point directly above and then from an angle of approximately  $45^\circ$ . If any evidence of fading is observed, particularly at the left end of the plaque, it is suggested that the one that is the more faded with respect to the other be discarded.

6.6.1.1 Alternatively, place a 20-mm ( $\frac{3}{4}$  in.) opaque strip (masking tape) across the top of the colored portion of the plaque when initially purchased. At intervals, remove the opaque strip and observe. If there is any evidence of fading of the exposed portion, it is suggested that the standard be replaced.

6.6.1.2 These plaques are full-color productions of typical strips. They have been printed on aluminum sheets by a four-color process and are encased in plastic for protection. Directions for their use are given on the reverse side of each plaque.

6.6.2 If the surface of the plastic cover shows excessive scratching, it is suggested that the plaque be replaced.

## 7. Reagents and Materials

7.1 *Acetone*—American Chemical Society Reagent Grade acetone is suitable.

~~Note 1—Warning: Extremely~~ (**Warning**—Extremely flammable. Harmful if inhaled. Vapors may cause flash fires.)

7.2 *Copper Strips*—Use strips  $12.5 \pm 2$  mm ( $\frac{1}{2} \pm \frac{1}{16}$  in.) wide, 1.5 mm to 3.0 mm ( $\frac{1}{16}$  in. to  $\frac{1}{8}$  in.) thick, cut  $75 \pm 5$  mm ( $3 \pm \frac{1}{4}$  in.) long from smooth-surfaced, hard-temper, cold-finished copper of 99.9 + % purity; electrical bus bar stock is generally suitable. (See the Appendix X1 on Optional Useful Equipment in Test Method D 130.) The strips may be used repeatedly but should be discarded when the surfaces become deformed on handling.

7.3 *Polishing Materials*—Silicon carbide grit paper of varying degrees of fineness, including 65- $\mu\text{m}$  (240-grit) paper or cloth, also a supply of 105- $\mu\text{m}$  (150-mesh) silicon carbide grain and pharmaceutical-grade absorbent cotton (cotton wool).

7.4 *Wash Solvent*—Volatile, sulfur-free hydrocarbon solvent may be used provided that it shows no tarnish at all when tested at  $50 \pm 1^\circ\text{C}$  (or  $122 \pm 2^\circ\text{F}$ ). Knock test-grade isooctane (**Warning**—see Note 2—see 8.1.2) or American Chemical Society Reagent Grade *n*-heptane (**Warning**—see Note 3—see 7.1) are suitable solvents. Because of possible toxic effects, the use of benzene should be avoided.

## 8. Preparation of Strip

8.1 *Mechanical Cleaning of Strips* :

8.1.1 *Surface Preparation*—Remove all surface blemishes from all six sides of the strip with silicon carbide paper of such degrees of fineness as are needed to accomplish the desired results efficiently. Finish with 65- $\mu\text{m}$  (240-grit) silicon carbide paper or cloth, removing all marks that may have been made by other grades of paper used previously. Immerse the strip in wash solvent (**Warning**—see Note 1 ~~Warning~~—see 7.1.) from which it can be withdrawn immediately for final polishing or in which it can be stored for future use.

8.1.1.1 As a practical manual procedure for surface preparation, place a sheet of the paper on a flat surface, moisten it with wash solvent, and rub the strip against the paper with a rotary motion, protecting the strip from contact with the fingers with an ashless filter paper or by wearing disposable polyethylene gloves. Alternatively, the surface of the strip may be prepared by use of motor-driven machines using appropriate grades of dry paper or cloth.

8.1.2 *Final Polishing*—Remove strip from the wash solvent. Holding it in the fingers protected with the ashless filter paper, polish first the ends and then the sides with the 105- $\mu\text{m}$  (150-mesh) silicon carbide grains picked up from a clean glass plate with a pad of cotton (cotton wool) moistened with a drop of wash solvent. Wipe vigorously with fresh pads of cotton (cotton wool) and subsequently handle only when wearing disposable polyethylene gloves or with stainless steel forceps (see Note 2); *do not touch with naked fingers*. Clamp the strip in a vise, and polish the main surfaces with silicon carbide grains on absorbent cotton. Rub in the direction of the long axis of the strip, carrying the stroke beyond the end of the strip before reversing the direction. Clean all metal dust from the strip before reversing the direction. Clean all metal dust from the strip by rubbing vigorously with clean pads of absorbent cotton until a fresh pad remains unsoiled. When the strip is clean, immediately immerse it in the prepared sample.

8.1.1.1 As a practical manual procedure for surface preparation, place a sheet of the paper on a flat surface, moisten it with wash solvent, and rub the strip against the paper with a rotary motion, protecting the strip from contact with the fingers or by wearing