



SLOVENSKI STANDARD SIST EN 3475-418:2019

01-september-2019

Nadomešča:

SIST EN 3475-418:2009

Aeronavtika - Električni kabli za uporabo v zračnih plovilih - Preskusne metode - 418. del: Toplotna vzdržljivost za vodnike

Aerospace series - Cables, electrical, aircraft use - Test methods - Part 418: Thermal endurance for conductors

Luft- und Raumfahrt - Elektrische Leitungen für Luftfahrtverwendung - Prüfverfahren - Teil 418: Thermische Gebrauchsdauer für Leiter

(standards.iteh.ai)

Série aérospatiale - Câbles électriques à usage aéronautique - Méthodes d'essais - Partie 418 : Endurance thermique des conducteurs

<https://standards.iteh.ai/catalog/standards/sist/cc024266-1020-4811-bf23-212c7e406395/sist-en-3475-418-2019>

Ta slovenski standard je istoveten z: EN 3475-418:2019

ICS:

29.060.20	Kabli	Cables
49.060	Letalska in vesoljska električna oprema in sistemi	Aerospace electric equipment and systems

SIST EN 3475-418:2019

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 3475-418:2019

<https://standards.iteh.ai/catalog/standards/sist/cc024266-1020-4811-bf23-212c7e406395/sist-en-3475-418-2019>

EUROPEAN STANDARD

EN 3475-418

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2019

ICS 49.060

English Version

Aerospace series - Cables, electrical, aircraft use - Test methods - Part 418: Thermal endurance for conductors

Série aérospatiale - Câbles électriques à usage
aéronautique - Méthodes d'essais - Partie 418 :
Endurance thermique des conducteurs

Luft- und Raumfahrt - Elektrische Leitungen für
Luftfahrtverwendung - Prüfverfahren - Teil 418:
Thermische Gebrauchsdauer für Leiter

This European Standard was approved by CEN on 6 January 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents		Page
European foreword		3
1	Scope.....	4
2	Normative references.....	4
3	Terms and definitions	4
4	Introduction.....	4
5	Preparation of specimens.....	5
6	Apparatus.....	6
7	Method	6
8	Requirements.....	6
Annex A (normative) Standard evolution form.....		7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3475-418:2019](https://standards.iteh.ai/catalog/standards/sist/cc024266-1020-4811-bf23-212c7e406395/sist-en-3475-418-2019)

<https://standards.iteh.ai/catalog/standards/sist/cc024266-1020-4811-bf23-212c7e406395/sist-en-3475-418-2019>

European foreword

This document (EN 3475-418:2019) has been prepared by the Aerospace and Defence Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2019, and conflicting national standards shall be withdrawn at the latest by December 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 3475-418:2007.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3475-418:2019](https://standards.iteh.ai/catalog/standards/sist/cc024266-1020-4811-bf23-212c7e406395/sist-en-3475-418-2019)

<https://standards.iteh.ai/catalog/standards/sist/cc024266-1020-4811-bf23-212c7e406395/sist-en-3475-418-2019>

EN 3475-418:2019 (E)**1 Scope**

This European Standard specifies a test method to value the thermal endurance of bi-metal conductors, by valuation of the influence of metallic migration on the electrical resistance per unit length.

It shall be used together with EN 3475-100.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 3475-100, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 100: General*

EN 3475-301, *Aerospace series — Cables, electrical, aircraft use — Test methods — Part 301: Ohmic resistance per unit length*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Introduction

<https://standards.iteh.ai/catalog/standards/sist/cc024266-1020-4811-bf23-212c7e406395/sist-en-3475-418-2019>

4.1 General

Various bi-metal conductors exist among which the most usual are tin-coated copper, copper clad steel and copper clad aluminium.

Inter-metallic compounds may appear at the interface of the various layers of such conductors. As these compounds have generally an increasing growth rate when exposed to elevated temperature, the characteristics of the cables (mechanical and electrical) can be affected depending on the time and the temperature of exposure.

A good example is tin-coated copper where the diffusion of tin into copper is a fast, well-known and important phenomenon between ambient temperature and 230 °C.

4.2 Theory

The inter-metallic layer formation at the interface of the various layers in the wires is due to a diffusion mechanism in association with solubility phenomenon.

The diffusion rate is characterized by a coefficient of diffusion of the two metals in contact at a given temperature. This coefficient of diffusion has generally the form of an Arrhenius law and is given by the formula.

$$D = D_0 \cdot e^{-\frac{Q}{R \cdot T}}$$

where

- R is the ideal gas constant;
- Q is the activation energy for the diffusion process; and
- T is the absolute temperature;
- D_0 is a constant given for a couple of diffusion.

Furthermore, in the case of the electrical wires, the calculation shows that there is a relation between the coefficient of diffusion D and the time t of exposure at different temperatures:

$$D \cdot t = \text{Const}$$

So that $D_1 \cdot t_1 = D_2 \cdot t_2$

This says that it is possible to calculate an equivalent time of exposure at a higher temperature but this must be done at a temperature for which the solubility limit and the metallurgic mechanisms involved are not too different, generally in a domain below 280 °C. If the test temperature is too high there is a risk of obtaining a degradation mechanism not representative of reality.

For example, on a copper-clad aluminium conductor to assess the behaviour for:

- 10 000 h at 180 °C, a test of 2 200 h at 200 °C can be performed;
- 140 000 h at 150 °C, a test of 2 500 h at 200 °C can be performed.

4.3 Technical consequences on conductors

When appeared, such inter-metallic compounds will affect the mechanical and electrical behaviour of the conductor. Even if all these characteristics do not evolve proportionally in relation with its thickness, it has been shown that an easy way to survey the growth of the inter-metallic part is to measure the increase of the linear resistance.

5 Preparation of specimens

5.1 Specimens

A sufficient length shall be taken from the same batch of a finished cable. Generally, the test is run on gauge 20.

5.2 Conditioning

This length shall not be bent with a radius less than 50 times the overall diameter of the cable, during temperature exposure.

5.3 Initial measurement

On this initial length take a minimum length of three meters to make three samples of at least one meter, make three measurements of the electrical resistance per unit length, according to EN 3475-301. Record the arithmetic mean value, of this sampling corrected to 20 °C, as the initial measurement without thermal ageing.

NOTE The temperature correction coefficient is generally given in the relevant conductor product standard.

EN 3475-418:2019 (E)**6 Apparatus**

An air-circulating oven shall be required for this test. Its size must be sufficient to hold all necessary specimens during the complete duration of the test.

7 Method

The initial length shall be placed in the oven for the time and the temperature specified in the product standard.

Each month, or specified period in the concerned product standard, after having cut 10 cm at the extremity, one (1) specimen of three (3) m minimum length shall be removed from the oven and cooled for at least one (1) h at ambient temperature. Then, make three (3) samples of at least one (1) m and performed three (3) measurements of the electrical resistance per unit length, according to EN 3475-301. Record the arithmetic mean value as the value of the concerned sampling corrected to 20 °C. All specimens shall be kept in order if necessary to be able to measure the thickness of the inter-metallic interface.

8 Requirements

The electrical resistance after test shall comply at least to one (1) of the two (2) conditions listed below:

Condition 1:

The electrical resistance increase shall be less or equal to the maximum resistance specified in the product standard.

NOTE If the condition 1 is not fulfilled, the condition 2 shall apply and shall be satisfied.

Condition 2:

- a) The electrical resistance increase of each mean measurement shall be less than X % of the initial mean measurement.
- b) The electrical resistance increase of each mean measurement shall be less than Y % of the maximum resistance specified in the product standard.

NOTE X and Y values shall be specified in the product standard.