



SLOVENSKI STANDARD
oSIST prEN ISO 26304:2017
01-februar-2017

Dodajni materiali za varjenje - Masivne žice, strženske žice in kombinacije žic in praškov za varjenje visokotrčnih jekel po EPP - Razvrstitev (ISO/DIS 26304:2017)

Welding consumables - Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of high strength steels - Classification (ISO/DIS 26304:2017)

Schweißzusätze - Massivdrahtelektroden, Fülldrahtelektroden und Draht-Pulver-Kombinationen zum Unterpulverschweißen von hochfesten Stählen - Einteilung (ISO/DIS 26304:2017)

Produits consommables pour le soudage - Fils-électrodes pleins, fils-électrodes fourrés et couples électrodes-flux pour le soudage à l'arc sous flux des aciers à haute résistance - Classification (ISO/DIS 26304:2017)

<https://standards.iteh.ai/catalog/standards/sist/22a31bc0-f6c0-4b9e-b512-32be8f44238c/sist-en-iso-26304-2018>

Ta slovenski standard je istoveten z: prEN ISO 26304

ICS:

25.160.20 Potrošni material pri varjenju Welding consumables

oSIST prEN ISO 26304:2017

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 26304

ISO/TC 44/SC 3

Secretariat: ANSI

Voting begins on:
2017-01-03Voting terminates on:
2017-03-27

Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of high strength steels — Classification

Produits consommables pour le soudage — Fils-électrodes pleins, fils-électrodes fourrés et couples électrodes-flux pour le soudage à l'arc sous flux des aciers à haute résistance — Classification

ICS: 25.160.20

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN ISO 26304:2018](https://standards.iteh.ai/catalog/standards/sist/22a31bc0-f6c0-4b9e-b512-32bc8f44238c/sist-en-iso-26304-2018)<https://standards.iteh.ai/catalog/standards/sist/22a31bc0-f6c0-4b9e-b512-32bc8f44238c/sist-en-iso-26304-2018>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 26304:2017(E)

© ISO 2017

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

SIST EN ISO 26304:2018

<https://standards.iteh.ai/catalog/standards/sist/22a31bc0-f6c0-4b9e-b512-32bc8f44238c/sist-en-iso-26304-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Foreword.....	iv
Introduction	v
1 Scope.....	1
2 Normative references	1
3 Terms and definitions.....	2
4 Classification	2
4.1 General.....	2
5 Symbols and requirements.....	3
5.1 General.....	3
5.2 Symbol for the product or process	4
5.2A Classification by yield strength and 47 J impact energy	4
5.2B Classification by tensile strength and 27 J impact energy.....	4
5.3 Symbols for the tensile properties of the all-weld metal deposit	4
5.3A Classification by yield strength and 47 J impact energy.....	4
5.3B Classification by tensile strength and 27 J impact energy.....	4
5.4 Symbol for the impact properties of the all-weld metal.....	5
5.4A Classification by yield strength and 47 J impact energy.....	5
5.4B Classification by tensile strength and 27 J impact energy.....	5
5.5 Symbol for the type of welding flux	5
5.6 Symbol for the chemical composition of solid wire electrodes and of the all-weld metal from tubular cored electrode-flux combinations.....	6
5.7 Symbol for the post-weld heat treatment	1
5.7A Classification by yield strength and 47 J impact energy.....	1
5.7B Classification by tensile strength and 27 J impact energy.....	1
5.8 Optional symbol for hydrogen content of deposited metal	2
6 Mechanical tests	3
6.1 Tensile and impact tests	3
6.1A Classification by yield strength and 47 J impact energy.....	3
6.1B Classification by tensile strength and 27 J impact energy.....	3
6.2 Preheating and interpass temperature	3
6.2A Classification by yield strength and 47 J impact energy.....	3
6.2B Classification by tensile strength and 27 J impact energy.....	3
6.3 Welding conditions and pass sequence	3
6.3A Classification by yield strength and 47 J impact energy.....	3
6.3B Classification by tensile strength and 27 J impact energy.....	3
7 Chemical analysis.....	4
8 Rounding procedure.....	4
9 Retests	4
10 Technical delivery conditions	5
11 Examples of designation	5
11A Classification by yield strength and 47 J impact energy.....	5
11B Classification by tensile strength and 27 J impact energy.....	5
Annex A (informative) Possible risk of weld metal hydrogen cracking	7
Bibliography	8

ISO/DIS 26304:2017(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is Technical Committee ISO/TC 44, Welding and allied processes, Subcommittee SC 3, Welding consumables.

This third edition cancels and replaces the second edition (ISO 26304:2011), which has been technically revised.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Introduction

This International Standard recognizes that there are two somewhat different approaches in the global market to classifying a given wire electrode, tubular cored electrode, and electrode-flux combination, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both where suitable) identifies a product as classified in accordance with this International Standard. The classification in accordance with system A is mainly based on EN 14295^[1]. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim. Future revisions aim to merge the two approaches into a single classification system.

This International Standard provides a classification for the designation of solid wire electrodes in terms of their chemical composition, tubular cored electrodes in terms of the deposit composition obtained with a particular submerged arc flux, and, where required, electrode-flux combinations in terms of the yield strength, tensile strength, elongation, and impact properties of the all-weld metal deposit. The ratio of yield to tensile strength of weld metal is generally higher than that of parent material. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent material. Thus, where the application requires matching tensile strength, selection of the consumable should be made by reference to column 3 of Table 1A or Table 1B, as appropriate.

Although combinations of electrodes and fluxes supplied by individual companies may have the same classification, the combination of an electrode with a flux from one manufacturer versus the flux from another manufacturer, both fluxes having the same classification, may not be interchangeable unless verified in accordance with this International Standard. Two tubular cored wires of the same classification may likewise produce different results with the same flux.

The mechanical properties of the all-weld metal test specimens used to classify the electrode-flux combinations vary from those obtained in production joints because of differences in welding procedures such as electrode size, width of weave, welding position, and material composition.

[SIST EN ISO 26304:2018](https://standards.iteh.ai/SIST-EN-ISO-26304-2018)

<https://standards.iteh.ai/catalog/standards/sist/22a31bc0-f6c0-4b9e-b512-32be8f44238c/sist-en-iso-26304-2018>

Welding consumables — Solid wire electrodes, tubular cored electrodes and electrode-flux combinations for submerged arc welding of high strength steels — Classification

1 Scope

This International Standard specifies requirements for classification of solid wire electrodes, tubular cored electrodes, and electrode-flux combinations (the all-weld metal deposits) in the as-welded condition and in the post-weld heat-treated condition for submerged arc welding of high strength steels with a minimum yield strength greater than 500 MPa or a minimum tensile strength greater than 570 MPa. One flux can be tested and classified with different electrodes. One electrode can be tested and classified with different fluxes. The solid wire electrode is also classified separately based on its chemical composition.

This International Standard is a combined specification providing for classification utilizing a system based upon the yield strength and average impact energy of 47 J for the all-weld metal, or utilizing a system based upon the tensile strength and average impact energy of 27 J for the all-weld metal.

a) Clauses, subclauses and tables which carry the suffix letter “A” are applicable only to solid wire electrodes, tubular cored electrodes and the all-weld metal deposits classified to the system based upon the yield strength and the average impact energy of 47 J for the all-weld metal obtained with electrode-flux combinations in accordance with this International Standard.

b) Clauses, subclauses and tables which carry the suffix letter “B” are applicable only to solid wire electrodes, tubular cored electrodes and the all-weld metal deposits classified to the system based upon the tensile strength and the average impact energy of 27 J for the all-weld metal obtained with electrode-flux combinations in accordance with this International Standard.

c) Clauses, subclauses and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all solid wire electrodes, tubular cored electrodes and electrode-flux combinations classified in accordance with this International Standard.

For comparison purposes, some tables include requirements for electrodes classified in accordance with both systems, placing individual electrodes from the two systems, which are similar in composition and properties, on adjacent lines in the particular table. In a particular line of the table that is mandatory in one system, the symbol for the similar electrode from the other system is indicated in parentheses. By appropriate restriction of the formulation of a particular electrode, it is often, but not always, possible to produce an electrode that can be classified in both systems, in which case the electrode, or its packaging, may be marked with the classification in either or both systems.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO/DIS 26304:2017(E)

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14174, *Welding consumables — Fluxes for submerged arc welding and electroslag welding — Classification*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys.*

ISO 15792 1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys* Amended by ISO 15792-1:2000/Amd 1:2011

ISO 15792 3, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld)*

ISO 80000-1:2009, *Quantities and units — Part 1: General. Corrected by ISO 80000-1:2009/Cor 1:2011*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Classification**4.1 General**

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode-flux combination. The two designation approaches include additional designators for the chemical composition of a solid wire electrode or the chemical composition of the all-weld metal deposit obtained with a tubular cored electrode and a specific flux. The two designation approaches include additional designators for some other classification requirements, but not all, as is clear from the following clauses. A given commercial product may be classified to the classification requirements in both systems; then either or both classification designations may be used for the product.

The classification includes the all-weld metal properties obtained with a specific electrode-flux combination as given in 4.1A and 4.1B. A solid wire electrode shall be classified in accordance with its chemical composition in Table 3.

A tubular cored electrode shall be classified in accordance with the all-weld metal deposit composition in Table 4, obtained with a specific flux.

When the solid wire electrode or tubular cored electrode is classified in combination with a flux for submerged arc welding, the classification shall be prefixed with a symbol in accordance with Clause 5 as appropriate.