



**SLOVENSKI STANDARD**  
**oSIST ISO 11475:2018**  
**01-september-2018**

---

**Papir, karton in lepenka - Določanje beline po CIE, D65/10° (zunanja dnevna svetloba)**

Paper and board -- Determination of CIE whiteness, D65/10 degrees (outdoor daylight)

Papier et carton -- Détermination du degré de blanc CIE, D65/10 degrés (lumière du jour extérieure)

**Ta slovenski standard je istoveten z:      ISO 11475:2017**

---

**ICS:**

85.060              Papir, karton in lepenka              Paper and board

**oSIST ISO 11475:2018**

**en,fr,de**



INTERNATIONAL  
STANDARD

ISO  
11475

Third edition  
2017-05

---

---

**Paper and board — Determination  
of CIE whiteness, D65/10° (outdoor  
daylight)**

*Papier et carton — Détermination du degré de blanc CIE, D65/10°  
(lumière du jour extérieure)*



Reference number  
ISO 11475:2017(E)

© ISO 2017



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

	Page
Foreword .....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>3</b>
<b>5 Apparatus and equipment</b> .....	<b>3</b>
<b>6 Calibration</b> .....	<b>4</b>
<b>7 Sampling</b> .....	<b>5</b>
<b>8 Preparation of test pieces</b> .....	<b>5</b>
<b>9 Procedure</b> .....	<b>5</b>
<b>10 Calculation and expression of results</b> .....	<b>6</b>
<b>11 Precision</b> .....	<b>7</b>
<b>12 Test report</b> .....	<b>7</b>
<b>Annex A (normative) Spectral characteristics of reflectometers for determining tristimulus values</b> .....	<b>8</b>
<b>Annex B (normative) UV calibration service</b> .....	<b>13</b>
<b>Annex C (informative) Precision</b> .....	<b>15</b>
<b>Bibliography</b> .....	<b>16</b>

## ISO 11475:2017(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 11475:2004), which has been technically revised. The major change is to allow for calculations to use ASTM E308 for instruments that have bandpass correction and still maintain the non-bandpass-correction procedure. This third edition also includes Precision Data.

# Paper and board — Determination of CIE whiteness, D65/10° (outdoor daylight)

## 1 Scope

This document specifies the procedure to be used for determining the whiteness of papers and boards. The values obtained correspond to the visual appearance of white papers and boards with or without fluorescent whitening agents when they are viewed under the CIE D65 daylight standard illuminant. It is based on reflectance data obtained over the full visible spectral range (VIS) in contrast to the measurement of ISO brightness which is limited to the blue region of VIS.

In addition, it specifies a method for adjustment of the UV content to correspond to the CIE D65 daylight illuminant<sup>[10][11]</sup>, insofar as results obtained when fluorescent whitening agents are present are dependent upon the UV content of the radiation falling upon the sample. It is specific for white fluorescent paper samples where the emission due to the fluorescent whitening agent (FWA) occurs in the blue region of the visible spectrum.

This method is not applicable to coloured papers containing fluorescent dyes.

This document should be read in conjunction with ISO 2469.

NOTE 1 This document is based on the CIE whiteness formula, published in CIE 15.3-2004<sup>[9]</sup>.

NOTE 2 A related International Standard, ISO 11476, specifying the procedure for obtaining values corresponding to the appearance of these products under indoor illumination, has also been published.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 2469:2014, *Paper, board and pulps — Measurement of diffuse radiance factor (diffuse reflectance factor)*

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

NOTE The symbols used here are selected to maintain consistency, wherever possible, with Reference <sup>[8]</sup>.

## ISO 11475:2017(E)

### 3.1 reflectance factor

$R$

ratio of the radiation reflected by a body to that reflected by the perfect reflecting diffuser under the same conditions

Note 1 to entry: The ratio is expressed as a percentage.

### 3.2 intrinsic reflectance factor

$R_{\infty}$

*reflectance factor* (3.1) of a layer or pad of the material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured reflectance factor

### 3.3 diffuse radiance factor

$\beta$

ratio of the diffusely reflected radiance of a body in a given direction to that of the perfect reflecting diffuser under specified conditions of irradiation

Note 1 to entry: For fluorescent (luminescent) materials, the specified conditions of irradiation in this document are for CIE Standard Illuminant D65 and the diffuse radiance factor is strictly the total radiance factor,  $\beta$ , which contains two components, the reflected radiance factor,  $\beta_R$ , and the luminescent radiance factor,  $\beta_L$ , so that

$$\beta = \beta_R + \beta_L$$

Note 2 to entry: For non-fluorescent materials, the diffuse radiance factor,  $\beta$ , is simply the *reflectance factor*,  $R$  (3.1).

### 3.4 intrinsic diffuse radiance factor

$\beta_{\infty}$

*diffuse radiance factor* (3.3) of a layer or pad of the material thick enough to be opaque, i.e. such that increasing the thickness of the pad by doubling the number of sheets results in no change in the measured diffuse radiance factor

Note 1 to entry: For fluorescent (luminescent) materials, the intrinsic diffuse radiance factor is, strictly speaking, the total intrinsic radiance factor,  $\beta_{\infty}$ , which contains two components: the intrinsic reflected radiance factor,  $\beta_{\infty,R}$ , and the intrinsic luminescent radiance factor,  $\beta_{\infty,L}$ , so that

$$\beta_{\infty} = \beta_{\infty,R} + \beta_{\infty,L}$$

Note 2 to entry: For non-fluorescent materials, the intrinsic diffuse radiance factor,  $\beta_R$ , is simply the *intrinsic reflectance factor*,  $R_{\infty}$  (3.2).

### 3.5 CIE whiteness value

$W_{10}$

measure of whiteness derived from the CIE tristimulus values

Note 1 to entry: CIE whiteness is dimensionless and is expressed as whiteness units.

### 3.6 green tint value red tint value

$T_{W10}$

measure of the deviation from whiteness of the test material towards the green or red region

Note 1 to entry: The tint value is dimensionless and is expressed as tint units.

Note 2 to entry: A positive value of  $T_{W10}$  indicates a greenish tint and a negative value indicates a reddish tint.