
**Fibre-reinforced polymer (FRP)
reinforcement of concrete — Test
methods —**

**Part 1:
FRP bars and grids**

iTeh STANDARD PREVIEW
(standards.iteh.ai)
*Polymère renforcé par des fibres (PRF) pour l'armature du béton —
Méthodes d'essai —
Partie 1: Barres et grilles en PRF*

[ISO 10406-1:2015](https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015)

<https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015>



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 10406-1:2015

<https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2015

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms, definitions, and symbols	1
3.1 Terms and definitions.....	1
3.2 Symbols.....	5
4 General provision concerning test pieces	6
5 Test method for cross-sectional properties	6
5.1 Test pieces.....	6
5.2 Test method.....	6
5.3 Calculations.....	7
5.4 Test report.....	8
6 Test method for tensile properties	8
6.1 Test pieces.....	8
6.2 Test equipment.....	9
6.3 Test method.....	9
6.4 Calculations.....	9
6.5 Test report.....	11
7 Test method for bond strength by pull-out testing	13
7.1 Test pieces.....	13
7.2 Testing machine and devices.....	15
7.3 Test method.....	16
7.4 Calculations.....	17
7.5 Test report.....	17
8 Test method for performance of anchorages and couplers	18
8.1 Test method for performance of anchorages.....	18
8.2 Test method for performance of couplers.....	19
8.3 Test report.....	19
9 Test method for long-term relaxation	20
9.1 Test pieces.....	20
9.2 Testing frame and devices.....	21
9.3 Test temperature.....	21
9.4 Test method.....	22
9.5 Calculations.....	22
9.6 Test report.....	23
10 Test method for tensile fatigue	23
10.1 Test pieces.....	23
10.2 Testing machine and devices.....	23
10.3 Test temperature.....	24
10.4 Test method.....	24
10.5 Calculations.....	25
10.6 Test report.....	25
11 Test method for alkali resistance	25
11.1 Test pieces.....	25
11.2 Immersion in alkaline solution.....	26
11.3 External appearance and mass change.....	26
11.4 Tensile test.....	27
11.5 Calculations.....	27
11.6 Test report.....	28
12 Test method for creep failure	29

ISO 10406-1:2015(E)

12.1	Test pieces.....	29
12.2	Testing frame and devices.....	29
12.3	Test temperature.....	29
12.4	Tensile capacity.....	29
12.5	Test method.....	29
12.6	Calculations.....	30
12.7	Test report.....	30
13	Test method for transverse shear strength.....	31
13.1	Test pieces.....	31
13.2	Testing machine and devices.....	31
13.3	Test temperature.....	32
13.4	Test method.....	33
13.5	Calculations.....	33
13.6	Test report.....	33
14	Test method for flexural tensile properties.....	34
14.1	Test pieces.....	34
14.2	Testing unit and devices.....	34
14.3	Test method.....	35
14.4	Calculations.....	35
14.5	Test report.....	35
15	Test method for the coefficient of longitudinal thermal expansion by thermo- mechanical analysis.....	36
15.1	Test pieces.....	36
15.2	Testing device.....	37
15.3	Test method.....	37
15.4	Calculations.....	38
15.5	Test report.....	38

ISO 10406-1:2015
<https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015>

ITeH STANDARD PREVIEW
(standards.iteh.ai)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT), see the following URL: Foreword — Supplementary information.

The committee responsible for this document is ISO/TC 71, *Concrete, reinforced concrete and pre-stressed concrete*, Subcommittee SC 6, *Non-traditional reinforcing materials for concrete structures*.

This second edition ~~cancels and replaces the first edition (ISO 10406-1:2008)~~, which has been technically revised.

ISO 10406 consists of the following parts, under the general title *Fibre-reinforced polymer (FRP) reinforcement of concrete — Test methods*:

- *Part 1: FRP bars and grids*
- *Part 2: FRP sheets*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 10406-1:2015

<https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015>

Fibre-reinforced polymer (FRP) reinforcement of concrete — Test methods —

Part 1: FRP bars and grids

1 Scope

This part of ISO 10406 specifies test methods applicable to fibre-reinforced polymer (FRP) bars and grids as reinforcements or pre-stressing tendons in concrete.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291:2008, *Plastics — Standard atmospheres for conditioning and testing*

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

ISO 4788, *Laboratory glassware — Graduated measuring cylinders*

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 13385-1, *Geometrical product specifications (GPS) — Dimensional measuring equipment — Part 1: Callipers; Design and metrological characteristics*

3 Terms, definitions, and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1

alkalinity

condition of having or containing hydroxyl (OH⁻) ions; containing alkaline substances

Note 1 to entry: In concrete, the initial alkaline environment has a pH above 13.

3.1.2

anchorage reinforcement

lattice or spiral reinforcing steel or FRP connected with the anchorage and arranged behind it

3.1.3

anchoring section

end part of a test piece where an anchorage is fitted to transmit loads from the testing machine to the test section

3.1.4

average load

<stress> average of the maximum and minimum repeated load (stress)

3.1.5

bending angle

angle formed by the straight sections of a test piece on either side of the deflector

3.1.6

bending diameter ratio

ratio of the external diameter of the deflector surface in contact with the FRP bar, and the nominal diameter of the FRP bar

3.1.7

bending tensile capacity

tensile load at the moment of failure of the test piece

3.1.8

coefficient of thermal expansion

average coefficient of linear thermal expansion between given temperatures

Note 1 to entry: The average of the given temperatures is taken as the representative temperature.

3.1.9

continuous fibre

general term for continuous fibres of materials such as carbon, aramid, and glass

3.1.10

coupler

device coupling tendons

3.1.11

creep failure capacity

load causing failure after a specified period of time from the start of a sustained load

Note 1 to entry: In particular, the load causing failure after 1 million hours is referred to as the million-hour creep failure capacity.

3.1.12

creep failure strength

stress causing failure after a specified period of time from the start of a sustained load

Note 1 to entry: In particular, the load causing failure after 1 million hours is referred to as the million-hour creep failure strength.

3.1.13

creep failure time

time between the start of a sustained load and failure of a test piece

3.1.14

creep failure

failure occurring in a test piece due to a sustained load

3.1.15

creep strain

differential change in length per unit length occurring in a test piece due to creep

3.1.16

creep

time-dependent deformation of an FRP bar subjected to a sustained load at a constant temperature

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 10406-1:2015](https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015)

<https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015>

3.1.17**deflected section**

section of an FRP bar that is bent and maintained at the required bending angle and bending diameter ratio

3.1.18**deflector**

device used to maintain the position, alter the bending angle, or alleviate the stress concentrations in the FRP bar and which is sometimes installed in the deflected section

3.1.19**fatigue strength**

maximum repeated stress at which the test piece does not fail at the prescribed number of cycles

3.1.20**fibre-reinforced polymer****FRP**

composite material, moulded and hardened to the intended shape, consisting of continuous fibres impregnated with a fibre-binding polymer

3.1.21**frequency**

number of loading (stressing) cycles in 1 s during the test

3.1.22**FRP bar**

composite material formed into a long, slender structural shape suitable for use as reinforcement in concrete and consisting primarily of longitudinal unidirectional fibres bound and shaped by a rigid polymer resin material

3.1.23**gauge length**

straight portion along the length of a test piece used to measure the elongation using an extensometer or a similar device

3.1.24**grid**

two-dimensional (planar) or three-dimensional (spatial) rigid array of interconnected FRP bars that form a continuous lattice that can be used to reinforce concrete

3.1.25**load amplitude****load (stress) amplitude**

one-half of the load (stress) range

3.1.26**load (stress) range**

difference between maximum and minimum repeated load (stress)

3.1.27**maximum repeated load (stress)**

maximum load (stress) during repeated loading

3.1.28**maximum tensile force**

maximum tensile load sustained by a test piece during the tensile test

3.1.29**minimum repeated load (stress)**

minimum load (stress) during repeated loading

3.1.30

nominal cross-sectional area

value obtained upon dividing the volume of the FRP specimen by its length

3.1.31

nominal diameter

diameter of FRP calculated assuming a circular section

3.1.32

nominal peripheral length

peripheral length of the FRP that forms the basis for calculating the bond strength and that shall be determined separately for each FRP

3.1.33

number of cycles

number of times the repeated load (stress) is applied to the test piece

3.1.34

relaxation

stress relaxation

time-dependent decrease in load in an FRP held at a given constant temperature with a prescribed initial load applied and held at a given constant strain

3.1.35

relaxation rate

percentage reduction in load relative to the initial load after a given period of time, under a fixed strain

Note 1 to entry: In particular, the relaxation value after 1 million hours (approximately 114 years) is referred to as the hundred-year relaxation rate.

3.1.36

repeated load (stress)

load (stress) alternating cyclically between fixed maximum and minimum values

3.1.37

S-N curve

curve plotted on a graph with repeated stress on the vertical axis and the number of cycles to fatigue failure on the horizontal axis

3.1.38

tendon

FRP

resin-bound construction made of continuous fibres in the shape of a tendon used to reinforce concrete uniaxially

Note 1 to entry: Tendons are usually used in pre-stressed concrete.

3.1.39

thermo-mechanical analysis

TMA

method for measuring deformation of a material as a function of either temperature or time, by varying the temperature of the material according to a calibrated programme, under a non-vibrating load

3.1.40

TMA curve

<TMA> graph with temperature or time represented on the horizontal axis and deformation on the vertical axis

3.1.41

ultimate strain

strain corresponding to the maximum tensile force

3.2 Symbols

See [Table 1](#).

Table 1 — Symbols

Symbol	Unit	Description	Reference
A	mm ²	Nominal cross-sectional area of test piece	5.3 , 6.4
D	mm	Nominal diameter	5.3
E	N/mm ²	Young's modulus	6.4
F_u	N	Maximum tensile force	6.4
f_u	N/mm ²	Tensile strength	6.4
ϵ_u	—	Ultimate strain	6.4
ΔF	N	Difference between loads at 20 % and 50 % of maximum tensile force	6.4
$\Delta \epsilon$	—	Strain difference between ΔF	6.4
τ	N/mm ²	Bond stress	7.4
P	N	Tensile load in the pull-out test	7.4
u	mm	Nominal peripheral length of test piece	7.4
l	mm	Bonded length	7.4
Y	%	Relaxation rate	9.5.2
t	h	Time	9.5.2
k_a	—	Empirical constant	9.5.2
k_b	—	Empirical constant	9.5.2
$R_{\Delta m}$	%	Mass loss ratio	
V_o	mm ³	Volume of water in the measuring cylinder	5.3
V_s	mm ³	Volume of the sum total of water and test piece	5.3
l_o	mm	Length of test piece	5.3
m_0	g	Mass before immersion	11.4
L_0	mm	Length before immersion	11.4
m_1	g	Mass after immersion	11.4
L_1	mm	Length after immersion	11.4
R_{et}	%	Tensile capacity retention rate	11.5.2
F_{u1}	N	Tensile capacity before immersion	11.5.2
F_{u0}	N	Tensile capacity after immersion	11.5.2
R_{Yc}	—	Creep load ratio	12.6.3
τ_s	N/mm ²	Shear stress	13.5.2
P_s	N	Shear failure load	13.5.2
α_{sp}	1/°C	Coefficient of thermal expansion	15.4.1
ΔL_{spm}	μ	Difference in length of test piece between temperatures T_1 and T_2	15.4.1
ΔL_{refm}	μ	Difference in length of specification test piece for length calibration between temperatures T_1 and T_2	15.4.1
L_0	m	Length of test piece at room temperature	15.4.1

Table 1 (continued)

Symbol	Unit	Description	Reference
T_2	°C	Maximum temperature for calculation of coefficient of thermal expansion (normally 60 °C)	15.4.1
T_1	°C	Minimum temperature for calculation of coefficient of thermal expansion (normally 0 °C)	15.4.1
α_{set}	1/°C	Coefficient of thermal expansion calculated for specification test piece for length calibration between temperatures T_1 and T_2	15.4.1

4 General provision concerning test pieces

Unless otherwise agreed, test pieces shall be taken from the bar or grid in the “as-delivered” condition.

In cases where test pieces are taken from a coil, they shall be straightened prior to any test by a simple bending operation with a minimum amount of plastic deformation.

For the determination of the mechanical properties in the tensile, bond, and anchorage tests, the test piece may be artificially aged (after straightening, if applicable) depending on the performance requirements of the product.

When a test piece is “aged”, the conditions of the ageing treatment shall be stated in the test report.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5 Test method for cross-sectional properties

5.1 Test pieces

[ISO 10406-1:2015](#)

<https://standards.iteh.ai/catalog/standards/sist/a5ab4d09-d264-4850-9de0-3faeb33236ad/iso-10406-1-2015>

5.1.1 Preparation of test pieces

Test pieces shall be cut to a predetermined length and finished flat at their cut end from the mother material (FRP) for tensile test.

5.1.2 Length of test pieces

The length of test pieces shall be 100 mm when approximate nominal diameter is 20 mm or less, and shall be 200 mm when approximate diameter is over 20 mm.

5.1.3 Number of test pieces

The number of test pieces is at least three, taken from the mother material of the same lot.

5.2 Test method

The test procedure is as follows.

- a) Measure the length of the test piece using the vernier callipers in accordance with ISO 13385-1. Measure a part and record the result to three places; round off the three averaged values to one place after the decimal point. Take this as the length of the test piece.
- b) Measure the volume of the test piece using a measuring cylinder in accordance with ISO 4788:2005, type 1a or 1b (class A or class B), according to the approximate diameter of the test piece. [Table 2](#) shows the relationship between the approximate diameter of the test piece and the capacity of the measuring cylinder. When two capacities are listed, choose the smaller-capacity cylinder for that range.

- c) Add the proper quantity of water to the measuring cylinder and measure the volume. When the test piece is in the measuring cylinder, the water should cover the test piece and the top of the water shall be in the range of scale.

NOTE If air bubbles are generated on the surface of the test piece, which can cause an error of measurement, a surface-tension-reducing solvent, such as ethanol, can be added to the water for the purpose of controlling the generation of air bubbles.

- d) Insert the test piece into the measuring cylinder and measure the volume of the combined water and the test piece.
- e) The test temperature shall be within the range of 15 °C to 25 °C. The temperature range of 20 °C to 30 °C is applicable for warm countries.

Table 2 — Relationship between the approximate diameter of test piece and the capacity of measuring cylinder

Approximate diameter of test piece mm	Capacity of measuring cylinder ml
under 10	10 or 20
11 to 13	25
14 to 20	50 or 100
21 to 25	100
over 25	300 or 500

iTeh STANDARD PREVIEW
(standards.iteh.ai)

5.3 Calculations

Calculate the nominal cross-sectional area, A , of the test piece from Formula (1) and round off to one place after the decimal point:

$$A = \frac{V_s - V_o}{l_o} \quad (1)$$

where

V_s is the volume of the sum total of water and test piece, expressed in cubic millimetres;

V_o is the volume of water in the measuring cylinder, expressed in cubic millimetres;

l_o is the length of the test piece, expressed in millimetres.

NOTE The nominal cross-sectional area includes the area of surface-bonded sand particles, surface-bonded transverse wraps, and other non-load-bearing areas.

Calculate the nominal diameter, D , from Formula (2) and round off to one place after the decimal point:

$$D = 2\sqrt{\frac{A}{\pi}} \quad (2)$$

where

A is the nominal cross-sectional area, expressed in square millimetres.