INTERNATIONAL STANDARD



First edition 2017-03

Thermal spraying — Powders —

Part 1: Characterization and technical supply conditions

Projection thermique — Poudres —

iTeh STPartie Dearacterisitation et conditions techniques de livraison (standards.iteh.ai)

ISO 14232-1:2017 https://standards.iteh.ai/catalog/standards/sist/cebabf9f-bb76-43b0-90c8-7cf3ceb5f287/iso-14232-1-2017



Reference number ISO 14232-1:2017(E)

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14232-1:2017 https://standards.iteh.ai/catalog/standards/sist/cebabf9f-bb76-43b0-90c8-7cf3ceb5f287/iso-14232-1-2017



© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Page

Contents

Fore	eword	iv				
Intr	roduction	v				
1 Scope						
2	2 Normative references					
3	3 Terms and definitions					
4	Properties and property determination of powders for thermal spraying4.1Sampling and sample splitting4.2Chemical composition4.3Particle size range — Particle size distribution4.4Manufacturing process — Particle shape4.5Apparent density4.6Flowability4.7Microstructure4.8Determination and composition of phases4.9Summary	1 1 2 2 3 3 3 3 3 4 4 4 4 4				
5	Classification of powders					
6	Powder identification and designation					
7 8	Conditions of supply STANDARD PREVIEW 4 Certificate 5					
Ann	ex A (informative) Powder shape and morphologies	6				
Bibl	liography	9				

7cf3ceb5f287/iso-14232-1-2017

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html. (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

This first edition of ISO 14282-1/stogether with ISO/TRI 14232-2) cancels/and replaces ISO 14232:2000. 7cf3ceb5f287/iso-14232-1-2017

A list of all parts in the ISO 14232 series can be found on the ISO website.

Introduction

For thermal spray processes that use material in a powder form, the powder can be considered as one of the main elements requiring control to produce an acceptable coating. The chemical and physical properties of powder play a fundamental role in the creation of desired coating properties. The size, shape and morphology of the powder particles determine the melting behaviour and therefore the processing of powders in general.

To keep the coating properties and the spray process as consistent as possible, it is very important to maintain all the characteristics of powder particles within limited tolerances.

An exception is granted to details on the properties of sprayed coatings. Such properties, which result from spraying conditions not covered by this document, e.g. gas composition, deposition efficiency, material flow rate, stand-off distance, etc., can differ greatly from the properties of the original powder.

The ISO 14232 series consists of two parts. This document examines the characterization of spray powders. ISO/TR 14232-2 is a technical report that examines how technical literature describes the application of powders.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14232-1:2017 https://standards.iteh.ai/catalog/standards/sist/cebabf9f-bb76-43b0-90c8-7cf3ceb5f287/iso-14232-1-2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14232-1:2017 https://standards.iteh.ai/catalog/standards/sist/cebabf9f-bb76-43b0-90c8-7cf3ceb5f287/iso-14232-1-2017

Thermal spraying — Powders —

Part 1: Characterization and technical supply conditions

1 Scope

This document specifies measuring methods for the characterization of powders and their technical supply conditions. It is applicable to powders that are used in thermal spraying on the basis of their physical and chemical properties.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3923-2, Metallic powders — Determination of apparent density — Part 2: Scott volumeter method ISO 3954, Powders for powder metallurgical purposes — Sampling

ISO 4490, Metallic powders — Determination of flow rate by means of a calibrated funnel (Hall flowmeter)

ISO 10474, Steel and steel products - Inspection documents

https://standards.iteh.ai/catalog/standards/sist/cebabf9f-bb76-43b0-90c8-

7cf3ceb5f287/iso-14232-1-2017 **Terms and definitions**

For the purposes of this document, the terms and definitions given in ISO 14917 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

IEC Electropedia: available at <u>http://www.electropedia.org/</u>

ISO Online browsing platform: available at http://www.iso.org/obp

3.1

3

particle size distribution

PSD

distribution of particle sizes in percentage within standard ranges

```
3.2
```

particle size range

range of particle sizes between an upper and lower limit

Properties and property determination of powders for thermal spraying 4

4.1 Sampling and sample splitting

Sampling and sample splitting is to be done from a homogeneous mixture uniform in particle size. Directions for adequate methods and equipment shall be as included in ISO 3954.

4.2 Chemical composition

The chemical composition shall be defined by any suitable testing procedure, e.g. ICP-OES (inductively coupled plasma optical emission spectrometry), wet chemical processes, atomic absorption spectrometry, flame emission spectroscopy, X-ray fluorescent analysis and energy dispersive X-ray spectroscopy (EDX).

4.3 Particle size range — Particle size distribution

Powders for thermal spraying always show a distribution of different particle sizes. This particle size distribution (PSD) has an immense influence on the melting and the feedability of the powder and thus, among other things, essential properties of the coating are assigned. The measuring of the PSD shall be made by sieve analysis, air-jet sieving, etc. or by optical measuring methods like laser scattering because of its high accuracy and reproducibility.

Particle size ranges are documented in specifications by upper and lower size limits like "(125 $\mu m/5\,\mu m)$ ".

Usually, the results of different measuring procedures and also measuring devices do not coincide, even when identical powders are used. Therefore, when comparing particle size distributions or when changing the particle size measuring procedure, a correlation of the measurement results is necessary. Therefore, it is essential to always indicate the measuring procedure together with the measurement results. Coarse powders (125 μ m/38 μ m) can be characterized by sieving methods, while for fine powders (45 μ m/5 μ m), laser scattering is more suitable.

Sizing methods used for spray powder characterization are restricted in their accuracy dependent on the absolute size of powders. The following limitations for oversized and undersized particles are common in the industry:

— Upper size limit (range from 125 μm to 15 μm):<u>14232-1:2017</u>

https://standards.iteh.ai/catalog/standards/sist/cebabf9f-bb76-43b0-90c8-Sieving method (used for size range 125 μ m to 38 μ m): max. 10 % coarser than the indicated upper limit, see footnote a in Table 1;

Sieving method "air-jet" (used for size range 45 μ m to 5 μ m): max. 5 % coarser than the upper size limit, see footnote ^a in <u>Table 1</u>;

Laser scattering: (used for size range 63 μ m to 15 μ m): max. 25 % coarser than the upper size limit, see footnote ^b in Table 1;

- Lower size limit (range 90 μ m to 5 μ m):

Sieving method (used for size range 90 μm to 38 μm): max. 10 % undersized particles, see footnote ^a in Table 1;

Sieving method "air-jet" (used for size range 38 μ m to 5 μ m): max. 10 % undersized particles, see footnote c in <u>Table 1</u>;

Laser scattering (used for size range 53 μm to 5 μm): max. 5 % undersized particles, see footnote c in Table 1.

EXAMPLE Size designation $63/38 \ \mu m$; Means: If measured by sieving: max. 10 % coarser than 63 μm and max. 10 % finer than 38 μm ; 0 % coarser than 90 μm and max. 1 % finer than 30 μm . "Air-jet" is usually not used for this size range. If measured by laser scattering: max. 25 % coarser than 63 μm and max. 5 % coarser than 90 μm ; max. 1 % finer than 30 μm . For further clarification, see the given examples in Table 1.

Measuring	Upper size limit		Remarks	Lower size limit	
method	(range 125 µm to 15 µm)			(range 90 µm to 5 µm)	
	Particle size range	Coarser than the in- dicated upper limit	Coarser at next but one higher standard screen	Particle size range	Undersized particles ^c
Sieving method	125 μm to 38 μm	max. 10 % ^a	coarsest particles 0 %	90 μm to 38 μm	max. 10 %
Sieving method "air-jet"	45 μm to 5 μm	max. 5 % ^a	coarsest particles 0 %	$38\mu m$ to $5\mu m$	max. 10 %
Laser scatter- ing	63 μm to 15 μm	max. 25 % ^b	max. 5 %	53 μm to 5 μm	max. 5 %

Table 1 — Particle size range

^a Coarsest particles 0 % at next but one higher nominal size of (sieve/subsieve) opening.

^b Max. 5 % coarser at next but one higher nominal size of (sieve/subsieve) opening.

^c Finest particles max. 1 % at next but one lower nominal size of (sieve/subsieve) opening. Nominal sizes of (sieve/subsieve) openings are: 5 μm, 10 μm, 16 μm, 20 μm, 25 μm, 32 μm, 38 μm, 45 μm, 53 μm, 63 μm, 75 μm, 90 μm, 106 μm, 125 μm, 150 μm, 180 μm.

It should be noted, when evaluating powders for HVOF (high-velocity oxygen fuel), special attention should be paid to fine particles (dust) because of their effect on the feeding and melting properties of the powder. Further, these fine dust particles can clog the spray nozzle and so stop the whole coating process. This, however, often leads to increased manufacturing costs of powder. These additional requirements in the measuring and the description of the measured values can exceed the minimum requirements of this document and shall be stipulated between the powder supplier and the user in the technical delivery conditions.

(standards.iteh.ai)

4.4 Manufacturing process — Particle shape

ISO 14232-1:2017 The manufacturing process of powder shall be indicated using a term such as fusing (f), sintering (s), agglomeration (ag), gas or water atomization (gat; 2wat), coating (c), spheroidization (sp), blending (bld). The particle shape and its surface can be illustrated by means of scanning electron or stereo microscopy. In order to check for similarity, the images can be compared to reference samples provided by the manufacturer.

Example figures are included in <u>Annex A</u>.

4.5 Apparent density

Apparent powder density shall be determined as specified in ISO 3923-2, and to be expressed as g/cm³.

Alternatively, ASTM-B 329, ASTM-B 417 and ASTM-B 212 can be used to analyse the apparent density.

4.6 Flowability

The determination of the flowability of free-flowing powders shall be according to ISO 4490 and expressed as s/50 g. Fine powders with a low specific weight are often not able to flow and it is not possible to determine the flowability in these cases.

Alternatively, ASTM-B 213 can be used to analyse flowability. For blends containing organic powder materials, specific flowability measurement methods are applied. These methods shall be documented in the certificate.

The results of the measurements of apparent density and flowability are determined by several properties of the material; for example, specific weight, shape and structure of the powder particle and size distribution. Corresponding measured values and tolerances are to be stipulated between the supplier and the user if these characteristics of the powder shall be stated in the technical delivery conditions.