

# SLOVENSKI STANDARD

## SIST EN 13110:2012+A1:2017

01-maj-2017

Nadomešča:  
SIST EN 13110:2012

---

**Oprema in pribor za utekočinjeni naftni plin (UNP) - Premične ponovno polnljive varjene jeklenke iz aluminija za UNP - Konstruiranje in izdelava (vključno z dopolnilom A1)**

LPG equipment and accessories - Transportable refillable welded aluminium cylinders for liquefied petroleum gas (LPG) - Design and construction

**iTeh STANDARD PREVIEW**

Flüssiggas-Geräte und Ausrüstungsteile - Ortsbewegliche wiederbefüllbare geschweißte Flaschen aus Aluminium für Flüssiggas (LPG) - Auslegung und Bau

[SIST EN 13110:2012+A1:2017](#)

Equipements pour gaz de pétrole liquéfiés et leurs accessoires - Bouteilles soudées transportables et rechargeables en aluminium pour gaz de pétrole liquéfié (GPL) - Conception et construction

**Ta slovenski standard je istoveten z: EN 13110:2012+A1:2017**

---

**ICS:**

23.020.35	Plinske jeklenke	Gas cylinders
77.150.10	Aluminijski izdelki	Aluminium products

**SIST EN 13110:2012+A1:2017** en

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 13110:2012+A1:2017](https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9f4f-7a290f84af59/sist-en-13110-2012a1-2017)

<https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9f4f-7a290f84af59/sist-en-13110-2012a1-2017>

EUROPEAN STANDARD

EN 13110:2012+A1

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2017

ICS 23.020.30

English Version

## LPG equipment and accessories - Transportable refillable welded aluminium cylinders for liquefied petroleum gas (LPG) - Design and construction

Equipements pour gaz de pétrole liquéfiés et leurs accessoires - Bouteilles soudées transportables et rechargeables en aluminium pour gaz de pétrole liquéfié (GPL) - Conception et construction

Flüssiggas-Geräte und Ausrüstungsteile - Ortsbewegliche wiederbefüllbare geschweißte Flaschen aus Aluminium für Flüssiggas (LPG) - Auslegung und Bau

This European Standard was approved by CEN on 13 April 2012 and includes Amendment 1 approved by CEN on 3 January 2017.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
European foreword.....	5
Introduction .....	5
<b>1 Scope</b> .....	<b>7</b>
<b>2 Normative references</b> .....	<b>7</b>
<b>3 Terms, definitions and symbols</b> .....	<b>8</b>
<b>3.1 Terms and definitions</b> .....	<b>8</b>
<b>3.2 Symbols</b> .....	<b>9</b>
<b>4 Materials</b> .....	<b>9</b>
<b>5 Design</b> .....	<b>11</b>
<b>5.1 General requirements</b> .....	<b>11</b>
<b>5.2 Calculation of cylindrical wall thickness</b> .....	<b>11</b>
<b>5.3 Design of ends concave to pressure</b> .....	<b>11</b>
<b>5.4 Other shapes of ends</b> .....	<b>12</b>
<b>5.5 Minimum wall thickness</b> .....	<b>12</b>
<b>5.6 Design of openings</b> .....	<b>12</b>
<b>5.7 Neck design</b> .....	<b>13</b>
<b>5.8 Stability</b> .....	<b>17</b>
<b>5.9 Valve protection</b> .....	<b>17</b>
<b>6 Construction and workmanship</b> .....	<b>17</b>
<b>6.1 Environment</b> .....	<b>17</b>
<b>6.2 Welding qualification</b> .....	<b>17</b>
<b>6.3 Plates and pressed parts</b> .....	<b>18</b>
<b>6.4 Welded joints</b> .....	<b>18</b>
<b>6.5 Tolerances</b> .....	<b>18</b>
<b>6.6 Non-pressure bearing attachments</b> .....	<b>18</b>
<b>6.7 Heat treatment</b> .....	<b>19</b>
<b>6.8 Closure of openings</b> .....	<b>19</b>
<b>7 Testing and examination</b> .....	<b>20</b>
<b>7.1 General</b> .....	<b>20</b>
<b>7.2 Types of test and evaluation of test results</b> .....	<b>20</b>
<b>7.3 Test specimens and related tests and examinations</b> .....	<b>21</b>
<b>7.3.1 Two piece cylinders</b> .....	<b>21</b>
<b>7.3.2 Three piece cylinders</b> .....	<b>21</b>
<b>7.3.3 Valve boss welds</b> .....	<b>21</b>
<b>7.4 Tensile test</b> .....	<b>23</b>
<b>7.4.1 General</b> .....	<b>23</b>
<b>7.4.2 Parent material</b> .....	<b>23</b>
<b>7.4.3 Welds</b> .....	<b>23</b>
<b>7.5 Bend test</b> .....	<b>23</b>
<b>7.5.1 Bend test on parent material</b> .....	<b>23</b>
<b>7.5.2 Bend test across the welds</b> .....	<b>24</b>
<b>7.5.3 Nick-break test across the welds</b> .....	<b>24</b>
<b>7.6 Macroscopic examination of welds</b> .....	<b>26</b>

7.6.1	Procedure .....	26
7.6.2	Requirements .....	26
7.7	Burst test under hydraulic pressure .....	27
7.7.1	Procedure .....	27
7.7.2	Requirements .....	28
7.8	Fatigue test .....	28
7.8.1	Procedure .....	28
7.8.2	Requirements .....	29
7.9	Drop test .....	29
7.9.1	Procedure .....	29
7.9.2	Requirements .....	29
7.10	Visual examination .....	29
7.10.1	Procedure .....	29
7.10.2	Requirements .....	29
7.11	Radiographic examination .....	30
7.11.1	Procedure .....	30
7.11.2	Assessment .....	30
7.11.3	Requirements .....	30
7.12	Pressure test .....	30
7.12.1	Procedure .....	30
7.12.2	Requirements .....	30
8	Technical requirements for type approval .....	32
8.1	New cylinder design .....	32
8.2	Extent of testing .....	32
8.3	Type approval certificate .....	33
9	Production testing and examination requirements .....	33
9.1	Tests and examinations applicable to all cylinders .....	33
9.2	Radiographic examination .....	34
9.3	Macro examination .....	34
9.4	Examination of valve boss weld .....	34
9.5	Examination of non-pressure containing attachment welds .....	34
9.6	Unacceptable imperfections found by radiographic or macro examinations .....	34
9.7	Production batch testing (mechanical/burst tests) .....	35
9.7.1	Production batch .....	35
9.7.2	Inspection lots .....	36
9.7.3	Rate of sampling .....	36
9.7.4	Additional checks .....	36
9.8	Failure to meet mechanical and burst test requirements .....	37
9.8.1	Mechanical .....	37
9.8.2	Burst .....	37
9.8.3	Production batch retest .....	37
9.8.4	Resubmission of a production batch .....	37
9.8.5	Weld repairs .....	38
10	Marking .....	38
11	Certificate of Conformity .....	38
Annex A (normative)	Corrosion tests .....	39
A.1	Test for assessing susceptibility to intercrystalline corrosion .....	39
A.1.1	Specimens .....	39
A.1.2	Pre-treatment of the specimen before corrosive etching .....	39

## EN 13110:2012+A1:2017 (E)

A.1.2.1 Chemicals required .....	39
A.1.2.2 Method .....	39
A.1.3 Corrosive etching process .....	40
A.1.3.1 Chemicals required .....	40
A.1.3.2 Method .....	40
A.1.4 Preparation of specimens for examination .....	41
A.1.4.1 Method .....	41
A.1.5 Micrographic examination of specimens.....	41
A.1.6 Interpretation of the micrographic examination.....	41
A.2 Tests for assessing susceptibility to stress corrosion.....	41
A.2.1 Specimens .....	41
A.2.2 Surface preparation before test.....	41
A.2.3 Method .....	42
A.2.3.1 Preparation of the corrosive solution .....	42
A.2.3.2 Applying the stress to the specimen.....	44
A.2.4 Interpretation of the results .....	46
A.2.5 Metallographical examination (additional examination).....	46
A.3 Conclusion of corrosion tests.....	46
A.4 Test report.....	46
Bibliography.....	48

iteh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 13110:2012+A1:2017

<https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9f4f-7a290f84af59/sist-en-13110-2012a1-2017>

## European foreword

This document (EN 13110:2012+A1:2017) has been prepared by Technical Committee CEN/TC 286 “Liquefied petroleum gas equipment and accessories”, the secretariat of which is held by NSAI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2017, and conflicting national standards shall be withdrawn at the latest by July 2017.

This document includes Amendment 1 approved by CEN on 03 January 2017.

This document supersedes A1 EN 13110:2012 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13110:2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

This standard has been submitted for reference into the RID and/or in the technical annexes of ADR (see [9] and [8]).

[SIST EN 13110:2012+A1:2017](https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9ef4-fa290184a159/sist-en-13110-2012a1-2017)

The main technical changes to this revision include the addition of:

- reference to the latest welding standards;
- the introduction of radioscopy as a permitted alternative to radiographic examination of welds;
- simplification of the marking requirements by reference to EN 14894; and
- environmental considerations recorded in Annex B.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

This European Standard calls for the use of substances and procedures that may be injurious to health and/or the environment if adequate precautions are not taken. It refers only to technical suitability: it does not absolve the user from their legal obligations at any stage.

**A1** Protection of the environment is a key political issue in Europe and elsewhere. For CEN/TC 286, this is covered in CEN/TS 16765. This Technical Specification should be read in conjunction with this European Standard. **A1**

It is recommended that manufacturers develop an environmental management policy. For guidance see ISO 14000- series.

Provisions need to be restricted to a general guidance. Limit values are specified in national laws.

It has been assumed in the drafting of this European Standard that the execution of its provisions is entrusted to appropriately qualified and experienced people.

All pressures are gauged unless otherwise stated.

**NOTE** This European Standard requires measurement of material properties, dimensions and pressures. All such measurements are subject to a degree of uncertainty due to tolerances in measuring equipment etc. It may be beneficial to refer to the leaflet "measurement uncertainty leaflet" SP INFO 2000 27 [11].

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13110:2012+A1:2017](https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9f4f-7a290f84af59/sist-en-13110-2012a1-2017)

<https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9f4f-7a290f84af59/sist-en-13110-2012a1-2017>

## 1 Scope

This European Standard specifies minimum requirements for material, design, construction and workmanship, testing and examination during the manufacture of transportable refillable welded aluminium liquefied petroleum gas (LPG) cylinders, having a water capacity from 0,5 l up to and including 150 l, exposed to ambient temperature.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10204:2004, *Metallic products - Types of inspection documents*

EN 12816, *LPG equipment and accessories - Transportable refillable LPG cylinders - Disposal*

EN 14717, *Welding and allied processes - Environmental check list*

EN 14784-1, *Non-destructive testing - Industrial computed radiography with storage phosphor imaging plates - Part 1: Classification of systems*

EN 14784-2, *Non-destructive testing - Industrial computed radiography with storage phosphor imaging plates - Part 2: General principles for testing of metallic materials using X-rays and gamma rays*

EN 14894, *LPG equipment and accessories - Cylinder and drum marking*

EN ISO 4136, *Destructive tests on welds in metallic materials - Transverse tensile test (ISO 4136)*

EN ISO 5173, *Destructive tests on welds in metallic materials - Bend tests (ISO 5173)*

EN ISO 5178, *Destructive tests on welds in metallic materials - Longitudinal tensile test on weld metal in fusion welded joints (ISO 5178)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 9606-2, *Qualification test of welders - Fusion welding - Part 2: Aluminium and aluminium alloys (ISO 9606-2)*

EN ISO 9712:2012, *Non-destructive testing - Qualification and certification of NDT personnel (ISO 9712:2012)*

EN ISO 10042:2005, *Welding - Arc-welded joints in aluminium and its alloys - Quality levels for imperfections (ISO 10042:2005)*

EN ISO 11114-1, *Gas cylinders - Compatibility of cylinder and valve materials with gas contents - Part 1: Metallic materials (ISO 11114-1)*

EN ISO 11117:2008, *Gas cylinders - Valve protection caps and valve guards - Design, construction and tests (ISO 11117:2008)*

**EN 13110:2012+A1:2017 (E)**

EN ISO 11363-1, *Gas cylinders - 17E and 25E taper threads for connection of valves to gas cylinders - Part 1: Specifications (ISO 11363-1)*

EN ISO 14731, *Welding coordination - Tasks and responsibilities (ISO 14731:2006)*

**A1** EN ISO 14732, *Welding personnel — Qualification testing of welding operators and weld setters for mechanized and automatic welding of metallic materials (ISO 14732) **A1***

EN ISO 15607, *Specification and qualification of welding procedures for metallic materials - General rules (ISO 15607)*

EN ISO 15609-1, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 1: Arc welding (ISO 15609-1)*

EN ISO 15614-2, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 2: Arc welding of aluminium and its alloys (ISO 15614-2)*

**A1** EN ISO 17636-1:2013, *Non-destructive testing of welds — Radiographic testing — Part 1: X- and gamma-ray techniques with film (ISO 17636-1:2013)*

EN ISO 17636-2:2013, *Non-destructive testing of welds - Radiographic testing - Part 2: X- and gamma-ray techniques with digital detectors (ISO 17636-2:2013) **A1***

EN ISO 17637, *Non-destructive testing of welds - Visual testing of fusion-welded joints (ISO 17637)*

**A1** EN ISO 17639, *Destructive tests on welds in metallic materials Macroscopic and microscopic examination of welds (ISO 17639)*

EN ISO 19232-1, *Non-destructive testing - Image quality of radiographs - Part 1: Determination of the image quality value using wire-type image quality indicators (ISO 19232-1)*

EN ISO 19232-2, *Non-destructive testing - Image quality of radiographs - Part 2: Determination of the image quality value using step/hole-type image quality indicators (ISO 19232-2) **A1***

### **3 Terms, definitions and symbols**

#### **3.1 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

##### **3.1.1**

##### **liquefied petroleum gas**

##### **LPG**

low pressure liquefied gas composed of one or more light hydrocarbons which are assigned to UN 1011, UN 1075, UN 1965, UN 1969 or UN 1978 only and which consists mainly of propane, propene, butane, butane isomers, butene with traces of other hydrocarbon gases

##### **3.1.2**

##### **cylinder**

**A1** transportable pressure receptacle with a water capacity not exceeding 150 l **A1**

**3.1.3****yield strength**

0,2 % proof strength  $R_{ea}$  (non-proportional elongation) for aluminium alloys, and the 1 % proof strength for unalloyed aluminium in the unhardened state

**3.1.4****heat treatment**

solution heat treatment, quenching and artificial or natural ageing that ensures the strength values required

**3.2 Symbols**

$a$	Calculated minimum thickness of the cylindrical part, in mm.
$A_a$	Actual elongation after fracture, determined by the tensile test specified in 7.4, in %.
$A_{min}$	Minimum elongation after fracture, guaranteed by the manufacturer for the finished cylinder, in %.
$b$	Calculated minimum thickness of the end of the cylinder, in mm.
$C$	Shape factor (see Table 2, Figure 2 and Figure 3).
$d$	Outside diameter of the bend test former, in mm (see Figure 6 and Figure 7).
$D$	Outside diameter of the cylinder as given in the design drawing, in mm (see Figure 1).
$h$	Height of the cylindrical part of the end, in mm (see Figure 1).
$H$	Outside height of the domed part of the end, in mm (see Figure 1).
$L$	Length of the cylinder, in mm.
$n$	Ratio of diameter of bend test former to the thickness of the test piece (see Table 4).
$P_b$	Maximum pressure attained during the burst test, in bar.
$P_h$	Minimum permissible test pressure, in bar.
$r$	Inside knuckle radius of the end, in mm (see Figure 1).
$R$	Inside dishing radius of the end, in mm (see Figure 1).
$R_{ea}$	Actual value of yield strength, determined by the tensile test specified in 7.4, in N/mm <sup>2</sup> .
$R_{eg}$	Minimum value of yield strength, guaranteed by the manufacturer for the finished cylinder, in N/mm <sup>2</sup> .
$R_{ma}$	Actual value of tensile strength, determined by the tensile test specified in 7.4, in N/mm <sup>2</sup> .
$R_{mg}$	Minimum value of tensile strength, guaranteed by the manufacturer for the finished cylinder, in N/mm <sup>2</sup> .
$v$	Utilization factor for the permissible calculated tension (stress reduction factor).

**4 Materials**

**4.1** The manufacturer shall endeavour to acquire materials and components from suppliers who have a declared environmental policy.

NOTE For further guidance, see EN ISO 14021, EN ISO 14024 and EN ISO 14025.

**4.2** The alloys used shall be in accordance with Table 1, except as permitted in 4.3.

## EN 13110:2012+A1:2017 (E)

The pressure bearing parts of the cylinder shall be AlMgSi1 or AlMg1Si1, providing that for AlMgSi1 the requirements for corrosion resistance according to Annex A are satisfied. For non-pressure bearing parts AlMgSi0,5 can be used.

The manufacturer shall specify the guaranteed minimum values for the yield strength, tensile strength and elongation in the finished cylinders. In all cases, the elongation after fracture shall not be less than 12 %.

Table 1 — Cast analysis

Element	Material designation		
	AlMgSi1	AlMg1Si1	AlMgSi0,5
	Chemical composition		
Silicon %	0,7 - 1,3	1,2 - 1,6	0,3 - 0,6
Iron %	0,5 max.	0,5 max.	0,1 - 0,3
Copper %	0,1 max.	0,1 max.	0,1 max.
Manganese %	0,4 - 1,0	0,8 - 1,0	0,1 max.
Magnesium %	0,6 - 1,2	1,0 - 1,4	0,35 - 0,6
Chromium %	0,25 max.	0,1 max.	0,05 max.
Zinc %	0,2 max.	0,2 max.	0,15 max.
Titanium %	0,1 max.	0,1 max.	0,1 max.
Others %	each element 0,05 max., total 0,15 max.		
Aluminium	Remainder	Remainder	Remainder
NOTE	Materials AlMgSi1 and AlMgSi0,5 are equivalent to alloys EN AW-6082 and EN AW-6060 respectively in EN 573-3.		

**4.3** Unalloyed aluminium, containing at least 99,5 % aluminium, or aluminium alloys other than those specified in Table 1 can also be used provided that all requirements of this European Standard, with the exception of 4.2, are met and;

- LPG/material compatibility is checked in accordance with EN ISO 11114-1;
- the requirements for corrosion resistance according to Annex A are satisfied; and
- the manufacturer shall demonstrate that the material used is suitable for the manufacture of cylinders, the expected service life and the likely conditions of use.

**4.4** The welding materials selected by the manufacturer shall be compatible with the base materials and shall produce welds which meet the minimum strength values used in the design of the cylinder and guaranteed by the manufacturer in the finished cylinders.

**4.5** The manufacturer shall keep certificates in accordance with EN 10204:2004 type 3.1, or higher, covering ladle analysis and mechanical properties for material used for pressure retaining parts of the cylinder.

**4.6** The manufacturer shall maintain a system of identification for materials used in the manufacture so that all materials used in the manufacture of the cylinder can be traced back to their origin.

## 5 Design

### 5.1 General requirements

**5.1.1** Calculation of the wall thickness of the pressure bearing parts shall be related to the minimum guaranteed yield strength ( $R_{eg}$ ) in the finished cylinder.

**5.1.2** For calculation purposes the value of  $R_{eg}$  shall be limited to a maximum of  $0,85 R_{mg}$ .

**5.1.3** The calculation of wall thickness shall be based on the test pressure  $P_h$  of 30 bar.

**5.1.4** A fully dimensioned drawing, including material specifications, shall be produced.

**5.1.5** The design of the cylinder shall take the following into account:

- a) minimizing the waste of materials;
- b) the fittings required for the cylinder;
- c) minimizing the environmental impact of in service maintenance and end of life disposal; and
- d) efficient transport of finished product.

### 5.2 Calculation of cylindrical wall thickness

The wall thickness of the cylindrical shell, including any cylindrical part of the ends, shall not be less than:

$$a = \frac{P_h D}{\left(20 R_{eg} v / 1,3\right) + P_h}$$

<https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-944f-7a290f84af59/sist-en-13110-2012a1-2017>

where:

- For parts of the cylinder without longitudinal seam:  $v = 1,0$
- For parts of the cylinder with longitudinal seam:  $v = 0,9$

In no case shall the actual thickness be less than that specified in 5.5.

### 5.3 Design of ends concave to pressure

**5.3.1** Except as permitted in 5.4, the shape of ends of cylinders shall meet the following limitations:

- for torispherical ends:  $R \leq D$ ;  $r \geq 0,1 D$ ;  $h \geq 4 b$  (see Figure 1);

$$H = (R + b) - \sqrt{\left[(R + b) - \frac{D}{2}\right] \left[(R + b) + \frac{D}{2} - 2(r + b)\right]}$$

- for semi-ellipsoidal ends  $H \geq 0,192 D$ ;  $h \geq 4b$  (see Figure 1).

**5.3.2** The wall thickness of the ends of cylinders shall not be less than:

## EN 13110:2012+A1:2017 (E)

$$b = \frac{P_h D C}{\left(20R_{eg}/1,3\right) + P_h}$$

The value of  $C$  shall be obtained from Table 2 or the graphs given in Figure 2 and Figure 3.

#### 5.4 Other shapes of ends

Shapes of ends other than those covered by 5.3 can be used provided that the adequacy of their design is demonstrated by a fatigue test in accordance to 7.8 or by a stress analysis.

**Table 2 — Relationship between  $H/D$  and shape factor  $C$**

$H/D$	$C$	$H/D$	$C$
0,25	1,000	0,38	0,612
0,26	0,931	0,39	0,604
0,27	0,885	0,40	0,596
0,28	0,845	0,41	0,588
0,29	0,809	0,42	0,581
0,30	0,775	0,43	0,576
0,31	0,743	0,44	0,572
0,32	0,713	0,45	0,570
0,33	0,687	0,46	0,568
0,34	0,667	0,47	0,566
0,35	0,649	0,48	0,565
0,36	0,633	0,49	0,564
0,37	0,621	0,50	0,564

NOTE Intermediate values can be obtained by linear interpolation.

#### 5.5 Minimum wall thickness

The minimum wall thickness of the cylindrical shell “ $a$ ” and of the end “ $b$ ” shall not be less than the value derived from the following formula:

$$a = b = \frac{D}{200} + 1,5$$

The formula applies to cylindrical shells and ends, including any integral cylindrical part, irrespective of whether they are designed by calculation as specified in 5.2 and 5.3 or by testing as specified in 5.4.

#### 5.6 Design of openings

**5.6.1** The location of all openings shall be restricted to one end of the cylinder.

**5.6.2** Each opening in the cylinder shall be reinforced by a valve boss (or by other means) so that it is of adequate strength and does not result in harmful stress concentrations. This shall be confirmed by design calculations or a fatigue test in accordance with 7.8.

## 5.7 Neck design

**5.7.1** Internal neck threads for single hole cylinders shall be in accordance with EN ISO 11363-1.

**5.7.2** The internal neck threads of multi-hole cylinders shall conform to an established dimensional specification.

**5.7.3** The external diameter and thickness of the valve boss or neck end of the cylinder shall be adequate for the torque applied in fitting the valve, including any additional turning for valve alignment. The manufacturer shall specify the maximum permitted torque and shall demonstrate by tests that the neck and thread can withstand the specified torque without significant damage.

**NOTE** The torque required can vary according to the thread diameter and form, and the type of sealant used. EN ISO 13341 gives guidance on the torque for valve fitting.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13110:2012+A1:2017](https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9f4f-7a290f84af59/sist-en-13110-2012a1-2017)

<https://standards.iteh.ai/catalog/standards/sist/903a4457-d7fa-4943-9f4f-7a290f84af59/sist-en-13110-2012a1-2017>