



Designation: B258 – 02(Reapproved 2008)

Standard Specification for Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires Used as Electrical Conductors¹

This standard is issued under the fixed designation B258; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification prescribes standard nominal diameters and cross-sectional areas of American Wire Gage (AWG) sizes of solid round wires, used as electrical conductors, and gives equations and rules for the calculation of standard nominal mass and lengths, resistances, and breaking strengths of such wires (Explanatory Note 1).

1.2 The values stated in inch-pound or SI units are to be regarded separately as standard. Each system shall be used independently of the other. Combining values of the two systems may result in nonconformance with the specification. For conductor sizes designated by AWG or kcmil sizes, the requirements in SI units have been numerically converted from the corresponding values stated or derived, in inch-pound units. For conductor sizes designated by SI units only, the requirements are stated or derived in SI units.

1.2.1 For density, resistivity and temperature, the values stated in SI units are to be regarded as standard.

2. Referenced Documents

2.1 ASTM Standards:²

- A111 Specification for Zinc-Coated (Galvanized) “Iron” Telephone and Telegraph Line Wire
- A326 Specification for Zinc-Coated (Galvanized) High Tensile Steel Telephone and Telegraph Line Wire (Withdrawn 1990)³
- B1 Specification for Hard-Drawn Copper Wire

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.02 on Methods of Test and Sampling Procedure.

Current edition approved Sept. 1, 2008. Published September 2008. Originally approved in 1951. Last previous edition approved in 2002 as B258 – 02. DOI: 10.1520/B0258-02R08.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

- B2 Specification for Medium-Hard-Drawn Copper Wire
- B3 Specification for Soft or Annealed Copper Wire
- B9 Specification for Bronze Trolley Wire
- B33 Specification for Tin-Coated Soft or Annealed Copper Wire for Electrical Purposes
- B47 Specification for Copper Trolley Wire
- B105 Specification for Hard-Drawn Copper Alloy Wires for Electric Conductors
- B189 Specification for Lead-Coated and Lead-Alloy-Coated Soft Copper Wire for Electrical Purposes
- B193 Test Method for Resistivity of Electrical Conductor Materials
- B227 Specification for Hard-Drawn Copper-Clad Steel Wire
- B230/B230M Specification for Aluminum 1350–H19 Wire for Electrical Purposes
- B314 Specification for Aluminum 1350 Wire for Communication Cable (Withdrawn 1994)³
- B396 Specification for Aluminum-Alloy 5005-H19 Wire for Electrical Purposes (Withdrawn 2003)³
- B398/B398M Specification for Aluminum-Alloy 6201-T81 Wire for Electrical Purposes
- B415 Specification for Hard-Drawn Aluminum-Clad Steel Wire
- B609/B609M Specification for Aluminum 1350 Round Wire, Annealed and Intermediate Tempers, for Electrical Purposes
- B800 Specification for 8000 Series Aluminum Alloy Wire for Electrical Purposes—Annealed and Intermediate Tempers
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- F205 Test Method for Measuring Diameter of Fine Wire by Weighing

3. Standard Reference Temperature

3.1 For the purpose of this specification, all wire dimensions and properties shall be considered as occurring at the internationally standardized reference temperature of 20°C (68°F).

TABLE 1 Standard Nominal Diameters and Cross-Sectional Areas of AWG Sizes of Solid Round Wires at 20°C

Size		Diameter		Cross-Sectional Area		Size		Diameter		Cross-Sectional Area				
AWG	mils	mm	cmils	mm ²	AWG	mils	mm	cmils	mm ²	AWG	mils	mm	cmils	mm ²
4/0	460.0	11.684	211 600	107.2	29	11.3	0.287	128	0.0647					
3/0	409.6	10.404	167 800	85.0	30	10.0	0.254	100	0.0507					
2/0	364.8	9.26	133 100	67.4	31	8.9	0.226	79.2	0.0401					
1/0	324.9	8.25	105 600	53.5	32	8.0	0.203	64.0	0.0324					
1	289.3	7.35	83 690	42.4	33	7.1	0.180	50.4	0.0255					
2	257.6	6.54	66 360	33.6	34	6.3	0.160	39.7	0.0201					
3	229.4	5.82	52 620	26.7	35	5.6	0.142	31.4	0.0159					
4	204.3	5.19	41 740	21.1	36	5.0	0.127	25.0	0.0127					
5	181.9	4.62	33 090	16.8	37	4.5	0.114	20.2	0.0103					
6	162.0	4.11	26 240	13.3	38	4.0	0.102	16.0	0.00811					
7	144.3	3.67	20 820	10.6	39	3.5	0.0890	12.2	0.00621					
8	128.5	3.26	16 510	8.37	40	3.1	0.0787	9.61	0.00487					
9	114.4	2.91	13 090	6.63	41	2.8	0.0711	7.84	0.00397					
10	101.9	2.59	10 380	5.26	42	2.5	0.0635	6.25	0.00317					
11	90.7	2.30	8 230	4.17	43	2.2	0.0559	4.84	0.00245					
12	80.8	2.05	6 530	3.31	44	2.0	0.0508	4.00	0.00203					
13	72.0	1.83	5 180	2.63	45	1.76	0.0447	3.10	0.00157					
14	64.1	1.63	4 110	2.08	46	1.57	0.0399	2.46	0.00125					
15	57.1	1.45	3 260	1.65	47	1.40	0.0356	1.96	0.000993					
16	50.8	1.29	2 580	1.31	48	1.24	0.0315	1.54	0.000779					
17	45.3	1.15	2 050	1.04	49	1.11	0.0282	1.23	0.000624					
18	40.3	1.02	1 620	0.823	50	0.99	0.0252	0.980	0.000497					
19	35.9	0.904	1 290	0.653	51	0.88	0.0224	0.774	0.000392					
20	32.0	0.813	1 020	0.519	52	0.78	0.0198	0.608	0.000308					
21	28.5	0.724	812	0.412	53	0.70	0.0178	0.490	0.000248					
22	25.3	0.643	640	0.324	54	0.62	0.0158	0.384	0.000195					
23	22.6	0.574	511	0.259	55	0.55	0.0140	0.302	0.000153					
24	20.1	0.511	404	0.205	56	0.49	0.0125	0.240	0.000122					
25	17.9	0.455	320	0.162										
26	15.9	0.404	253	0.128										
27	14.2	0.361	202	0.102										
28	12.6	0.320	159	0.0804										

(<https://standards.iteh.ai>)

4. Standard Rules for Rounding

4.1 All calculations for the standard nominal dimensions and properties of solid round wires shall be rounded in the *final* value only, in accordance with rounding method of Practice E29.

5. Standard Nominal Diameters

5.1 Standard nominal diameters of AWG sizes of solid round wires shall be calculated in accordance with the conventional mathematical law of the American Wire Gage (see Explanatory Note 1) and in accordance with Section 4.

5.2 For wire sizes 4/0 to 44 AWG, inclusive, nominal diameters shall be expressed in no more than four significant figures but in no case closer than the nearest 0.1 mil (0.0001 in.).

5.3 For wire sizes 45 to 56 AWG, inclusive, nominal diameters shall be expressed to the nearest 0.01 mil (0.00001 in.).

5.4 The standard nominal diameters expressed in mils have been calculated in accordance with these rules and are given in Table 1 for convenient reference (Explanatory Note 2).

6. Standard Nominal Cross-Sectional Areas

6.1 Standard nominal cross-sectional areas in circular mils and square millimetres shall be calculated in accordance with

the following equations and shall be rounded in accordance with Section 4 to the same number of significant figures as used in expressing the standard diameters, but in no case to less than three significant figures:

$$\text{Area, cmil} = d^2$$

$$\text{Area, mm}^2 = d^2 \times 5.067 \times 10^{-4}$$

where:

d = diameter of the wire in mils as given in Table 1.

Standard nominal cross-sectional areas in circular mils and square millimetres have been calculated in accordance with the foregoing rules and are given in Table 1 for convenient reference.

7. Rules for Calculations Involving Mass and Length

7.1 Standard nominal mass and lengths shall be calculated from the standard wire diameters specified in Table 1, in accordance with the following equations. They shall be rounded in the *final* value only, in accordance with Section 4, to the same number of significant figures as used in expressing the standard diameters, but in no case to less than three significant figures:

$$W = d^2 \times \delta \times 0.34049 \times 10^{-3}$$

$$L = (1/d^2) \times (1/\delta) \times 2.9369 \times 10^6$$

where: