

---

---

**Plastics — Biobased content —  
Part 4:  
Determination of biobased mass  
content**

*Plastiques — Teneur biosourcée —*

*Partie 4: Détermination de la teneur en masse biosourcée*

**iTEH Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO 16620-4:2016](#)

<https://standards.iteh.ai/catalog/standards/iso/cafac21e-9f93-46cc-9530-223fed2f93b5/iso-16620-4-2016>



Reference number  
ISO 16620-4:2016(E)

# iTeh Standards

## (<https://standards.iteh.ai>)

### Document Preview

[ISO 16620-4:2016](#)

<https://standards.iteh.ai/catalog/standards/iso/cafac21e-9f93-46cc-9530-223fed2f93b5/iso-16620-4-2016>



#### COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

Page

<b>Foreword</b>	iv
<b>Introduction</b>	v
<b>1 Scope</b>	1
<b>2 Normative references</b>	1
<b>3 Terms, definitions, symbols and abbreviated terms</b>	1
3.1 Terms and definitions	1
3.2 Symbols	1
3.3 Abbreviated terms	2
<b>4 Principle</b>	2
4.1 Product groups	2
4.2 Group I products	2
4.3 Group II products	2
4.4 Natural constituents	3
4.5 Monomers and additives	3
<b>5 Rules for allocation of elements</b>	3
<b>6 Group I products</b>	4
6.1 Statement	4
6.2 Sampling	4
6.3 Determination of the biobased carbon content and elemental composition	4
6.3.1 Procedure	4
6.3.2 Variability of test results	5
6.4 Validation criteria of the biobased mass content	5
6.5 Examples of application of the decision scheme	6
6.6 Test report	7
<b>7 Group II products</b>	8
7.1 Statement	8
7.2 Sampling	8
7.3 Determination of the biobased carbon content	8
7.3.1 Procedure	8
7.3.2 Variability of test results	9
7.4 Validation criteria of the biobased mass content	9
7.5 Example of application of the decision scheme	10
7.6 Test report	10
<b>Annex A (informative) Example of format for reporting results for Group I products</b>	11
<b>Annex B (normative) Calculation of the biobased carbon content and biobased mass content for Group II products</b>	12
<b>Annex C (informative) Example of format for reporting results for Group II products</b>	13
<b>Bibliography</b>	14

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

## Document Preview

A list of all parts in the ISO 16620 series can be found on the ISO website.

[ISO 16620-4:2016](http://www.iso.org/iso/16620-4:2016)

<https://standards.iteh.ai/catalog/standards/iso/cafac21e-9f93-46cc-9530-223fed2f93b5/iso-16620-4-2016>

## Introduction

Increased use of biomass resources for manufacturing plastics products is effective in reducing global warming and the depletion of fossil resources.

Current plastics products are composed of biobased synthetic polymers, fossil-based synthetic polymers, natural polymers and additives that can include biobased materials.

“Biobased plastics” refer to plastics that contain materials wholly or partly of biogenic origin.

In ISO 16620 series, the “biobased content” of biobased plastics refers to the amount of the biobased carbon content, the amount of the biobased synthetic polymer content or the amount of the biobased mass content only.

This document is harmonized with EN 16785-1:2015[12].

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO 16620-4:2016](#)

<https://standards.iteh.ai/catalog/standards/iso/cafac21e-9f93-46cc-9530-223fed2f93b5/iso-16620-4-2016>



# Plastics — Biobased content —

## Part 4: Determination of biobased mass content

### 1 Scope

This document specifies a method of determining the biobased mass content in plastics products, based on the radiocarbon analysis and elemental analysis.

This document is applicable to plastic products and plastic materials, polymer resins, monomers or additives, which are made from biobased or fossil-based constituents.

This method is applicable, provided that the plastic product contains carbon element and that a statement giving its elemental composition and its biobased mass content is available.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 16620-2:2015, *Plastics — Biobased content — Part 2: Determination of biobased carbon content*

### 3 Terms, definitions, symbols and abbreviated terms

[ISO 16620-4:2016](#)

#### 3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 16620-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp/>

#### 3.2 Symbols

$^{14}\text{C}$  carbon isotope with an atomic mass of 14

C symbol for element carbon

H symbol for element hydrogen

N symbol for element nitrogen

O symbol for element oxygen

$m_{\text{B}}$  biobased mass content, expressed as a percentage of the total mass of sample

$x_{\text{B}}$  biobased carbon content, expressed as a percentage of the total mass of the sample

$x_{TC}$	total carbon content, expressed as a percentage of the total mass of the sample
$x_{TH}$	total hydrogen content, expressed as a percentage of the total mass of the sample
$x_{TN}$	total nitrogen content, expressed as a percentage of the total mass of the sample
$x_{TO}$	total oxygen content, expressed as a percentage of the total mass of the sample
$W$	mass of a sample, expressed in grams

### 3.3 Abbreviated terms

CL	confidence level
TC	total carbon
TH	total hydrogen
TN	total nitrogen
TO	total oxygen

## 4 Principle

### iTeh Standards

#### 4.1 Product groups

For the purpose of this document, two groups of products are distinguished as follows:

- Group I products are obtained by chemical or biological reaction(s);
- Group II products are obtained by mixing Group I products without chemical or biological reaction.

Natural constituents (4.4) can be used to produce Group I products or as constituent(s) of Group II products.

#### 4.2 Group I products

This method, supported by rules described in Clause 6, consists in

- the determination of the biobased carbon content and elemental composition of the product by using the radiocarbon analysis and elemental analysis respectively (6.3), and
- the comparison between
  - the data of the statement (6.1) comprising the composition and the origin (biobased and/or fossil resources) of the product, and
  - the data resulting from the radiocarbon analysis and elemental analysis of the product (6.3).

NOTE The “statement” in the sense of this document is to be distinguished from the “declaration” of the biobased mass content resulting of this method, which is in the scope of ISO 16620-5<sup>1</sup>.

#### 4.3 Group II products

This method consists in

- the determination of the biobased carbon content of the product by using the radiocarbon analysis (7.3), and

---

- To be published.

b) the comparison between

- 1) the data of the statement (7.1) comprising the composition and the origin (biobased and/or fossil resources) of the product, and
- 2) the data resulting from the radiocarbon analysis of the product (7.3).

NOTE The “statement” in the sense of this document is to be distinguished from the “declaration” of the biobased mass content resulting of this method, which is in the scope of ISO 16620-5<sup>1</sup>.

#### 4.4 Natural constituents

This method is not needed for the determination of the biobased mass content in natural constituents (e.g. natural polymers) wholly derived from biomass.

The biobased mass content of a natural constituent is equal to 100 %.

The biobased carbon content of a natural constituent, expressed as a percentage of the total carbon content, is equal to 100 %.

NOTE This differentiates the calculation of the biobased mass content according to this document from the calculation of the biobased synthetic polymer content according to ISO 16620-3, where the biobased synthetic polymer content of a natural constituent is 0 % (see ISO 16620-1:2015, Clause 4).

#### 4.5 Monomers and additives

In case of monomers and additives for which the composition and raw material(s)/chemical(s) from which they are made are known, and whose chemical identification is unequivocal, the method may consist only in a determination of the biobased carbon content. The biobased mass content may be validated by applying the validation criteria (6.4), considering only the biobased carbon content.

### 5 Rules for allocation of elements

ISO 16620-4:2016

NOTE According to the current state of the art, it is not possible by isotopic measurements to establish a distinction between elements originating from biomass and elements originating from non-biomass for elements such as oxygen, hydrogen or nitrogen.

For a product/constituent of a product obtained by chemical or biological reaction(s) (Group I), the following rules shall apply:

- a) if the reactants are exclusively derived from biomass, the biobased mass content of the product/constituent of the product is 100 %;
- b) if none of the reactants is derived from biomass, the biobased mass content of the product/constituent of the product is 0 %;
- c) if the reactants are derived from both biomass and non-biomass, the following conventions apply:
  - 1) if oxygen (O) and/or hydrogen (H) and/or nitrogen (N) element(s) is(are) bound to a carbon structure derived from biomass, its(their) fraction is(are) considered to be part(s) of the biobased mass content;
  - 2) element(s) other than C, H, O and N elements are not considered in this document.

EXAMPLE Esters derived from the condensation of an acid with a primary alcohol keep the O element coming from the alcohol.

## 6 Group I products

### 6.1 Statement

The statement to be provided with the product under consideration shall include

- a) information related to the relevant chemical or biological reaction(s) and the raw materials/chemicals from which the product is made,
- b) a complete elemental composition of the product ( $x_1^{\text{TC}}$ ,  $x_1^{\text{TH}}$ ,  $x_1^{\text{TO}}$  and  $x_1^{\text{TN}}$ ), and
- c) the biobased carbon content ( $x_{\text{B1}}$ ) and biobased mass content ( $m_{\text{B1}}$ ), of the product, obtained by calculation, following the rules defined in [Clause 5](#).

NOTE 1 The biobased carbon content can be expressed on the basis of total organic carbon (TOC) or total carbon (TC) or total mass.

NOTE 2 In this document, “biobased carbon content” refers to “biobased carbon content by mass, expressed as a percentage of the total mass”.

For products which contain water, the biobased mass content ( $m_{\text{B1}}$ ) is expressed by mass of dry matter.

EXAMPLE Poly(ethylene terephthalate) obtained by polycondensation of terephthalic acid from fossil resources with biobased ethylene glycol (see [Table 1](#)).

**Table 1 — Example of calculation for poly(ethylene terephthalate)**

Fraction	C %	H %	O %	Total %	
Fossil fraction (from terephthalic acid)	50,0	2,1	16,6	68,7	
Biobased fraction (from ethylene glycol)	12,5	2,1	16,6	31,2	
Total	62,5	4,2	33,3	100,0	
$x_1^{\text{TC}} = 62,5 \%$ $x_1^{\text{TH}} = 4,2 \%$ $x_1^{\text{TO}} = 33,3 \%$		$x_{\text{B1}} = 12,5 \%$ $m_{\text{B1}} = 31,2 \%$			

### 6.2 Sampling

The samples shall be representative of the product under consideration.

If available, product sampling procedures for the determination of the biobased carbon content and elemental composition shall be used and the details shall be documented.

### 6.3 Determination of the biobased carbon content and elemental composition

#### 6.3.1 Procedure

Determine the biobased carbon content of the sample according to ISO 16620-2.

Express the biobased carbon content ( $x_{\text{B2}}$ ) as a percentage of the total mass of the sample.

Determine the contents of total carbon ( $x_2^{\text{TC}}$ ), hydrogen ( $x_2^{\text{TH}}$ ), oxygen ( $x_2^{\text{TO}}$ ) and/or nitrogen ( $x_2^{\text{TN}}$ ) of the sample according to suitable standard analytical methods. If other element(s) is(are) present, its(their) content(s) may be also determined.