



Designation: ~~B 400-94~~ Designation: **B400 - 08**

Standard Specification for Compact Round Concentric-Lay-Stranded Aluminum 1350 Conductors¹

This standard is issued under the fixed designation B400; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers aluminum 1350-H19 (extra hard), 1350-H16 or -H26 ([n]hard), 1350-H14 or -H24 (½ hard) and 1350-H142 or -H242 (½ hard) bare compact-round concentric-lay-stranded conductors made from round or shaped wires for use as uninsulated electrical conductors or in covered or insulated electrical conductors. These conductors shall be composed of a central core surrounded by one or more roller or die compacted layers of helically applied wires (Explanatory Note 1 and Note 2).

1.2 The SI values of density and resistivity are to be regarded as standard. For all other properties the inch-pound values are to be regarded as standard and the SI units may be approximate.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

NOTE 1—Prior to 1975, aluminum 1350 was designated as EC aluminum.

NOTE 2—The aluminum and temper designations conform to ANSI Standard H35.1. Aluminum 1350 corresponds to Unified Numbering System A91350 in accordance with Practice E-527E527.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 ~~ASTM Standards:~~

2.1 ~~ASTM Standards:~~²

~~B230~~B230/B230M [Specification for Aluminum 1350-H19 1350H19 Wire for Electrical Purposes](#)

~~B231~~B231/B231M [Specification for Concentric-Lay-Stranded Aluminum 1350 Conductors](#)

B263 [Test Method for Determination of Cross-Sectional Area of Stranded Conductors](#)

B354 [Terminology Relating to Uninsulated Metallic Electrical Conductors](#) [f6-beb8-a3fb6bc74e79/astm-b400-08](#)

~~B609~~B609M [Specification for Aluminum 1350 Round Wire, Annealed and Intermediate Tempers, for Electrical Purposes](#)

E29 [Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

~~E527~~ [Practice for Numbering Metals and Alloys \(UNS\)](#)

2.3 ~~Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)~~

2.2 ~~Other Documents:~~

~~ANSI H35.1~~ [ANSI H35.1/H35.1\(M\) Alloy and Temper Designation Systems for Aluminum](#)³

NBS [Handbook 100-Copper Wire Tables, of the National Bureau of Standards](#)⁴

3. Classification

3.1 For the purpose of this specification, conductors are classified as follows:

¹ This specification is under the jurisdiction of ASTM Committee B-1/B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.07 on Conductors of Light Metals.

Current edition approved Dec. 15, 1994. Published February 1995. Originally published as B 400-63 T. Last previous edition B 400-92.

Current edition approved Sept. 1, 2008. Published October 2008. Originally approved in 1963. Last previous edition approved in 2004 as B400-04. DOI: 10.1520/B0400-08.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards*, Vol 02.03, volume information, refer to the standard's Document Summary page on the ASTM website.

³ *Annual Book of ASTM Standards*, Vol 14.02.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

⁴ *Annual Book of ASTM Standards*, Vol 01.01.

⁴ Available from National Technical Information Service (NTIS), 5285 Port Royal Rd., Springfield, VA 22161, http://www.ntis.gov.

3.1.1 *Class AA*—For bare conductors usually used in overhead lines.

3.1.2 *Class A*—For conductors to be covered with weather-resistant materials, and for bare conductors where greater flexibility than is afforded by Class AA is required. Conductors indicated for further fabrication into tree wire or to be insulated and laid helically with or around aluminum or ACSR messengers, shall be regarded as Class A conductors with respect to direction of lay only (see 6.3).

3.1.3 *Class B*—For conductors to be insulated with various materials such as rubber, paper, varnished cloth, etc., and so forth, and for the conductors indicated under Class A where greater flexibility is required.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity of each size and class (Table 1),

4.1.2 Conductor size; circular-mil area or AWG (Section 7),

4.1.3 Class (Section 3),

4.1.4 Temper (Section 13),

4.1.5 Lay direction if nonstandard (see 6.3 and 6.4), reversed or unidirectional (see 6.4) or special (see 6.5),

4.1.6 Special tension test, if required (see 17.2),

TABLE 1 Construction of Compact-Round Concentric-Lay-Stranded, Aluminum Conductors

NOTE 1—Metric values listed below represent a soft conversion and as such they may not be the same as those metric values which are calculated from the basic metric density.

Conductor Size			Class	Number of Wires	Nominal Compact Conductor Diameter		Nominal Mass per 1000 ft, lb	Nominal Mass per Kilometer, kg ^A	Nominal D-C Resistance at 20°C	
Circular Mils	AWG	mm ²			in.	mm			Ω/1000 ft	Ω/km
1 100 000		557	B	61 ^B	1.112	28.2	1031	1537	0.0157	0.0516
1 000 000		507	B	61 ^B	1.060	26.9	937	1394	0.0173	0.0563
900 000		456	B	61 ^B	0.999	25.4	844	1257	0.0193	0.0632
800 000		405	B	61 ^B	0.938	23.8	750	1116	0.0217	0.0712
750 000		380	B	61 ^B	0.908	23.1	703	1046	0.0231	0.0759
700 000		355	B	61 ^B	0.877	22.3	656	976	0.0248	0.0813
650 000		329	B	61 ^B	0.845	21.5	609	906	0.0267	0.0875
600 000		304	B	61 ^B	0.813	20.7	563	838	0.0289	0.0948
556 500		282	AA	19 ^C	0.780	19.8	521	775	0.0312	0.102
550 000		279	B	61 ^B	0.775	19.7	516	768	0.0315	0.103
500 000		253	B	37 ^D	0.736	18.7	468	696	0.0347	0.114
500 000		253	AA	19 ^C	0.736	18.7	468	696	0.0347	0.114
477 000		242	AA	19 ^C	0.722	18.3	447	665	0.0364	0.119
450 000		228	B	37 ^D	0.700	17.8	422	628	0.0385	0.126
400 000		203	B	37 ^D	0.659	16.7	375	558	0.0434	0.142
397 500		201	AA, A	19 ^C	0.659	16.7	372	554	0.0436	0.143
350 000		177	B	37 ^D	0.616	15.6	328	488	0.0495	0.162
350 000		177	A	19 ^C	0.616	15.6	328	488	0.0495	0.162
336 400		170	A	19 ^C	0.603	15.3	315	469	0.0516	0.169
336 400		170	AA	7	0.603	15.3	315	469	0.0516	0.169
300 000		152	B	37 ^D	0.570	14.5	281	418	0.0578	0.190
300 000		152	A	19 ^C	0.570	14.5	281	418	0.0578	0.190
300 000		152	AA	7	0.570	14.5	281	418	0.0578	0.190
266 800		135	A	19 ^C	0.537	13.6	250	372	0.0650	0.213
266 800		135	AA	7	0.537	13.6	250	372	0.0650	0.213
250 000		127	B	37 ^D	0.520	13.2	234	348	0.0694	0.228
250 000		127	A	19 ^C	0.520	13.2	234	348	0.0694	0.228
250 000		127	AA	7	0.520	13.2	234	348	0.0694	0.228
211 600	0000	107	B	19 ^C	0.475	12.1	198	295	0.0820	0.269
211 600	0000	107	AA, A	7	0.475	12.1	198	295	0.0820	0.269
167 800	000	85.0	B	19 ^C	0.423	10.7	157	234	0.103	0.338
167 800	000	85.0	AA, A	7	0.423	10.7	157	234	0.103	0.338
133 100	00	67.4	B	19 ^C	0.376	9.55	125	186	0.130	0.428
133 100	00	67.4	AA, A	7	0.376	9.55	125	186	0.130	0.428
105 600	0	53.5	B	19 ^C	0.336	8.53	98.9	147	0.164	0.539
105 600	0	53.5	AA, A	7	0.336	8.53	98.9	147	0.164	0.539
83 690	1	42.4	B	19 ^C	0.299	7.59	78.4	117	0.207	0.680
83 690	1	42.4	AA, A	7	0.299	7.59	78.4	117	0.207	0.680
66 360	2	33.6	AA, A, B	7	0.268	6.81	62.2	92.6	0.261	0.857
52 620	3	26.7	A, B	7	0.238	6.05	49.3	73.3	0.330	1.08
41 740	4	21.2	A, B	7	0.213	5.41	39.1	58.2	0.416	1.36
26 240	6	13.3	A, B	7	0.169	4.29	24.6	36.6	0.661	2.17
16 510	8	8.37	A, B	7	0.134	3.40	15.5	23.1	1.05	3.44

^A 1 lb/1000 ft = 1.488 kg/km.

^B 58 wires minimum.

^C 18 wires minimum.

^D 35 wires minimum.

- 4.1.7 Place of inspection (Section 18), and
 4.1.8 Packaging and Package Marking (Section 19).

4.2 ~~In addition, supplementary requirements shall apply only when specified by the purchaser in the inquiry, contract, or purchase order for direct procurement by agencies of the U.S. Government (S1, S2, and S3).~~

5. Joints

5.1 1350-H19 Conductors for Use in Bare Overhead Lines:

5.1.1 Joints may be made in the six outer wires of seven-strand conductors by cold-pressure welding or by electric-butt, cold-upset welding, but not by electric-butt welding. Joints are not permitted in the finished center wire of seven-stranded conductors.

5.1.2 Joints may be made in any of the wires in conductors of 18 or more wires by electric-butt welding, cold-pressure welding, or electric butt, cold-upset welding.

5.1.3 The minimum distance between a wire joint and another joint either in the same wire or in other wires of the completed conductor shall be 50 ft (15 m).

5.2 Conductors of All Tempers to Be Insulated or Covered:

5.2.1 Joints may be made in any of the wires of any stranding by electric-butt welding, cold-pressure welding, or electric-butt, cold-upset welding.

5.2.2 Joints in the individual wires in a finished conductor shall be not closer together than 1 ft (0.3 m) for conductors of 19 wires or less, or closer than 1 ft in a layer for conductors of more than 19 wires.

5.3 No joint or splice shall be made in a stranded conductor as a whole.

6. Lay

6.1 The length of lay or each layer for Classes AA and A shall be not less than 11 nor more than 17.5 times the outside diameter of that layer.

6.2 The length of lay of the outer layer for Class B shall be not less than 8 nor more than 16 times the outside diameter of the completed conductor, except that for sizes No. 2 AWG (33.6 mm²) and smaller, the maximum length of lay shall be not more than 17.5 times the outside diameter of the completed conductor.

6.3 ~~The direction of lay of the outer layer shall be right-hand for Classes AA and A, and it shall be reversed in successive layers.~~
 The direction of lay of the outer layer shall be right-hand for Classes AA and A, and it shall be reversed in successive layers. For Class A stranding where the conductors are to be insulated and laid helically with or around aluminum or ACSR messengers, the stranding lay direction may be unidirectional or unilay in successive layers.

6.4 The direction of lay of the outer layer shall be left-hand for Class B, and it ~~may~~ shall be reversed ~~or unidirectional/unilay~~ in successive layers, unidirectional, or unilay.

6.5 Other lay requirements may be furnished by special agreement between the manufacturer and the purchaser.

7. Construction

7.1 The construction of the conductors shall be as shown in Table 1 as to number of wires and cross-sectional area of the completed conductor, and the lay shall be in accordance with Section 6.

7.2 Wire used in the fabrication of conductor shall be of such dimensions as to produce a finished conductor having a nominal cross-sectional area and diameter as prescribed in Table 1.

8. Rated Strength of Conductor

8.1 The rated strength of 1350-H19 conductors shall be taken as the percentage, indicated in Table 2, of the sum of the strengths of the component wires, calculated on the basis of the nominal wire diameter for the corresponding noncompacted construction given in Specification ~~B-231B-231~~ B231/B231M and the specified minimum average tensile strength given in Specification ~~B-230B-230~~ B230/B230M for 1350-H19 wire. A value of 0.1343 (3.41 mm) shall be used for the nominal wire diameter for the 1100 kcmil compacted construction.

TABLE 2 Rating Factors

Stranding		
Number of Wires in Conductor	Number of Layers	Rating Factor, %
7	1	96
19 ^A	2	93
37 ^B	3	91
61 ^C	4	90

^A 18 wires minimum.

^B 35 wires minimum.

^C 58 wires minimum.

8.2 Calculations for rated strengths of 1350-H16, -H26, -H14, -H24, -H142, and -H242 conductors shall be made on the basis of the strengths of the component wires using the nominal wire diameter for the noncompacted construction given in Specification B-231B-231B231/B231M and the specified maximum and minimum tensile strengths for the appropriate temper of the respective component wires given in Specification B-609B-609B609/B609M. The minimum rated strengths of the conductors shall be taken as the sum of the calculated minimum strengths of the component wires multiplied by the rating factor given in Table 2. The maximum rated strength of the conductors shall be taken as the sum of the calculated maximum strengths of the component wires. A value of 0.1343 (3.41 mm) shall be used for the nominal wire diameter for the 1100 kcmil compacted construction.

8.3 Rated-strength and breaking-strength values shall be rounded to three significant figures, in the final value only, in accordance with the rounding method of Practice E-29E29.

8.4 Rated strengths of conductors are given in Table 3.

9. Density

9.1 For the purpose of calculating mass, linear density, cross sections, etc., and so forth, the density of aluminum 1350 shall be taken as 2705 kg/m³(0.0975 lb/in.³) at 20°C.

10. Mass and Electrical Resistance

10.1 The mass and electrical resistance of a unit length of stranded conductor are a function of the length of lay. The approximate mass and electrical resistance may be determined using an increment of 2 %. When greater accuracy is desired, the

TABLE 3 Conductor Rated Strengths

Conductor Size			Number of Wires	1350-H19		1350-H16, -H26				1350-H14, -H24			
						Min		Max		Min		Max	
						kips	KN	kips	KN	kips	KN	kips	KN
cmil	AWG	mm ²											
1 100 000		557	61 ^A	19.4	85.2	13.2	57.7	19.0	83.6	11.7	50.1	17.3	72.2
1 000 000		507	61 ^A	17.7	78.6	12.0	53.4	17.3	76.8	10.60	47.1	15.7	69.8
900 000		456	61 ^A	15.9	70.8	10.8	48.1	15.6	69.2	9.55	42.5	14.1	62.9
800 000		405	61 ^A	14.4	64.1	9.61	42.7	13.8	61.5	8.48	37.7	12.6	55.9
750 000		380	61 ^A	13.5	60.2	9.02	40.1	13.0	57.7	7.95	35.4	11.8	52.4
700 000		355	61 ^A	12.9	57.2	8.41	37.4	12.1	53.8	7.42	33.0	11.0	48.9
650 000		329	61 ^A	11.9	53.1	7.81	34.7	11.2	49.9	6.89	30.6	10.2	45.4
600 000		304	61 ^A	11.50	51.0	7.21	32.1	10.4	46.1	6.36	28.3	9.43	41.9
556 500		282	19 ^B	9.75	43.4	6.91	30.7	9.61	42.8	6.09	27.1	8.74	38.9
550 000		279	61 ^A	10.50	46.7	6.62	29.4	9.51	42.3	5.84	26.0	8.65	38.5
500 000		253	37 ^C	9.11	40.5	6.07	27.0	8.63	38.4	5.36	23.8	7.85	34.9
500 000		253	19 ^B	8.76	39.0	6.21	27.6	8.64	38.4	5.48	24.4	7.85	34.9
477 000		242	19 ^B	8.36	37.2	5.92	26.3	8.24	36.6	5.22	23.2	7.49	33.3
450 000		228	37 ^C	8.20	36.5	5.47	24.3	7.78	34.6	4.83	21.5	7.07	31.5
400 000		203	37 ^C	7.44	33.1	4.86	21.6	6.91	30.8	4.29	19.1	6.29	28.0
397 500		201	19 ^B	7.11	31.6	4.93	21.9	6.86	30.5	4.35	19.4	6.24	27.8
350 000		177	37 ^C	6.76	30.1	4.26	18.9	6.05	26.9	3.76	16.7	5.50	24.5
350 000		177	19 ^B	6.39	28.4	4.34	19.3	6.05	26.9	3.83	17.1	5.50	24.4
336 400		170	19 ^B	6.15	27.3	4.18	18.6	5.82	25.9	3.69	16.4	5.29	23.5
336 400		170	7	5.96	26.5	4.31	19.2	5.81	25.9	3.80	16.9	5.28	23.5
300 000		152	37 ^C	5.89	26.2	3.64	16.2	5.18	23.0	3.21	14.3	4.71	20.9
300 000		152	19 ^B	5.48	24.4	3.73	16.6	5.19	23.1	3.29	14.6	4.72	21.0
300 000		152	7	5.43	24.1	3.84	17.1	5.18	23.1	3.39	15.1	4.71	21.0
266 800		135	19 ^B	4.97	22.1	3.31	14.7	4.61	20.5	2.92	13.0	4.19	18.6
266 800		135	7	4.83	21.5	3.42	15.2	4.61	20.5	3.02	13.4	4.19	18.6
250 000		127	37 ^C	4.91	21.9	3.04	13.5	4.32	19.2	2.68	11.9	3.93	17.5
250 000		127	19 ^B	4.66	20.7	3.10	13.8	4.32	19.2	2.74	12.2	3.93	17.5
250 000		127	7	4.52	20.1	3.21	14.3	4.32	19.2	2.83	12.6	3.93	17.5
211 600	0000	107	19 ^B	4.02	17.9	2.63	11.7	3.65	16.3	2.32	10.3	3.32	14.8
211 600	0000	107	7	3.83	17.0	2.71	12.1	3.66	16.3	2.39	10.6	3.33	14.8
167 800	000	85.0	19 ^B	3.31	14.7	2.08	9.27	2.90	12.9	1.84	8.18	2.64	11.7
167 800	000	85.0	7	3.04	13.5	2.15	9.56	2.90	12.9	1.90	8.44	2.63	11.7
133 100	00	67.4	19 ^B	2.67	11.9	1.65	7.35	2.30	10.2	1.46	6.49	2.09	9.30
133 100	00	67.4	7	2.51	11.2	1.71	7.59	2.30	10.2	1.51	6.70	2.09	9.30
105 600	0	53.5	19 ^B	2.16	9.62	1.31	5.84	1.83	8.13	1.16	5.15	1.66	7.39
105 600	0	53.5	7	1.99	8.85	1.35	6.02	1.82	8.11	1.19	5.31	1.66	7.38
83 690	1	42.4	19 ^B	1.74	7.76	1.04	4.63	1.45	6.44	0.918	4.08	1.32	5.85
83 690	1	42.4	7	1.64	7.29	1.07	4.77	1.44	6.43	0.946	4.21	1.31	5.84
66 360	2	33.6	7	1.35	6.01	0.851	3.79	1.15	5.10	0.751	3.34	1.04	4.64
52 620	3	26.7	7	1.09	4.85	0.674	3.00	0.909	4.04	0.595	2.65	0.827	3.68
41 740	4	21.1	7	0.881	3.92	0.535	2.38	0.721	3.21	0.472	2.10	0.655	2.92
26 240	6	13.3	7	0.563	2.51	0.336	1.49	0.453	2.02	0.297	1.32	0.412	1.83
16 510	8	8.37	7	0.312	1.39	0.212	0.943	0.286	1.27	0.187	0.832	0.260	1.16

^A 58 wires minimum.

^B 18 wires minimum.

^C 35 wires minimum.