



SLOVENSKI STANDARD
SIST EN 1307:2014+A1:2016/oprA2:2017
01-maj-2017

Tekstilne talne obloge - Razvrščanje

Textile floor coverings - Classification

Textile Bodenbeläge - Einstufung

Revêtements de sol textile - Classement d'usage

Ta slovenski standard je istoveten z: EN 1307:2014+A1:2016/prA2

ICS:

97.150

Talne obloge

Floor coverings

SIST EN 1307:2014+A1:2016/oprA2:2017 en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
EN 1307:2014+A1:2016
prA2

April 2017

ICS 97.150

English Version

Textile floor coverings - Classification

Revêtements de sol textile - Classement d'usage

Textile Bodenbeläge - Einstufung

This draft amendment is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 134.

This draft amendment A2, if approved, will modify the European Standard EN 1307:2014+A1:2016. If this draft becomes an amendment, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration.

This draft amendment was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

EN1307:2014+A1:2016/prA2 (E)

Contents

Page

European foreword.....	3
1 Modification to Clause 6: Table 3 – Basic requirements.....	4

European foreword

This document (EN 1307:2014+A1:2016/prA2) has been prepared by Technical Committee CEN/TC 134 “Resilient, textile and laminate floor coverings”, the secretariat of which is held by NBN.

This document is currently submitted to the CEN Enquiry.


EN1307:2014+A1:2016/prA2 (E)

1 Modification to Clause 6: Table 3 – Basic requirements

Delete the 6th row, counting from the bottom, starting with "Fibre bind for cut-pile carpets with ≥ 80 % natural fibres" as indicated below.

"

Table 3 — Basic requirements

Characteristic	Test method	Requirements	Applicable for (X means required)				
			Carpets with pile	Carpets without pile	Flat Needed	Pile Needed	Flocked
Colour fastness to light ^{a b}	EN ISO 105-B0 2		X	X	X	X	X
- Man-made fibres		≥ 5					
- Natural fibres		≥ 4					
Colour fastness to rubbing ^{a b}	EN ISO 105-X1 2		X	X	X	X	X
- Wet		≥ 3					
- Dry		$\geq 3-4$					
Colour fastness to water (change in colour) ^{a b}	EN ISO 105-E0 1		X	X	X	X	X
- Plain carpets		$\geq 3-4$					
- Other carpets		≥ 4					
Colour fastness to water(staining) ^{a b}			X	X	X	X	X
- All carpets		$\geq 2-3$					
Fibre bind < 80 % natural fibres							
- Loop pile carpets	EN 1963:2007 test C	Fuzzing below level of reference photographs	X				
- Cut pile carpets	EN 1963 test A (Number of cycles defined by calibration)	Loss of mass < 25 %	X				X
Fibre bind for cut-pile carpets with ≥ 80 % natural fibres	ISO 11856	Weight loss < 250 mg at 10 000 rubs and < 70 mg between 10 000 and 30 000 rubs	X	-	-	-	
Dimensional stability ^c	ISO 2551	Shrinkage $\leq 1,2$ % Extension $\leq 0,5$ %		X	X	X	X

EN1307:2014+A1:2016/prA2 (E)

Characteristic	Test method	Requirements	Applicable for (X means required)				
			Carpets with pile	Carpets without pile	Flat Needled	Pile Needled	Flocked
Assessment of impregnation	EN 1269	≥ 2-3			X		
^(A1) Hairiness/pilling	EN 1963 test D 200 cycles	≥ 2,5		X ^d	X	Type B1	
Peel resistance	EN ISO 24345	≥ 40 N per 50 mm					X
Water impermeability	Annex G	pass					X
<p>a Conformity to be declared by manufacturer for each colour.</p> <p>b In case of blends, the predominant fibre is leading. In case of 50/50 blends, the most stringent criterion is valid.</p> <p>c At the final stage due to the effects of varied heat and water conditions, only applicable if loose laid.</p> <p>d Requirement to be met after testing in both directions (machine and across) for carpets without pile. ^(A1)</p>							

"