



# SLOVENSKI STANDARD

## SIST EN IEC 60793-1-49:2019

01-januar-2019

Nadomešča:

SIST EN 60793-1-49:2007

---

**Optična vlakna - 1-49. del: Merilne metode in postopki preskušanja - Diferenčna zakasnitev rodov (IEC 60793-1-49:2018)**

Optical fibres - Part 1-49: Measurement methods and test procedures - Differential mode delay (IEC 60793-1-49:2018)

Lichtwellenleiter - Teil 1-49: Messmethoden und Prüfverfahren - Gruppenlaufzeitdifferenz (IEC 60793-1-49:2018)

Fibres optiques - Partie 1-49: Méthodes de mesure et procédures d'essai - Retard différentiel de mode (IEC 60793-1-49:2018)

**Ta slovenski standard je istoveten z: EN IEC 60793-1-49:2018**

---

**ICS:**

33.180.10 (Optična) vlakna in kabli Fibres and cables

**SIST EN IEC 60793-1-49:2019 en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN IEC 60793-1-49:2019](https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-a03e2b42a429/sist-en-iec-60793-1-49-2019)

<https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-a03e2b42a429/sist-en-iec-60793-1-49-2019>

EUROPEAN STANDARD

**EN IEC 60793-1-49**

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2018

ICS 33.180.10

Supersedes EN 60793-1-49:2006

English Version

**Optical fibres - Part 1-49: Measurement methods and test procedures - Differential mode delay (IEC 60793-1-49:2018)**

Fibres optiques - Partie 1-49: Méthodes de mesure et procédures d'essai - Retard différentiel de mode (IEC 60793-1-49:2018)

Lichtwellenleiter - Teil 1-49: Messmethoden und Prüfverfahren - Gruppenlaufzeitdifferenz (IEC 60793-1-49:2018)

This European Standard was approved by CENELEC on 2018-09-19. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**EN IEC 60793-1-49:2018 (E)****European foreword**

The text of document 86A/1812/CDV, future edition 3 of IEC 60793-1-49, prepared by SC 86A "Fibres and cables" of IEC/TC 86 "Fibre optics" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 60793-1-49:2018.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2019-06-19
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2021-09-19

This document supersedes EN 60793-1-49:2006.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

### Endorsement notice

[SIST EN IEC 60793-1-49:2019](https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-a03e2b42a429/sist-en-iec-60793-1-49-2019)

[https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-](https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-a03e2b42a429/sist-en-iec-60793-1-49-2019)

[a03e2b42a429/sist-en-iec-60793-1-49-2019](https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-a03e2b42a429/sist-en-iec-60793-1-49-2019)

The text of the International Standard IEC 60793-1-49:2018 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 60793-2-10 NOTE Harmonized as EN 60793-2-10

IEC 60793-1-42 NOTE Harmonized as EN 60793-1-42

## Annex ZA (normative)

### Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: [www.cenelec.eu](http://www.cenelec.eu).

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60793-1-1	2017	Optical fibres - Part 1-1: Measurement methods and test procedures - General and guidance	EN 60793-1-1	2017
IEC 60793-1-22	-	Optical fibres - Part 1-22: Measurement methods and test procedures - Length measurement	EN 60793-1-22	-
IEC 60793-1-41	-	Optical fibres - Part 1-41: Measurement methods and test procedures - Bandwidth	-	-
IEC 60793-1-45	-	Optical fibres - Part 1-45: Measurement methods and test procedures - Mode field diameter	EN IEC 60793-1-45	-
IEC 60825-1	-	Safety of laser products - Part 1: Equipment classification and requirements	EN 60825-1	-
IEC 60825-2	-	Safety of laser products - Part 2: Safety of optical fibre communication systems (OFCS)	EN 60825-2	-
IEC 61280-1-4	-	Fibre optic communication subsystem test procedures - Part 1-4: General communication subsystems - Light source encircled flux measurement method	EN 61280-1-4	-

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN IEC 60793-1-49:2019

<https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-a03e2b42a429/sist-en-iec-60793-1-49-2019>



IEC 60793-1-49

Edition 3.0 2018-08

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

Optical fibres – **iTeh STANDARD PREVIEW**  
Part 1-49: Measurement methods and test procedures – Differential mode delay  
(standards.iteh.ai)

Fibres optiques –  
Partie 1-49: Méthodes de mesure et procédures d'essai – Retard différentiel de  
mode

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

ICS 33.180.10

ISBN 978-2-8322-5954-2

**Warning! Make sure that you obtained this publication from an authorized distributor.**  
**Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references .....	6
3 Terms and definitions .....	7
4 Apparatus.....	8
4.1 Overview.....	8
4.2 Optical source.....	9
4.3 Probe fibre.....	10
4.4 Scanning stage.....	10
4.5 Probe to test sample coupling.....	10
4.6 Cladding mode stripper.....	10
4.7 Detection system.....	10
4.8 Sampler and digitizer.....	11
4.9 Computational equipment.....	11
4.10 System performance.....	11
4.10.1 General.....	11
4.10.2 Pulse temporal stability.....	12
4.10.3 System stability frequency limit ( <i>SSFL</i> ).....	12
5 Sampling and specimens.....	13
5.1 Test sample.....	13
5.2 Specimen end-faces.....	13
5.3 Specimen length.....	13
5.4 Specimen deployment.....	13
5.5 Specimen positioning.....	13
6 Procedure.....	13
6.1 Fibre coupling and system setup.....	13
6.2 Determination of centre.....	14
6.3 Measurement of the test sample.....	14
6.3.1 Selection of radii and quadrant.....	14
6.3.2 Collection of scan data.....	14
6.4 Determination of $\Delta T_{\text{PULSE}}$ and $\Delta T_{\text{REF}}$ .....	14
6.5 Reference test method.....	14
7 Calculations and interpretation of results.....	15
7.1 General.....	15
7.2 Differential mode delay ( <i>DMD</i> ).....	15
7.2.1 General.....	15
7.2.2 Deconvolution.....	15
7.2.3 Pulse folding.....	15
7.2.4 Determination of <i>DMD</i> .....	16
7.3 Minimum calculated effective modal bandwidth.....	17
7.3.1 General.....	17
7.3.2 Time domain pulse computation.....	17
7.3.3 Calculate the transfer function.....	18
7.3.4 Compute the power spectrum.....	18
7.3.5 Compute $EMB_C$ and $minEMB_C$ .....	18
7.4 Length normalization.....	18



8	Documentation .....	18
8.1	Information to be reported .....	18
8.2	Information available upon request .....	19
9	Specification information .....	19
Annex A (normative)	Source spectral width limitation .....	20
A.1	Limiting the effect of chromatic dispersion (CD) on the value of <i>DMD</i> .....	20
A.1.1	General .....	20
A.1.2	Limit CD contribution to <i>DMD</i> to be measured .....	20
A.1.3	Limit CD contribution to reference width .....	20
A.1.4	Adjust $\Delta T_{REF}$ to account for CD contribution .....	21
A.1.5	High-performance <i>DMD</i> fibres and spectral requirements .....	21
A.2	Chromatic dispersion in multimode fibres .....	22
Annex B (informative)	Determination of fibre optical centre .....	23
B.1	General .....	23
B.2	Method .....	23
Annex C (normative)	Detection system modal measurement .....	26
C.1	General .....	26
C.2	Determination of coupling function .....	26
C.2.1	Overview .....	26
C.2.2	Fibre sample and coupling .....	26
C.2.3	Detector response .....	26
C.2.4	Reference response .....	27
C.2.5	Coupling function determination .....	28
Annex D (informative)	Discussion of measurement details .....	29
D.1	<i>DMD</i> .....	29
D.2	$EMB_C$ calculation .....	30
Annex E (informative)	Determining <i>DMD</i> weights for $EMB_C$ calculation .....	33
E.1	Selecting a set of weightings .....	33
E.2	Procedure for generating <i>DMD</i> weightings given encircled flux data .....	33
Annex F (informative)	$EMB_C$ calculation information .....	35
F.1	Default <i>DMD</i> weightings for transmitters conforming to IEC 60793-2-10 .....	35
F.2	Example method to determine if an adjusted bandwidth (BW) metric is adequate .....	36
Bibliography	.....	38
Figure 1	– Example apparatus .....	9
Figure B.1	– Typical area data from centring waveforms .....	24
Figure D.1	– Idealized <i>DMD</i> data .....	29
Table A.1	– Worst-case chromatic dispersion .....	22
Table C.1	– Theoretical normalized coupling efficiency .....	27
Table F.1	– <i>DMD</i> weightings .....	35
Table F.2	– <i>DMD</i> weightings .....	36

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## OPTICAL FIBRES –

**Part 1-49: Measurement methods and test procedures –  
Differential mode delay**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.  
<https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b->
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-1-49 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This third edition cancels and replaces the second edition published in 2006. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) better alignment with original intent by filling some omissions and therefore improving measurement rigor;

- b) the measurement of fibres with smaller differential mode delay (and higher modal bandwidth) such as type A1a.3 fibres of IEC 60793-2-10 [1]<sup>1</sup> that are used in constructing OM4 performance category cables; new requirements on specifying detector amplitude and temporal response, specimen deployment conditions, four-quadrant scanning, and uniformity of radial locations for calculating bandwidth.

The text of this International Standard is based on the following documents:

CDV	Report on voting
86A/1812/CDV	86A/1860/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

This International Standard is to be used in conjunction with IEC 60793-1-1:2017.

A list of all parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iteh STANDARD PREVIEW  
 (standards.iteh.ai)  
 SIST EN IEC 60793-1-49:2019  
<https://standards.iteh.ai/catalog/standards/sist/445286d7-e2b8-4cb2-bc6b-a03e2b42a429/sist-en-iec-60793-1-49-2019>

<sup>1</sup> Numbers in square brackets refer to the Bibliography.

## OPTICAL FIBRES –

### Part 1-49: Measurement methods and test procedures – Differential mode delay

#### 1 Scope

This part of IEC 60793 applies only to multimode, graded-index glass-core (category A1) fibres. The test method is commonly used in production and research facilities, but is not easily accomplished in the field.

This document describes a method for characterizing the modal structure of a graded-index multimode fibre. This information is useful for assessing the bandwidth performance of a fibre especially when the fibre is intended to support a range of launch conditions, for example, those produced by standardized laser transmitters.

With this method, the output from a probe fibre that is single-moded at the test wavelength excites the multimode fibre under test. The probe spot is scanned across the end-face of the fibre under test at specified radial positions, and a set of response pulses are acquired at these positions.

Three specifiable parameters can be derived from the collected set of data.

- The first parameter, differential modal delay (*DMD*), is the difference in optical pulse delay time between the fastest and slowest mode groups of the fibre under test. *DMD* specifications place limits on modal delay over a specified range of probe fibre radial offset positions. *DMD* specifications are determined by modeling and experimentation to correspond to a minimum effective modal bandwidth (*EMB*) for the expected range of transmitters used in a link at a given performance level.
- The second specifiable parameter is derived by combining the pulses using sets of specific radial weights to determine an approximation of a set of pulses from typical transmitters. Using Fourier transforms, the calculated effective modal bandwidth (*EMB<sub>c</sub>*) is determined for each weight set. The minimum of these *EMB<sub>c</sub>* values (*minEMB<sub>c</sub>*) is the specifiable parameter.
- The third specifiable parameter, the computed overfilled launch bandwidth, *OMB<sub>c</sub>*, is determined in a manner similar to *EMB<sub>c</sub>*, but by applying just one weight set to the set of pulses; this weight set corresponds to the overfilling condition, where all mode groups are equally excited.

The test's intent is to quantify the effects of interactions of the fibre modal structure and the source modal characteristics excluding the source's spectral interaction with fibre chromatic dispersion. Adding the effects of fibre chromatic dispersion and the source spectral characteristics will reduce the overall transmission bandwidth, but this is a separate calculation in most transmission models. In this test, the contribution of chromatic dispersion is controlled by limiting the spectral width of usable test sources. Practical test sources will have non-zero spectral width and will thus slightly distort the *DMD*, *minEMB<sub>c</sub>* and *OMB<sub>c</sub>* values. These chromatic dispersion effects are considered in Annex A.

NOTE Comparison between IEC 60793-1-49 and ITU recommendations: ITU-T Recommendation G.650.1 [2] contains no information on how to measure the *DMD* of a graded-index multimode fibre.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition

cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-1:2017, *Optical fibres – Part 1-1: Measurement methods and test procedures – General and guidance*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-41, *Optical fibres – Part 1-41: Measurement methods and test procedures – Bandwidth*

IEC 60793-1-45, *Optical fibres – Part 1-45: Measurement methods and test procedures – Mode field diameter*

IEC 60825-1, *Safety of laser products – Part 1: Equipment classification and requirements*

IEC 60825-2, *Safety of laser products – Part 2: Safety of optical fibre communication systems (OFCS)*

IEC 61280-1-4, *Fibre optic communication subsystem test procedures – Part 1-4: General communication subsystems – Light source encircled flux measurement method*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1

##### maximum *DMD*

maximum *DMD* occurring between the outer ( $R_{OUTER}$ ) and inner ( $R_{INNER}$ ) limits of radial offset position over which the probe spot is scanned for one or more sets of  $R_{OUTER}$  and  $R_{INNER}$

#### 3.2

##### minimum $EMB_c$

$minEMB_c$

minimum  $EMB_c$  among the  $EMB_c$  values calculated from a sequence of *DMD* weightings

Note 1 to entry: The user of this document may also specify the calculated overfilled modal bandwidth ( $OMB_c$ ).

#### 3.3

##### differential mode delay

*DMD*

estimated difference in optical pulse delay time between the fastest and slowest modes excited for all radial offset positions between and including  $R_{INNER}$  and  $R_{OUTER}$

Note 1 to entry: This note applies to the French language only.