



SLOVENSKI STANDARD SIST EN IEC 62364:2019

01-maj-2019

Nadomešča:
SIST EN 62364:2014

Hidravlični stroji - Navodilo za obravnavanje hidroabrazivne erozije pri Kaplanovih, Francisovih in Peltonovih turbinah (IEC 62364:2019)

Hydraulic machines - Guide for dealing with hydro-abrasive erosion in Kaplan, Francis, and Pelton turbines (IEC 62364:2019)

Wasserturbinen - Leitfaden für den Umgang mit hydroabrasiver Erosion in Kaplan-, Francis- und Pelton-Turbinen (IEC 62364:2019)

Machines hydrauliques - Guide relatif au traitement de l'érosion hydro-abrasive des turbines Kaplan, Francis et Pelton (IEC 62364:2019)

Ta slovenski standard je istoveten z: EN IEC 62364:2019

ICS:

23.100.10	Hidravlične črpalke in motorji	Pumps and motors
27.140	Vodna energija	Hydraulic energy engineering

SIST EN IEC 62364:2019 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN IEC 62364:2019](#)

<https://standards.iteh.ai/catalog/standards/sist/4ec3be51-3a6d-4cdd-baf0-4f13ff29e0d1/sist-en-iec-62364-2019>

EUROPEAN STANDARD

EN IEC 62364

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2019

ICS 23.100.10; 27.140

Supersedes EN 62364:2013

English Version

Hydraulic machines - Guidelines for dealing with hydro-abrasive erosion in kaplan, francis and pelton turbines (IEC 62364:2019)

Machines hydrauliques - Lignes directrices relatives au traitement de l'érosion hydro-abrasive des turbines kaplan, francis et pelton
(IEC 62364:2019)

Wasserturbinen - Leitfaden für den Umgang mit hydroabrasiver Erosion in Kaplan-, Francis und Pelton-Turbinen
(IEC 62364:2019)

This European Standard was approved by CENELEC on 2019-02-18. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

[SIST EN IEC 62364:2019](#)

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN IEC 62364:2019 (E)**European foreword**

The text of document 4/351/FDIS, future edition 2 of IEC 62364, prepared by IEC TC 4 "Hydraulic turbines" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 62364:2019.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2019-11-18
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2022-02-18

This document supersedes EN 62364:2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

Endorsement notice

iTeh STANDARD PREVIEW
(standards.iteh.ai)

The text of the International Standard IEC 62364:2019 was approved by CENELEC as a European Standard without any modification.

[SIST EN IEC 62364:2019](https://standards.iteh.ai/catalog/standards/sist/4ec3be51-3a6d-4cdd-baff-4113129e0d1/sist-en-iec-62364-2019)

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 60193:1999	NOTE	Harmonized as EN 60193:1999.
IEC 60609-2:1997	NOTE	Harmonized as EN 60609-2:1999.
IEC 60041	NOTE	Harmonized as EN 60041.
ISO 4288	NOTE	Harmonized as EN ISO 4288.
ISO 2178	NOTE	Harmonized as EN ISO 2178.
ISO 6507-1	NOTE	Harmonized as EN ISO 6507-1.
ISO 14916:2017	NOTE	Harmonized as EN ISO 14916:2017.



IEC 62364

Edition 2.0 2019-01

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Hydraulic machines – Guidelines for dealing with hydro-abrasive erosion
in kaplan, francis, and pelton turbines**

**Machines hydrauliques – Lignes directrices relatives
au traitement de l'érosion hydro-abrasive des turbines kaplan, francis et pelton**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 23.100.10; 27.140

ISBN 978-2-8322-6286-3

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	5
INTRODUCTION.....	7
1 Scope.....	8
2 Terms, definitions and symbols.....	8
3 Prediction of hydro-abrasive erosion rate.....	12
3.1 Model for hydro-abrasive erosion depth	12
3.2 Reference model.....	13
3.3 Simplified hydro-abrasive erosion evaluation	14
4 Design.....	15
4.1 General.....	15
4.2 Selection of materials with high resistance to hydro-abrasive erosion and coating.....	16
4.3 Stainless steel overlays	16
4.4 Water conveyance system	16
4.5 Valve	17
4.5.1 General	17
4.5.2 Protection (closing) of the gap between housing and trunnion.....	17
4.5.3 Stops located outside the valve	17
4.5.4 Proper capacity of inlet valve operator.....	18
4.5.5 Increase bypass size to allow higher guide vane leakage	18
4.5.6 Bypass system design	18
4.6 Turbine	18
4.6.1 General	18
4.6.2 Hydraulic design.....	18
4.6.3 Mechanical design.....	20
5 Operation and maintenance.....	26
5.1 Operation.....	26
5.2 Spares and regular inspections	28
5.3 Particle sampling and monitoring	28
6 Materials with high resistance to hydro-abrasive erosion	29
6.1 Guidelines concerning relative hydro-abrasive erosion resistance of materials including hydro-abrasive erosion resistant coatings	29
6.1.1 General	29
6.1.2 Discussion and conclusions	30
6.2 Guidelines concerning maintainability of hydro-abrasive erosion resistant coating materials	30
6.2.1 Definition of terms used in this subclause	30
6.2.2 Time between overhaul for protective coatings	30
6.2.3 Repair of protective coatings	31
7 Guidelines on insertions into specifications.....	32
7.1 General.....	32
7.2 Properties of particles going through the turbine	33
7.3 Size distribution of particles	34
Annex A (informative) <i>PL</i> calculation example.....	35
Annex B (informative) Measuring and recording hydro-abrasive erosion damages	37
B.1 Recording hydro-abrasive erosion damage	37

B.2	Pelton runner without coating.....	37
B.3	Needle tip and mouth piece without coating	38
B.4	Pelton runner with hardcoating.....	38
B.5	Needle tip, seat ring and nozzle housing with coating	38
B.6	Francis runner and stationary labyrinth without coating.....	39
B.7	Francis runner with coating and stationary labyrinth.....	39
B.8	Guide vanes and facing plates without coating.....	39
B.9	Guide vanes and facing plates with coating.....	40
B.10	Stay vanes.....	40
B.11	Francis labyrinth seals uncoated.....	40
B.12	Kaplan uncoated.....	40
B.13	Kaplan coated.....	41
B.14	Sample data sheets	41
B.15	Inspection record, runner blade inlet.....	42
B.16	Inspection record, runner blade outlet.....	43
B.17	Inspection record, runner band	44
B.18	Inspection record, guide vanes	45
B.19	Inspection record, facing plates and covers	46
B.20	Inspection record, upper stationary seal.....	47
B.21	Inspection record, upper rotating seal	48
B.22	Inspection record, lower stationary seal	49
B.23	Inspection record, lower rotating seal.....	50
B.24	Inspection record, runner bucket.....	51
B.25	Inspection record, Pelton runner splitter.....	52
Annex C (informative)	Monitoring of particle concentration and properties and water sampling procedure	53
C.1	General.....	53
C.2	Sampling before building a power station.....	53
C.3	Sampling in existing power stations	54
C.4	Logging of samples.....	54
Annex D (informative)	Procedures for analysis of particle concentration, size, hardness and shape	55
D.1	General.....	55
D.2	Particle concentration	55
D.3	Particle size distribution	55
D.4	Mineralogical composition	55
D.5	Particle geometry.....	55
Annex E (informative)	Frequency of sediment sampling	58
Annex F (informative)	Typical criteria to determine overhaul time due to hydro-abrasive erosion	59
F.1	General.....	59
F.2	Parameters which are observable while the unit is in operation.....	59
F.3	Criteria that require internal inspection of the unit.....	60
Annex G (informative)	Example to calculate the hydro-abrasive erosion depth.....	61
Annex H (informative)	Examples to calculate the TBO in the reference model.....	63
Annex I (informative)	Background for hydro-abrasive erosion depth model	66
I.1	Model background and derivation.....	66
I.2	Introduction to the <i>PL</i> variable.....	67
I.3	Calibration of the formula.....	69

Annex J (informative) Quality control of thermal sprayed WC-CoCr.....	71
J.1 Specification	71
J.2 Quality control	71
Bibliography.....	72
Figure 1 – Estimation of the characteristic velocities in guide vanes, W_{gv} , and runner, W_{run} , as a function of turbine specific speed	13
Figure 2 – Simplified evaluation of risk of hydro-abrasive erosion for first assessment.....	15
Figure 3 – Example of protection of transition area	17
Figure 4 – Runner blade overhang in refurbishment project	19
Figure 5 – Example of cavitation on runner band due to thicker blades	20
Figure 6 – Example of design of guide vane trunnion seals.....	21
Figure 7 – Example of fixing of facing plates from the dry side (bolt to the left)	23
Figure 8 – Head cover balancing pipes with bends.....	24
Figure 9 – Step labyrinth with optimized shape for hardcoating.....	26
Figure 10 – Sample plot of particle concentration versus time.....	28
Figure D.1 – Typical examples of particle geometry	57
Figure I.1 – Example of flow pattern in a Pelton injector at different load	68
iTeh STANDARD PREVIEW (standards.iteh.ai)	
Table 1 – Values of K_f and p for various components.....	13
Table 2 – Overview over the feasibility for repair C on site.....	31
Table 3 – Form for properties of particles going through the turbine.....	33
Table 4 – Form for size distribution of particles.....	34
Table A.1 – Example of documenting sample tests	35
Table A.2 – Example of documenting sample results	36
Table B.1 – Inspection record, runner blade inlet form	42
Table B.2 – Inspection record, runner blade outlet form	43
Table B.3 – Inspection record, runner band form.....	44
Table B.4 – Inspection record, guide vanes form.....	45
Table B.5 – Inspection record, facing plates and covers form.....	46
Table B.6 – Inspection record, upper stationary seal form.....	47
Table B.7 – Inspection record, upper rotating seal form	48
Table B.8 – Inspection record, lower stationary seal form	49
Table B.9 – Inspection record, lower rotating seal form.....	50
Table B.10 – Inspection record, runner bucket.....	51
Table B.11 – Inspection record, Pelton runner splitter	52
Table G.1 – Calculations.....	62
Table H.1 – Pelton turbine calculation example.....	63
Table H.2 – Francis turbine calculation example	64
Table I.1 – Analysis of the calibration constant K_f and p	70
Table J.1 – Recommended items to include in HVOF inspection	71

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**HYDRAULIC MACHINES –
GUIDELINES FOR DEALING WITH HYDRO-ABRASIVE
EROSION IN KAPLAN, FRANCIS, AND PELTON TURBINES**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62364 has been prepared by IEC technical committee 4: Hydraulic turbines.

This second edition cancels and replaces the first edition published in 2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the formula for TBO in Pelton reference model has been modified;
- b) the formula for calculating sampling interval has been modified;
- c) the chapter in hydro-abrasive erosion resistant coatings has been substantially modified;
- d) the annex with test data for hydro-abrasive erosion resistant materials has been removed;
- e) a simplified hydro-abrasive erosion evaluation has been added.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
4/351/FDIS	4/366/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

[SIST EN IEC 62364:2019](https://standards.iteh.ai/catalog/standards/sist/4ec3be51-3a6d-4cdd-baf0-4f13ff29e0d1/sist-en-iec-62364-2019)

<https://standards.iteh.ai/catalog/standards/sist/4ec3be51-3a6d-4cdd-baf0-4f13ff29e0d1/sist-en-iec-62364-2019>

INTRODUCTION

The number of hydro power plants with hydro-abrasive erosion is increasing worldwide.

An overall approach is needed to minimize the impact of this phenomenon. Already at the start of the planning phase an evaluation should be done to quantify the hydro-abrasive erosion and the impact on the operation. For this, the influencing parameters and their impact on the hydro-abrasive erosion have to be known. The necessary information for the evaluation comprises among others the future design, the particle parameters of the water, which will pass the turbine, the reservoir sedimentation and the power plant owner's framework for the future operation like availability or maximum allowable efficiency loss, before an overhaul needs to be done.

Based on this evaluation of the hydro-abrasive erosion, an optimised solution can then be found, by analysing all measures in relation to investments, energy production and maintenance costs as decision parameters. Often a more hydro-abrasive erosion-resistant design, instead of choosing the turbine design with the highest efficiency, will lead to higher revenue. This analysis is best performed by the overall plant designer.

With regards to the machines, owners should find the means to communicate to potential suppliers for their sites, their desire to have the particular attention of the designers at the turbine design phase, directed to the minimization of the severity and effects of hydro-abrasive erosion.

Limited consensus and very little quantitative data exists on the steps which the designer could and should take to extend the useful life before major overhaul of the turbine components when they are operated under severe hydro-abrasive erosion service. This has led some owners to write into their specifications, conditions which cannot be met with known methods and materials.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
[SIST EN IEC 62364:2019](https://standards.iteh.ai/catalog/standards/sist/4ec3be51-3a6d-4cdd-baf0-4f13ff29e0d1/sist-en-iec-62364-2019)
<https://standards.iteh.ai/catalog/standards/sist/4ec3be51-3a6d-4cdd-baf0-4f13ff29e0d1/sist-en-iec-62364-2019>

HYDRAULIC MACHINES – GUIDELINES FOR DEALING WITH HYDRO-ABRASIVE EROSION IN KAPLAN, FRANCIS, AND PELTON TURBINES

1 Scope

This document gives guidelines for:

- a) presenting data on hydro-abrasive erosion rates on several combinations of water quality, operating conditions, component materials, and component properties collected from a variety of hydro sites;
- b) developing guidelines for the methods of minimizing hydro-abrasive erosion by modifications to hydraulic design for clean water. These guidelines do not include details such as hydraulic profile shapes which are determined by the hydraulic design experts for a given site;
- c) developing guidelines based on “experience data” concerning the relative resistance of materials faced with hydro-abrasive erosion problems;
- d) developing guidelines concerning the maintainability of materials with high resistance to hydro-abrasive erosion and hardcoatings;
- e) developing guidelines on a recommended approach, which owners could and should take to ensure that specifications communicate the need for particular attention to this aspect of hydraulic design at their sites without establishing criteria which cannot be satisfied because the means are beyond the control of the manufacturers;
- f) developing guidelines concerning operation mode of the hydro turbines in water with particle materials to increase the operation life.

It is assumed in this document that the water is not chemically aggressive. Since chemical aggressiveness is dependent upon so many possible chemical compositions, and the materials of the machine, it is beyond the scope of this document to address these issues.

It is assumed in this document that cavitation is not present in the turbine. Cavitation and hydro-abrasive erosion can reinforce each other so that the resulting erosion is larger than the sum of cavitation erosion plus hydro-abrasive erosion. The quantitative relationship of the resulting hydro-abrasive erosion is not known and it is beyond the scope of this document to assess it, except to suggest that special efforts be made in the turbine design phase to minimize cavitation.

Large solids (e.g. stones, wood, ice, metal objects, etc.) traveling with the water can impact turbine components and produce damage. This damage can in turn increase the flow turbulence thereby accelerating wear by both cavitation and hydro-abrasive erosion. Hydro-abrasive erosion resistant coatings can also be damaged locally by impact of large solids. It is beyond the scope of this document to address these issues.

This document focuses mainly on hydroelectric powerplant equipment. Certain portions can also be applicable to other hydraulic machines.

2 Terms, definitions and symbols

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

NOTE 1 Terms and definitions are also based, where relevant, on IEC TR 61364.

NOTE 2 The International System of Units (S.I.) is adopted throughout this document but other systems are allowed.

Sub-clause	Term	Definition	Symbol	Unit
2.2.1	specific hydraulic energy of a machine	specific energy of water available between the high and low pressure reference sections 1 and 2 of the machine Note 1 to entry: For full information, see IEC 60193.	E	J/kg
2.2.2	acceleration due to gravity	local value of gravitational acceleration at the place of testing Note 1 to entry: For full information, see IEC 60193.	g	m/s ²
2.2.3	turbine head pump head	available head at hydraulic machine terminal $H = E/g$	H	m
2.2.4	reference diameter	reference diameter of the hydraulic machine Note 1 to entry: For Pelton turbines this is the pitch diameter, for Kaplan turbines this is the runner chamber diameter and for Francis and Francis type pump turbines this is the blade low pressure section diameter at the band Note 2 to entry: See IEC 60193 for further information.	D	m
2.2.5	hub diameter	the diameter of runner hub for Kaplan turbines	D_h	mm
2.2.6	hydro-abrasive erosion depth	depth of material removed (measured perpendicular to the original surface) from a component due to hydro-abrasive erosion	S	mm
2.2.7	characteristic velocity	characteristic velocity defined for each machine component and used to quantify hydro-abrasive erosion damage Note 1 to entry: See also 2.2.20 to 2.2.24.	W	m/s
2.2.8	particle concentration	mass concentration of particles, i.e. the mass of solid particles per volume of water-particle mixture Note 1 to entry: In case the particle concentration is expressed in parts per million (ppm) it is recommended to use the mass of particles per volume of water, so that 1 000 ppm approximately corresponds to 1 kg/m ³ .	C	kg/m ³

Sub-clause	Term	Definition	Symbol	Unit
2.2.9	particle load	<p>the integral of the modified particle concentration over time:</p> $PL = \int_0^T C(t) \times K_{\text{size}}(t) \times K_{\text{shape}}(t) \times K_{\text{hardness}}(t) dt$ $\left(\approx \sum_{n=1}^N C_n \times K_{\text{size},n} \times K_{\text{shape},n} \times K_{\text{hardness},n} \times T_{s,n} \right)$ <p>$C(t) = 0$ if no water is flowing through the turbine.</p> <p>Note 1 to entry: For Francis turbines $C(t) = 0$ when calculating PL for runner and labyrinth seals, if the unit is at standstill with pressurized spiral case, but $C(t) \neq 0$ when calculating PL for guide vanes and facing plates.</p>	PL	$\text{kg} \times \text{h}/\text{m}^3$
2.2.10	size factor	factor that characterizes how the hydro-abrasive erosion relates to the size of the abrasive particles = median particle size dP_{50} in mm	K_{size}	
2.2.11	shape factor	<p>factor that characterizes how the hydro-abrasive erosion relates to the shape of the abrasive particles</p> <p>Note 1 to entry: See Annex D.</p>	K_{shape}	
2.2.12	hardness factor	<p>factor that characterizes how the hydro-abrasive erosion relates to the hardness of the abrasive particles</p> <p>for 13Cr4Ni stainless steel: $K_{\text{hardness}} =$ fraction of particles harder than Mohs 4,5.</p> <p>for hard coated surfaces: $K_{\text{hardness}} =$ fraction of particles harder than Mohs 7,0.</p>	K_{hardness}	
2.2.13	material factor	factor that characterizes how the hydro-abrasive erosion relates to the material properties of the base material	K_m	
2.2.14	flow coefficient	coefficient that characterizes how the hydro-abrasive erosion relates to the water flow around each component	K_f	$\frac{\text{mm} \times \text{s}^{3,4}}{\text{kg} \times \text{h} \times \text{m}^\alpha}$
2.2.15	sampling interval	time interval between two water samples taken to determine the concentration of abrasive particles in the water	T_s	h
2.2.16	yearly particle load	Total load (PL) for 1 year of operation, i.e. PL for $T = 8\,760$ h calculated in accordance with 2.2.9	PL_{year}	$\text{kg} \times \text{h}/\text{m}^3$
2.2.17	maximum particle load	<p>maximum value of the integrand in the PL integral during a specified time interval, i.e. the maximum value of the following expression</p> $PL_{\text{max}} = C(t) \times K_{\text{size}}(t) \times K_{\text{shape}}(t) \times K_{\text{hardness}}(t)$	PL_{max}	kg/m^3
2.2.18	particle median diameter	median diameter of abrasive particles in a sample, i.e. such diameter that the particles with size smaller than the value under consideration represent 50 % of the total mass of particles in the sample	dP_{50}	mm
2.2.19	impingement angle	angle between the particle trajectory and the surface of the substrate		°

Sub-clause	Term	Definition	Symbol	Unit
2.2.20	characteristic velocity in Francis guide vanes characteristic velocity in Kaplan guide vanes	flow through unit divided by the minimum flow area at the guide vane apparatus at best efficiency point $W_{gv} = \frac{Q}{a \times Z_0 \times B_0}$	W_{gv}	m/s
2.2.21	characteristic velocity in Pelton injector	speed of the water flow at injector location $W_{inj} = \sqrt{2 \times E}$	W_{inj}	m/s
2.2.22	characteristic velocity in turbine runner	relative velocity between the water and the runner blade estimated with below formulas at best efficiency point $W_{run} = \sqrt{u_2^2 + c_2^2}$ $u_2 = n \times \pi \times D$ $c_2 = \frac{Q \times 4}{\pi \times D^2} \text{ (Francis)}$ $c_2 = \frac{Q \times 4}{\pi \times (D^2 - D_h^2)} \text{ (Kaplan)}$	W_{run}	m/s
2.2.23	characteristic velocity in Pelton runner	relative velocity between the water and the runner bucket $W_{run} = 0,5 \times \sqrt{2 \times E}$	W_{run}	m/s
2.2.24	discharge	volume of water per unit time passing through any section in the system	Q	m ³ /s
2.2.25	guide vane opening	average shortest distance between adjacent guide vanes (at a specified section if necessary) Note 1 to entry: For further information, see IEC 60193.	a	m
2.2.26	number of guide vanes	total number of guide vanes in a turbine	z_0	
2.2.27	distributor height	height of the distributor in a turbine	B_0	m
2.2.28	rotational speed	number of revolutions per unit time	n	1/s
2.2.29	specific speed	commonly used specific speed of a hydraulic machine $n_s = \frac{60 \times n \times \sqrt{P}}{H^{5/4}}$ P and H are taken in the rated operating point and given in kW and m respectively	n_s	rpm
2.2.30	output	output of the turbine in the rated operating point	P	kW
2.2.31	hydro-abrasive erosion depth of target unit	estimated actual depth of metal that will be removed from a component of the target turbine due to particle hydro-abrasive erosion Note 1 to entry: For use with the reference model.	S_{target}	mm
2.2.32	hydro-abrasive erosion depth of reference unit	hydro-abrasive erosion depth of metal that has been removed from a component of the reference turbine due to hydro-abrasive erosion Note 1 to entry: For use with the reference model.	S_{ref}	mm