



Designation: F1537-07 ~~Designation: F 1537 - 08~~

Standard Specification for Wrought Cobalt-28Chromium-6Molybdenum Alloys for Surgical Implants (UNS R31537, UNS R31538, and UNS R31539)¹

This standard is issued under the fixed designation F 1537; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for three wrought cobalt-28chromium-6molybdenum alloys used for surgical implants. The properties specified apply specifically to wrought bar, rod, and wire.

~~1.2 The values stated in inch-pound units are to be regarded as the standard. The SI equivalents in parentheses are for information only.~~

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards:²

E 8 Test Methods for Tension Testing of Metallic Materials

E 18 Test Methods for Rockwell Hardness of Metallic Materials

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E 112 Test Methods for Determining Average Grain Size

E 354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

F 75 Specification for Cobalt-28 Chromium-6 Molybdenum Alloy Castings and Casting Alloy for Surgical Implants (UNS R30075)

F 799 Specification for Cobalt-28Chromium-6Molybdenum Alloy Forgings for Surgical Implants (UNS R31537, R31538, R31539)

2.2 Aerospace Material Specifications:³

AMS 2248 Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

AMS 2269 Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys

AMS 2630 Ultrasonic Inspection

2.3 ISO Standards:⁴

ISO 5832-12 Implants for Surgery—Metallic Materials—Part 12: Wrought Cobalt-Chromium-Molybdenum Alloy

ISO 6892 Metallic Materials Tensile Testing at Ambient Temperature

ISO 9001 Quality Management Systems—Requirements

2.4 American Society for Quality Standard:⁵

ASQ C1 Specification of General Requirements for a Quality Program

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

¹ This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved July Oct. 1, 2007-2008. Published August 2007-October 2008. Originally approved in 1994. Last previous edition approved in 20002007 as F 1537 - 087.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, http://www.sae.org.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

⁵ Available from American Society for Quality (ASQ), 600 N. Plankinton Ave., Milwaukee, WI 53203, http://www.asq.org.

*A Summary of Changes section appears at the end of this standard.

3.1.1 *lot*—the total number of mill products produced from the same melt heat under the same conditions at essentially the same time.

4. Ordering Information

4.1 Inquiries and orders for material under this specification shall include the following information:

- 4.1.1 Quantity,
- 4.1.2 ASTM designation, alloy number, and date of issue,
- 4.1.3 Mechanical properties (See Section 7),
- 4.1.4 Form (bar, rod or wire),
- 4.1.5 Applicable dimensions including size, thickness, width, and length (exact, random, or multiples) or drawing number,
- 4.1.6 Condition (See Section 5),
- 4.1.7 Special tests (if any), and
- 4.1.8 Other requirements.

5. Materials and Manufacture

5.1 Product shall be furnished as specified below:

- 5.1.1 The annealed condition is typically supplied as a hot rolled and annealed product.
- 5.1.2 The hot worked condition is typically supplied as a hot rolled and unannealed product.
- 5.1.3 The warm worked condition is typically supplied as a thermomechanically processed product to achieve a strain-hardened structure.

6. Chemical Requirements

6.1 The cobalt-28chromium-6molybdenum alloys shall conform to the chemical requirements prescribed in Table 1. The supplier shall not ship material that is outside the limits specified in Table 1 for the applicable alloy.

6.1.1 Requirements for the major and minor elemental constituents are listed in Table 1. Also listed are important residual elements. Analysis for elements not listed in Table 1 is not required to verify compliance with this specification.

6.2 *Product Analysis*— The product analysis is either for the purpose of verifying the composition of a heat or lot or to determine variations in the composition within the heat.

6.2.1 Acceptance or rejection of a heat or lot of material may be made by the purchaser on the basis of this product analysis.

6.2.2 Product analysis tolerances do not broaden the specified heat analysis requirements but cover variations between laboratories in the measurement of chemical content. Product analysis limits shall be as specified in Table 2.

7. Mechanical Requirements

7.1 *Tensile Properties:*

7.1.1 Perform at least two tension and two bend tests from each lot. Should any of these test pieces not meet the specified requirements, test two additional test pieces representative of the same lot, in the same manner, for each failed test piece. The lot shall be considered in compliance only if all additional test pieces meet the specified requirements.

7.1.2 Tensile test results for which any specimen fractures outside the gauge length shall be considered acceptable, if both the elongation and reduction of area meet the minimum requirements specified. Refer to subsections 7.11.4 and 7.11.5 of Test Methods E 8.

TABLE 1 Chemical Composition

Element	Composition % (mass/mass)					
	Alloy 1		Alloy 2		Alloy 3	
	UNS R31537 (Low Carbon)		UNS R31538 (High Carbon)		UNS R31539 (Dispersion Strengthened)	
	min	max	min	max	min	max
Carbon	0.14	0.15	0.35	0.14
Aluminum	0.30	1.00
Lanthanum	0.03	0.20
Chromium	26.0	30.0	26.0	30.0	26.0	30.0
Molybdenum	5.0	7.0	5.0	7.0	5.0	7.0
Nickel	1.0	1.0	1.0
Iron	0.75	0.75	0.75
Silicon	1.0	1.0	1.0
Manganese	1.0	1.0	1.0
Nitrogen	0.25	0.25	0.25
Cobalt ^A	Balance		Balance		Balance	

^A Approximately equal to the difference of 100 % and the sum percentage of the other specified elements. The percentage of cobalt difference is not required to be reported.