

### SLOVENSKI STANDARD oSIST prEN ISO 17703:2018

01-julij-2018

Obutev - Preskusne metode za zgornje dele - Obnašanje pri visoki temperaturi (ISO 17703:2003)

Footwear - Test methods for uppers - High temperature behaviour (ISO 17703:2003)

Schuhe - Prüfverfahren für Obermaterialien - Verhalten bei hohen Temperaturen (ISO 17703:2003)

Chaussures - Méthodes d'essai des tiges - Comportement aux températures élevées (ISO 17703:2003)

Ta slovenski standard je istoveten z: prEN ISO 17703

ICS:

61.060 Obuvala Footwear

oSIST prEN ISO 17703:2018 en,fr,de

**oSIST prEN ISO 17703:2018** 

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN ISO 17703:2018</u>

oSIST prEN ISO 17703:2018

## INTERNATIONAL STANDARD

ISO 17703

First edition 2003-11-01

### Footwear — Test methods for uppers — High temperature behaviour

Chaussures — Méthodes d'essai des tiges — Comportement aux températures élevées

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN ISO 17/03:2018</u> https://standards.iteh.ai/catalog/standards/sist/f96b075c-fe5e-44f1-a378-bd8c929501af/sist en-iso-17703-2018



#### PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 17703:2018

https://standards.iteh.ai/catalog/standards/sist/f96b075c-fe5e-44f1-a378-bd8c929501af/sist-en-iso-17703-2018

#### © ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17703 was prepared by CEN (as EN 13519:2001) and was adopted, under a special "fast-track procedure", by Technical Committee ISO/TC 216, *Footwear*, in parallel with its approval by the ISO member bodies.

For the purposes of international standardization, a list of corresponding International and European Standards for which equivalents are not given in EN 13519 has been added as Annex ZZ.

EN 13519:2001 (E)

### **Contents**

		page
Forew	vord	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	2
4	Apparatus and material	4
5	Sampling and conditioning	
6	Test method	5
6.1	Principle	5
6.2	PrincipleProcedure	5
7	Expression of results	
8	Test report	
-	·	
Biblio	ography	7

(standards.iteh.ai)

SIST EN ISO 17703:2018

EN 13519:2001 (E)

#### **Foreword**

This European Standard has been prepared by Technical Committee CEN/TC 309 "Footwear", the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2002, and conflicting national standards shall be withdrawn at the latest by May 2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN ISO 17/03:2018</u> https://standards.iteh.ai/catalog/standards/sist/f96b075c-fe5e-44f1-a378-bd8c929501af/sist-en-iso-17703-2018 **oSIST prEN ISO 17703:2018** 

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN ISO 17703:2018</u>

#### EN 13519:2001 (E)

### 1 Scope

This European Standard specifies a test method for determining the effect of heat on the tensile strength of uppers or complete upper assembly irrespective of the material, in order to assess the suitability for the end use.

#### 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12222 Footwear – Standard atmospheres for conditioning and testing of footwear and components for footwear.

prEN 13522 Footwear - Test methods for uppers - Tensile strength and elongation.

#### 3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

#### 3.1

#### high temperature behaviour

resistance of a material to elevated temperatures as measured by the effect on the tensile properties of the material. Particularly applicable to materials used in vulcanised footwear

### 3.2 h

#### upper

materials forming the outer surface of the footwear which is attached to the sole assembly and covers the upper dorsal surface of the foot. In the case of boots this also includes the outer face of the material covering the leg. Only the materials that are visible are included, no account should be taken of underlying materials

#### 3.3

#### complete upper assembly

finished upper, fully seamed, joined or laminated as appropriate, comprising the centre material and any lining(s) together with all components such as interlinings, adhesives, membranes, foams or reinforcements, but excluding toe puffs and stiffeners

NOTE The complete upper assembly can be flat, 2-dimensional or comprise lasted upper in the final footwear.

#### 4 Apparatus and material

The following apparatus and material shall be used:

#### 4.1 A rapid acting platen press with:

- **4.1.1** The capability of applying a pressure of 1 000 kPa ± 50 kPa on an area of 160 mm x 25 mm.
- **4.1.2** Upper and lower platens with smooth metal surfaces.
- **4.1.3** Means of maintaining upper and lower platen temperatures as specified in Table 1.
- 4.2 A thermometer capable of measuring the temperature of the surface of the platens to the nearest 1 °C.

4

EN 13519:2001 (E)

NOTE A surface mounting thermocouple and digital meter is suitable.

### 5 Sampling and conditioning

**5.1** Prepare test specimens in accordance with prEN 13522.

NOTE Test specimens can be taken from materials likely to be used for uppers or from made-up uppers or finished footwear. Prepare test pieces from complete upper assemblies when the lining material is permanently attached to the upper material.

#### 6 Test method

#### 6.1 Principle

Test specimens are pressed between two hot rigid surfaces for a predetermined time. The effect of this heat treatment on breaking strength and elongation is then determined in accordance with prEN 13522.

#### 6.2 Procedure

- **6.2.1** Adjust the temperature of the platens (4.1.2) to the required temperature, see Table 1.
- **6.2.2** Place one of the test specimens in the press (4.1) so that the surface which would be closer to the foot in the finished footwear is lowermost. Immediately close the press and apply a pressure of 1 000 kPa  $\pm$  50 kPa to the rectangular pieces of material for the required time, see Table 1.
- **6.2.3** Repeat the procedure in 6.2.2 for the remaining test specimens.
- 6.2.4 Store all the test specimens in a standard controlled environment as specified in EN 12222 for at least 72 h.

  https://standards.ireh.ai/gatalog/standards/sist/19660756\_fe5e\_44f1\_a378\_bd8e929501af/sist\_
- **6.2.5** Follow the procedure described in prEN 13522 to determine the mean breaking force and mean elongation at break.

Table 1 — Suggested platen temperatures and pressing times for simulating the moulding-on of rubber

Application	Upper platen temperature °C	Lower platen temperature °C	Pressing time min
Unheated lasts	105 ± 5	85 ± 5	12,0 ± 0,5
Heated lasts	180 ± 5	110 ± 5	$8.0 \pm 0.5$

#### 7 Expression of results

The percentage change in the values of the breaking force or the elongation break at break is calculated using the formula:

$$\frac{\overline{x_a} - \overline{x_0}}{\overline{x_0}} \cdot 100$$

where

 $x_0$  is the mean value of the tensile property before the heat treatment;