



SLOVENSKI STANDARD
oSIST prEN ISO 19277:2017
01-november-2017

**Petrokemična industrija ter industrija za predelavo nafte in zemeljskega plina -
Preskušanje primernosti in sprejeta merila za zaščitne premazne sisteme pod
izolacijo (ISO/DIS 19277:2017)**

Petroleum, petrochemical and natural gas industries - Qualification testing and
acceptance criteria for protective coating systems under insulation (ISO/DIS 19277:2017)

Erdöl-, petrochemische und Erdgasindustrie - Qualifikationsprüfungen und
Abnahmekriterien für Beschichtungssysteme unter Isolierung (ISO/DIS 19277:2017)

Essais de qualification des systèmes de revêtement protecteurs sous isolation (ISO/DIS
19277:2017)

Ta slovenski standard je istoveten z: prEN ISO 19277

ICS:

75.200	Oprema za skladiščenje nafte, naftnih proizvodov in zemeljskega plina	Petroleum products and natural gas handling equipment
--------	---	---

oSIST prEN ISO 19277:2017

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 19277

ISO/TC 67

Secretariat: NEN

Voting begins on:
2017-08-24Voting terminates on:
2017-11-15

Petroleum, petrochemical and natural gas industries — Qualification testing and acceptance criteria for protective coating systems under insulation

Titre manque

ICS: 75.200.00

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 19277:2019

<https://standards.iteh.ai/catalog/standards/sist/58da6fad-3482-43db-8f92-7bddb2f1b602/sist-en-iso-19277-2019>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 19277:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 19277:2019

<https://standards.iteh.ai/catalog/standards/sist/58da6fad-3482-43db-8f92-7bddb2f1b602/sist-en-iso-19277-2019>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Foreword	v
Introduction.....	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Performance testing design.....	3
4.1 Relationship between artificial testing and natural exposure	3
4.2 Laboratory tests.....	3
4.3 Additional laboratory tests.....	4
5 CUI classification environments	4
6 Test samples.....	4
6.1 Test panels.....	4
6.2 Steel substrates.....	4
6.3 Sampling of coatings.....	5
6.4 Number of test panels.....	5
6.5 Coating systems.....	5
6.5.1 Coating application.....	5
6.5.2 Dry film thickness	6
6.5.3 Overcoating interval.....	6
6.5.4 Conditioning.....	6
6.5.5 Heat conditioning.....	6
6.6 Scribe	6
6.7 Reference system	6
7 Test procedures and assessment.....	6
7.1 Assessment and acceptance	6
7.2 Assessment of adhesion and artificial ageing	7
7.2.1 Adhesion testing before artificial ageing.....	7
7.2.2 Artificial ageing.....	7
7.2.3 Adhesion testing after artificial ageing	8
7.3 Thermal cycling test.....	8
7.4 Multi-phase CUI cyclic corrosion test.....	8
7.4.1 Description of test.....	8
7.4.2 Test equipment-apparatus	9
7.4.3 Test set-up and preparation.....	11
7.4.4 Test procedure	11
7.4.5 Acceptance.....	12
8 Optional tests.....	13
8.1 Optional cryogenic cycling testing	13
8.1.1 General.....	13
8.1.2 Cryogenic test	13
8.1.3 Adhesion testing after cryogenic test aging.....	14
8.2 Optional vertical pipe test.....	14
8.2.1 Description of test.....	14
8.2.2 Test equipment - apparatus	14
8.2.3 Test process scope	15
8.2.4 Temperature profile calibration	16
8.2.5 Test equipment - procedure.....	16
8.3 Additional performance tests	16

ISO/DIS 19277:2017(E)

9	Test report	16
	Annex A (informative) Corrosion testing of conditioned and heat conditioned test samples	18
	Annex B (informative) Example of test report for CUI coating acceptance	19
	Annex C (informative) Example of test report for cryogenic testing	23
	Annex D (informative) Example of test report for optional vertical pipe test	24
	Bibliography	27

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 19277:2019

<https://standards.iteh.ai/catalog/standards/sist/58da6fad-3482-43db-8f92-7bddb2f1b602/sist-en-iso-19277-2019>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*.

ISO/DIS 19277:2017(E)**Introduction**

Unprotected carbon steel in insulated service with presence of water and concentrating contaminants from the atmosphere, or surrounding sources, is subject to accelerated corrosion that can lead to severe corrosion, significant section loss of the substrate and damage. Additionally, unprotected austenitic and duplex stainless steels can suffer as the result of external chloride induced stress corrosion cracking if contaminants, such as chlorides from the atmosphere and or the insulation, are present at the steel surface. Therefore, steel structures are normally protected to prevent the corrosion related damage during the operational life required of the equipment.

There are different ways of protecting steel structures from corrosion under insulation. This document deals with protection by use of coating when used as part of a system, including insulation and cladding materials, which can work together to prevent corrosion under insulation (CUI). All components of the corrosion prevention system are important in achieving adequate corrosion protection. This document only deals with the coating part of the system with focus on typical CUI coating environments. Further, this document focuses on accelerated testing protocols and acceptance criteria, so that interested parties can make informed decisions.

In order to ensure effective corrosion protection of steel structures and equipment, it is necessary for owners of such structures, planners, consultants, companies carrying out corrosion protection work, inspectors of protective coatings and manufacturers of coating materials to have at their disposal state-of-the-art information in concise form on corrosion protection by coating systems. Such information has to be as complete as possible, unambiguous and easily understandable to avoid difficulties and is understandings between the parties concerned with the practical implementation of protection work. This document is intended to give this information for those who have some technical knowledge of coatings and process operations of the equipment. It is also assumed that the user of this document is familiar with other relevant International Standards, in particular those dealing with surface preparation, testing of coatings, and relevant regulations. Although this document does not deal with financial and contractual questions, attention is drawn to the fact that, because of the considerable implications of inadequate corrosion protection especially under insulation, non-compliance with requirements and recommendations given in this document can result in not only serious financial consequences, but also potential injury to works and to the environment.

Future parts of this document are planned and can include higher temperature, cyclic and intermittent service, testing of coatings for maintenance and repair, tape applied coating materials and others as can be developed.

Petroleum, petrochemical and natural gas industries — Qualification testing for protective coating systems under insulation

1 Scope

This document describes various corrosion under insulation (CUI) environments in refineries and other related industries and environments, and establishes CUI environmental categories including operating temperature ranges from -45 °C to 204 °C . This document specifies both established and other test methods for the assessment of coatings used for prevention of CUI for each given environment. This document also provides acceptance criteria for each CUI environment.

NOTE The test results and acceptance criteria can be considered an aid in the selection of suitable coating systems. For service or peak temperatures below -45 °C an optional cryogenic test can be incorporated and for over 204 °C testing acceptance criteria can be agreed between interested parties. Additional or other test and acceptance measures are possible, but require particular agreement between the interested parties.

This document covers spray applied coatings applied on new carbon and austenitic stainless steel for use in CUI service. This document does not cover testing of sacrificial coatings, such as inorganic zinc, as these coatings can be consumed quickly in wet environments. Developing accelerated corrosion testing for what can be continuous wet service with sacrificial coatings is beyond the scope of this document.

This document does not cover tape and sheet applied products for use in preventing CUI. Further, “non-through porosity” thermal spray aluminium coatings typically greater than $250\text{ }\mu\text{m}$ dry film thickness can be tested in accordance with this document.

This document does not deal with other aspects of coating degradation, such as can be caused by abrasion, erosion ultraviolet degradation or other methods that can exist given specific environment and construction methods.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

ISO 1513, *Coatings and varnishes — Examination and preparation of samples for testing*

ISO 2409, *Coatings and varnishes — Cross-cut test*

ISO 2812-2, *Coatings and varnishes — Determination of resistance to liquids — Part 2: Water immersion method*

ISO 4624, *Coatings and varnishes — Pull-off test for adhesion*

ISO 4628-2, *Coatings and varnishes — Evaluation of degradation of coating coatings — Designation of intensity, quantity and size of common types of defect — Part 2: Designation of degree of blistering*

ISO 4628-3, *Coatings and varnishes — Evaluation of degradation of coating coatings — Designation of intensity, quantity and size of common types of defect — Part 3: Designation of degree of rusting*

ISO/DIS 19277:2017(E)

ISO 4628-4, *Coatings and varnishes — Evaluation of degradation of coating coatings — Designation of intensity, quantity and size of common types of defect — Part 4: Designation of degree of cracking*

ISO 4628-5, *Coatings and varnishes — Evaluation of degradation of coating coatings — Designation of intensity, quantity and size of common types of defect — Part 5: Designation of degree of flaking*

ISO 4628-8, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 8: Assessment of degree of delamination and corrosion around a scribe*

ISO 7384, *Corrosion tests in artificial atmospheres — General requirements*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 12944-6:1998, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 6: Laboratory performance test methods and associated assessment criteria*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

ISO 19840, *Paints and varnishes – Corrosion protection of steel structures by protective paint systems – Measurements of, and acceptance criteria for, the thickness of dry films on rough surfaces*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <http://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1**artificial ageing**

procedure designed to accelerate the ageing of a coating system, i.e. to reduce the corrosion-protective efficiency more rapidly than by natural weathering

3.2**corrosion under insulation****CUI**

corrosion that is a result of the effect of moisture and contaminants, on the steel surfaces under thermal insulation

3.3**dry film thickness****DFT**

thickness of a coating remaining on the surface when the coating has hardened

3.4**durability**

expected life of a protective coating system to the first major maintenance coating

3.5**nominal dry film thickness****NDFT**

dry film thickness specified for each coat or for the whole coating system

3.6

peak temperature

maximum temperature for the designed system, including possible upsets and temperature reached as a result of maintenance efforts such as steam cleaning

3.7

sacrificial coating

coating that provides corrosion protection by sacrificing or being consumed in the act of protecting the substrate

4 Performance testing design

4.1 Relationship between artificial testing and natural exposure

The selection of a coating system for a specific situation should preferably be based on experience from the use of the system in similar cases. The reason is that the durability of a CUI coating system depends on many external factors, such as the environment, the design of the structure, the insulation material, the weather proofing (cladding), the surface preparation, the application, drying procedures, service temperature, thermal shock, thermal cycling, peak temperature, amount of moisture, contaminants and other variables.

The durability is also linked to the chemical and physical characteristics of the system, e.g. the type of binder, the dry film thickness. These CUI related performance characteristics can be evaluated by artificial tests. Resistance to water or moisture, boiling water, steam interface, electrolytes in the system, thermal exposure, thermal shock, and thermal cycling are of primary interest.

Artificial tests and durations specified in this document have been selected to help ensure that potential coatings systems will have the characteristics needed for the durability required in the intended service. Results from artificial tests shall be used with caution, because artificial testing will not necessarily have the same effect as natural exposure. Many factors have an influence on the progress of degradation and, in the laboratory, it is not possible to accelerate all of them in the most effective method. It is therefore difficult to make a reliable ranking of coating systems of very different compositions from artificial tests in the laboratory. This can sometimes lead to efficient protective coating systems being rejected because they cannot pass these tests.

4.2 Laboratory tests

As CUI environments are very specific and have special requirements, several tests are included so that coatings products can exhibit performance in harsh environments typical of CUI exposure. These include thermal performance, boiling water, thermal shock, thermal cycling, peak temperature performance, and long term isothermal conditions. In addition, these coating products shall provide corrosion protection for long periods of time at ambient conditions, and in possibly wet conditions related to initial coating application prior to process start up, time associated with process shutdowns, and short term mothballing of the facility.

Standard weathering testing procedures shall be used to establish ambient related corrosion control test procedures and acceptance criteria. Both air dried and conditioned test samples and heat conditions test samples shall be evaluated.

Additional CUI and high temperature related tests shall also be used in order to verify a coatings ability to work under insulation at the prescribed conditions.

Inorganic zinc primers or other sacrificial coatings are no longer recommended in CUI environments due to the accelerated corrosion related to wet environments. If testing and acceptance is required, additional testing as agreed between the parties can be performed. However, long term wet

ISO/DIS 19277:2017(E)

environments are difficult to accelerate and as such the specifier/owner should be careful with any acceptance criteria for sacrificial coatings.

4.3 Additional laboratory tests

Other tests methods may also be used by agreement between interested parties.

5 CUI classification environments

Table 1 provides a list of CUI classification environments including the minimum and maximum temperatures for all environments. These descriptions include both isothermal and cyclic conditions.

Table 1 — CUI classification environments

Classification	Minimum temperature	Peak temperature
CUI-1	−45 °C	to 60 °C
CUI-2	−45 °C	60 °C to 150 °C
CUI-3	−45 °C	150 °C to 204 °C

Further, each coating should be qualified for each specific CUI classifications where it is intended to be used. A coating that meets the requirements of a CUI-1 classification does not necessarily meet the requirements of a CUI-3 classification, and a coating that meets the requirements of a CUI-3 classification does not necessarily meet the requirements of a CUI-1 classification. By consolidating testing some tests can be used for more than one classification.

For insulated service for temperatures above 204 °C additional testing can be performed as agreed to by interested parties.

An optional classification for cryogenic cycling exposure (“-Cryo”) can be added to each of the classifications in Table 1, when cryogenic testing and acceptance are included. In such cases the classifications as presented in Table 2 are appropriate.

Table 2 — CUI classification cryogenic environments

Classification	Minimum temperature	Peak temperature
CUI-1-Cryo	−196 °C	to 60 °C
CUI-2-Cryo	−196 °C	60 °C to 150 °C
CUI-3-Cryo	−196 °C	150 °C to 204 °C

6 Test samples**6.1 Test panels**

This document requires the use of test panels and other testing surfaces that are available as standard shapes typically available on the market place. Both A-36 or S275 carbon steel and 316 (316L) austenitic stainless steel test panels shall be incorporated in testing and also shapes as described in 6.2 through 6.7.

6.2 Steel substrates

Test panels will be as follows unless otherwise agreed to and documented: