NOTICE: This standard has either been superseded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.



AMERICAN SOCIETY FOR TESTING AND MATERIALS 100 Barr Harbor Dr., West Conshohocken, PA 19428 Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Specification for Prediluted Aqueous Ethylene Glycol Base Low-Silicate Engine Coolant (50 Volume Percent Minimum) for Heavy-Duty Engines Requiring an Initial Charge of Supplemental Coolant Additive (SCA)¹

This standard is issued under the fixed designation D 5345; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the requirements for a prediluted aqueous ethylene glycol base low-silicate engine coolant (50 volume percent minimum) for cooling systems of heavyduty engines. When used without further dilution, this product will function effectively during both summer and winter to provide protection from corrosion, freezing at least to -36.7° C (-34.0° F), and boiling at least to 108° C (226° F).

1.2 Prediluted coolant meeting this specification requires both an initial charge of a supplemental coolant additive (SCA) and regular maintenance doses of an SCA to continue the protection in certain operating heavy-duty engine cooling systems, particularly those of the wet cylinder liner-in-block design. The SCA additions are defined by and are the primary responsibility of the engine or vehicle manufacturer. If they provide no instructions, follow the SCA supplier's recommended instructions.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only. \underline{AST}

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:

- D 512 Test Methods for Chloride Ion in Water²
- D 516 Test Method for Sulfate Ion in Water²
- D 1119 Test Method for Ash Content of Engine Coolants and Antirusts³
- D 1120 Test Method for Boiling Point of Engine Coolants³
- D 1121 Test Method for Reserve Alkalinity of Engine Coolants and Antirusts³

- D 1122 Test Method for Density or Relative Density of Engine Coolants Concentrates and Engine Coolants by the Hydrometer³
- D 1126 Test Method for Hardness in Water²
- D 1177 Test Method for Freezing Point of Aqueous Engine Coolants³
- D 1193 Specification for Reagent Water²
- D 1287 Test Method for pH of Engine Coolants and Antirusts³
- D 1293 Test Methods for pH of Water²
- D 1384 Test Method for Corrosion Test for Engine Coolants in Glassware³
- D 1881 Test Method for Foaming Tendencies of Engine Coolants in Glassware³
- D 1882 Test Method for Effect of Cooling System Chemical Solutions on Organic Finishes for Automotive Vehicles³
- D 1888 Test Methods for Particulate and Dissolved Matter in Water⁴
- D 2570 Test Method for Simulated Service Corrosion Testing of Engine Coolants³
- D 2809 Test Method for Cavitation Corrosion and Erosion-Corrosion Characteristics of Aluminum Pumps with Engine Coolants³
- D 3306 Specification for Ethylene Glycol Base Engine Coolant for Automobile and Light Duty Service³
- D 3321 Test Method for Use of the Refractometer for Field Test Determination of the Freezing Point of Aqueous Engine Coolants³
- D 4327 Test Method for Anions in Water by Chemically Suppressed Ion Chromatography²
- D 4656 Specification for a Prediluted Aqueous Ethylene Glycol Based Engine Coolant (50 Volume % Minimum) for Automobiles and Light-Duty Service³
- D 4985 Specification for Low Silicate Ethylene Glycol Base Engine Coolant for Heavy Duty Engines Requiring a Pre-Charge of Supplemental Coolant Additive (SCA)³

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

¹ This specification is under the jurisdiction of ASTM Committee D-15 on Engine Coolants and is the direct responsibility of Subcommittee D15.13 on Prediluted Engine Coolant.

Current edition approved October 10, 1998. Published January 1999. Originally published as D 5345 – 93. Last previous edition D 5345 – 95.

² Annual Book of ASTM Standards, Vol 11.01.

³ Annual Book of ASTM Standards, Vol 15.05.

⁴ Discontinued—See 1990 Annual Book of ASTM Standards, Vol 11.01.

3.1.1 *heavy duty engine*—a diesel, gasoline, or similarly fueled internal combustion engine, having operating characteristics of a long duty cycle at or near maximum rated conditions.

3.1.2 *Discussion*—Such engines are typically used in offhighway machinery for agriculture, mining, earth-moving, and construction; Classes 5 through 8 over the road trucks and buses; high output stationary engine installations; and locomotive and marine installations (see Specifications D 3306 and D 4656 for coolant requirements for automobiles, vans, and pickup trucks, Classes 1 through 4).

3.1.3 *supplement coolant additive (SCA)*—a material added to the cooling system of a heavy-duty engine to provide additional cavitation protection and corrosion inhibition and to minimize deposits on heat transfer surfaces.

4. General Requirements

4.1 Prediluted aqueous ethylene glycol base engine coolant shall consist essentially of ethylene glycol and water and shall contain suitable corrosion inhibitors, dye, and a foam suppressor. Other glycols, such as propylene and diethylene, may be included up to a maximum of 15 % of the glycols contained in the product, if the chemical and physical properties in Table 1 are met. For example, 15 % of a 50 % aqueous glycol solution could contain up to 7.5 % of glycols other than ethylene glycol. The coolant also shall conform to the general requirements given in Table 2.

4.2 This product shall be prepared using deionized water that meets Type IV reagent water specifications (see Specification D 1193). This practice minimizes the formation of hard water scale and avoids the introduction of mineral components, such as chlorides and sulfates, which can increase the corrosion rate of aluminum and iron. The use of Type IV reagent water also minimizes interferences that may cause coolant instability or SCA compatibility problems.

4.3 When installed in accordance with the vehicle manufacturers' recommendations and those on the product label, this product shall be suitable for use in a properly maintained cooling system (see Appendix X1) in normal service for a minimum of 1 year without adversely affecting fluid flow and heat transfer.

5. Detailed Requirements

5.1 Prediluted aqueous ethylene glycol base engine coolant,

TABLE 1 Chemical and Physical Requirements of the

| Unadiusted | Prediliuted | Product |
|------------|-------------|---------|

| Property | Specified Values | ASTM Test Method |
|--|--------------------------|---------------------|
| Density or relative density, 15.5/15.5°C (60°F) | 1.0650 min | D 1122 |
| Freezing point, °C (°F) | -37 (-34) max or lower | D 1177 |
| Boiling point, °C (°F) | 108 (226) min | D 1120 |
| Ash content, mass % | 2.5 max | D 1119 |
| pH | 7.5 to 11.0 ^A | D 1287 |
| Reserve alkalinity, mL | report ^B | D 1121 |
| Chloride, ppm | 25 max | D 3634 |
| Silicon, ppm | 125 max | under consideration |
| Effect on engine or vehicle | no effect | D 1882 ^C |
| finish | | |

4.4.4.4.1.1.

^AAlso report on the adjusted product.

^BValue as agreed upon between the supplier and the customer. ^CCurrently, many heavy duty engine manufacturers and vehicle manufacturers

that use these engines prepare test panels using the specific paint finishes employed on their actual products. Coolant and equipment builders should agree on the exact test procedures and acceptance criteria on an individual case basis.

TABLE 2 General Requirements of the Unadjusted Prediliuted Product

| i i oddot | | | | |
|-------------------------------|---|-------------------------|--|--|
| Property | Specified Values | ASTM Test Method | | |
| Color Effect on non-metals | Distinctive ^A No adverse affect | | | |
| Storage stability | | under consideration | | |
| Foaming | | D 1881 | | |
| Volume, mL | 150 max | | | |
| Break time, s | 5 max | | | |
| ADreferred color green to | blue groop | | | |

^APreferred color, green to blue-green.

before SCA addition, shall conform to the chemical and physical property requirements prescribed in Table 1 and to the general requirements prescribed in Table 2.

5.2 Prediluted aqueous ethylene glycol base engine coolant, after adjustment and before SCA addition, shall conform to the laboratory test performance requirements prescribed in Table 3.

5.3 Report the freezing point of the prediluted aqueous ethylene glycol base coolant as packaged. This freezing point shall be -37° C (-34° F) or below.

5.4 Adjust the freezing point of the prediluted aqueous ethylene glycol base coolant to $-37^{\circ}C$ ($-34^{\circ}F$) with deionized water. Use this concentration-adjusted product for all of the performance requirements testing specified under this specification and listed in Table 3 and for Footnote A of Table 1.

6. Keywords

6.1 engine coolant; ethylene glycol; heavy-duty engine service; low-silicate coolant; prediluted

TABLE 3 Performance Requirements of the Adjusted^A Prediluted Product

| Property | Specified Values | ASTM Test Method |
|---|------------------|---------------------|
| Corrosion in glassware | | D 1384 ^B |
| Weight loss, mg/specimen | | |
| Copper 06-4190-0096-90 | 10 max astr | |
| Solder | 30 max | |
| Brass | 10 max | |
| Steel | 10 max | |
| Cast iron | 10 max | |
| Aluminum | 30 max | |
| Simulated service test | | D 2570 ^C |
| Weight loss, mg/specimen | | |
| Copper | 20 max | |
| Solder | 60 max | |
| Brass | 20 max | |
| Steel | 20 max | |
| Cast iron | 20 max | |
| Aluminum | 60 max | |
| Foaming | | D 1881 |
| Volume, mL | 150 max | |
| Break time, s | 5 max | |
| Cavitation-erosion | 8 min | D 2809 ^D |
| Rating for pitting cavitation or erosion of the water pump | | |

ASee 5.4

^BThe adjusted product shall be mixed with the proper quantity of Type IV reagent water (Specification D 1193) to provide the resulting solution with a freezing point of $-18 \pm 1^{\circ}$ C ($0 \pm 2^{\circ}$ F). To each litre of test solution, add 99 mg of sodium sulfate, 110 mg of sodium chloride, and 92 mg of sodium bicarbonate.

^CThe adjusted product shall be mixed with the proper quantity of Type IV reagent water (Specification D 1193) to provide the resulting solution a freezing point of $-29\pm$ 1°C ($-20\pm$ 2°F). To each litre of test solution, add 83 mg of sodium sulfate, 92 mg of sodium chloride, and 77 mg of sodium bicarbonate.

^DOne volume of the adjusted product shall be mixed with two volumes of Type IV reagent water (Specification D 1193). To each litre of test solution, add 123 mg of sodium sulfate, 137 mg of sodium chloride, and 115 mg of sodium bicarbonate.