
Welding consumables — Covered electrodes for manual metal arc welding of stainless and heat-resisting steels — Classification

Produits consommables pour le soudage — Électrodes enrobées pour le soudage manuel à l'arc des aciers inoxydables et résistant aux températures élevées — Classification

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sui/14e92b-ab9e-4454-b2aa-fa4854b97d/iso-3581-2016>



iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/1e1e92b-ab9e-4454-b2aa-fa4854b9f7d/iso-3581-2016>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

| | |
|--|-----------|
| Foreword | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Classification | 2 |
| 4 Symbols and requirements | 4 |
| 4.1 Symbol for the product/process | 4 |
| 4.2 Symbol for the chemical composition of all-weld metal | 4 |
| 4.3 Symbol for type of electrode covering | 5 |
| 4.4 Symbol for effective electrode efficiency and type of current | 13 |
| 4.5 Symbol for welding position | 14 |
| 5 Chemical analysis | 14 |
| 6 Mechanical property tests | 14 |
| 6.1 General | 14 |
| 6.2 Preheat and interpass temperatures | 15 |
| 6.3 Pass sequence | 15 |
| 7 Fillet weld test | 16 |
| 8 Rounding procedure | 16 |
| 9 Retests | 17 |
| 10 Technical delivery conditions | 17 |
| 11 Examples of designation | 17 |
| Annex A (informative) Types of covering | 19 |
| Annex B (informative) Considerations on weld metal ferrite contents | 20 |
| Bibliography | 23 |

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

The committee responsible for this document is ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This third edition cancels and replaces the second edition (ISO 3581:2003), which has been technically revised. It also incorporates the Technical Corrigendum ISO 3581:2003/Cor 1:2008 and the Amendment ISO 3581:2003/Amd 1:2011.

Requests for official interpretations of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Introduction

This International Standard provides a classification system for stainless steel, covered welding electrodes in terms of chemical composition of deposited weld metal and type of electrode covering. Other properties of the electrodes are specified by reference to tables.

This International Standard recognizes that there are two somewhat different approaches in the global market for classifying a given stainless steel, covered electrode, and allows for either or both to be used to suit a particular need. Application of either (or both) type(s) of classification designation identifies a product as classified according to this International Standard. It is important to note that the two systems are not exactly equivalent; therefore, each system must be used independent of the other, without combining designators in any way.

The classification according to ISO 3581, system A, is mainly based upon EN 1600 while the classification according to ISO 3581, system B, is mainly based upon standards used around the Pacific Rim.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/1e1e92b-ab9e-4454-b2aa-fa4854b9f7d/iso-3581-2016>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/1e1e92b-ab9e-4454-b2aa-fa4854b9f7d/iso-3581-2016>

Welding consumables — Covered electrodes for manual metal arc welding of stainless and heat-resisting steels — Classification

1 Scope

This International Standard specifies requirements for classification of covered electrodes, based on the all-weld metal chemical composition, the type of electrode covering and other electrode properties, and the all-weld metal mechanical properties, in the as-welded or heat-treated conditions, for manual metal arc welding of stainless and heat-resisting steels.

This International Standard is a combined standard providing for classification utilizing a system based upon classification according to nominal composition or utilizing a system based upon classification according to alloy type.

- a) Paragraphs and tables which carry the label “classification according to nominal composition” or “ISO 3581-A” are applicable only to products classified to that system.
- b) Paragraphs and tables which carry the label “classification according to alloy type” or “ISO 3581-B” are applicable only to products classified to that system.
- c) Paragraphs and tables which carry neither label are applicable to products classified according to either or both systems.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 2401, *Covered electrodes — Determination of the efficiency, metal recovery and deposition coefficient*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947:2011, *Welding and allied processes — Welding positions*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*. Amended by ISO 15792-1:2000/Amd 1:2011

ISO 15792-3, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

ISO 80000-1:2009, *Quantities and units — Part 1: General* Corrected by ISO 80000-1:2009/Cor 1:2011

3 Classification

Classification designations are based upon two approaches for indicating the chemical composition of the all-weld metal deposit obtained with a given electrode.

The “nominal composition” approach uses designation components indicating directly the nominal levels of certain alloying elements, given in a particular order, and some symbols for low but significant levels of other elements, whose levels are not conveniently expressed as integers. The “alloy type” approach uses tradition-based three-digit or four-digit designations for alloy families, and occasionally an additional character or characters for compositional modifications of each original alloy within the family. Both designation approaches include additional designators for some other classification requirements, but not entirely the same classification requirements, as will be clear from the following clauses.

Table 1 lists the tests required for classification of an electrode in each approach.

In many cases, a given commercial product can be classified using both approaches. Then either or both classification designations can be used for the product.

Table 1 — Summary of test requirements

| Electrode designation | | Size ^a mm | Chemical analysis test | | Position of welding ^b All-weld metal tension test | | Fillet weld test | |
|--|--|-------------------------|------------------------|----------------|---|----------------|------------------|----------------|
| ISO 3581-A | ISO 3581-B | | ISO 3581-A | ISO 3581-B | ISO 3581-A | ISO 3581-B | ISO 3581-A | ISO 3581-B |
| Coating type symbol B and position symbols 1 and 2 | Position and coating type symbol - 15 | 2,5 (or 2,4 or 2,6) | Not required | PA | Not required | Not required | Not required | Not required |
| | | 3,2 or 3,0 | PA | PA | Not required | Not required | Not required | Not required |
| | | 4,0 | PA | PA | PA | PA | Not required | PB, PF, PD |
| | | 5,0 or 4,8 | Not required | PA | Not required | Not required | Not required | PB |
| | | 6,0 (or 5,6 or 6,4) | Not required | PA | Not required | Not required | Not required | PB |
| All coating types and position symbol 3 | Not applicable | 3,2 or 3,0 | PA | Not applicable | Not required | Not applicable | Not required | Not applicable |
| | | 4,0 | PA | | PA | | Not required | |
| | | 5,0 or 4,8 | Not required | | Not required | | Not required | |
| All coating types and position symbol 4 | Position symbol - 4 and all coat-ing types | 2,5 (or 2,4 or 2,6) | Not required | PA | Not required | Not required | Not required | PG |
| | | 3,2 or 3,0 | PA | PA | Not required | Not required | Not required | PG |
| | | 4,0 | PA | PA | PA | PA | Not required | PG |
| | | 5,0 or 4,8 | Not required | PA | Not required | Not required | Not required | PG |

^a If the size is not manufactured, the next nearest size may be substituted (provided that the substituted size is different from those specified in this table).

^b The abbreviation PA, PB, PD, PF and PG indicate welding positions in accordance with ISO 6947, as follows:

PA = flat;

PB = horizontal vertical;

PD = horizontal overhead;

PF = vertical up;

PG = vertical down.

Table 1 (continued)

| Electrode designation | | Size ^a mm | Chemical analysis test | | Position of welding ^b | | Fillet weld test | |
|--|---|-------------------------|------------------------|----------------|----------------------------------|----------------|------------------|----------------|
| ISO 3581-A | ISO 3581-B | | ISO 3581-A | ISO 3581-B | ISO 3581-A | ISO 3581-B | ISO 3581-A | ISO 3581-B |
| All coating types and position symbol 5 | Not applicable | 3,2 (or 3,0) | PA | Not applicable | Not required | Not applicable | Not required | Not applicable |
| | | 4,0 | PA | | PA | | Not required | |
| | | 5,0 (or 4,8) | Not required | | Not required | | Not required | |
| Coating type symbol R and position symbols 1 and 2 | Position and coating type symbols - 16 and - 17 | 2,5 (or 2,4 or 2,6) | Not required | PA | Not required | Not required | Not required | Not required |
| | | 3,2 (or 3,0) | PA | PA | Not required | Not required | Not required | Not required |
| | | 4,0 | PA | PA | PA | PA | Not required | PB, PF, PD |
| | | 5,0 (or 4,8) | Not required | PA | Not required | Not required | Not required | PB |
| | | 6,0 (or 5,6 or 6,4) | Not required | PA | Not required | Not required | Not required | PB |
| Not applicable | Position and coating type symbols - 26 and - 27 | 2,5 (or 2,4 or 2,6) | Not applicable | PA | Not applicable | Not required | Not applicable | Not required |
| | | 3,2 (or 3,0) | | PA | | Not required | | Not required |
| | | 4,0 | | PA | | PA | | PB |
| | | 5,0 (or 4,8) | | PA | | Not required | | PB |
| | | 6,0 (or 5,6 or 6,4) | | PA | | Not required | | PB |

^a If the size is not manufactured, the next nearest size may be substituted (provided that the substituted size is different from those specified in this table).

^b The abbreviation PA, PB, PD, PF and PG indicate welding positions in accordance with ISO 6947, as follows:

PA = flat;

PB = horizontal vertical;

PD = horizontal overhead;

PF = vertical up;

PG = vertical down.

3A Classification according to nominal composition

The classification includes all-weld metal properties obtained with a covered electrode as given below. The classification is based on an electrode diameter of 4 mm with the exception of testing for welding position. When 4 mm diameter electrodes are not manufactured, the next closest diameter shall be tested.

The classification is divided into the following five parts:

3B Classification according to alloy type

The classification includes all-weld metal properties obtained with a covered electrode as given below. The classification is based on an electrode diameter of 4 mm for mechanical properties, with the exception of testing for welding position and for chemical analysis of the weld metal. When 4 mm diameter electrodes are not manufactured, the next closest diameter shall be tested.

The classification is divided into the following four parts:

- 1) the first part gives a symbol indicating the product/process to be identified (see [4.1A](#));
- 2) the second part gives a symbol indicating the chemical composition of all-weld metal (see [Table 2](#));
- 3) the third part gives a symbol indicating the type of electrode covering (see [4.3A](#));
- 4) the fourth part gives a symbol indicating the effective electrode efficiency and type of current (see [Table 4A](#));
- 5) the fifth part gives a symbol indicating the welding position (see [Table 5A](#)).

In order to promote the use of this International Standard, the classification to ISO 3581-A is split into two sections.

— Compulsory section

This section includes the symbols for the type of product, the chemical composition and the type of covering, i.e. symbols defined in [4.1A](#), [4.2](#) and [4.3A](#).

— Optional section

This section includes the symbols for the weld metal recovery, the type of current and the welding positions for which the electrode is suitable, i.e. the symbols defined in [4.4A](#) and [Table 5A](#).

The full designation (compulsory and optional sections) shall be used on packages and in the manufacturer's literature and data sheets.

NOTE The composition of the core wire, which can be substantially different from the weld metal composition, is not considered a classification criterion.

- 1) the first part gives a symbol indicating the product/process to be identified (see [4.1B](#));
- 2) the second part gives a symbol indicating the chemical composition of all-weld metal (see [Table 2](#));
- 3) the third part gives a symbol indicating the welding position (see [Table 5B](#));
- 4) the fourth part gives a symbol indicating the type of electrode covering. This also serves to define the type of current which can be used with the electrode classified (see [4.3B](#)).

In classifying welding electrodes to ISO 3581-B, the symbols for all four parts (product/process, alloy type, welding position and type of electrode covering) as defined in [4.1B](#), [4.2](#), [4.3](#) and [Table 5B](#), are compulsory.

The full designation shall be used on packages and in the manufacturer's literature and data sheets.

4 Symbols and requirements

4.1 Symbol for the product/process

4.1A Classification according to nominal composition

The symbol for the covered electrode used in the manual metal arc welding process for stainless and heat-resisting steels in accordance with ISO 3581-A shall be the letter E.

4.1B Classification according to alloy type

The symbol for the covered electrode used in the manual metal arc welding process for stainless and heat-resisting steels in accordance with ISO 3581-B shall be the letters ES. The initial letter "E" indicates a covered electrode while the letter "S" indicates stainless and heat-resisting steels.

4.2 Symbol for the chemical composition of all-weld metal

The symbol in [Table 2](#) indicates the chemical composition of all-weld metal determined in accordance with [Clause 5](#). The all-weld metal obtained with the covered electrodes in [Table 2](#), in accordance with

[Clause 6](#), shall also fulfil the mechanical property requirements for that electrode as specified in [Table 3](#).

4.3 Symbol for type of electrode covering

The type of covering of the electrodes determines, to a large extent, usability characteristics of the electrode and properties of the weld metal. See [Annex A](#) for information on coating types.

4.3A Classification according to nominal composition

The following two symbols are used to describe the type of covering:

- B denotes a basic covering;
- R denotes a rutile based covering.

4.3B Classification according to alloy type

The following three symbols are used to define the type of covering on the electrode:

- 5 denotes a basic covering, intended for DC welding;
- 6 denotes a rutile based coating, intended for DC or AC welding (except that position and coating type -46 is DC);
- 7 denotes a modified rutile based coating containing a considerable amount of silica, intended for DC or AC welding (except that position and coating type -47 is DC).

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/1e1e2b-ab9e-4454-b2aa-fa4854b97d/iso-3581-2016>