

DRAFT INTERNATIONAL STANDARD

ISO/DIS 17632

ISO/TC 44/SC 3

Secretariat: ANSI

Voting begins on:
2013-09-12

Voting terminates on:
2014-02-12

Welding consumables — Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of non-alloy and fine grain steels — Classification

Produits consommables pour le soudage — Fils-électrodes fourrés pour soudage à l'arc avec ou sans gaz de protection des aciers non alliés et des aciers à grains fins — Classification

[Revision of first edition (ISO 17632:2004)]

ICS: 25.160.20

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/f5898d65-cbc0-4b79-ab28-2dd709d1145/iso-17632-2015>

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.



Reference number
ISO/DIS 17632:2013(E)

© ISO 2013

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/f5898d65-cbc0-4b79-ab28-2ddf709d1145/iso-17632-2015>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Classification.....	2
4 Symbols and requirements	4
4.1 Symbol for the product/process	4
4.2 Symbol for tensile properties of all-weld metal or welded joint	4
4.2.1 Multi-run technique.....	4
4.2.2 Single-run technique	5
4.3 Symbol for impact properties of all-weld metal or welded joint.....	5
4.4 Symbol for chemical composition of all-weld metal	6
4.5 Symbol for type of electrode core or for the usability characteristics of the electrode	9
4.6 Symbol for shielding gas	10
4.7 Symbol for welding position	13
4.8 Symbol for hydrogen content of deposited metal.....	13
4.9 Symbol for condition of postweld heat treatment of all-weld metal.....	14
5 Mechanical tests	14
5.1 Multi-run technique.....	14
5.1.1 Preheating and interpass temperatures.....	14
5.1.2 Procedure requirements for welding multi-run test assemblies.....	15
5.1.3 Post-weld heat treatment (PWHT) condition.....	16
5.2 Single-run technique	16
6 Chemical analysis	16
7 Rounding procedure.....	16
8 Fillet weld test	16
9 Retests.....	17
10 Technical delivery conditions	17
11 Examples of designation.....	18
Annex A (informative) Classification systems	20
Annex B (informative) Description of types of electrode core in the classification system based upon yield strength and average impact energy of 47 J.....	23
Annex C (informative) Description of types of usability characteristics in the classification system based upon tensile strength and average impact energy of 27 J	25
Annex D (informative) Notes on hydrogen content	28

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17632 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This second/third/... edition cancels and replaces the first/second/... edition (), [clause(s) / subclause(s) / table(s) / figure(s) / annex(es)] of which [has / have] been technically revised.

!Teh STANDARD PREVIEW
(standards.iteh.ai)
Full standards catalog/standards/sis/17632-2015
<https://standards.iteh.ai/catalog/standards/sis/17632-2015/cbc0-4b79-ab28-2ddf709d1145>

Introduction

This International Standard provides a classification system for tubular cored electrodes in terms of tensile properties, impact properties, chemical composition of the all-weld metal, type of electrode core, shielding gas and welding position. The ratio of yield to tensile strength of weld metal is generally higher than that of parent metal. Users should note that matching weld metal yield strength to parent metal yield strength will not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Where the application requires matching tensile strength, therefore, selection of the consumable should be made by reference to column 3 of Table 1A or Table 1B.

It should be noted that the mechanical properties of all-weld metal test specimens used to classify the tubular cored electrodes will vary from those obtained in production joints because of differences in welding procedure such as electrode size, width of weave, welding position and parent metal composition.

The classification according to system A is mainly based on EN 758:1997, *Welding consumables — Tubular cored electrodes for metal arc welding with and without a gas shield of non alloy and fine grain steels — Classification*. The classification according to system B is mainly based upon standards used around the Pacific Rim.

PRELIMINARY
NOT FOR REPRODUCTION
PRELIMINARY
NOT FOR REPRODUCTION
iTeh STANDARD PREVIEW
(standards.itih.ai)
Full standard:
<https://standards.itih.ai/catalog/standards/sist/f58980d3-cbc0-4b79-ab28-2ddf709d1145/iso-17632-2015>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Full standard:
<https://standards.iteh.ai/catalog/standards/sist/f5898d65-cbc0-4b79-ab28-2ddf709d1145/iso-17632-2015>

Welding consumables — Tubular cored electrodes for gas shielded and non-gas shielded metal arc welding of non-alloy and fine grain steels — Classification

1 Scope

This International Standard specifies requirements for classification of tubular cored electrodes with or without a gas shield for metal arc welding of non-alloy and fine grain steels in the as-welded condition or in the post-weld heat-treated condition with a minimum yield strength of up to 500 MPa or a minimum tensile strength of up to 570 MPa. One tubular cored electrode can be tested and classified with different shielding gases, if any.

This International Standard is a combined specification providing classification utilizing a system based upon the yield strength and the average impact energy of 47 J of all-weld metal, or utilizing a system based upon the tensile strength and the average impact energy of 27 J of all-weld metal.

- 1) Paragraphs and tables which carry the suffix letter "A" are applicable only to tubular cored electrodes classified to the system based upon the yield strength and the average impact energy of 47 J of all-weld metal in accordance with this International Standard.
- 2) Paragraphs and tables which carry the suffix letter "B" are applicable only to tubular cored electrodes classified to the system based upon the tensile strength and the average impact energy of 27 J of all-weld metal in accordance with this International Standard.
- 3) Paragraphs and tables which have neither the suffix letter "A" nor the suffix letter "B" are applicable to all tubular cored electrodes classified in accordance with this International Standard.

It is recognized that the operating characteristics of tubular cored electrodes can be modified by the use of pulsed current, but for the purposes of this International Standard, pulsed current is not permitted for determining the electrode classification.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables – Technical delivery conditions for filler materials and fluxes – Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes -- Determination of hydrogen content in arc weld metal*

ISO 6847, *Welding consumables -- Deposition of a weld metal pad for chemical analysis*

ISO 6947:2011, *Welding and allied processes -- Welding positions*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14175:2008, *Welding consumables – Gases and gas mixtures for fusion welding and allied processes*

ISO 14344, *Welding consumables – Procurement of filler materials and fluxes*

ISO 15792-1:2000/ Amd 1:2011, *Welding Consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 15792-2:2000, *Welding Consumables — Test methods — Part 2: Preparation of single-run and two-run technique test specimens in steel*

ISO 15792-3, *Welding Consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all, as will be clear from the following. In most cases, a given commercial product can be classified in both systems. Then either or both classification designations can be used for the product. See Annex A.

The classification includes all-weld metal properties obtained with a tubular cored electrode and appropriate shielding gas combination as given below. With the exception of the symbol for welding position which is based on ISO 15792-3, the classification of gas shielded tubular cored electrodes is based on the 1,2 mm electrode size or, if this size is not manufactured, the next larger diameter manufactured. The classification of self-shielded tubular cored electrodes is based on the 2,4 mm diameter or the largest diameter manufactured if less than 2,4 mm.

3.1A Classification by yield strength and 47 J impact energy

The classification is divided into eight parts:

- 1) the first part (T) indicates a tubular cored electrode;
- 2) the second part gives a symbol indicating the strength and elongation of all-weld metal for multi-run technique or the strength of the parent material used in classification for the single-run technique (see Table 1A or Table 2A);
- 3) the third part gives a symbol indicating the impact properties of all-weld metal or welded joint (see Table 3);
- 4) the fourth part gives a symbol indicating the chemical composition of all-weld metal (see Table 4A);
- 5) the fifth part gives a symbol indicating the type of electrode core (see Table 5A);

3.1B Classification by tensile strength and 27 J impact energy

The classification is divided into nine parts:

- 1) the first part (T) indicates a tubular cored electrode;
- 2) the second part gives a symbol indicating the strength and elongation of all-weld metal for multi-run technique or the strength of the parent material used in classification for the single-run technique (see Table 1B or Table 2B);
- 3) the third part gives a symbol indicating the impact properties of all-weld metal (see Table 3). The symbol "U", added as an optional supplemental designator at or near the end of the complete tubular cored electrode designation, indicates that the deposit meets an average optional requirement of 47 J at the designated Charpy test temperature;
- 4) the fourth part gives a symbol indicating the usability characteristics of the electrode (see Table 5B);
- 5) the fifth part gives a symbol indicating the welding position (see Table 6B);

- | | |
|--|--|
| <p>6) the sixth part gives a symbol indicating the shielding gas (see 4.6);</p> <p>7) the seventh part gives a symbol indicating the welding position (see Table 6A);</p> <p>8) the eighth part gives a symbol indicating the hydrogen content of deposited metal (see Table 7).</p> | <p>6) the sixth part gives a symbol indicating the shielding gas (see 4.6). The letter “S” added to this designator indicates that the electrode is classified for single-pass welding;</p> <p>7) the seventh part gives a symbol indicating whether the classification tests were conducted in the as-welded (A) or post-weld heat-treated condition (P). If the electrode has been classified in both conditions, the symbol AP shall be added to the classification. This designator is omitted in the classification for single-pass welding electrodes as these are tested only in the as-welded condition;</p> <p>8) the eighth part gives a symbol indicating the chemical composition of all-weld metal (see Table 4B). The symbol is omitted for weld deposits conforming to the “No symbol” in Table 4B;</p> <p>9) the ninth part gives a symbol indicating the hydrogen content of deposited metal (see Table 7).</p> |
|--|--|

Electrodes may be classified under any number of classifications for either or both the as-welded and post-weld heat-treated condition.

In both systems, the electrode classification shall include all compulsory sections and may include optional sections as outlined below.

3.2A Compulsory and optional sections in the classification by yield strength and 47 J impact energy

a) Compulsory section

This section includes the symbols for type of product, strength and elongation, impact properties, chemical composition, type of electrode core and shielding gas, i.e. the symbols defined in 4.1, 4.2.1A, 4.2.2, 4.3A, 4.4, 4.5A and 4.6.

b) Optional section

This section includes the symbols for the welding positions for which the electrode is suitable and the symbol for hydrogen content, i.e. the symbols defined in 4.7 and 4.8.

3.2B Compulsory and optional sections in the classification by tensile strength and 27 J impact energy

a) Compulsory section

This section includes the symbols for type of product, strength and elongation in the as-welded condition or post-weld heat-treated condition, welding positions for which the electrode is suitable, usability characteristics, shielding gas, impact properties and chemical composition, i.e. the symbols defined in 4.1, 4.2.1B, 4.2.2, 4.3B, 4.4, 4.5B, 4.6, 4.7 and 4.9B.

b) Optional section

This section includes the symbol “U” to indicate that the weld metal has an average of 47J impact energy at the classification test temperature and the symbol for hydrogen content, i.e. the symbol “U” defined in 4.3B and the symbols defined in 4.8.

The full designation shall comprise the compulsory symbols and may include optional symbols chosen by the manufacturer. The full designation (see Clause 10) shall be used on packages and in the manufacturer’s literature and data sheets.

4 Symbols and requirements

4.1 Symbol for the product/process

The symbol for the tubular cored electrode used in the metal arc welding process is the letter T.

4.2 Symbol for tensile properties of all-weld metal or welded joint

4.2.1 Multi-run technique

4.2.1A Classification by yield strength and 47 J impact energy

For products suitable for single- and multi-run welding, the symbol in Table 1A indicates yield strength, tensile strength and elongation of the all-weld metal in the as-welded condition determined in accordance with 5.1A.

4.2.1B Classification by tensile strength and 27 J impact energy

For electrodes suitable for single- and multi-run welding, the symbol in Table 1B indicates yield strength, tensile strength and elongation of the all-weld metal in the as-welded condition or in the post-weld heat-treated condition determined in accordance with 5.1B.

Classification of products suitable for both single- and multi-run welding does not require the single-run test of 5.2.

Table 1A — Symbol for tensile properties by multi-run technique (classification by yield strength and 47 J impact energy)

Symbol	Minimum yield strength ^a MPa	Tensile strength MPa	Minimum elongation ^b %
35	355	440 to 570	22
38	380	470 to 600	20
42	420	500 to 640	20
46	460	530 to 680	20
50	500	560 to 720	18

^a For yield strength the lower yield, R_{eL} , is used when yielding occurs, otherwise the 0,2 % proof strength, $R_{p0,2}$, is used.

^b Gauge length is equal to five times the test specimen diameter.

Table 1B — Symbol for tensile properties by multi-run technique (classification by tensile strength and 27 J impact energy)

Symbol	Minimum yield strength ^a MPa	Tensile strength MPa	Minimum elongation ^b %
43	330	430 to 600	20
49	390	490 to 670	18
55	460	550 to 740	17
57	490	570 to 770	17

^a For yield strength the lower yield, R_{eL} , is used when yielding occurs, otherwise the 0,2 % proof strength, $R_{p0,2}$, is used.

^b Gauge length is equal to five times the test specimen diameter.

4.2.2 Single-run technique

For tubular cored electrodes suitable for single-run welding only, the symbol in Table 2A or Table 2B indicates strength of the welded joint in the as-welded condition in relation to the parent material used in single-run tests satisfactorily completed in accordance with 5.2.

Table 2A — Symbol for tensile properties by single-run technique (classification by yield strength and 47 J impact energy)

Symbol	Minimum parent material yield strength MPa	Minimum tensile strength of the welded joint MPa
3T	355	470
4T	420	520
5T	500	600

Table 2B — Symbol for tensile properties by single-run technique (classification by tensile strength and 27 J impact energy)

Symbol	Minimum tensile strength of the parent metal and of the welded joint MPa
43	430
49	490
55	550
57	570

4.3 Symbol for impact properties of all-weld metal or welded joint

4.3A Classification by yield strength and 47 J impact energy

The symbol in Table 3 indicates the temperature at which an impact energy of 47 J is achieved under the conditions given in 5.1A or 5.2. Three test specimens shall be tested. Only one individual value may be lower than 47 J but no lower than 32 J.

4.3B Classification by tensile strength and 27 J impact energy

The symbol in Table 3 indicates the temperature at which an impact energy of 27 J is achieved in the as-welded condition or in the post-weld heat-treated condition under the conditions given in 5.1B or 5.2. Five test specimens shall be tested. The lowest and highest values obtained shall be disregarded. Two of the three remaining values shall be greater than the specified 27 J level, one of the three may be lower but shall be no less than 20 J. The average of the three remaining values shall be at least 27 J. Three test specimens shall be tested when the optional supplemental designator "U" is used to indicate that the weld deposit will meet a minimum impact energy of 47 J at the test temperature. The impact value shall be determined by the average of the three test specimens. The average of three values shall be 47 J or greater. Only one individual value may be lower than 47 J but no lower than 32 J.