

INTERNATIONAL
STANDARD

ISO
11114-1

Second edition
2012-03-15

AMENDMENT 1
2017-01

**Gas cylinders — Compatibility of
cylinder and valve materials with gas
contents —**

**Part 1:
Metallic materials**

iTeh STANDARD REVIEW

(standards.iteh.ai)
*Bouteilles à gaz — Compatibilité des matériaux des bouteilles et des
robinets avec les contenus gazeux —*

ISO 11114-1:2012/Amd.1:2017

<https://standards.iteh.ai/catalog/standards/sist01e3fd87-c100-4b8c-b57f1ed2fbe>
AMENDMENT 1:2012-amd-1-2017



Reference number
ISO 11114-1:2012/Amd.1:2017(E)

© ISO 2017

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 11114-1:2012/Amd 1:2017](https://standards.iteh.ai/catalog/standards/sist/01e3fd87-c100-4b8c-b57f-1ed2fbe5216c/iso-11114-1-2012-amd-1-2017)
<https://standards.iteh.ai/catalog/standards/sist/01e3fd87-c100-4b8c-b57f-1ed2fbe5216c/iso-11114-1-2012-amd-1-2017>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

Amendment 1 to ISO 11114-1:2012 was prepared by Technical Committee ISO/TC 58, *Gas cylinders*.

[ISO 11114-1:2012/Amd 1:2017
https://standards.iteh.ai/catalog/standards/sist/01e3fd87-c100-4b8c-b57f1ed2fbe5216c/iso-11114-1-2012-amd-1-2017](https://standards.iteh.ai/catalog/standards/sist/01e3fd87-c100-4b8c-b57f1ed2fbe5216c/iso-11114-1-2012-amd-1-2017)

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 11114-1:2012/Amd 1:2017](#)

<https://standards.iteh.ai/catalog/standards/sist/01e3fd87-c100-4b8c-b57f-1ed2fbe5216c/iso-11114-1-2012-amd-1-2017>

Gas cylinders — Compatibility of cylinder and valve materials with gas contents —

Part 1: Metallic materials

AMENDMENT 1

Page 3, 4.3.2 Particular considerations

Replace the note with the following:

NOTE Reference is made in this document to stainless steels by their commonly used AISI identification numbers, i.e. 304. For example, the equivalent grades according to EN 10088-1 are as follows:

304	1.4301
304L	1.4306 and 1.4307
316	iTech STANDARD PREVIEW (standards.itech.ai)
316L	1.4404
316Ti	1.4571 ISO 11114-1:2012/Amd 1:2017
321	https://standards.itech.ai/catalog/standards/sist/01e3fd87-c100-4b8c-b57f-led2fbe5216c/iso-11114-1-2012-amd-1-2017
904L	1.4539

Page 5, 6.2 Compatibility for gas mixtures

Replace the NOTE with the following:

NOTE In a gas mixture, the partial pressure for hydrogen sulphide and methyl mercaptan is reduced to 0,25 MPa (2,5 bar) at a maximum UTS of 950 MPa.

For the halogenated gases non compatible with aluminium alloys cylinder, the maximum acceptable concentration in a gas mixtures shall be limited to 0,1 % as indicated in Table 1 unless higher concentrations have been validated after conducting specific tests (example of such tests are given in EIGA document 161/16 Gas compatibility with Aluminium alloy cylinder). The moisture content in these mixtures shall be limited to a maximum of 10 ppmV.

Page 6, 6.3.2 Abbreviations of materials

Replace the whole lines corresponding to gases number 7, 8, 9, 13, 18, 20, 22, 46, 49, 60, 63, 69, 74, 83, 90, 91, 96, 100, 101, 102, 103 with the following:

No.	Gas number UN number	Name	Formula	Key compatibility characteristics				Material Cylinder	Material Valve (body and components)
				A	N	A	N		
7	(UN 1974)	BROMOCHLORODIFLUOROMETHANE	CBrClF ₂ (R12B1)	No reaction with any common materials when dry but in the presence of water, corrosion can occur.	NS QTS AA SS	B CS SS AA			
8	(UN 1009)	BROMOTRIFLUOROMETHANE	CBrF ₃ (R13B1)	No reaction with any common materials when dry but in the presence of water, corrosion can occur.	NS QTS AA SS	B CS SS AA			
9	(UN 2419)	BROMOTRIFLUOROETHYLENE	C ₂ BrF ₃	No reaction with any common materials when dry but in the presence of water, corrosion can occur.	NS	B			
13	(UN 1012)	BUTENE-1	CH ₃ CH ₂ CH:CH ₂	No reaction with any common materials. See 5.2.3 for the effect of impurities in wet conditions.	NS QTS AA SS	B CS SS AA			
18	(UN 1982)	TETRAFLUOROMETHANE (CARBON TETRAFLUORIDE)	CF ₄ (R14)	No reaction with any common materials when dry but in the presence of water, corrosion may occur.	NS QTS AA SS	B CS SS AA			
20	(UN 1017)	CHLORINE	Cl ₂	Hydrolyses to hypochlorous acid and to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. The service life of brass valves strongly depends on the operating service conditions. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS	AA B ^a SS Ni ASB	CS AA		

^a Brass is only acceptable as valve body but not as general valve component material.

No.	Gas number UN number	Name	Formula	Key compatibility characteristics				Material			
				Cylinder	A	N	A	N	Valve (body and components)	A	B
22	(UN 1063)	METHYL CHLORIDE	CH ₃ Cl (R40)	In the presence of water, corrosion can occur. Mixtures of dry gas containing not more than 0,1 % of this gas may be filled into AA cylinders. ^a	QTS	NS	AA	B	AA	CS	SS
46	(UN 1037)	ETHYL CHLORIDE	C ₂ H ₅ Cl (R160)	No reaction with any common materials when dry but in the presence of water corrosion can occur. Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	QTS	NS	AA	B	AA	CS	SS
49	(UN 1045)	FLUORINE	F ₂	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most of the materials and risk of hydrogen embrittlement. Risk of violent reaction with AA. Recommended materials are also Ni alloy and nickel. Mixtures containing less than 0,1 % of this gas may be filled into AA cylinders.	QTS	NS	AA	CS	AA	SS	Ni
60	(UN 1051)	HYDROGEN CYANIDE	HCN	This compound is highly hygroscopic. Risk of corrosion in wet conditions, depending on type of alloy.	QTS	NS	B	CS	AA	SS	AA

^a Brass is only acceptable as valve body but not as general valve component material.

No.	Gas number UN number	Name	Formula	Key compatibility characteristics				Material Cylinder	Valve (body and components)	
				A	N	A	N			
63	(UN 1053)	HYDROGEN SULPHIDE	H ₂ S	<ul style="list-style-type: none"> — In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316. — In wet conditions, risk of stress corrosion cracking for QTS. Risk of hydrogen embrittlement with NS, QTS. — SS shall not be used for springs or diaphragms except if the failure of such components does not result in an unsafe situation because of possibility of hydrogen embrittlement. — For mixtures with higher partial pressure than the one defined in 6.2 and stored at a total pressure greater than 50 % of the normal service pressure of the cylinder, NS, and QTS at a limited strength shall be used (see 6.2). — Nickel is unacceptable for bursting disks and components.^a 	NS QTS AA SS	CS SS AA	B	N	Material Cylinder	Valve (body and components)
69	(UN 1062)	METHYL BROMIDE	CH ₃ Br (R40B1)	<p>In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316.</p> <p>Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.</p>	NS QTS SS Ni	AA CS SS Ni	B	AA	Material Cylinder	Valve (body and components)
74	(UN 1660)	NITRIC OXIDE	NO	<p>In the presence of water, pitting corrosion can occur. Pitting corrosion can be minimized by using SS alloys such as 316.</p> <p>Risk of stress corrosion cracking with brass (and other copper alloys) valves due to atmospheric moisture. This applies to all mixtures containing even traces of NO.</p>	NS QTS SS AA	CS SS AA	B	AA	Material Cylinder	Valve (body and components)

a Brass is only acceptable as valve body but not as general valve component material.

No.	Gas number UN number	Name	Formula	Key compatibility characteristics				Material Cylinder	Valve (body and components)
				A	N	A	N		
83	(UN 1076)	PHOSGENE	COCl ₂	In wet conditions, phosgene is corrosive with most materials, particularly aluminium alloys (hydrolyses to HCl). Mixtures of dry gas containing not more than 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA CS SS Ni	B AA Ni	AA	N
90	(UN 1818)	SILICON TETRACHLORIDE	SiCl ₄	Hydrolyses to hydrogen chloride in contact with moisture. In wet conditions, see specific risk of hydrogen chloride compatibility, i.e. severe corrosion of most materials. ISO 141-111:2017 Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA B SS Ni	CS AA	AA	N
91	(UN 1859)	SILICON TETRAFLUORIDE	SiF ₄	Hydrolyses to hydrogen fluoride in contact with moisture. In wet conditions, see specific risk of hydrogen fluoride compatibility, i.e. severe corrosion of most materials. ISO 141-111:2017 Mixtures of dry gas not exceeding 0,1 % of this gas may be filled into AA cylinders.	NS QTS SS Ni	AA B SS Ni	CS AA	AA	N

a Brass is only acceptable as valve body but not as general valve component material.