

---

---

**Implants for surgery —  
Hydroxyapatite —  
Part 2:  
Thermally sprayed coatings of  
hydroxyapatite**

**iTeh STANDARD PREVIEW**  
*Implants chirurgicaux — Hydroxyapatite —*

*(standards.iteh.ai)*  
*Partie 2: Revêtements à base d'hydroxyapatite, obtenus par projection thermique*

[ISO 13779-2:2018](https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018)

<https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018>



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 13779-2:2018

<https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword .....	iv
Introduction .....	v
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Coating preparation</b> .....	<b>2</b>
<b>5 Requirements</b> .....	<b>2</b>
5.1 General .....	2
5.2 Calcium to phosphorus ratio ( <i>Ca:P</i> ) .....	2
5.3 Trace elements .....	2
5.4 Foreign crystalline phases .....	3
5.5 Crystallinity ratio .....	3
5.6 Morphology .....	4
5.7 Coating strength .....	4
5.8 Accuracy of test methods .....	4
<b>6 Test report</b> .....	<b>5</b>
<b>Annex A (informative) Other possible characterization tests</b> .....	<b>6</b>
<b>Annex B (informative) Comparison of foreign crystalline phases content limits</b> .....	<b>7</b>
<b>Bibliography</b> .....	<b>10</b>

<https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018>  
 ISO 13779-2:2018  
 (standards.iteh.ai)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html). (standards.iteh.ai)

This document was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.  
ISO 13779-2:2018

<https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b61945b871fd-3-13779-2>

This third edition cancels and replaces the second edition (ISO 13779-2:2008), which has been technically revised.

A list of all parts in the ISO 13779 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

No known surgical implant material has ever been shown to be completely free of adverse reactions in the human body. However, long-term clinical experience of the use of the material referred to in ISO 13779 has shown that an acceptable level of biological response can be expected, if the material is used in appropriate applications.

The biological response to hydroxyapatite coatings has been demonstrated by a history of clinical use and by laboratory studies (see References [1], [2], [3], [4], [5], [6]).

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 13779-2:2018](https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018)

<https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 13779-2:2018

<https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018>

# Implants for surgery — Hydroxyapatite —

## Part 2:

# Thermally sprayed coatings of hydroxyapatite

## 1 Scope

This document specifies requirements for single layer thermally sprayed hydroxyapatite coatings applied to metallic surgical implants.

These requirements are intended to describe properties of the materials and to communicate these between organizations. These requirements are not written with the objective of replacing a company's internal operational and assessment requirements although they could be used as such.

NOTE 1 For thin coatings with a thickness of less than 50  $\mu\text{m}$ , some of the test methods described in this document might be difficult to apply without modification.

NOTE 2 The requirements of the hydroxyapatite layer of dual-layer coatings (consisting of a lower layer of metallic coating and an upper layer of hydroxyapatite coating) can follow this document; however, testing methods referred to in this document cannot be applied to dual layer coatings. If this document is taken in reference for the requirements of the hydroxyapatite layer of dual layer coatings, a rationale on how the single-layer tested coupons are representative of the dual-layer coated implant might be considered necessary.

This document does not cover coatings made from glasses, glass ceramics, alpha- and beta-tricalcium phosphate, biphasic calcium phosphate or other forms of calcium phosphate.

NOTE 3 While the requirements in this document are intended to be used as specifications of a thermally sprayed coating of hydroxyapatite, it might be necessary to establish routine control procedures specifying control tests and their time intervals to make sure the characteristics of the coating stay within specified limits.

NOTE 4 This document was developed with a focus on plasma sprayed coating of hydroxyapatite. It might also be used to characterize other thermally sprayed coatings of hydroxyapatite. However, thermally sprayed coatings that do not have a history of clinical use might present different risks and might need additional characterizations beyond those identified in this document.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4288, *Geometrical Product Specifications (GPS) — Surface texture: Profile method — Rules and procedures for the assessment of surface texture*

ISO 10993-1, *Biological evaluation of medical devices — Part 1: Evaluation and testing within a risk management process*

ISO 13779-3, *Implants for surgery — Hydroxyapatite — Part 3: Chemical analysis and characterization of crystallinity ratio and phase purity*

ISO 13779-4, *Implants for surgery — Hydroxyapatite — Part 4: Determination of coating adhesion strength*

ISO 13779-6, *Implants for surgery — Hydroxyapatite — Part 6: Powders*

ASTM F1044, *Standard Test Method for Shear Testing of Calcium Phosphate Coatings and Metallic Coatings*

ASTM F1854, *Standard Test Method for Stereological Evaluation of Porous Coatings on Medical Implants*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 13779-3 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

#### 3.1

##### **thermally sprayed hydroxyapatite coating**

coating formed by thermal spraying of hydroxyapatite powders

Note 1 to entry: For the purpose of this document, the terms “coating” and “hydroxyapatite coating” both mean “thermally sprayed hydroxyapatite coating”

### 4 Coating preparation

The powder used for thermal spraying of the hydroxyapatite coating shall be in accordance with ISO 13779-6.

Unless documented and justified by the manufacturer, all test specimens shall be prepared using the same production methods of regular implant components, including initial hydroxyapatite powder, substrate material, production installations, substrate surface preparation process, coating process parameters, cleaning and sterilization.

ISO 13779-2:2018

### 5 Requirements

<https://standards.iteh.ai/catalog/standards/sist/0bbdaef6-683d-4781-a69f-b5fc947bff1c/iso-13779-2-2018>

#### 5.1 General

The minimum requirements for the hydroxyapatite coating are established in [5.2](#) to [5.8](#).

Other characterization tests, such as those described in [A.2](#), [A.3](#) and [A.4](#), might also be requested (e.g. in order to satisfy applicable national or regional regulation).

NOTE 1 In addition to the tests described in [5.2](#) to [5.8](#), some regulatory bodies can request the tests given in [Annex A](#) to characterize the hydroxyapatite coating.

#### 5.2 Calcium to phosphorus ratio (*Ca:P*)

Coating shall be scraped from the substrate before testing.

The calcium to phosphorus ratio, *Ca:P*, of the hydroxyapatite ceramic coating shall be determined in accordance with ISO 13779-3.

The calcium to phosphorus ratio, *Ca:P*, shall have a value in the range of 1,61 to 1,76 for the atomic ratio.

NOTE Calcium to phosphorous ratio is usually not influenced by the thickness of the coating.

#### 5.3 Trace elements

Coating shall be scraped from the substrate before testing. The amount of sample required for chemical analysis is dependent on the chemical analysis technique used. The amount of sample used shall be sufficient to achieve adequate quantification limits. The technique used to remove the coating shall



minimize the chance of contamination of the coating: care shall be taken to use appropriate tools and avoid contamination with particles coming from the substrate.

The trace element concentrations shall be determined as specified in ISO 13779-3. Heavy metals shall be as specified in ISO 13779-3.

The maximum allowable limits of specific trace elements and heavy metals for hydroxyapatite coatings are given in [Table 1](#).

Any trace element likely to be present with more than 1 000 mg/kg shall be identified. These elements shall be quantified and if present with more than 1 000 mg/kg, their influence on biocompatibility shall be assessed according to ISO 10993-1 as well as their influence on bone healing.

**Table 1 — Limits of specific trace elements**

Trace element	Maximum limit mg/kg
Arsenic	3,0
Cadmium	5,0
Mercury	5,0
Lead	30,0
Heavy metals (total)	50,0

#### 5.4 Foreign crystalline phases

Coating shall be scraped from the substrate before testing.

The foreign crystalline phases content, expressed as the foreign crystalline phase to crystalline hydroxyapatite ratio, shall be determined as specified in ISO 13779-3. The sum of  $\alpha$ -tricalcium phosphate,  $\beta$ -tricalcium phosphate and tetracalcium phosphate shall not exceed 30,0 % and the CaO content shall not exceed 5,0 %.

NOTE 1 For coatings with a thickness over 50  $\mu\text{m}$  the foreign crystalline phases content is usually not influenced by the thickness of the coating.

NOTE 2 A rationale on the limits set for foreign crystalline phases content is included in [Annex B](#).

NOTE 3 Within the limits allowable per the present document, any increase of the  $\alpha$ -tricalcium phosphate,  $\beta$ -tricalcium phosphate and tetracalcium phosphate total content might increase the solubility of the coating. A significant variation in this total content might impact the functionality of the coating.

#### 5.5 Crystallinity ratio

Coating shall be scraped from the substrate before testing.

The crystallinity ratio shall be determined following the method described in the ISO 13779-3.

The crystallinity ratio shall be not less than 45 %.

NOTE 1 The crystallinity ratio of the coating can be influenced by the thickness of the coating. First deposited layers of the coating can have a lower crystallinity ratio than upper layers. Therefore, it might be sensible within a validation process to determine crystallinity ratio on coupons with a coating thickness within or below the lowest quartile of the specification for the thickness of the coating.

NOTE 2 A method to evaluate the thickness of the coating can be found in ASTM F1854. This method requires to prepare metallographic sections and is thus destructive. However, it can be correlated to, but might not provide identical results as, non-destructive methods like Eddy current or micrometer.