



Designation: D 5356 – 93 (Reapproved 1998)

## Standard Test Method for pH of Chrome Tanning Solutions<sup>1</sup>

This standard is issued under the fixed designation D 5356; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the determination of the pH of chrome tanning solutions.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 3898 Test Method for Chromium in Basic Chromium Tanning Liquors<sup>2</sup>

E 70 Test Method for pH of Aqueous Solutions with the Glass Electrode<sup>3</sup>

### 3. Terminology

#### 3.1 Definition of Term Specific to This Standard:

3.1.1 *pH, of a solution*—the negative logarithm of the hydrogen ion activity.

3.1.1.1 *Discussion*—A solution of pH 7 is neutral at 24°C. Lower numbers indicate increasing acidity, higher numbers indicate increasing alkalinity.

### 4. Summary of Test Method

4.1 The chrome tanning liquor is diluted to a concentration of  $25.0 \pm 0.5$  g chromic oxide equivalent per litre, allowed to come to equilibrium and the pH is then measured with the appropriate meter. For general details of a procedure, Test Method E 70 should be consulted. The provisions of the standard shall be governing except where the text of this test method specifically deviates.

### 5. Significance and Use

5.1 This test method is designed to measure the pH of a chrome tanning solution which has been diluted to a specific

concentration. This is considered to be a measure of the acidity or alkalinity of the solution.

5.2 This test method is suitable for quality control in the manufacture of leather.

### 6. Apparatus

6.1 *pH Meter*, either battery or line-operated equipped with appropriate electrodes. The meter shall have a maximum scale division of 0.1 pH unit and reproducibility of 0.05 pH unit.

NOTE 1—Sellers list reasonably priced models having more sensitivity and greater reproducibility.

### 7. Reagents

7.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>4</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean distilled water or water of equal purity.

7.3 *Buffer Solutions*—Commercially available buffer solutions of  $2.00 \pm 0.02$  pH and  $4.00 \pm 0.02$  pH shall be used for meter standardization, in accordance with the manufacturer's recommendations and the provisions set forth in Test Method E 70.

### 8. Standardization

8.1 Standardize the meter against the pH 4.00 standard, in accordance with the manufacturer's recommendations and the provisions set forth in Test Method E 70. The buffer standard shall be at room temperature and the temperature compensator shall be set at this temperature.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-31 on Leather and is the direct responsibility of Subcommittee D31.06 on Chemical Analysis—General Methods.

Current edition approved Jan. 15, 1993. Published March 1993.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 15.04.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 15.05.

<sup>4</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.