



Designation: D 5359 – 98

Standard Specification for Glass Cullet Recovered from Waste for Use in Manufacture of Glass Fiber¹

This standard is issued under the fixed designation D 5359; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification describes glass cullet recovered from municipal waste destined for disposal. The recovered cullet is intended for use in the manufacture of glass fiber used for insulation-type products.

2. Referenced Documents

2.1 ASTM Standards:

- C 162 Terminology of Glass and Glass Products²
- D 4129 Test Method for Total and Organic Carbon in Water by High-Temperature Oxidation and Coulometric Detection³
- E 688 Test Methods for Waste Glass as a Raw Material for Glass Manufacturing⁴

3. Terminology

3.1 For definitions of terms used in this specification, refer to Terminology C 162.

4. General Requirements

4.1 Glass cullet from municipal waste is primarily soda-lime bottle glass and shall be one of three grades depending upon the total usage rate requirement of the user. The three grades shall satisfy the following chemical composition, color mix, contamination, and particle size requirements as listed in Section 4:

4.2 *Chemical Composition*—See Table 1.

4.3 *Color Mix*—Color is an indicator of the oxidation state of container cullet. SO₃ gas solubility in the glass melt is a function of the glass oxidation state. Changes in the oxidation state of cullet added to the fiberglass batch can shift the glass oxidation state causing the release of dissolved SO₃ gas, which can upset the furnace. A change in the glass oxidation state also

¹ This specification is under the jurisdiction of ASTM Committee D-34 on Waste Management and is the direct responsibility of Subcommittee D34.06 on Recovery and Reuse.

Current edition approved Sept. 10, 1998. Published December 1998. Originally published as D 5359-93. Last previous edition D 5359-93.

² *Annual Book of ASTM Standards*, Vol 15.02.

³ *Annual Book of ASTM Standards*, Vol 11.02.

⁴ *Annual Book of ASTM Standards*, Vol 11.04.

TABLE 1 Chemical Composition

Grade	1		2		3	
Use Range	0 to 5 % in batch		5 to 15 % in batch		>15 % in batch	
Oxide	Weight %	±Range %	Weight %	±Range %	Weight %	±Range %
SiO ₂	68–77	NA	68–77	1.00	68–77	1.00
Al ₂ O ₃	0–7	NA	0–7	0.50	0–7	0.50
CaO	5–15	NA	5–15	0.50	5–15	0.50
MgO	0–5	NA	0–5	0.50	0–5	0.50
Na ₂ O	8–18	NA	8–18	0.50	8–18	0.50
K ₂ O	0–4	NA	0–4	0.50	0–4	0.50
Fe ₂ O ₃	<0.5	NA	<0.5	0.05	<0.5	0.05
Cr ₂ O ₃	<0.2	NA	<0.15	0.03	<0.1	0.02
SO ₃	<0.4	NA	<0.3	0.03	<0.2	0.02
All other oxides	<0.5	NA	<0.3	0.05	<0.1	0.02
C ^A	<0.15	NA	<0.10	0.02	<0.05	0.01
H ₂ O	<0.5	NA	<0.5	0.05	<0.5	0.05
LOI	<0.45	NA	<0.30	0.05	<0.15	0.03

^A Carbon is determined directly by instrumental method such as Coulometrics, Inc. Model 5010 Coulometer. Test Method D 4129 uses this instrumentation for total and organic carbon in water. The instrument can be readily adapted to solid materials such as cullet.

means a change in the glass FeO content. This affects the heat transfer in the melt and can affect furnace efficiency and glass quality. See Table 2.

4.4 *Contaminants*—Free metals, magnetic or nonmagnetic, are not oxidized in the glass melting process and, therefore, are insoluble. Metals will pool on the furnace floor and leak through joints causing premature wear of refractories and electrical shorts, which can lead to glass leaks. Some metals will attack and destroy precious metal skimmers and thermocouples and molybdenum electrodes. Examples are silver, tin, lead, and aluminum.

4.4.1 Other inorganic materials and refractories will not melt in the glass melting process. Other inorganics can be porcelains, ceramics, or high-temperature glasses. Refractories can be remnants of furnace construction materials or minerals contained as unmelted inclusions in the cullet. See Table 3.

4.4.1.1 The container cullet mixture must not contain glass types or other materials whose composition contains anything that is either harmful to the fiberglass production process or which affects the user's ability to meet Federal or state environmental, safety, or health laws. Examples of such