



Designation: A 389/A 389M-03 (Reapproved 2007) Designation: A 389/A 389M – 08

Standard Specification for Steel Castings, Alloy, Specially Heat-Treated, for Pressure- Containing Parts, Suitable for High-Temperature Service¹

This standard is issued under the fixed designation A 389/A 389M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers alloy steel castings, which have been subjected to special heat treatment, for valves, flanges, fittings, and other pressure-containing parts (Note 1) intended primarily for high-temperature service.

1.2 The high-temperature properties of the materials covered in this specification are dependent upon special heat treatment that is required. Although the high-temperature properties are not specified, they are implied by control of chemistry, heat treatment, and room-temperature properties.

1.3 Two grades of ferritic alloy steel are covered (Note 2). Selection will depend on the design and service conditions, mechanical properties, and high-temperature characteristics.

NOTE 1—Carbon steel castings for pressure-containing parts are covered by Specification A 216/A 216M. Alloy steel castings are covered by Specification A 217/A 217M.

NOTE 2—The grades covered by this specification represent materials that are generally suitable for assembly with other castings or wrought steel parts by fusion welding. It is not intended to imply that these grades possess equal degrees of weldability; therefore, it is the responsibility of the purchaser to establish for himself a suitable welding technique. Since these grades possess varying degrees of suitability for resistance to oxidation and for high-temperature service, it is also the responsibility of the purchaser to determine which grade shall be furnished, due consideration being given to the requirements of the applicable construction codes.

1.4 The values stated in either ~~inch-pound~~SI units or ~~SI~~inch-pound units are to be regarded separately as standard. ~~Within the text, the SI units are shown in brackets. The values stated in each system are~~may not be exact equivalents; therefore, each system ~~must~~shall be used independently of the other. Combining values from the two systems may result in non-conformance with the ~~specification.~~ standard.

2. Referenced Documents

- 2.1 *ASTM Standards:*²
- A 216/A 216M Specification for Steel Castings, Carbon, Suitable for Fusion Welding, for High-Temperature Service
 - A 217/A 217M Specification for Steel Castings, Martensitic Stainless and Alloy, for Pressure-Containing Parts, Suitable for High-Temperature Service
 - A 488/A 488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel
 - A 703/A 703M ~~Specification for Steel Castings, General Requirements, for Pressure-Containing Parts~~ Specification for Steel Castings, General Requirements, for Pressure-Containing Parts
 - A 985/A 985M Specification for Steel Investment Castings General Requirements, for Pressure-Containing Parts
- 2.2 *Manufacturers' Standardization Society of the Valve and Fittings Industry Standard:*
- SP-55 Quality Standard for Steel Castings for Valves, Flanges, and Fittings and other Components (Visual Method)³

3. General Conditions of Delivery

~~3.1 Material furnished to this specification shall conform to the requirements of Specification A 703/A 703M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of A~~

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Nov. Oct. 1, 2007-2008. Published November 2007-2008. Originally approved in 1955. Last previous edition approved in 2003-2007 as A 389 – 03 (2007).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, http://www.mss-hq.com.

*A Summary of Changes section appears at the end of this standard.

703/A703M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and A 703/A703M, this specification shall prevail.

3.1 Except for steel investment castings, material furnished to this specification shall conform to the requirements of Specification A 703/A 703M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of A 703/A 703M constitutes nonconformance with the specification. In case of conflict between the requirements of this specification and A 703/A 703M, this specification shall prevail.

3.2 Steel investment castings furnished to this specification shall conform to the requirements of Specification A 985/A 985M, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A 985/A 985M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A 985/A 985M, Specification A 985/A 985M shall prevail.

4. Ordering Information

4.1 The inquiry and order should include or indicate the following:

4.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

4.1.2 Grade of steel,

4.1.3 Options in the specification, and

4.1.4 The supplementary requirements desired including the standards of acceptance.

5. Heat Treatment

5.1 All castings shall receive a heat treatment proper to their design and chemical composition. Heat treatment shall be performed before machining except in instances when reheat treating is necessary. All castings shall have been allowed to cool, after pouring, to a temperature below the critical range before heat treatment.

5.2 At the option of the manufacturer the castings may be given any preliminary heat treatment that will aid in their processing.

5.3 All castings shall receive a final heat treatment consisting of normalizing and tempering at the temperature prescribed for each grade in Table 1.

5.4 Furnace temperatures for heat treating shall be effectively controlled by use of pyrometers.

6. Chemical Composition

6.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 2.

7. Tensile Requirements Tensile Requirements

7.1 Steel used for the castings shall conform to the requirements as to tensile properties prescribed in Table 3.

8. Quality

8.1 The surface of the casting shall be examined visually and shall be free of adhering sand, scale, cracks, and hot tears. Other surface discontinuities shall meet the visual acceptance standards specified in the order. Visual Method SP-55 or other visual standards may be used to define acceptable surface discontinuities and finish. Unacceptable visual surface discontinuities shall be removed and their removal verified by visual examination of the resultant cavities. When methods involving high temperature are used in the removal of discontinuities, castings shall be preheated to at least the minimum temperatures in Table 4.

8.2 The castings shall not be peened, plugged, or impregnated to stop leaks.

9. Repair by Welding

9.1 Repair shall be made by using a welding procedure and operators qualified in accordance with Practice A 488/A 488M. The composition of the deposit weld material shall be similar to that of the casting, or of other composition as may be agreed upon between the manufacturer and the purchaser. The castings after complement of weld repairing shall be retempered except that local tempering of the weld repairs will be permitted if, in the manufacturer's opinion, complete furnace-heat treatment would be damaging to the finished surfaces of a machined casting. Heat treatments after weld repair other than tempering shall be performed only when agreed upon between the manufacturer and the purchaser.

TABLE 1 Heat Treating Temperatures

Grade	Normalizing Temperature, °F[°C]	Tempering	
		Temperature, °F[°C]	Holding Time, h
C23	1850–1950 [1010–1065]	1250–1350 [675–730]	1 ^A
C24	1850–1950 [1010–1065]	1250–1350 [675–730]	12

^A Per inch or less of thickness.