



**SLOVENSKI STANDARD**  
**SIST EN IEC 60404-16:2018**  
**01-september-2018**

---

**Magnetni materiali - 16. del: Metode merjenja magnetnih lastnosti amorfnega traku na osnovi železa z uporabo enolistnega preskuševalnika (IEC 60404-16:2018)**

Magnetic materials - Part 16: Methods of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester (IEC 60404-16:2018)

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

Ta slovenski standard je istoveten z: **EN IEC 60404-16:2018**  
<https://standards.iteh.ai/catalog/standards/sist/a5156395-ab71-4a71-f86b4-07bd82431fc8/sist-en-iec-60404-16-2018>

**ICS:**

17.220.20	Merjenje električnih in magnetnih veličin	Measurement of electrical and magnetic quantities
29.030	Magnetni materiali	Magnetic materials

**SIST EN IEC 60404-16:2018**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN IEC 60404-16:2018

<https://standards.iteh.ai/catalog/standards/sist/a5f58593-ab71-4a7f-86b4-07bd82431fc8/sist-en-iec-60404-16-2018>

EUROPEAN STANDARD

EN IEC 60404-16

NORME EUROPÉENNE

EUROPÄISCHE NORM

July 2018

ICS 17.220.20; 29.030

English Version

Magnetic materials - Part 16: Methods of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester  
(IEC 60404-16:2018)

Matériaux magnétiques - Partie 16: Méthodes de mesure des propriétés magnétiques des bandes en alliage amorphe à base de fer à l'aide de l'essai sur tôle unique  
(IEC 60404-16:2018)

Magnetische Werkstoffe - Teil 16 : Verfahren zur Messung der magnetischen Eigenschaften von eisenbasiertem, amorphem Band unter Verwendung eines Tafelmessgerätes  
(IEC 60404-16:2018)

This European Standard was approved by CENELEC on 2018-04-12. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization  
Comité Européen de Normalisation Electrotechnique  
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

**EN IEC 60404-16:2018****European foreword**

The text of document 68/570/CDV, future edition 1 of IEC 60404-16, prepared by IEC/TC 68 "Magnetic alloys and steels" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 60404-16:2018.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2019-01-12
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2021-04-12

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

**Endorsement notice**

The text of the International Standard IEC 60404-16:2018 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following note has to be added for the standard indicated:

IEC 60404-6:2003 NOTE Harmonized as EN 60404-6:2003 (not modified).  
<https://standards.iteh.ai/catalog/standards/sist/a5f58593-ab71-4a7f-86b4-07bd82431fc8/sist-en-iec-60404-16-2018>

## Annex ZA (normative)

### Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: [www.cenelec.eu](http://www.cenelec.eu).

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60050-121	-	International Electrotechnical Vocabulary (IEV) - Part 121: Electromagnetism	-	-
IEC 60050-221	-	International Electrotechnical Vocabulary (IEV) - Chapter 221: Magnetic materials and components	-	-
IEC 60404-8-11	-	Magnetic materials - Part 8-11: Specifications for individual materials - Fe-based amorphous strip delivered in the semi-processed state	EN IEC 60404-8-11 -	-

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN IEC 60404-16:2018

<https://standards.iteh.ai/catalog/standards/sist/a5f58593-ab71-4a7f-86b4-07bd82431fc8/sist-en-iec-60404-16-2018>



IEC 60404-16

Edition 1.0 2018-03

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

**Magnetic materials – Part 16: Methods of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester**

**Matériaux magnétiques – Partie 16: Méthodes de mesure des propriétés magnétiques des bandes en alliage amorphe à base de fer à l'aide de l'essai sur tôle unique**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

ICS 17.220.20; 29.030

ISBN 978-2-8322-5426-4

**Warning! Make sure that you obtained this publication from an authorized distributor.  
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD.....	4
INTRODUCTION.....	6
1 Scope.....	7
2 Normative references .....	7
3 Terms and definitions .....	7
4 General principles .....	8
4.1 Principle of the method .....	8
4.2 Test specimen .....	9
4.3 Test apparatus.....	9
4.3.1 General .....	9
4.3.2 Yoke .....	10
4.3.3 Windings .....	10
4.3.4 Air flux compensation .....	11
4.3.5 Magnetic shielding.....	11
4.4 Power supply .....	11
4.5 Measuring instruments.....	12
4.6 Digital sampling technique .....	12
5 Measurement procedure.....	13
5.1 Principle of measurement.....	13
5.2 Preparation of measurement.....	13
5.3 Adjustment of power supply .....	14
6 Determination of characteristics.....	14
6.1 Determination of the magnetic polarization.....	14
6.2 Determination of the magnetic field strength .....	15
6.3 Determination of the specific total loss.....	15
6.4 Determination of the specific apparent power.....	16
7 Reproducibility.....	16
Annex A (informative) Requirements of the single sheet tester for Fe-based amorphous strip.....	17
A.1 Shape of test specimen.....	17
A.2 H coil method.....	17
A.3 Yoke .....	17
A.4 Wirings .....	17
A.5 Non-inductive precision resistor .....	18
A.6 Magnetic shielding .....	18
A.7 Method for checking the stability of the installed H coil from time to time .....	18
Annex B (informative) Digital sampling technique for the determination of the magnetic properties and numerical air flux compensation .....	19
B.1 General.....	19
B.2 Technical details and requirements.....	19
B.3 Calibration aspects .....	22
B.4 Numerical air flux compensation .....	22
Annex C (informative) Sinusoidal waveform control of the magnetic polarization by digital means .....	24
Bibliography.....	26



Figure 1 – Schematic diagram of the test apparatus.....	8
Figure 2 – Circuit of the wattmeter method with H coil mode .....	9
Figure 3 – Yoke dimensions .....	10
Figure 4 – Circuit of the wattmeter method with H coil mode adopting the digital sampling technique .....	12

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN IEC 60404-16:2018](https://standards.iteh.ai/catalog/standards/sist/a5f58593-ab71-4a7f-86b4-07bd82431fc8/sist-en-iec-60404-16-2018)

<https://standards.iteh.ai/catalog/standards/sist/a5f58593-ab71-4a7f-86b4-07bd82431fc8/sist-en-iec-60404-16-2018>

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## MAGNETIC MATERIALS –

**Part 16: Methods of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.  
<https://standards.iteh.ai/catalog/standards/sist/a5f58593-ab71-4a7f-86b4-33a12451c893/iec-60404-16>
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60404-16 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

The text of this International Standard is based on the following documents:

CDV	Report on voting
68/570/CDV	68/583A/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60404 series, published under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

## **iTeh STANDARD PREVIEW (standards.iteh.ai)**

SIST EN IEC 60404-16:2018

<https://standards.iteh.ai/catalog/standards/sist/a5f58593-ab71-4a7f-86b4-07bd82431fc8/sist-en-iec-60404-16-2018>

## INTRODUCTION

A method of measuring the magnetic properties of Fe-based amorphous strip is required to grade what is regarded as a promising material to reduce energy loss in transformer cores and, consequently, to reduce global warming.

Fe-based amorphous strip is produced by a rapidly-solidifying, direct-casting process. The strip is intended primarily for the construction of wound cores of distribution transformers for commercial power frequency (50 Hz and 60 Hz) applications.

After appropriate heat treatment, the strip exhibits a significantly lower value of specific total loss compared to grain-oriented electrical steel strip. It is associated with low hysteresis loss due to low magnetic anisotropy and low eddy current loss due to high resistivity and reduced thickness. However, significant deterioration can occur by applying stress on the strip due to the large magnetostriction and low magnetic anisotropy characteristics of the material.

Therefore, a method of measurement of the magnetic properties of Fe-based amorphous strip by means of a single sheet tester (SST) is required, independent of IEC 60404-3 [1]<sup>1</sup>, which is specified for electrical steel sheets.

The almost exclusively applied wattmeter method is used also in this standard. However, the widely used version with the determination of the magnetic field strength from the magnetizing current ("MC method") is not applicable to this kind of material, because the influence of the yokes on the loss measurement is significantly greater for the thinner and magnetically softer test specimen of this material. Thus, the wattmeter method with H coil mode ("H coil method") has been included for the magnetic field determination. International round robin tests of SST and Fe-based amorphous test specimens have been carried out, resulting in a suitable configuration of the SST for amorphous material. The single-yoke concept was adopted in order to avoid the effect of the impact of the upper yoke caused by the high magneto-elastic sensitivity of the material.

---

<sup>1</sup> Numbers in square brackets refer to the Bibliography.