



**Designation: B 428-93 (Reapproved 2004) Designation: B 428 - 08**

## Standard Test Method for Angle of Twist in Rectangular and Square Copper and Copper Alloy Tube<sup>1</sup>

This standard is issued under the fixed designation B 428; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This test method establishes the requirements for the determination of the angle of twist in rectangular and square copper and copper alloy tube.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Significance and Use

~~2.1 The rectangular or square copper alloy tube covered by this test method may be used in applications in which control of twist is important to proper fit in final assembly and to minimize rework to bring the tube into compliance. It is recognized that the amount of twist, in degrees, per increment of length can change as a result of the weight of the product and its length during measurement.~~

~~2.2 This test method provides a procedure for measuring the twist in square and rectangular copper and copper alloy tubes as a measure of the deviation from straightness.~~

~~2.3 This test method allows the purchaser and supplier or manufacturer to inspect square and rectangular copper and copper alloy tube with a standard technique that provides acceptable twist in delivered tubes. Referenced Documents~~

~~2.1 ASTM Standards:<sup>2</sup>~~

~~B 846 Terminology for Copper and Copper Alloys~~

### 3. Terminology

~~3.1 For definitions of terms related to copper and copper alloys, refer to Terminology B 846.~~

### 4. Significance and Use

~~4.1 The rectangular or square copper alloy tube covered by this test method may be used in applications in which control of twist is important to proper fit in final assembly and to minimize rework to bring the tube into compliance. It is recognized that the amount of twist, in degrees, per increment of length can change as a result of the weight of the product and its length during measurement.~~

~~4.2 This test method provides a procedure for measuring the twist in square and rectangular copper and copper alloy tubes as a measure of the deviation from straightness.~~

~~4.3 This test method allows the purchaser and supplier or manufacturer to inspect square and rectangular copper and copper alloy tube with a standard technique that provides acceptable twist in delivered tubes.~~

### 5. Apparatus

~~3-1~~

~~5.1 Horizontal Reference Plane (see Fig. 1 and Fig. 2) of sufficient length to support the tube specimen and a clamping device to hold one end of the specimen against the reference plane.~~

~~3-2~~

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.06 on Methods of Test.

Current edition approved May 1, 2004. Published May 2004. Originally approved in 1965. Last previous edition approved in 1998 as B428-93 (1998)<sup>ε1</sup>.

Current edition approved Oct. 1, 2008. Published November 2008. Originally approved in 1965. Last previous edition approved in 2004 as B 428 - 93 (2004).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.