



SLOVENSKI STANDARD
SIST EN IEC 63093-8:2019

01-september-2019

Nadomešča:

SIST EN 60424-3:2016

SIST EN 62317-8:2007

**Feritna jedra - Smernice o merah in mejnih vrednostih površinskih nepravilnosti -
8. del: E-jedra**

Ferrite cores - Guidelines on dimensions and the limits of surface irregularities - Part 8:
E-cores

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN IEC 63093-8:2019](https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019)

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019>

Ta slovenski standard je istoveten z: EN IEC 63093-8:2018

ICS:

29.100.10 Magnetne komponente Magnetic components

SIST EN IEC 63093-8:2019 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN IEC 63093-8:2019

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019>

EUROPEAN STANDARD

EN IEC 63093-8

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2018

ICS 29.100.10

Supersedes EN 60424-3:2016 (partially), EN 62317-8:2006

English Version

Ferrite cores - Guidelines on dimensions and the limits of surface irregularities - Part 8: E-cores (IEC 63093-8:2018)

Noyaux ferrites - Lignes directrices relatives aux dimensions et limites des irrégularités de surface - Partie 8 :
Noyaux E
(IEC 63093-8:2018)

Ferritkerne - Richtlinien zu Maßen und Grenzen von Oberflächenbeschädigungen - Teil 8: E-Kerne
(IEC 63093-8:2018)

This European Standard was approved by CENELEC on 2018-06-04. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

[SIST EN IEC 63093-8:2019](https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-sist/en-iec-63093-8-2019)

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-sist/en-iec-63093-8-2019>

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.



European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

EN IEC 63093-8:2018 (E)**European foreword**

The text of document 51/1213/CDV, future edition 1 of IEC 63093-8, prepared by IEC/TC 51 "Magnetic components, ferrite and magnetic powder materials" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN IEC 63093-8:2018.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2018-03-28
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2021-09-28

This document supersedes EN 62317-8:2006.

This document together with EN IEC 63093-6:2018, EN IEC 63083-7:2018 and EN IEC 63093-11:2018 supersedes EN 60424-3:2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC shall not be held responsible for identifying any or all such patent rights.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Endorsement notice

SIST EN IEC 63093-8:2019

The text of the International Standard IEC 63093-8:2018 was approved by CENELEC as a European Standard without any modification.

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 60424-3:2015 NOTE Harmonized as EN 60424-3:2016 (not modified)

IEC 62317-8:2006 NOTE Harmonized as EN 62317-8:2006 (not modified)

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE 1 Where an International Publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

NOTE 2 Up-to-date information on the latest versions of the European Standards listed in this annex is available here: www.cenelec.eu.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60205	-	Calculation of the effective parameters of magnetic piece parts	EN 60205	-
IEC 60401-1	-	Terms and nomenclature for cores made of magnetically soft ferrites - Part 1: Terms used for physical irregularities	EN 60401-1	-
IEC 60424-1	-	Ferrite cores - Guidelines on the limits of surface irregularities - Part 1: General specification	EN 60424-1	-

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN IEC 63093-8:2019

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019>



IEC 63093-8

Edition 1.0 2018-06

INTERNATIONAL STANDARD

**Ferrite cores – Guidelines on dimensions and the limits of surface
irregularities –
Part 8: E-cores**

ITh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN IEC 63093-8:2019](https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019)

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.100.10

ISBN 978-2-8322-5835-4

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	6
4 Primary dimensions	6
4.1 General.....	6
4.2 Dimensions of E-cores	7
4.2.1 Main dimensions.....	7
4.2.2 Effective parameter and A_{\min} values	9
4.3 Dimensional limits for coil formers	11
5 Limits of surface irregularities.....	15
5.1 General.....	15
5.2 Examples of surface irregularities	15
5.3 Chips and ragged edges	15
5.3.1 General	15
5.3.2 Chips and ragged edges on the mating surfaces.....	15
5.3.3 Chips and ragged edges on the other surfaces	15
5.4 Cracks	18
5.5 Flash	18
5.6 Pull-outs	18
5.7 Crystallites.....	19
5.8 Pores.....	19
Annex A (normative) Derived standards.....	21
Annex B (normative) Example of dimensions for gauges to check the dimensions of E-cores complying with this document	22
B.1 General.....	22
B.2 Procedure and requirements	24
Annex C (informative) Reference of allowable areas of chips	25
Bibliography.....	26
Figure 1 – Dimensions of E-cores with rectangular cross-section	7
Figure 2 – Main dimensions of coil formers	12
Figure 3 – Examples of surface irregularities	15
Figure 4 – Chip location for E-cores	16
Figure 5 – Crack and pull-out locations for E-cores	18
Figure 6 – Crystallite location for E-cores	19
Figure 7 – Pore location for E-cores.....	20
Figure B.1 – Gauge dimensions	22
Table 1 – Dimensions of E-cores with rectangular cross-section	8
Table 2 – Effective parameter and A_{\min} values.....	10
Table 3 – Dimensional limits for coil formers	13
Table 4 – Area and length reference for visual inspection	17
Table 5 – Limits for cracks	19

Table B.1 – Gauge dimensions	23
Table C.1 – Allowable areas of chips for E-cores	25

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN IEC 63093-8:2019](https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019)

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**FERRITE CORES – GUIDELINES ON DIMENSIONS
AND THE LIMITS OF SURFACE IRREGULARITIES –****Part 8: E-cores**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 63093-8 has been prepared by IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

This first edition cancels and replaces the first edition of IEC 62317-8 published in 2006 and the second edition of IEC 60424-3 published in 2015. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to IEC 62317-8:2006 and IEC 60424-3:2015:

- a) This document integrates IEC 62317-8:2006 and IEC 60424-3:2015;
- b) Table 4 – Allowable areas of chips for E-cores, of IEC 60424-3:2015, has been moved to Annex C (informative) of this document.

The text of this International Standard is based on the following documents:

CDV	Report on voting
51/1213/CDV	51/1235/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 63093 series, published under the general title *Ferrite cores – Guidelines on dimensions and the limits of surface irregularities*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN IEC 63093-8:2019](https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019)

<https://standards.iteh.ai/catalog/standards/sist/260e3eb9-2f34-4813-a864-982e471b278c/sist-en-iec-63093-8-2019>

FERRITE CORES – GUIDELINES ON DIMENSIONS AND THE LIMITS OF SURFACE IRREGULARITIES –

Part 8: E-cores

1 Scope

This part of IEC 63093 specifies the dimensions that are of importance for mechanical interchangeability for a preferred range of E-cores made of ferrite and the essential dimensions of coil formers to be used with them, as well the effective parameter values to be used in calculations involving them. It also gives guidelines on allowable limits of surface irregularities applicable to E-cores.

The specifications contained in this document are useful in negotiations between ferrite core manufacturers and customers about surface irregularities.

The use of derived standards, which give more detailed specifications of component parts while still permitting compliance with this standard, is discussed in Annex A.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60205, *Calculation of the effective parameters of magnetic piece parts*

IEC 60401-1, *Terms and nomenclature for cores made of magnetically soft ferrites – Part 1: Terms used for physical irregularities*

IEC 60424-1, *Ferrite cores – Guidelines on the limits of surface irregularities – Part 1: General specification*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in IEC 60401-1 and IEC 60424-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Primary dimensions

4.1 General

Compliance with the following requirements ensures mechanical interchangeability of complete assemblies and coil formers.